



Designation: C980 – 17

# Standard Specification for Industrial Chimney Lining Brick<sup>1</sup>

This standard is issued under the fixed designation C980; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers solid kiln fired brick made from clay, shale, or mixtures thereof suitable for use in masonry construction in contact with the chemicals present in flue gases found in industrial chimneys. These brick are normally used with chemical-resistant mortars.

1.2 Terminology related to industrial floor brick is found in Terminology C1232.

1.3 *Units*—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

C20 Test Methods for Apparent Porosity, Water Absorption, Apparent Specific Gravity, and Bulk Density of Burned Refractory Brick and Shapes by Boiling Water

C67 Test Methods for Sampling and Testing Brick and Structural Clay Tile

C1232 Terminology of Masonry

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.02 on Brick and Structural Clay Tile.

Current edition approved June 1, 2017. Published July 2017. Originally approved in 1982. Last previous edition approved in 2013 as C980 – 13a. DOI: 10.1520/C0980-17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Terminology

3.1 *Definitions*—For definitions relating to industrial chimney lining brick, refer to Terminology C1232.

## 4. Classification

4.1 The physical and chemical properties of chimney lining brick differ from supplier to supplier mainly because their composition is determined by the source of raw materials. Chimney lining brick, regardless of these differences, are considered to be of three types noted as follows:

4.1.1 *Type I*—For use where low absorption and high acid resistance are not major factors.

4.1.2 *Type II*—For use where lower absorption and higher acid resistance are required.

4.1.3 *Type III*—For use where lowest absorption and highest acid resistance are required.

NOTE 1—Types I, II, and III may not differ significantly in their resistance to thermal shock, and selection of brick type should be based upon their absorption and acid-resistant service requirements.

## 5. Sulfuric Acid Boil Test

5.1 When tested in accordance with Section 9, the brick shall conform to the requirements for “Maximum Average Weight Loss by H<sub>2</sub>SO<sub>4</sub> Boil Test” as shown in Table 1.

## 6. Physical Properties

6.1 *Compressive Strength*—When tested in accordance with Test Methods C67, Section 6 (Compressive Strength), the brick shall conform to the requirements for “Minimum Compressive Strength” as shown in Table 1.

6.2 *Water Absorption*—When tested in accordance with Test Methods C20, the brick shall conform to the requirements for “Maximum Water Absorption by 2-h Boiling” as shown in Table 1.

## 7. Dimensions, Mass, and Permissible Variations

7.1 *Sizes*—The sizes of brick shall be as specified by the purchaser. When tested in accordance with Test Methods C67, Section 11 (Measurement of Size), the brick shall conform to the requirements for “Permissible Variations in Dimensions” as shown in Table 2.

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Physical Properties and Chemical Requirements<sup>A</sup>**

| Designation | Minimum Compressive Strength, Gross Area, psi (MPa) |               | Maximum Water Absorption by 2-h Boiling, % |            | Maximum Average Weight Loss by H <sub>2</sub> SO <sub>4</sub> Boil Test, % |
|-------------|---|---------------|--|------------|--|
|             | Average of 10                                       | Individual    | Average of 10                              | Individual |  |
| Type I      | 8 500 (58.6)  | 8 000 (55.2)  | 6.0  | 7.0        | 20   |
| Type II     | 10 000 (69.0)                                       | 9 000 (62.2)  | 4.0  | 5.0        | 12   |
| Type III    | 12 000 (82.8)                                       | 10 000 (69.0) | 1.0  | 1.5        | 8  |

<sup>A</sup> One complete set of tests for each of the above requirements shall be performed from brick randomly selected from every 100 000 bricks.

**TABLE 2 Permissible Variations in Dimensions and Warpage<sup>A</sup>**

| Dimensions | Dimensions  |  |   |
|------------|---|--|---|
|            | Maximum Permissible Variations in Dimensions Between Largest and Smallest Brick in a Random Sampling of 10 Brick, % | Warpage  |   |
|            |   | Maximum Face and Diagonal Dimensions, in. (mm) | Maximum Permissible Deviation, in. (mm) |
| Height     | 3   | up to 9 ½ (241) incl                           | ⅛ (3.0)                                 |
| Length     | 5   | ...  | ...                                     |
| Width      | 5   | ...  | ...                                     |

<sup>A</sup>One complete set of tests for each of the above requirements shall be performed from brick randomly selected from every 100 000 bricks.

**7.2 Warpage**—When tested in accordance with Test Methods C67, Section 12 (Measurement of Warpage), the tolerance on warpage of the brick shall be as indicated in Table 2.

## 8. Finish and Appearance

**8.1 Black Heart**—Brick when broken may have a dark area that has a steely appearance and is sharply delineated from the surrounding normal color of the brick it is known as black heart or black core. Black heart is generally the result of the reduction of iron minerals during the firing process. Its presence, regardless of size in brick that otherwise meet the physical and chemical requirements of this specification, shall not be cause for rejection.

**8.2 Texture**—Scoring or matte texturing, or both, of the brick is recommended. However, no flutes or scores shall exceed ⅛ in. (3.0 mm) in height of protrusion or in depth.

## 9. Test for Solubility in Sulfuric Acid

**9.1 Significance and Use**—This test with sulphuric acid represents an extremely severe one and may not be significant for chemical-resistant brick in less demanding applications. It can be assumed that sulphuric acid in this test concentration will be more corrosive than most other acids excluding those containing flourine. A similar test procedure using other chemicals may be more suitable for specific purposes. The performance of these other tests and appropriate qualifying data should be resolved between the purchaser and the seller.

### 9.2 Apparatus:

#### 9.2.1 Crusher, jaw-type.

9.2.2 Sieves, ¼-in. (6.3-mm) and No. 4 (4.75-mm), (equivalent to 3-mesh and 4-mesh sieves, respectively, in the Tyler series), conforming to Specification E11.

9.2.3 *Mechanical Shaking Device*, producing a lateral and vertical motion of the sieve, accompanied by a jarring action so as to keep the sample moving continuously over the surface of the sieve.

#### 9.2.4 Drying Oven.

9.2.5 *Analytical Balance and Weights*, 0.01-g sensitivity.

#### 9.2.6 Desiccator.

9.2.7 *Erlenmeyer Flask*, 750-mL, of heat-resistant and chemically resistant glass.

#### 9.2.8 Water-Cooled Condenser.

#### 9.2.9 Hot Plate.

#### 9.2.10 Fritted-Glass Funnel, fine porosity.

#### 9.2.11 Suction Pump.

**9.3 Preparation of Sample**—Prepare the sample from at least five masonry units selected in accordance with Test Methods C67. Remove the skin surface from a quarter of each unit selected, and crush the remaining pieces in a jaw-type crusher, with the jaws set so that the grain size of the product ranges from material retained on a ¼-in. (6.3-mm) sieve to material passing a No. 4 (4.75-mm) sieve. Reduce this material either by mixing and quartering or by a mechanical splitter to approximately a 1000-g sample, and screen in a mechanical shaking device for 15 min, using the No. 3 and No. 4 sieves. Thoroughly mix the portion of the material passing the No. 3 sieve and remaining on the No. 4 sieves (Note 2), and then quarter down to obtain two 50-g samples. Dry these samples in a drying oven at 221 to 239°F (105 to 115°C) for at least 16 h, and then cool in a desiccator.

NOTE 2—Although it is recognized that some types of material tend to break down in a manner yielding various-shaped particles, no attempt shall be made at hand selection.

**9.4 Procedure**—Transfer each of the 50-g samples, weighed to the nearest 0.01 g, and 250 mL of sulfuric acid (sp gr 1.706) or 60° Baumé (78 weight %) into separate 750-mL Erlenmeyer flasks. Insert water-cooled condensers and boil on hot plates for 48 h (Note 3). Cool the flasks and contents sufficiently to permit handling, and decant the solutions through fritted-glass funnels with the aid of suction, retaining the samples in the flasks. Add about 250 mL of water to the flasks, boil for 10 min, and decant with the aid of suction through the same funnels as used previously. Repeat this washing procedure three times. On the fourth decantation of wash water, transfer the samples to the funnels, using hot water to aid in the transfer. Dry the funnels and contents in the oven at 221 to 239°F (105 to 115°C) for at least 16 h, and cool in a desiccator. Remove material from the funnels, brushing out the fines if necessary, and weigh to the nearest 0.01 g.

NOTE 3—Regulate the temperature of the hot plate so as to maintain a gentle boiling solution, avoiding any considerable agitation of the sample.

The use of a variable transformer in series with the hot plate is suggested.

**9.5 Calculations and Report**—Calculate the loss in weight as a percentage of the original weight. Make duplicate determinations, and report an average of the two results to the nearest 0.1 %.

**9.6 Precision and Bias**—A statement on precision and bias will be added at a later date.

## **10. Sampling and Testing**

**10.1** The brick shall be sampled and tested in accordance with applicable sections in Test Methods **C67** and Sections **5** and **8**.

**10.2** The manufacturer or the seller shall furnish specimens for test. The place or places of selection shall be designated when the purchase order is placed.

## **11. Keywords**

11.1 absorption; acid resistance; acid solubility; ceramic; industrial chimney; masonry; physical properties; solid brick

## **SUMMARY OF CHANGES**

Committee C15 has identified the location of selected changes to this standard since the last issue (C980 – 13a) that may impact the use of this standard. (June 1, 2017)

(1) Changed drying temperature ranges in **9.3** and **9.4**.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*