



## Designation: D1061/D1061M – 95 (Reapproved 2017)

# Standard Specification for Asbestos Lap<sup>1</sup>

This standard is issued under the fixed designation D1061/D1061M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers asbestos lap, a felted asbestos product, having a minimum of 75 mass % of asbestos fiber.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 **Warning**—Breathing of asbestos dust is hazardous. Asbestos and asbestos products present demonstrated health risks for users and for those with whom they come into contact. In addition to other precautions, when working with asbestos-cement products, minimize the dust that results. For information on the safe use of chrysotile asbestos, refer to “Safe Use of Chrysotile Asbestos: A Manual on Preventive and Control Measures.”<sup>2</sup>

1.4 The following safety hazards caveat pertains only to the test methods, Section 12, described in this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific safety hazard, see 1.3.

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C17 on Fiber-Reinforced Cement Products and is the direct responsibility of Subcommittee C17.03 on Asbestos - Cement Sheet Products and Accessories.

Current edition approved June 1, 2017. Published July 2017. Originally approved in 1949. Last previous edition approved in 2009 as D1061/D1061M – 95(2009)<sup>ε1</sup>. DOI: 10.1520/D1061\_D1061M-95R17.

<sup>2</sup> Available from The Asbestos Institute, [http://www.chrysotile.com/en/sr\\_use/manual.htm](http://www.chrysotile.com/en/sr_use/manual.htm).

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>3</sup>

D123 Terminology Relating to Textiles

D1118 Test Method for Magnetic Rating of Asbestos Fiber and Asbestos Textiles

D1918 Test Method for Asbestos Content of Asbestos Textiles

D2946 Terminology for Asbestos and Asbestos-Cement Products

## 3. Terminology

3.1 For definitions of other textile terms used in this specification refer to Terminology D123. For asbestos terms refer to Terminology D2946.

### 3.2 Definitions:

3.2.1 *asbestos*—a group of impure silicate minerals occurring in fibrous form.

3.2.2 *asbestos fiber*—the hydrous magnesium silicate serpentine mineral designated as chrysotile and having the empirical formula  $\text{Mg}_3\text{Si}_2\text{O}_5(\text{OH})_4$ .

3.2.3 *atmosphere for testing textiles*—for asbestos, air maintained at a relative humidity of  $50 \pm 2\%$  at  $21 \pm 1^\circ\text{C}$ .

3.2.4 *lap, n*—for asbestos, a flat compressed form of carded or otherwise felted asbestos fiber, with or without carrier fibers.

3.2.5 *magnetic rating (MR)*—an empirical value that reflects the effect of magnetic particles, such as magnetic iron compounds, in asbestos material as measured by a magnetic analyzer.

NOTE 1—Magnetic rating is not a quantitative measure of the number or mass of magnetic particles in the material.

## 4. Classifications

4.1 *Styles*—The style of asbestos lap refers to the physical construction. Two styles are available:

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4.1.1 *Style 1*—A single compressed flat formation of carded or otherwise felted asbestos fibers, and

4.1.2 *Style 2*—A flat parallel assemblage of compressed carded asbestos slivers.

4.2 *Grades*—The grades of asbestos lap are based on the mass percentage of asbestos content as stated in **Table 1**.

4.3 *Mass per Unit Length*—Asbestos lap is normally furnished in the following nominal linear densities:

g/m	[lb/100 yd]
20	[4]
50	[10]
70	[14]
100	[20]
150	[30]

Other linear densities may be furnished as agreed upon between the purchaser and the seller.

#### 4.4 *Types*:

4.4.1 Asbestos lap as made for the electrical industry is furnished in three types, classified on the basis of magnetic rating determinations (Test Method **D1118**) as follows:

4.4.2 *Type II (Magnetic Rating 0.75 Maximum)* is intended only for special applications where the asbestos is of primary importance as electrical insulation used on magnet wire and when used primarily as a dielectric.

4.4.3 *Type IV (Magnetic Rating 2.00 Maximum)* is intended for use where the asbestos is of secondary importance as electrical insulation and where it is applied in combination with other materials of comparably higher dielectric strength, as in the construction of heat and flame resistant electrical insulating walls over unit conductors of electric cables.

4.4.4 *Type VI (Magnetic Rating 4.00 Maximum)* is intended for use where the asbestos is of minor importance as a dielectric, as in the construction of filler or heat and flame resistant walls of electric cables or when used as a lining for control enclosures subject to exposure to electric arcs (arc chutes).

## 5. Ordering Information

5.1 State the style, grade, mass per unit length (weight), and quantity required.

5.2 If required for electrical insulation, state this requirement and the type needed.

5.3 Dimensions of the finished lap and the packaging are as agreed upon between the purchaser and the seller. See **14.1**.

## 6. Materials and Manufacture

6.1 Asbestos lap shall be made from a uniformly carded or otherwise felted blend of fibers.

**TABLE 1 Grades of Asbestos Lap**

Grade	Asbestos Content, mass, %
Commercial	75 up to but excluding 80
Underwriters'	80 up to but excluding 85
A	85 up to but excluding 90
AA	90 up to but excluding 95
AAA	95 up to but excluding 99
AAAA	99 to 100 inclusive

## 7. Chemical Composition

7.1 *Asbestos Content*—The asbestos content of the particular grade shall be within the limits stated in **Table 1**.

7.2 *Carrier Fibers*—The chemical composition of carrier fibers shall be as agreed upon between the purchaser and the seller.

## 8. Physical Properties

8.1 *Electromagnetic Properties*—The magnetic rating of the particular type of lap shall be within the limits in **4.4** to **4.4.4**.

8.2 *Carrier Fibers*—The physical properties of the carrier fibers shall be as agreed upon between the purchaser and the seller.

## 9. Dimensions, Mass, and Permissible Variations

9.1 *Mass per Unit Length*—The linear density in grams per metres [or pounds per 100 yards] shall conform to the limits stated in **Table 2**.

9.2 *Width*—The width of the lap shall be within 6 mm [0.25 in.] of the width agreed upon by the purchaser and the seller.

## 10. Sampling

10.1 Take five sample rolls at random from each lot of 700 to 900 kg [1500 to 2000 lb] or fraction thereof.

## 11. Specimen Preparation

11.1 *Conditioning*—Condition all specimens in the atmosphere for testing asbestos textiles (without preconditioning) for a minimum of 4 h, or until the specimen shows no progressive change in mass of more than 0.1 % after an exposure of 0.5 h.

### 11.2 *Number of Specimens*:

11.2.1 Unless otherwise agreed upon, as when specified in an applicable material specification, take a number of specimens such that the user may expect at the 95 % probability level that the test result is more than 15.0 grains per linear yard [1.13 g/m] above or below the true average (for the lot). Determine the number of specimens as follows:

11.2.2 *Reliable Estimate of Standard Deviation*—When there is a reliable estimate of standard deviation(s) based upon extensive past records for similar materials tested in the user's laboratory as directed in the method, calculate the number of specimens using **Eq 1**:

$$n = (t^2 \times s^2) / E^2 = 0.0170 \times s^2 \quad (1)$$

**TABLE 2 Limits in Mass per Unit Length for Asbestos Lap**

Nominal Mass per Unit Length	Permissible Range for 1-m [or 1-yd] Specimens			
	Average of Five Specimens		Individual Specimens	
g/m [lb/100 yd]	g/m	[lb/100 yd]	g/m	[lb/100 yd]
20 [4]	17.0 to 18.4	[3.43 to 3.71]	16.0 to 19.5	[3.21 to 3.93]
50 [10]	50.3 to 56.0	[10.14 to 11.29]	47.9 to 58.5	[9.64 to 11.79]
70 [14]	67.4 to 74.4	[13.57 to 15.00]	63.8 to 78.0	[12.86 to 15.71]
100 [20]	101.0 to 111.7	[20.36 to 22.50]	95.7 to 117.0	[19.29 to 23.57]
150 [30]	134.7 to 148.9	[27.14 to 30.00]	127.6 to 156.0	[25.71 to 31.43]

where:

- $n$  = number of specimens (rounded upward to a whole number),
- $s$  = reliable estimate of the standard deviation of individual observations on similar materials in the user's laboratory under conditions of single-operator precision,
- $t$  = 1.960, the value of Student's  $t$  for infinite degrees of freedom, for two-sided limits, and a 95 % probability level ( $t^2 = 3.842$ ),
- $E$  = 1.13 g/m [21.4 lb/100 yd], the value of the allowable variation, and
- 0.0170 = value calculated from  $t^2/E^2$ .

**11.3 No Reliable Estimate of Standard Deviation**—When there is no reliable estimate of standard deviation(s) for the user's laboratory, **Eq 1** should not be used directly. Instead, specify the fixed number of ten specimens. This number of specimens is calculated using  $s = 1.64$  g/m [0.33 lb/100 yd], which is a somewhat larger value of  $s$  than is usually found in practice. When a reliable estimate of  $s$  for the user's laboratory becomes available, **Eq 1** will usually require fewer than ten specimens.

## 12. Test Methods

### 12.1 Mass per Unit Length:

**12.1.1 Scope**—This test method covers the determination of length per unit mass (weight) of asbestos lap.

**12.1.2 Significance and Use**—The length per unit mass (weight) is the most significant dimension of asbestos lap. This determines its suitability with regard to bulk for specific applications.

**12.1.3 Hazards—Warning**—see .

**12.1.4 Procedure**—From each of the five rolls selected as directed in Section 11, take a  $1 \pm 0.01$  m [ $1 \pm 0.01$ -yd] test specimen. Take care that each specimen is not scuffed or torn. Weigh each of the five conditioned specimens to the nearest 0.5 g [0.001 lb] and calculate the average mass per unit length of the five specimens.

**TABLE 3 Precision and Reproducibility**

Number of Observations in Each Average	Critical Differences <sup>A</sup> for the Conditions Described			
	Single-Operator Precision (Repeatability)		Interlaboratory (Reproducibility)	
	g/m	[lb/100 yd]	g/m	[lb/100 yd]
1	3.25	[0.653]	3.25	[0.653]
2	2.30	[0.461]	2.30	[0.461]
5	1.45	[0.293]	1.45	[0.293]
10	1.03	[0.207]	1.03	[0.207]

<sup>A</sup> The critical differences were calculated using  $\tau = 1.96$ , which is based on infinite degrees of freedom.

### 12.1.5 Precision and Bias:

**12.1.5.1 Summary**—In comparing two averages of five observations, the differences should not exceed in 95 out of 100 cases where all observations are taken by the same well-trained operator using the same equipment and specimens randomly drawn from the sample of material. Larger differences are likely to occur under all other circumstances.

**12.1.5.2 Interlaboratory Test Data<sup>4</sup>**—An interlaboratory test was run in 1973 in which randomly drawn samples of one material were tested in each of five laboratories. Each laboratory used one operator who tested five specimens. The components of variance for linear density results were calculated to be as follows:

Single-operator component	1.17 g/m [0.236 lb/100 yd]
Between-laboratory component	0.00 g/m [0.000 lb/100 yd]

**12.1.5.3 Precision**—For the components of variance reported in **12.1.5.2**, two averages of observed values should be considered significantly different at the 95 % probability level if the difference equals or exceeds the critical differences listed in **Table 3**.

**NOTE 2**—The tabulated values of the critical differences in **Table 3** should be considered to be a general statement, particularly with respect to between-laboratory precision. Before a meaningful statement can be made about two specific laboratories, the amount of statistical bias, if any, between them must be established; with each comparison being based on recent data obtained on randomized specimens from one sample of the materials to be tested.

**12.1.5.4 Bias**—No justifiable statement on the accuracy of this procedure can be made since the true value of the property cannot be established by an accepted referee method.

**12.2 Electromagnetic Properties**—Determine the magnetic rating on one or more specimens from each lot or unit taken for test, as directed in Test Method **D1118**.

**12.3 Asbestos Content**—Determine the asbestos content as directed in Test Method **D1918**.

## 13. Rejection and Rehearing

**13.1** The purchaser and the seller may agree on a procedure to establish conformance, including control charts furnished by the seller, a sequential sampling plan, or the double-sampling plan outlined in **13.2**.

**13.2** In the absence of a control-chart or sequential-sampling plan, proceed as directed in **13.2.1** through **13.2.3**.

**13.2.1** If the test results for the lot conform to the tolerances for all characteristics specified in Section 4 to 9, consider the lot a valid delivery.

**13.2.2** If the test results for one or more characteristics do not conform to the tolerances, take a new laboratory sample from either the original lot sample or a new lot sample. Test the new sample for the characteristic(s) that did not conform to the tolerances in the first test, and average the results of the first and second samples as if all results were from one test of double the original number of specimens. If the new average(s) conform(s) to the specified tolerances, consider the lot a valid delivery.

**13.2.3** If the test results obtained as directed in **13.2.2** do not conform to the specified tolerances, consider the lot a nonvalid delivery.

## 14. Packaging

**14.1** Asbestos lap, wound on paper tubes, is packaged in rolls that vary in size in accordance with the number of slivers in the assemblage.

<sup>4</sup> Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:D13-1063.

## **15. Keywords**

### **15.1 asbestos; asbestos lap; classification; lap; testing**

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*