



Designation: D1573/D1573M – 95 (Reapproved 2017)

Standard Test Method for Heat Aging of Asbestos Textiles¹

This standard is issued under the fixed designation D1573/D1573M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the heat aging of asbestos textiles. It may be used to determine the resistance to the deterioration of tensile strength at temperatures up to 450°C [800°F].

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 **Warning**—Breathing of asbestos dust is hazardous. Asbestos and asbestos products present demonstrated health risks for users and for those with whom they come into contact. In addition to other precautions, when working with asbestos-cement products, minimize the dust that results. For information on the safe use of chrysotile asbestos, refer to “Safe Use of Chrysotile Asbestos: A Manual on Preventive and Control Measures.”²

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. For specific safety hazard, see 1.3.*

1.5 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This test method is under the jurisdiction of ASTM Committee C17 on Fiber-Reinforced Cement Products and is the direct responsibility of C17.03 on Asbestos - Cement Sheet Products and Accessories.

Current edition approved June 1, 2017. Published July 2017. Originally approved in 1958. Last previous edition approved in 2009 as D1573/D1573M – 95(2009)^{ε1}. DOI: 10.1520/D1573_D1573M-95R17.

² Available from The Asbestos Institute, http://www.chrysotile.com/en/sr_use/manual.htm.

2. Referenced Documents

2.1 ASTM Standards:³

D123 Terminology Relating to Textiles

D1571 Specification for Woven Asbestos Cloth

D1682 Test Method for Breaking Load and Elongation of Textile Fabric (Withdrawn 1992)⁴

D2946 Terminology for Asbestos and Asbestos-Cement Products

3. Terminology

3.1 For textile terms, refer to Terminology D123. For asbestos terms, refer to Terminology D2946.

4. Significance and Use

4.1 This test method covers the evaluation of asbestos textiles with regard to (1) quality and (2) elevated temperature serviceability characteristics. Since asbestos textiles are usually composed of blends of asbestos with cotton or other organic carrier fibers, the latter being present in amounts up to 25 %, temperatures above 150°C [300°F] will promote the degradation of the cotton content and will reduce the structural reinforcement derived therefrom. In the higher grade asbestos textiles, wherein little or no carrier fibers are used and in which the longer asbestos fibers are necessary if a satisfactory yarn is to be produced, the degradation in strength resulting from heat-aging up to 540°C [1000°F] is low. In the case of the lower grade asbestos textiles, however, wherein amounts from 15 to 25 % carrier fibers are incorporated, asbestos fibers having shorter lengths may be utilized. Under the relatively low service temperatures to which such materials may be subjected, neither the cotton nor the cloth properties are greatly affected. However, the strength-imparting influence of the carrier fibers is reduced at elevated temperatures and the entwining properties of the shorter asbestos fibers primarily

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

serve to establish the resultant tensile strength and other physical properties of the textile. In view of this, elevated temperature tests may serve to indicate the asbestos fiber grade or quality that may be used in a textile construction.

4.2 Another use and perhaps more practical application for the information to be derived from elevated temperature studies is the revelation of the ability of a subject textile to withstand known elevated temperature service conditions. It will be appreciated that temperature alone may not be the only degrading influence in the destruction of such materials; however, under normal operating conditions, high temperatures are usually the dominating factors in such degradation. The results obtained through such investigations therefore may be interpreted in terms of elevated temperature serviceability.

5. Apparatus

5.1 Test Oven:

5.1.1 The oven shall be electrically heated and have the necessary controls to maintain temperatures to within $\pm 3^{\circ}\text{C}$ [5.4°F] at any designated testing temperature up to 430°C [800°F] and shall have determinable and controllable air circulation. The air circulation provisions shall be capable of delivering between 3 and 6 m^3/min [100 and 200 ft^3/min] continuously to the oven during the testing period.

5.1.2 The minimum inside dimensions of the oven shall be 500 by 500 by 500 mm [18 by 18 by 18 in.], and it shall be provided with two hardware cloth trays, 20 mm [0.75 in.] mesh, at least 500 by 500 mm [18 by 18 in.], upon which the test specimens may be deployed.

5.2 The temperature indicating device shall be a chromel-alumel thermocouple, or its equivalent, coupled with an accurate potentiometer capable of being calibrated and adjusted to compensate for room temperature and cold junction differentials. Other devices ensuring at least equal precision and accuracy may be used.

6. Hazards

6.1 **Warning**—see 1.3.

7. Preparation of Apparatus

7.1 When starting a test, the oven temperature controls shall be set at the desired test temperature at the beginning of the heating-up period. The oven temperatures shall be determined by placing the junction of the thermocouple on a specimen of cloth supported on the upper hardware cloth tray, which will be located not less than 150 mm [6 in.] from the top of the oven nor less than 150 mm [6 in.] above the next lower tray.

7.2 Air circulation shall be maintained continually from the beginning of the heating period throughout the test cycle. The initial heating-up period, during which no test specimens shall be in the oven, shall be maintained for a minimum of 2 h or until such a time as the oven conditions have attained the degree of stability that will assure temperature variations no greater than prescribed in 5.1.1.

8. Procedure

8.1 Time and Temperature for Test:

8.1.1 All cloths shall be tested for a period of 2 h.

8.1.2 The temperature for testing shall be dependent upon the grade of the material under investigation, as follows:

Commercial Grade	204°C [400°F]
Underwriter's Grade	204°C [400°F]
Grade A	316°C [600°F]
Grade AA	316°C [600°F]
Grade AAA	427°C [800°F]
Grade AAAA	427°C [800°F]

8.1.2.1 Grades are defined in Specification **D1571**.

8.2 *Deployment of Test Samples in Oven*—Following the attainment of stabilized conditions, specimens of the samples under test shall be individually positioned on the wire mesh trays. There shall be not less than 150 mm [6 in.] placed in the oven and not more than 150 mm [6 in.] between the top tray and the top of the oven or between the bottom tray and the bottom of the oven. With a hearth size 500 by 500 mm [18 by 18 in.] the individual trays will be 500 by 500 mm [18 by 18 in.] and on each may be positioned 12 individual grade test specimens. The placements shall be made as quickly as possible so that the oven door will remain open for a minimum length of time in order that the oven temperature may not drop markedly below the testing temperature in accordance with Test Methods **D1682**.

8.3 Immediately upon closing the oven door begin the test period and continue the test for 2 h.

8.4 Upon completion of the test period, remove the specimens from the oven and permit them to condition at room temperature for 35 ± 5 min. Following this conditioning period, test the specimens for tensile strength. It is to be understood that tensile strength values (**Note 1**) and tensile strength retention values must be established on the basis of cloth constructions, as well as grade, and should be considered individually.

NOTE 1—The determination of actual strength values and the decision as to whether such values of tensile strength shall be in terms of kilograms (pounds) break resistance by the grab method or in terms of the percentage strength retention based on the grab test breaks are matters that can best be determined on the basis of the ultimate use to which such information is to be applied.

9. Report

9.1 Fully identify the samples tested.

9.2 Report the tensile strength values and tensile strength retention values in terms of breaking load in Newtons or pounds force and also in terms of the percentage strength retention based on the grab test breaks (**Note 1**).

10. Precision and Bias

10.1 *Precision*—The variance introduced into the eventual tensile test results obtained on specimens heat-treated by this test method is statistically insignificant compared against the inter-specimen variance and the variance due to the tensile test method.

10.2 *Bias*—Bias cannot be established on asbestos textiles for lack of a referee method.

11. Keywords

11.1 aging; asbestos; heat; heat-aging; tensile; textile

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>