

Designation: D1865/D1865M - 09 (Reapproved 2017)

Standard Test Method for Hardness of Mineral Aggregate Used on Built-Up Roofs¹

This standard is issued under the fixed designation D1865/D1865M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of hardness of all types of mineral surfacing for use on built-up roofs and is intended to provide an index of their ability to withstand physical breakdown in handling.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- D75/D75M Practice for Sampling Aggregates
- D451/D451M Test Method for Sieve Analysis of Granular Mineral Surfacing For Asphalt Roofing Products
- E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

3. Summary of Test Method

3.1 Mineral aggregate is empirically evaluated for degree of breakdown into smaller pieces. The procedure calls for a sample, free of fines, to be dropped a nominal distance of 1.2 m [4 ft] 400 times while inside a standardized test apparatus.

4. Significance and Use

4.1 This test method measures the resistance to physical breakdown in handling of built-up roofing aggregates.

5. Apparatus

5.1 A 1.2-m [4-ft] length of clean 50-mm [2-in.] iron pipe fitted with a removable screw cap on both ends, and mounted on a suitable stand so that it can be rotated about an axis perpendicular to the long dimension of the pipe.

5.2 *Balance*, 500-g [1 lb] capacity, sensitive to 0.01 % of the capacity.

5.3 Sample Splitter, riffle-type.

5.4 *Sieves*—A series of square-opening sieves, 8 in. in diameter, conforming to the requirements prescribed in Specification E11 and consisting of the following:

Sieve Designation	
9.5-mm	[¾ in.]
6.3-mm	[¼ in.]
3.35-mm	[No. 6]

A solid collecting pan shall be fitted to the bottom of the stack of sieves.

5.5 *Mechanical Sieve Shaker*, conforming to the requirements prescribed in Test Method D451/D451M.

6. Sampling

6.1 Sample aggregates received in bulk in accordance with Practice D75/D75M.

6.2 For aggregates received in bags or small containers, select a number of bags or small containers at random equivalent to the cube root of the total number in the shipment.

7. Procedure

7.1 Fractionate the aggregate, previously dried at 110° C [230°F] utilizing the riffle-type sample splitter, until a fraction is obtained that will permit the recovery, after hand sieving, of about 227 g [0.5-lb] of aggregate passing through the 9.5-mm [3/8-in.] sieve and retained on the 6.3-mm [1/4-in.] sieve.

7.2 Place the 9.5-mm [$\frac{3}{e}$ -in.] and 6.3-mm [$\frac{1}{4}$ -in.] sieves containing the 227 g [0.5-lb] sample on the mechanical sieve shaker and agitate for 10 min to ensure complete removal of the finer materials.

7.3 Weigh out 200 g [0.44 lb] of the aggregate retained on the 6.3-mm [$\frac{1}{4}$ -in.] sieve and place inside the 50-mm [2-in.] pipe tester. Screw the caps tightly in place. Beginning with the pipe in a substantially vertical position, rotate the pipe in an arc of 180°, reverse direction, and repeat this action by turning

¹ This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.03 on Surfacing and Bituminous Materials for Membrane Waterproofing and Built-up Roofing.

Current edition approved Jan. 1, 2017. Published January 2017. Originally approved in 1961. Last previous edition approved in 2009 as D1865/D1865M – 09. DOI: 10.1520/D1865_D1865M-09R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D1865/D1865M – 09 (2017)

end-for-end 200 complete revolutions (400 half turns), controlling the rate of travel so that the aggregate drops cleanly without sliding.

7.4 At the end of the test, unscrew the top cap, turn the pipe over, and empty the contents onto a nest consisting of the 6.3-mm [¼-in.] and No. 6 [3.35-mm] sieves and the pan. Tap the tube sharply to remove all of the sample. Place the nest of sieves in the mechanical sieve shaker and run for 5 min. Carefully weigh the portion of the sample retained on each of the sieves and on the pan to an accuracy of 2×0.1 g [10^{-4} -lb].

8. Report

8.1 Record the percentage retained on each sieve and in the pan to the nearest 0.1 % on the basis of the original sample weight.

8.2 Report the breakdown of the mineral surfacing as the percentage passing the No. 6 [3.35-mm] sieve, on the basis of the original sample weight.

9. Precision and Bias

9.1 The following data should be used for judging the acceptability of results (95 % probability) on samples from the same lot from the same supplier.

9.1.1 Duplicate results by the same operator should not be considered suspect unless they differ by more than the following amount:

Breakdown Range, %	Repeatability, percentage points
0 to 15	±5

9.1.2 The results submitted by each of two laboratories should not be considered suspect unless they differ by more than the following amount:

Breakdown Range, %	Reproducibility, percentage points
0 to 25	±10

9.2 *Bias*—The procedure in Test Method D1865/D1865M for measuring the hardness of mineral aggregate has no bias because the value obtained can be defined only in terms of the test method.

10. Keywords

10.1 aggregate fiber; built-up roofs; mineral aggregate; sieve analysis

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/