



Designation: D2397/D2397M – 17

Standard Specification for Cationic Emulsified Asphalt¹

This standard is issued under the fixed designation D2397/D2397M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification covers seven grades of cationic emulsified asphalt for use in pavement construction in the manner designated.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

D5/D5M Test Method for Penetration of Bituminous Materials

D113 Test Method for Ductility of Bituminous Materials (Withdrawn 2016)³

D140/D140M Practice for Sampling Asphalt Materials

D244 Test Methods and Practices for Emulsified Asphalts

D2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene

D3910 Practices for Design, Testing, and Construction of Slurry Seal

D6930 Test Method for Settlement and Storage Stability of Emulsified Asphalts

D6933 Test Method for Oversized Particles in Emulsified Asphalts (Sieve Test)

D6935 Test Method for Determining Cement Mixing of Emulsified Asphalt

D6936 Test Method for Determining Demulsibility of Emulsified Asphalt

D6997 Test Method for Distillation of Emulsified Asphalt

D7226 Test Method for Determining the Viscosity of Emulsified Asphalts Using a Rotational Paddle Viscometer

D7402 Practice for Identifying Cationic Emulsified Asphalts

D7496 Test Method for Viscosity of Emulsified Asphalt by Saybolt Furol Viscometer

D7553 Test Method for Solubility of Asphalt Materials in N-Propyl Bromide

3. Requirements

3.1 The emulsified asphalt shall be tested within 14 days of delivery. The emulsified asphalt shall be homogeneous after thorough mixing provided separation has not been caused by freezing. Emulsions separated by freezing shall not be tested.

3.2 Emulsified asphalt shall conform to the requirements prescribed in Table 1. Specify the test method to be used. Specify either Test Method D7226 or D7496.

4. Sampling

4.1 Samples of emulsified asphalt shall be taken in accordance with Practice D140/D140M.

4.2 Samples shall be stored in clean, airtight sealed containers at a temperature of not less than 4 °C [39.2 °F] until tested.

5. Test Methods

5.1 The properties of the emulsified asphalts given in Table 1 shall be determined in accordance with the following ASTM standards:

5.1.1 Viscosity—Test Method D7496 or D7226 for Table 1.

5.1.2 Storage Stability—Test Method D6930.

5.1.3 Demulsibility—Test Method D6936.

5.1.4 Coating Ability and Water Resistance—Test Methods D244.

5.1.5 Particle Charge—Practice D7402.

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.41 on Emulsified Asphalt Specifications.

Current edition approved June 1, 2017. Published June 2017. Originally approved in 1965. Last previous edition approved in 2013 as D2397/D2397M – 13. DOI: 10.1520/D2397_D2397M-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.



TABLE 1 Requirements for Cationic Emulsified Asphalt

NOTE 1—CQS-1h emulsions shall meet the requirements outlined in Practices D3910.

NOTE 2—CQS-1h is used for quick-set slurry seal systems.

Type Grade	Rapid-Setting				Medium-Setting				Slow-Setting				Quick-Setting	
	CRS-1		CRS-2		CMS-2		CMS-2h		CSS-1		CSS-1h		CQS-1h	
	min	max	min	max	min	max	min	max	min	max	min	max	min	max
<i>Test on Emulsions:</i>														
Viscosity, Saybolt Furol at 25 °C (77 °F) SFS														
Viscosity, Saybolt Furol at 50 °C (122 °F) SFS	20	100	100	400	50	450	50	450	20	100	20	100	20	100
Viscosity, Rotational Paddle Viscometer at 25 °C (77 °F) mPa s														
Viscosity, Rotational Paddle Viscometer at 50 °C (122 °F) mPa s	45	220	220	880	110	990	110	990	45	220	45	220	45	220
Coating ability and water resistance:														
Coating, dry aggregate					good			good						
Coating, after spraying					fair			fair						
Coating, wet aggregate					fair			fair						
Coating, after spraying					fair			fair						
Particle charge test					positive			positive					positive	
Sieve test, % ^A	positive	0.10			0.10			0.10	positive	0.10	positive	0.10	positive	0.10
Cement mixing test, %										2.0		2.0		N/A
Distillation:														
Oil distillate, by volume of emulsion, %														
Residue, %	60	3	65	3	65	12	65	12	57		57		57	
<i>Tests on Residue from Distillation Test:</i>														
Penetration, 25 °C (77 °F), 100 g, 5 s	100	250	100	250	100	250	40	90	100	250	40	90	40	90
Ductility, 25 °C (77 °F), 5 cm/min, cm	40		40		40		40		40		40		40	
Solubility in trichloroethylene, %	97.5		97.5		97.5		97.5		97.5		97.5		97.5	

^AThis test requirement on representative samples is waived if successful application of the material has been achieved in the field.



5.1.6 *Sieve Test*—Test Method **D6933**, except use distilled water in all wetting and washing operations in place of the nonionic surfactant solution (1 %).

5.1.7 *Cement Mixing*—Test Method **D6935**.

5.1.8 *Distillation*—Test Method **D6997**.

5.1.9 *Tests on Residue from Distillation*—Test Methods **D5/D5M**, **D113**, **D2042**, and **D7553**.

6. Keywords

6.1 cationic; emulsified asphalt; emulsion; medium setting; rapid setting; slow setting

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>