



Standard Specification for Mineral Filler For Bituminous Paving Mixtures¹

This standard is issued under the fixed designation D242/D242M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers mineral filler added as a separate ingredient for use in bituminous paving mixtures.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 The text of this standard references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

2. Referenced Documents

2.1 *ASTM Standards*:²

C50 Practice for Sampling, Sample Preparation, Packaging, and Marking of Lime and Limestone Products

C183 Practice for Sampling and the Amount of Testing of Hydraulic Cement

C311 Test Methods for Sampling and Testing Fly Ash or Natural Pozzolans for Use in Portland-Cement Concrete

D546 Test Method for Sieve Analysis of Mineral Filler for Bituminous Paving Mixtures

¹ This specification is under the jurisdiction of ASTM Committee D04 on Road and Paving Materials and is the direct responsibility of Subcommittee D04.50 on Aggregate Specifications.

Current edition approved June 1, 2014. Published October 2014. Originally approved in 1926. Last previous edition approved in 2009 as D242/D242M – 09. DOI: 10.1520/D0242_D0242M-09R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D4318 Test Methods for Liquid Limit, Plastic Limit, and Plasticity Index of Soils

3. General Description

3.1 Mineral filler shall consist of finely divided mineral matter such as rock dust, slag dust, hydrated lime, hydraulic cement, fly ash, loess, or other suitable mineral matter. At the time of use, it shall be sufficiently dry to flow freely and essentially free from agglomerations.

4. Physical Requirements

4.1 Mineral filler shall be graded within the following limits:

Sieve	Percent Passing (by Mass)
1.18 mm [No. 16]	100
600- μ m [No. 30]	97 to 100
300- μ m [No. 50]	95 to 100
75- μ m [No. 200]	70 to 100

4.2 Mineral Filler prepared from rock dust, slag dust, loess, and similar materials shall be essentially free from organic impurities and have a plasticity index not greater than 4.

NOTE 1—Plasticity index limits are not appropriate for hydrated lime and hydraulic cement.

5. Methods of Sampling and Testing

5.1 Sample the mineral filler according to Practice **C50**, **C183**, or Test Methods **C311**, whichever is most appropriate for the material being sampled, except as noted in 5.1.1.

5.1.1 Obtain samples at random intervals not to exceed each 300 tons of material as delivered.

5.2 The minimum size of field samples shall be 5.0 kg [11 lbs]. Reduce the field sample to a minimum size of 2.5 kg [5 lbs] for testing.

5.3 Determine the grading of the material by Test Method **D546**.

5.4 Determine the plasticity index by Test Method **D4318**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>