



## Standard Specification for Asphalt Used in Canal, Ditch, and Pond Lining<sup>1</sup>

This standard is issued under the fixed designation D2521/D2521M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

<sup>ε1</sup> NOTE—Units information was editorially corrected in January 2014.

### 1. Scope

1.1 This specification covers an oxidized petroleum asphalt, which, when applied in a sufficient thickness over a suitable subgrade and covered with a suitable cover material, will provide a satisfactory waterproof membrane for use as a canal, ditch, and pond lining.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system should be used independently of the other. Combining values in any way may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

- D5 Test Method for Penetration of Bituminous Materials
- D6 Test Method for Loss on Heating of Oil and Asphaltic Compounds
- D92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester
- D113 Test Method for Ductility of Bituminous Materials
- D140 Practice for Sampling Bituminous Materials
- D2042 Test Method for Solubility of Asphalt Materials in Trichloroethylene

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.03 on Surfacing and Bituminous Materials for Membrane Waterproofing and Built-up Roofing.

Current edition approved Jan. 1, 2014. Published January 2014. Originally approved in 1966. Last previous edition approved in 2008 as D2521 – 76 (2008) DOI: 10.1520/D2521-76R14E01.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D2398 Test Method for Softening Point of Bitumen in Ethylene Glycol (Ring-and-Ball) (Withdrawn 1984)<sup>3</sup>

### 3. Physical Requirements

3.1 The asphalt shall not foam when heated to 205°C [400°F], and shall conform to the requirements prescribed in Table 1.

3.2 At the purchaser's option, phosphorus pentoxide (P<sub>2</sub>O<sub>5</sub>) may be specified as a catalyst or blowing aid in the preparation of the membrane asphalt.

### 4. Sampling and Test Methods

4.1 Sample the material and determine the properties enumerated in this specification in accordance with the following methods:

- 4.1.1 Sampling—Practice D140.
- 4.1.2 Softening Point—Test Method D2398.
- 4.1.3 Penetration—Test Method D5.
- 4.1.4 Ductility—Test Method D113.
- 4.1.5 Flash Point—Test Method D92.
- 4.1.6 Solubility in Trichloroethylene—Test Method D2042.
- 4.1.7 Loss on Heating—Test Method D6.

### 5. Inspection

5.1 Inspection of the material shall be agreed upon between the purchaser and the seller as part of the purchase contract.

### 6. Rejection and Resubmittal

6.1 Failure to conform to any of the requirements prescribed in this specification shall constitute grounds for rejection. In case of rejection, the seller shall have the right to reinspect the rejected material and resubmit the lot after removal of the packages not conforming to the requirements.

### 7. Keywords

7.1 bituminous materials; canal lining; ditch lining; membrane asphalt

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

**TABLE 1 Requirements for Asphalt for Use in Waterproof Membrane Construction**

Property	min	max
Softening point (ring and ball), °C [°F]	79 [175]	93 [200]
Penetration of original sample, 0.1 mm:		
at 25°C [77°F], 100 g, 5 s	50	60
at 0°C [32°F], 200 g, 60 s	30	...
at 46°C [115°F], 50 g, 5 s	...	120
Ductility at 25°C [77°F], mm	35	...
Flash point (Cleveland open cup), °C [°F]	218 [425]	...
Solubility in trichloroethylene, %	97.0	...
Loss on heating, %	...	1.0
Penetration after loss on heating, % of original at 25°C [77°F], 100 g, 5 s	60	...

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the ASTM website ([www.astm.org](http://www.astm.org)/COPYRIGHT/).*