



## Standard Test Method for Adhesion of Asphalt-Roof Cement to Damp, Wet, or Underwater Surfaces<sup>1</sup>

This standard is issued under the fixed designation D3409/D3409M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

---

<sup>ε1</sup> NOTE—Units information was editorially corrected in January 2016.

---

### 1. Scope

1.1 This test method covers the determination of the adhesion of asphalt roofing cements to damp, wet, or underwater surfaces.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Summary of Test Method

2.1 A metal lid is covered with a coating of asphalt roofing cement and immersed in water. A similar metal lid which has been flamed and wet with water is pressed on the asphaltic surface. The degree of adhesion is evaluated by estimating the percentage of area covered by the cement on the water-wet flamed metal lid.

### 3. Significance and Use

3.1 This test method offers a means of evaluating the adhesive properties of asphalt roofing cements used to repair roofs under adverse conditions. Weathered roof surfaces are easily coated with asphalt roofing cements when they are dry, however when wet or during a rain, asphalt roofing cements may not adhere readily to water-wet surfaces such as metal flashings or asphalt roll roofing. The flamed metal lids used in this test method simulate weathered roof surfaces.

---

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.05 on Solvent-Bearing Bituminous Compounds for Roofing and Waterproofing.

Current edition approved Jan. 1, 2016. Published January 2016. Originally approved in 1975. Last previous edition approved in 2008 as D3409 – 93 (2008). DOI: 10.1520/D3409\_D3409M-93R16E01.

### 4. Apparatus

4.1 *Metal Lids*<sup>2</sup>—Slip-on covers supplied with 89-mL [3-fluid oz] capacity seamless metal containers, approximately 55 mm in diameter and with a raised rim 1 mm high and 3 mm wide.

4.2 *Water Bath*—A bath with a flat bottom surface having a capacity of at least 1 L [1 qt] which can be filled with tap water to a minimum depth of 51 mm [2 in.] and maintained at  $20 \pm 3^\circ\text{C}$  [ $68 \pm 5^\circ\text{F}$ ].

### 5. Sampling

5.1 Stir the sample thoroughly to ensure homogeneity before removing a portion for testing.

5.2 If the size of the sample is 4 L [1 gal] or over, a portion may be removed and stored in a 1-L [1-qt] triple-seal, friction-top can.

### 6. Procedure

6.1 Spread 5 g of the cement on the top surface of each of three metal lids and place them in the water bath.

6.2 Flame three other metal lids in an open gas flame until each entire lid has an oxidized blue-gray surface and place them in the water bath after they have cooled to room temperature.

6.3 After 5 min, place a flamed lid on top of each cement-covered lid, and press only on the rim of the flamed lid for 1 min or until the flow of the cement stops.

NOTE 1—Covers that have a raised rim [1 mm] on the top surface are intended for this test. When the two lids are pressed together, approximately 4 g of the 5-g sample will be contained between the surfaces. If lids with raised rims are not available, smooth lids may be used except that care should be exercised in pressing the lids together to prevent squeezing out all of the sample.

6.4 Remove each set of lids from the water bath and scrape off the excess cement around the edges with a spatula or knife.

---

<sup>2</sup> Deep Style 22 Seamless Cans, available from Ellisco Inc., Myers Div., 6850 River Rd., Pennsauken, NJ 08110, have been found satisfactory for this purpose.

6.5 Separate the lids without twisting and estimate the percentage of area covered by the cement on each of the flamed lids.

## **7. Report**

7.1 Report the average of the three estimates on coverage of the cement on the flamed lids as the adhesion, in percent, at 20°C [68°F].

NOTE 2—There may be a need for testing at lower temperatures. Committee D08 would welcome data supporting suitable modifications.

## **8. Precision**

8.1 The precision of this test method has not yet been determined.

## **9. Keywords**

9.1 adhesion; asphalt cement; wet surface

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*