



Standard Test Method for the Compatibility of Mechanical Pump Dispenser Components¹

This standard is issued under the fixed designation D4333/D4333M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Units information was corrected editorially in March 2011.

1. Scope

1.1 This test method covers testing of the components of mechanical pump dispensers (spray or flow types) for compatibility with products.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 *This standard may involve hazardous materials, operations, and equipment. This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Significance and Use

2.1 This test method identifies the compatibility of the mechanical pump dispenser components with consumer-type products.

3. Apparatus

3.1 *Balance*, accurate to 1 mg.

3.2 *Micrometers*, or calipers or other appropriate instruments, capable of measuring dimensions of test specimens to 0.025 mm [0.001 in.].

3.3 *Glass Containers*, with covers, suitable for immersing test specimens in test products.

3.4 *Oven*, with chamber capable of maintaining temperature within $\pm 2^{\circ}\text{C}$ [$\pm 3.6^{\circ}\text{F}$] of the specified test temperatures.

4. Test Specimen

4.1 At least three individual components should be used for each part tested with each product involved at each test condition.

4.2 At least three individual components are used as controls at each test condition.

4.3 Individual unassembled components shall be clean and previously unused.

5. Conditioning

5.1 Condition test specimens at $23 \pm 3^{\circ}\text{C}$ [$73.4 \pm 5.4^{\circ}\text{F}$] for at least 4 h prior to testing. If test specimen conditioning is not possible, the environmental conditioning of the test specimens tested should be included in the report as discussed in 7.1.

5.2 Test conditions shall be an elevated temperature of $45 \pm 3^{\circ}\text{C}$ [$113 \pm 5.4^{\circ}\text{F}$] and an ambient room temperature of $23 \pm 3^{\circ}\text{C}$ [$73.4 \pm 5.4^{\circ}\text{F}$]. If a different temperature is used, this should be noted in the test report discussed in 7.1.

6. Procedure

6.1 Dimensional and Weight Changes:

6.1.1 Prior to immersion into the product, weigh the part and record as W1 (see 7). Measure the thickness or overall length of the part to the nearest 0.025 mm [0.001 in.] of each component depending on which of these dimensions are most important (for example, thickness for a gasket or liner, and overall length for a molded component). Optionally, measure a diameter of the part to its nearest 0.025 mm [0.001 in.]. Report the data as initial dimension D1 (see 7). This data is reported as a mean value of the dimension for the components measured for that particular part.

6.1.2 Maintain at least three test specimens as visual comparison controls. Do not immerse these control test specimens in any solution and store at each test condition. Label the storage container of these test specimens as control.

6.1.3 Place the test specimens in appropriate containers for the solutions being used and allow the test specimens to be totally immersed in fresh test product for 7 days in each test condition. Several test specimens of a given material may be

¹ This test method is under the jurisdiction of ASTM Committee D10 on Packaging and is the direct responsibility of Subcommittee D10.33 on Mechanical Dispensers.

Current edition approved Oct. 1, 2010. Published March 2011. Originally approved in 1984. Last previous edition approved in 2005 as D4333 – 05. DOI: 10.1520/D4333_D4333M-05R10E01.

immersed in the same container provided sufficient product is available for the total surface area exposed. Cover the container.

NOTE 1—When the components being tested are of the same type but of different material, it is recommended that separate glass containers are used for each material for the purpose of eliminating unplanned material interactions and for ease of identification.

6.1.4 After 7 days, remove all glass containers of test specimens from the 45°C environment, and allow the test specimens to equilibrate to room temperature [23°C] for a minimum of 4 h.

6.1.5 Carefully remove each test specimen from the glass container, wipe dry, and remeasure the dimension(s) on each part as they were measured in 6.1.1. Be careful not to damage or distort the parts during removal. Measure parts immediately. Report the mean value of the dimensions measured at this time as D2 (see 7.1).

6.1.6 Weigh the test parts separately and report in 7 as W2.

6.1.7 Observe the appearance of each test specimen after exposure to the test product and compare the test specimens to the controls described in 6.1.2. Observe and report appearance on the basis of examination for loss of gloss, developed texture, decomposition, discoloration, swelling, clouding, tackiness, rubberiness, crazing, bubbling, cracking, solubility, and so forth.

6.1.8 Return test specimens to the test products and allow exposure in their respective environments for an additional 21 days.

6.1.9 After a total exposure of 28 days, remove the test specimens and repeat 6.1.5 and 6.1.7. Report the mean value of the final dimensions as D3 (see 7.1).

6.1.10 After a total exposure of 28 days, remove the test specimen and repeat 6.1.5 and 6.1.7. Report the mean value of the final weighs as W3 (see 7.1).

7. Report

7.1 The report shall include the following:

7.1.1 Complete identification of the material tested including type, source, manufacturer's code, and information as appropriate,

7.1.2 Temperature of tests,

7.1.3 Test product(s),

7.1.4 Duration of immersion,

7.1.5 D1 data, that is, initial thickness, overall length, or diameter(s), or a combination thereof, to the nearest 0.025 mm [0.001 in.],

7.1.6 D2 data, that is, thickness, overall length, or diameter(s), or a combination thereof, after immersion to the nearest 0.025 mm [0.001 in.],

7.1.7 D3 data, that is, final thickness, overall length, or diameter(s), or a combination thereof, after immersion to the nearest 0.025 mm [0.001 in.],

7.1.8 The percentage dimensional change for the first 7 days to the nearest 0.1 %, as calculated based upon the formula $(D2-D1)/D1 \times 100$ in which positive percentages signify swell and negative outcomes signify shrinkage,

7.1.9 The percentage dimensional change for the 28 days to the nearest 0.1 %, as calculated based upon the formula $(D3-D1)/D1 \times 100$ in which positive percentages signify shrinkage and negative outcomes signify swell, and

7.1.10 General appearance of test specimens after immersion along with the appearance of the product.

7.1.11 W1—initial weight data within two decimal places.

7.1.12 W2—7-day weight data within two decimal places.

7.1.13 W3—28-day weight data within two decimal places.

7.1.14 The percentage weight change for the first 7 days to the nearest 0.1 %, as calculated based upon the formula $(W2-W1) \times 100$, in which positive percentages signify swell and negative outcomes signify shrinkage.

7.1.15 The percentage weight change for 28 days to the nearest 0.1 %, as calculated based upon the formula $(W3-W1)/W1 \times 100$, in which positive percentages signify swell and negative outcomes signify shrinkage.

8. Precision and Bias

8.1 *Precision*—The precision of Test Method D4333 is highly dependent on the particular component material and contents tested. One laboratory has investigated one particular polyethylene pump gasket and a hair spray product with three replicate tests, yielding the results given in Table 1. Other pumps and contents will have other averages of dimensional changes due to chemical compatibility and will have more or less variability between replicate tests. Users of this test method are encouraged to reference historical files of previous tests of similar pump components and contents for an estimate of within-laboratory repeatability. Because of this strong product and component material dependency, further investigation of repeatability and reproducibility is not practicable.

8.2 *Bias*—Test Method D4333 has no bias because an accepted reference or referee value is not available.

9. Keywords

9.1 chemical resistance; compatibility; mechanical pump dispenser components

TABLE 1 Interlaboratory Test Results

	Thickness					Diameter				
	Average, in.	Shrink or Swell, %	Standard Deviation, in.	Maximum, in.	Minimum, in.	Average, in.	Shrink or Swell, %	Standard Deviation, in.	Maximum, in.	Minimum, in.
Initial	0.0613	. . .	0.0006	0.062	0.061	0.8548	. . .	0.002	0.8566	0.8530
7-day	0.0613	0	0.0006	0.062	0.061	0.8546	0.02	0.002	0.8566	0.8526
28-day	0.0623	1.63 swell	0.0006	0.063	0.062	0.8556	shrink 0.09 swell	0.006	0.8573	0.8539

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).