



# Standard Performance Specification for Knitted Upholstery Fabrics for Indoor Furniture<sup>1</sup>

This standard is issued under the fixed designation D4771/D4771M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This performance specification covers the performance requirements for knitted upholstery fabrics as used in the manufacture of new indoor furniture for general domestic use. These requirements apply to both the wale and course directions for those factors where each fabric direction is pertinent.

1.2 This performance specification is not applicable to fabrics used in contract, porch, deck, or lawn furniture; nor for woven fabrics, bonded or laminated fabrics, or surface-coated fabrics (such as vinyls and urethanes).

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 The following safety hazards caveat pertains only to the test methods described in this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* See [Note 2](#).

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

[D123 Terminology Relating to Textiles](#)

[D4033 Test Method for Resistance to Yarn Slippage at the Sewn Seam in Upholstery Fabrics \(Dynamic Fatigue](#)

[Method\)](#) (Withdrawn 2001)<sup>3</sup>

[D7023 Terminology Relating to Home Furnishings](#)

[2.2 AATCC Methods:](#)<sup>4</sup>

[8 Colorfastness to Crocking: AATCC Crockmeter Method](#)

[16 Colorfastness to Light](#)

[23 Colorfastness to Burnt Gas Fumes](#)

[107 Colorfastness to Water](#)

[116 Colorfastness to Crocking: Rotary Vertical Crockmeter Method](#)

[129 Colorfastness to Ozone in the Atmosphere Under High Humidities](#)

[Evaluation Procedure No. 1 Gray Scale for Color Change](#)

[Evaluation Procedure No. 2 Gray Scale for Staining](#)

[Evaluation Procedure No. 9—Step AATCC Chromatic Transference Scale](#)

[2.3 Federal Standard:](#)

[16CFR, Chapter II—Consumer Product Safety Commission, Subchapter D—Flammable Fabrics Act Regulations](#)<sup>5</sup>

[2.4 Military Standard:](#)

[ASQ/ANSI Z1.4 Sampling Procedures and Tables for Inspection by Attributes](#)<sup>6</sup>

[2.5 Other Documents:](#)

[Joint Industry Knit Upholstery Fabric Standards and Guidelines](#)<sup>7</sup>

[Guides for the Household Furniture Industry](#)<sup>8</sup>

[California Bulletin 117](#)<sup>9</sup>

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

<sup>4</sup> *AATCC Technical Manual*, available from American Association of Textile Chemists and Colorists (AATCC), P.O. Box 12215, Research Triangle Park, NC 27709, <http://www.aatcc.org>.

<sup>5</sup> Available from Superintendent of Documents, U.S. Government Printing Office, Washington, DC 20402.

<sup>6</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

<sup>7</sup> Issued 1980, available from American Furniture Manufacturers Association, Box HP-7, High Point, NC 27261.

<sup>8</sup> Available from the Bureau of Consumer Protection, Federal Trade Commission, Washington, DC 20580. Promulgated by the FTC on Dec. 21, 1973, to be effective on March 21, 1974.

<sup>9</sup> Available from California Department of Consumer Affairs, Bureau of Home Furnishings, 3485 Orange Grove Ave., North Highlands, CA 95660.

<sup>1</sup> This performance specification is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.63 on Home Furnishings.

Current edition approved Sept. 1, 2009. Published September 2009. Originally approved in 1988. Last previous edition approved in 2008 as D4771 – 02(2008). DOI: 10.1520/D4771\_D4771M-09.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



## UFAC Fabric Classification Test Method for Cigarette Smolder Resistance<sup>10</sup>

NOTE 1—Reference to test methods in this specification give only the permanent part of the designation of ASTM, AATCC, or other test methods. The current editions of each test method cited shall prevail.<sup>11</sup>

### 3. Terminology

3.1 For all terminology relating to D13.54, Home Furnishings refer to Terminology **D7023**

3.1.1 The following terms are relevant to this specification: contract furniture, indoor furniture, upholstery fabric, upholstered furniture.

3.2 For definitions of other textile terms used in this specification, refer to Terminology **D123**, **D7023**. Definitions found in a dictionary of common terms are suitable for terms used in this specification.

### 4. Specification Requirements

4.1 The properties of knitted upholstery fabrics shall conform to the specification requirements in **Table 1**.

### 5. Significance and Use

5.1 Fabrics intended for this end-use should meet all of the requirements listed in **Table 1**.

<sup>10</sup> Available from UFAC Central, Box 2436, High Point, NC 27261.

<sup>11</sup> The carbon-arc and xenon fade-ometers available from the Atlas Electric Devices Co., 4114 N. Ravenswood Ave., Chicago, IL 60613, have been found satisfactory for this test method.

**TABLE 1 Specification Requirements**

Characteristics	Requirements	Section
Resistance to yarn slippage	½ in. max at 7000 cycles	<b>6.1</b>
Dimensional change:		
Wale or course	5.0 % shrinkage max, to 2.0 % gain max	<b>6.2</b>
Colorfastness to: <sup>A</sup>		
Water, Color Change	Grade 4 <sup>B</sup> min	<b>6.3</b>
Solvent, Color Change	Grade 4 <sup>B</sup> min	<b>6.4</b>
Crocking:		
Dry	Grade 4 <sup>C</sup> min	<b>6.5</b>
Wet	Grade 3 <sup>C</sup> min	<b>6.5</b>
Burnt gas fumes—2 cycles	Grade 4 <sup>B</sup> min	<b>6.6</b>
Light—40 AATCC Fading Units	Grade 4 <sup>B</sup> min	<b>6.7</b>
Ozone 1 cycle	Grade 4 <sup>B</sup> min	<b>6.8</b>
Retention of hand, character, and appearance	Shall not change more than limitations set by prior agreement between the buyer and the seller	<b>6.9</b>
Durability of back coating	No peeling or cracking of the backcoating shall occur; durability shall be compatible with cleaning code	<b>6.10</b>
Flammability:		
California Bulletin 117	pass	<b>6.11.1</b>
UFAC Fabric Classification	Class I—vertical char length is equal to or less than 1.75 in. Class II—vertical char length is greater than 1.75 in.	<b>6.11.2</b>
FTC Requirements	pass	<b>6.12</b>

<sup>A</sup> The grade rating in the colorfastness requirements is based on a numerical scale of 5 for negligible for no color change or color transfer to 1 for very severe color change or color transfer.

<sup>B</sup> AATCC Gray Scale for Color Change.

<sup>C</sup> AATCC Chromatic Transference Scale.

5.2 It should be recognized that fabrics can be produced utilizing an almost infinite number of combinations of construction variables (for example, type of fibers, percentage of fibers, yarn twist, yarn number, warp and pick count, chemical and mechanical finishes.) Additionally, fashion or aesthetics dictate that the ultimate consumer may find acceptable articles made from fabrics that do not conform to all of the requirements in **Table 1**.

5.2.1 Hence, no single performance specification can possibly apply to all the various fabrics that could be utilized for this end-use.

5.3 The uses and significance of particular properties and test method are discussed in the appropriate sections of the specified test methods.

### 6. Test Methods

6.1 *Resistance to Yarn Slippage*—Determine the resistance to yarn slippage (seam integrity) as directed in Test Method **D4033**.

NOTE 2—Yarn slippage at the seams in knit fabrics is a relatively rare occurrence, limited to certain types of knit fabrics, for example, coarse-gage Raschels and weft insertion knits. By a substantial majority, the failures which occur at the seams in knit fabrics are splitting or tearing caused by needle cutting or weak yarns, or both, and stitch line thread breakage. All or any of these problems can be discovered in Test Method **D4033** if they exist in any fabric or stitch line. If it is suspected that the problem is needle cutting, seams should be sewn with progressively smaller needles until a “passing” result is obtained. Then it is equally important to specify that production on that particular fabric should be sewn only with the needle size and type with which the “passing” result was obtained. The sewn seam shall contain a stitch density of seven stitches per inch (25.4 mm) and a minimum of 0.5-in. (12.7-mm) seam allowance. Experience has indicated that a Size 22 (or smaller) needle with a light ball point will successfully sew most knitted upholstery fabrics; however, if needle cutting problems do occur, simply changing to smaller ball point needles will usually solve most problems. If production conditions dictate that smaller needles cannot be used because of breakage problems, then the knit construction must be reviewed for potential change. Another point of equal importance is that knit upholstery fabrics should never be sewn with regular point, sharp point (SET), or cutting point needles. Knit fabrics should also never be sewn with medium or heavy ball point needles, that is nothing but the light ball point (SES) needle should be used.

6.2 *Dimensional Change*—Determine dimensional change as directed in the Joint-Industry Knit Upholstery Fabric Standards and Guidelines.

6.3 *Colorfastness to Water*:

6.3.1 Determine colorfastness to water as directed in AATCC 107.

6.3.2 This method provides a procedure to evaluate color change within the cleaned area under standardized conditions. Although not directly related to consumer cleansing with water-base or solvent-base cleansing agents, it will give reliable information on the fastness of the fabric coloration to water and solvent, which are the principal agents that would cause color migration or bleeding, or both. In this context, the color change occurring in these tests denotes any change due to color loss or bleeding and migration of one color to another within the cleaned area.

6.3.3 In the evaluation of the test results, the fabric tested is compared against the original to establish color change.



6.3.4 Those fabrics that are not fast to water or solvent media, or both, and show a color change, should be so labeled.

6.4 *Colorfastness to Solvent*—Determine the colorfastness to solvent as directed in AATCC Method 107 using the modifications presented in 6.4.1 and 6.4.2.

6.4.1 Use technical grade perchloroethylene for the test solution.

NOTE 3—**Warning:** Perchloroethylene is toxic, and the usual precautions for handling chlorinated solvents should be taken. Use only under well-ventilated conditions. The solvent is nonflammable.

NOTE 4—The rollers in the wringer used should be such that they will not be affected by the solvent.

6.4.2 After loading the specimens in the Perspiration Tester, Perspirometer, or similar device, allow them to stand for 2 h in the prevailing room atmosphere. Do not press or iron the specimens.

6.4.3 See 6.3.2-6.3.4.

6.4.4 The precision and bias for the modified procedure for determining colorfastness to solvent has not been established. The method is accordingly not recommended for acceptance testing unless preceded by an interlaboratory check test in the laboratory of the purchaser and the laboratory of the supplier using randomized replicate specimens of the material(s) to be evaluated.

6.5 *Colorfastness to Crocking*—Determine the colorfastness to wet and dry crocking as directed in AATCC Method 8 for solid shades and AATCC Method 116 for prints, or as agreed upon between the purchaser and the supplier.

6.6 *Colorfastness to Burnt Gas Fumes*—Determine the colorfastness to burnt gas fumes as directed in AATCC Method 23. Do not wash or dry-clean these fabric specimens either before or after testing.

6.7 *Colorfastness to Light*—Determine the colorfastness to light as directed in AATCC Method 16.

NOTE 5—There are distinct differences in spectral distribution between the various types of machines listed in AATCC Method 16, with no overall correlations between them. Consequently, these machines cannot be used

interchangeably. In case of controversy, results obtained with the water-cooled xenon-arc machine listed in Option 3 shall prevail.

6.8 *Colorfastness to Ozone*—Determine the colorfastness to ozone as directed in AATCC Method 129.

6.9 *Retention of Hand, Character, and Appearance*—After the fabric has been tested as directed in 6.3-6.5, it should be evaluated for any change in hand, character, or appearance.

NOTE 6—Water tests would not apply, if labeled “Solvent Clean Only.”

6.10 *Durability of Back Coating*—After the fabric has been tested as directed in 6.3-6.5, it should be evaluated for cracking or peeling of the back coating.

6.11 *Flammability*—The flammability requirements shall be as agreed upon between the purchaser and the supplier, provided they meet or exceed those of Part 1610 of the Flammable Fabric Act Regulations.

6.11.1 Fabrics sold and used in California must be tested as directed in California Bulletin 117.

6.11.2 All upholstery fabrics shall be evaluated for cigarette ignition resistance by the UFAC Fabric Classification Test Method.

6.12 *Federal Trade Commission (FTC) Requirements*—The FTC promulgated the Guides for the Household Furniture Industry<sup>5</sup>. Although the Textile Fiber Products Identification Act specifically exempts outer coverings of furniture from the application of the act, the FTC has very specific regulations covered in detail in Guide 5 of the Guides for the Household Furniture Industry. In brief, this rule covers the following:

6.12.1 False or deceptive representation as to fiber content.

6.12.2 How to identify fibers properly in advertising.

6.12.3 How to identify fibers properly on tags or labels.

6.12.4 Restrictions concerning representation of fabric tests.

6.12.5 Restrictions concerning representation of performance characteristics of upholstery fabrics.

## 7. Keywords

7.1 indoor furniture; knitted upholstery fabric

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*