

Designation: D5240/D5240M – 12 (Reapproved 2013)

Standard Test Method for Evaluation of Durability of Rock for Erosion Control Using Sodium Sulfate or Magnesium Sulfate¹

This standard is issued under the fixed designation D5240/D5240M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers test procedures for evaluating the soundness of rock for erosion control by the effects of a sodium or magnesium sulfate solution on slabs of rock. The test is an accelerated weathering test that simulates the freezing and thawing of cold weather exposure. The rock slabs, prepared in accordance with procedures in Practice D5121, are intended to be representative of erosion control sized materials and their inherent weaknesses. The test is appropriate for breakwater stone, armor stone, riprap and gabion sized rock materials.

The limitations of this test are twofold. First the test is a simulation of freezing and thawing conditions. The internal expansive force, derived from the rehydration of the salt upon re-immersion, simulates the expansion of water on freezing relying on chemical crystal formation to simulate freezing rather than the actual freezing of water. Secondly the size of the cut rock slab specimens may eliminate some of the internal defects present in the rock structure. The test specimens may not be representative of the quality of the larger rock samples used in construction. Careful examination of the rock source and proper sampling are essential in minimizing this limitation.

1.2 The use of reclaimed concrete and other materials is beyond the scope of this test method.

1.3 Units—The values stated in either SI units or inchpound units [presented in brackets] are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 All observed and calculated values shall conform to the guidelines for significant digits and rounding established in Practice D6026, unless superseded by this standard.

1.4.1 For purposes of comparing measured or calculated value(s) with specified limits, the measured or calculated

value(s) shall be rounded to the nearest decimal or significant digits in the specified limits.

1.4.2 The procedures used to specify how data are collected/ recorded or calculated, in this standard are regarded as the industry standard. In addition, they are representative of the significant digits that generally should be retained. The procedures used do not consider material variation, purpose for obtaining the data, special purpose studies, or any considerations for the user's objectives; and it is common practice to increase or reduce significant digits of reported data to be commensurate with these considerations. It is beyond the scope of this standard to consider significant digits used in analytical methods for engineering design.

1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:²
- C88 Test Method for Soundness of Aggregates by Use of Sodium Sulfate or Magnesium Sulfate
- C295 Guide for Petrographic Examination of Aggregates for Concrete
- D653 Terminology Relating to Soil, Rock, and Contained Fluids
- D2216 Test Methods for Laboratory Determination of Water (Moisture) Content of Soil and Rock by Mass
- D3740 Practice for Minimum Requirements for Agencies Engaged in Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction
- D4753 Guide for Evaluating, Selecting, and Specifying Balances and Standard Masses for Use in Soil, Rock, and Construction Materials Testing
- D4992 Practice for Evaluation of Rock to be Used for Erosion Control

¹ This test method is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.17 on Rock for Erosion Control.

Current edition approved Jan. 15, 2013. Published January 2013. Originally approved in 1992. Last previous edition approved in 2012 as D5240/D5240M – 12. DOI: 10.1520/D5240_D5240M-12R13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D5121 Practice for Preparation of Rock Slabs for Durability Testing

D6026 Practice for Using Significant Digits in Geotechnical Data

E100 Specification for ASTM Hydrometers

E145 Specification for Gravity-Convection and Forced-Ventilation Ovens

3. Terminology

3.1 *Definitions*—See Terminology D653 for general definitions.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *rock saw, n*—a saw capable of cutting rock. The term "rock saw" shall include the blade which saws the rock, any components that control or power the sawing process or both, and framework on which the blade and any other associated components are mounted.

3.2.2 *slab,* n—a section of rock having two smooth, approximately parallel faces, produced by two saw cuts. The thickness of the slab is generally less than the other dimensions of the rock. The slab will be the rock specimen which will subsequently undergo durability tests. The words "slab" and "specimen" are interchangeable throughout the test method.

3.2.3 *armor stone*, n—stone generally 900 to 2700 kg [one to three tons] resulting from blasting, cutting, or by other methods placed along shorelines or in jetties to protect the shoreline from erosion due to the action of large waves.

3.2.4 *breakwater stone*, *n*—stone generally 2700 to 18 000 kg [three to twenty tons] resulting from blasting, cutting, or by other methods placed along shorelines or in jetties to protect the shoreline from erosion due to the action of large waves.

3.2.5 *riprap stone*, *n*—stone generally less than 1800 kg [two tons] specially selected and graded, when properly placed prevents erosion through minor wave action, or strong currents and thereby preserves the shape of a surface, slope, or underlying structure.

3.2.6 *gabion-fill stone, n*—stone generally less than 22 kg [50 lb] and placed in baskets of wire or other suitable material. These baskets are then tied together to form an integral structure designed to resist erosion along stream banks and around bridge piers.

4. Summary of Test Method

4.1 Erosion control rock samples are trimmed into saw-cut slab specimens. The trimmed slabs are oven dried to a constant mass. The specimens are repeatedly immersed in saturated solutions of sodium sulfate or magnesium sulfate followed by oven drying. At the completion of the test, the percent loss by mass for each specimen set is determined. A visual examination of the slabs is performed at the end of testing. The type of deterioration and changes to previously noted planes of weakness are recorded.

5. Significance and Use

5.1 Rock for erosion control consists of individual pieces of natural stone. The ability of these individual pieces of stone to resist deterioration due to weathering action affects the stability

of the integral placement of rock for erosion control and hence, the stability of construction projects, structures, shorelines, and stream banks.

5.2 The sodium sulfate or magnesium sulfate soundness test is one method by which to estimate qualitatively the durability of rock under weathering conditions. This test method was developed to be used in conjunction with additional test methods listed in Practice D4992. This test method does not provide an absolute value, but rather an indication of the resistance to freezing and thawing; therefore, the results of this test method are not to be used as the sole basis for the determination of rock durability.

5.3 This test method has been used to evaluate many different types of rocks. There have been occasions when test results have provided data that have not agreed with the durability of rock under actual field conditions; samples yielding a low soundness loss have disintegrated in actual usage, and the reverse has been true.

Note 1—The quality of results produced by this standard is dependent on the competence of the personnel performing it and suitability of the equipment and facilities used. Agencies that meet the criteria of Practice D3740 are generally considered capable of competent and objective testing/sampling/inspection/etc. Users of this standard are cautioned that compliance with Practice D3740 does not in itself assure reliable results. Reliable results depend on many factors and Practice D3740 provides a means of evaluating some of them.

6. Apparatus

6.1 *Rock Saw*—A laboratory water-cooled diamond saw used to cut geological and concrete specimens, or a diamond saw used for lapidary purposes, shall be acceptable. A minimum blade diameter of 36 cm [14 in.] will be needed to obtain the required slab sizes (a larger blade is preferable). The blade shall be a circular diamond blade.

6.1.1 The rock saw apparatus shall have a fixed or removeable vise to hold the samples during the cutting process. An automatic feed (either gravity, hydraulic, or screwfeed operated) that controls the cutting action is preferred; however, a manual feed is also acceptable. The saw shall have a platform to prevent the cut slab from falling and shattering.

Note 2—Coolants other than water may interfere with subsequent testing or evaluation, or both.

6.2 *Containers*—Of sufficient size to hold the specimens and baskets fully immersed in a sulfate solution. It is advised that these containers be sealable, non-reactive, resistant to breakage and resistant to deformation and degradation when exposed to the chemicals and temperatures encountered in this test method.

6.3 *Baskets*—Baskets for immersing the slab specimens in the solution, in accordance with the procedure described in this test method, shall be perforated in such a manner as to permit free access of the solution to the specimen and drainage of the solution from the specimen without loss of material.

Note 3—Baskets made of suitable wire mesh or sieves with suitable openings are satisfactory containers for the samples.

6.4 *Temperature Regulation*—Suitable means for regulating the temperature of the samples at 21 ± 1 °C [70 ± 2 °F] during immersion in the sodium sulfate or magnesium sulfate solution shall be provided.

6.5 *Balances*—The balance shall meet the requirements of Specification D4753. A Class GP 10 balance of 5 g readability and accuracy is acceptable.

6.6 Drying Oven—Thermostatically controlled oven meeting the requirements of Specification E145 and capable of maintaining a uniform temperature of 110 ± 5 °C [230 ± 9 °F] throughout the drying chamber. These requirements typically require the use of a forced-draft type oven. Preferably the oven should be vented outside the building. The rate of evaporation, at this range of temperature, shall be at least 25 g/h for 4 h, during which period the doors of the oven shall be kept closed. This rate shall be determined by the loss of water from 1-L Griffin low-form beakers, each initially containing 500 g [1 lb] of water at a temperature of 21 ± 2 °C [70 ± 3 °F], placed at each corner and the center of each shelf of the oven. The evaporation requirement is to apply to all test locations when the oven is empty except for the beakers of water.

6.7 Specific Gravity Measurement—Hydrometers conforming to the requirements of Specification E100, or a suitable combination of graduated glassware and balance, capable of measuring the solution specific gravity within ± 0.001 .

6.8 *Camera*—A digital or film camera capable of producing good quality, color photographs for "before" and "after" photographs.

6.9 *Photographic Scale*—A scale of appropriate dimension and division when compared to the field of view and the detail being studied. When selecting a scale, always choose the scale that will provide at least as precise a measurement as the system that will be measuring the photographic information. If the system has a precision to one millimeter, make sure the scale used is accurate and precise to at least one millimeter across the entire scale.

7. Special Solutions Required

7.1 Prepare the solution for immersion of test samples from either sodium or magnesium sulfate in accordance with 7.1.1 or 7.1.2 (Note 4). The volume of the solution shall be at least five times the solid volume of all samples immersed at any one time.

Note 4—Some rock containing carbonates of calcium or magnesium are attacked chemically by fresh sulfate solution, resulting in erroneously high measured losses. If this condition is encountered or is suspected, repeat the test using a filtered solution that has been used previously to test the same type of carbonate rock, provided that the solution meets the requirements of 7.1.1 and 7.1.2 for specific gravity.

7.1.1 Sodium Sulfate Solution—Prepare a saturated solution of sodium sulfate by dissolving a reagent grade of the salt in water at a temperature of 25 to 30 °C [77 to 86 °F]. Add sufficient salt (Note 5), of either the anhydrous (Na₂SO₄) or the crystalline (Na₂SO₄ ·10H₂O) form, to ensure not only saturation but also the presence of excess crystals when the solution is ready for use in the tests. Thoroughly stir the mixture during the addition of the salt and stir the solution at frequent intervals until used. To reduce evaporation and prevent contamination, keep the solution covered at all times when access is not needed. Allow the solution to cool to 21 ± 1 °C [70 ± 2 °F]. Again stir, and allow the solution to remain at the designated temperature for at least 48 h before use. Prior to each use, break up the salt cake, if any, in the container, stir the solution thoroughly, and determine and record the specific gravity of the solution.

When used, the solution shall have a specific gravity of 1.151 to 1.174. Discard a discolored solution, or filter it and check for specific gravity.

Note 5—For the solution, 215 g of anhydrous salt or 700 g of the decahydrate per litre of water are sufficient for saturation at 22 °C [71.6 °F]. However, since these salts are not completely stable and since it is desirable that an excess of crystals be present, the use of not less than 350 g of the anhydrous salt or 750 g of the decahydrate salt per litre of water is recommended.

7.1.2 Magnesium Sulfate Solution—Prepare a saturated solution of magnesium sulfate by dissolving a reagent grade of the salt in water at a temperature of 25 to 30 °C [77 to 86 °F]. Add sufficient salt (Note 6), of either the anhydrous (MgSO₄) or the crystalline (MgSO₄·7H₂O) (Epsom salt) form, to ensure saturation and the presence of excess crystals when the solution is ready for use in the tests. Thoroughly stir the mixture during the addition of the salt and stir the solution at frequent intervals until used. To reduce evaporation and prevent contamination, keep the solution covered at all times when access is not needed. Allow the solution to cool to 21 ± 1 °C [70 ± 2 °F]. Again stir, and allow the solution to remain at the designated temperature for at least 48 h before use. Prior to each use, break up the salt cake, if any, in the container, stir the solution thoroughly, and determine and record the specific gravity of the solution. When used, the solution shall have a specific gravity of 1.295 to 1.308. Discard a discolored solution, or filter it and check for specific gravity.

Note 6—For the solution, 350 g of anhydrous salt or 1230 g of the heptahydrate per litre of water are sufficient for saturation at 23 °C [73.4 °F]. However, since these salts are not completely stable, with the hydrous salt being the more stable of the two, and since it is desirable that an excess of crystals be present, it is recommended that the heptahydrate salt be used and in an amount of not less than 1400 g/litre of water.

7.1.3 *Barium Chloride Solution*—Prepare 100 mL of 5 % barium chloride solution by dissolving 5 g of $BaCl_2$ in 100 mL of distilled water.

Note 7—The previous iteration of this procedure, Test Method D5240-04, referred to Test Method C88. The references were to provide guidance in 1) the preparation of special solutions required and 2) the storage, drying, and cyclic requirements of the test specimens. The sections that had previously only cited Test Method C88 have been expanded verbatim from Test Method C88, including all time temperature and special solution-specific gravity requirements, to permit Test Method D5240/ D5240M to be a stand-alone method.

8. Sampling, Test Specimens, and Test Units

8.1 Rock source sampling shall be guided by the principles in Practice D4992.

8.2 Rock sources may be from mine, quarry, outcrop, or field boulders. Visual observation of color, texture, mineralogy, or some other feature, will be the key to proper representative sampling.

8.2.1 A rock source that is macroscopically uniform shall be represented by a minimum of five pieces of the material

obtained from separate locations within the source area. This group is considered as a specimen set.

8.2.2 A rock source that is macroscopically non-uniform shall be represented by a minimum of eight pieces of the material obtained from separate locations within the source area. This group is considered as a specimen set.

8.2.3 Sample the rock types in their approximate proportion to the types that occur at the source.

8.3 Planes of weakness will be included in each sample such that a determination may be made as to the durability of the various planes of weakness and their effect on the overall durability of a rock mass that would contain these planes of weakness.

8.4 Each rock sample shall be of sufficient size to provide the finished size specimens described in Section 9.

8.5 In all cases, the rock pieces selected for the sample shall be chosen to be representative of the majority of the rock at the source. Rock pieces, as determined by their macroscopic properties, which comprise less than 5 percent of the source material, may be ignored unless their presence in a sample will significantly affect the test results and subsequent proposed use of the rock.

8.6 Each piece will be of a size such that testing may proceed without further mechanical crushing; however, the chosen pieces shall be as large as the laboratory can handle but in no case shall the sample be less than 125 mm (5 in.) on a side.

9. Preparation of Test Specimen

9.1 Prepare a separate slab for each orientation of the various planes of weakness unless all such planes can be intersected with one orientation.

9.2 Saw each sample, as obtained per 8.2.1 and 8.2.2, in accordance with Practice D5121. Cut each specimen to 65 ± 5 mm [2.5 \pm 0.25 in.] thick and cut normal to bedding or any potential planes of weakness which may be observed in the samples. In no case will the size of the slab be less than 125 mm [5 in.] on a side, excluding the thickness.

Note 8—Test specimens may also be prepared by cutting a 65 \pm 5 mm [2.5 \pm 0.25 in.] thick slab from a 150-mm [6-in.] diameter diamond drill core such that any apparent zones of weakness are included.

Note 9—The best estimates of rock durability are those estimates that are based on the results of tests performed on the largest possible slabs of rock. The maximum slab size shall be limited only by the capacity of the laboratory and its equipment.

10. Procedure

10.1 Label each test specimen with a suitable waterproof marker. Photograph each test specimen digitally or using color film and in such a way that the slab fills most of the photograph. Wet or partially wet test specimens usually show more detail than dry specimens. Include a scale in all photographs.

10.2 Describe each slab as indicated in Practice D5121. Note the presence of bedding planes, fractures, and other planes of weakness and their condition.

10.3 Dry each trimmed slab in an oven to a constant mass ($\pm 0.1 \%$ of total mass) at $110 \pm 5 \degree$ C [$230 \pm 9 \degree$ F] and record the mass. When determining constant mass, rock that contains gypsum, (calcium sulfate dihydrate), shall be dried at the 60 °C [140 °F] temperature recommended in Test Method D2216. In most cases, drying slabs overnight (12 to 16 h) is sufficient. In cases where there is doubt concerning the adequacy of drying, drying should be continued until the change in mass after two time intervals (greater than 1 h) of drying is less than 0.1 %.

10.4 Storage of Specimens in Solution—Immerse the slabs in the prepared solution of sodium sulfate or magnesium sulfate for 16 to18 h in such a manner that the solution covers them to a depth of at least 12.5 mm [0.5 in.]. Cover the containers to reduce evaporation and to prevent contamination. Maintain the specimens immersed in the solution at a temperature of 21 ± 1 °C [70 ± 2 °F] for the immersion period.

10.5 Drying Specimens After Immersion-After the immersion period, remove the specimens from the solution, permit them to drain for 15 ± 5 min, and place in the drying oven. The temperature of the oven shall have been brought previously to $110 \pm 5 \text{ °C} [230 \pm 9 \text{ °F}]$. Dry the specimens at the specified temperature until constant weight has been achieved. Establish the time required to attain constant weight as follows: with the oven containing the maximum sample load expected, check the weight losses of test specimens by removing and weighing them, without cooling, at intervals of 2 to 4 h; make enough checks to establish required drying time for the least favorable oven location (see 6.6) and specimen condition (Note 10). Constant weight will be considered to have been achieved when weight loss is less than 0.1 % of specimen weight in 4 h of drying. After constant weight has been achieved, allow the specimens to cool to room temperature, when they shall again be immersed in the prepared solution as described in 10.4.

Note 10—Drying time required to reach constant weight may vary considerably for several reasons. Efficiency of drying will be reduced as cycles accumulate because of salt adhering to particles and, in some cases, because of increase in surface area due to breakdown.

10.6 Repeat the process of immersion and drying for a total of five cycles. Preferably, the test shall be performed continuously until the specified number of cycles is obtained. However, if the test must be interrupted, leave the specimens in the oven, at 110 ± 5 °C [230 ± 9 °F] until the testing can be resumed.

10.7 After the completion of the final cycle and after the specimens have cooled, wash the specimens free from the sodium sulfate or magnesium sulfate as determined by the reaction of the wash water with barium chloride (BaCl₂). Wash by circulating water at 43 ± 6 °C [110 ± 10 °F] through the specimens in their baskets. This may be done by placing them in a tank into which the hot water can be introduced near the bottom and allowed to overflow. In the washing operation, the samples shall not be subjected to impact or abrasion that may tend to break up the slabs.

10.8 Photograph and perform a qualitative examination on each slab as specified in Section 12.

Note 11—Tap water containing sulfates when used for the wash water will cloud when tested with the barium chloride solution. The cloudiness of a solution of tap water and the barium chloride solution should be

(12) D5240/D5240M – 12 (2013)

judged so that tested wash water with the same degree of cloudiness can be assumed to be free of sulfates from the test.

11. Quantitative Examination

11.1 Calculate the percent loss determined to the nearest 0.1 percent for each specimen:

% soundness loss =
$$(A - B)/A \times 100$$
 (1)

where:

A = oven-dried mass of the slab prior to testing, and

B = oven-dried mass of the largest remaining piece of each slab after testing.

11.2 Calculate the percent loss determined to the nearest 0.1 percent from the cumulative initial and final masses for the specimen set:

% average soundness loss =
$$(C - D)/C \times 100$$
 (2)

where:

- C = oven-dried cumulative mass of all slabs prior to testing, and
- D = oven-dried cumulative mass of the largest remaining pieces of all slabs after testing.

12. Qualitative Examination

12.1 Visually examine the slabs at the completion of testing for any changes that have taken place over the duration of the test and describe the changes. Identify the type of deterioration (spalling, splitting, disintegration, and other types of deterioration). Observe and record any changes to previously noted planes of weakness.

12.2 Take color photographs of each slab at the completion of testing. Provide close-ups of any unusual features. Include a scale in all photographs.

13. Report: Test Data Sheet(s)/Form(s)

13.1 The methodology used to specify how data are recorded on the test data sheet(s)/form(s), as given below, is covered in 1.3.

13.2 Record as a minimum the following general information (data):

13.2.1 Sample/specimen identifying information, such as Project No., Sample No., Type of rock, Sample source location, Depth, etc.

13.3 Record as a minimum the following test specimen data:

13.3.1 The name and initials of testing personnel.

13.3.2 The initial oven-dried specimen mass.

13.3.3 The start and finish time and date for each cycle.

13.3.4 The specific gravity of the special solution prior to each use.

13.3.5 The initial qualitative examination observations and those made at the completion of testing.

13.3.6 The final oven-dried specimen mass.

13.4 Report as a minimum the following information:

13.4.1 Sample identification number.

13.4.2 Sample source location.

13.4.3 Location of intended use.

13.4.4 Rock type.

13.4.5 Type of solution used in the soundness test.

13.4.6 The cumulative percent loss of the quantitative examination required in 11.2 to the nearest 0.1 %,

13.4.7 A written description of the qualitative examination for each specimen per section 12.1, and the findings of this examination.

13.4.8 "Before" and "after" color photographs.

13.5 The following items are optional for the report:

13.5.1 Geological formation name.

13.5.2 Geological setting of the source with pertinent information on planes of weakness noted in the field.

14. Precision and Bias

14.1 Due to the nature of the rock materials tested by this test method, it is not possible to produce multiple specimens that have uniform physical properties. ASTM Subcommittee D18.17 is instituting a program of specimen testing to determine the feasibility of precision measurements and welcomes proposals that would allow for the development of a valid precision statement. No accepted reference value exists for this test method; therefore, bias cannot be determined.

15. Keywords

15.1 riprap; rock defects; rock durability; rock weathering; soundness of riprap



APPENDIX

(Nonmandatory Information)

X1. EVALUATION OF DURABILITY OF ROCK FOR EROSION CONTROL USING SODIUM SULFATE OR MAGNESIUM SULFATE WORKSHEET

ASTM D5240 Evaluation of Durability of Rock for Erosion Control Using Sodium Sulfate or Magnesium Sulfate				
Project:		Lab Number:		
(A) Initial Oven Dried Specimen Mass, g:		(B) Final Oven Dried Specimen Mass, g:		
Solution Used - (Check One):	Sodium Sulfate	Magnesium Sulfate		
Initial Qualitative Description:		č		

	Hydrometer	In Solution	In Oven
	Reading	Date and Time	Date and Time
Initial			
Cycle			
By			
Cycle			
2			
By			
Cycle			
3			
By			
Cycle			
4			
By			
Final			
Cycle			
By			

Final Qualitative Description:	
Calculations	% Loss = (A – B) / A × 100
Ву	



SUMMARY OF CHANGES

Committee D18 has identified the location of selected changes to this standard since the last issue (D5240 - 04) that may impact the use of this standard. (Approved July 1, 2012.)

(1) The title was revised to better reflect that this test method is appropriate for evaluating numerous types of rock for erosion control, not just riprap.

(2) The Scope (Section 1) was expanded to indicate the test method's intent and limitations. Clarification and reference to Practice D6026 was expanded and a statement was added indicating that the values stated in either SI units or inch-pound units [presented in brackets] are to be regarded separately as standard.

(3) Reference Documents (Section 2) was expanded to include the reference to Specification E100 and Specification E145. The reference to Test Method C88 was deleted as the Apparatus, Special Solutions and Procedure sections were adapted for slab specimen use and incorporated within the text of Test Method D5240/D5240M.

(4) The Terminology (Section 3) was expanded to include terms specific to the standard.

(5) A Summary of Test Method (Section 4) was added to present a clear and concise summary of the test method.

(6) The Significance and Use (Section 5) was updated to improve readability.

(7) The Apparatus (Section 6) was clarified to reflect the wording in Practice D5121, to eliminate superlative wording and expanded to better define required and optional apparatus. (8) Special Solutions Required (Section 7) was added to reflect that Test Method D5240/D5240M is now a stand-alone test and does not require the user to cross-reference Test Method C88 during testing. The Test Method C88 content was adapted for

slab specimen testing and incorporated within the text of Test Method D5240/D5240M.

(9) The Sampling, Test Specimens, and Test Units (Section 8) was expanded and broken down into simple sections for clarification and to improve readability.

(10) The Preparation of Test Specimens (Section 9) was updated to improve readability.

(11) The Procedure (Section 10) was updated to clarify the sequencing of, and to remove ambiguity from, the test. The section was expanded to reflect that Test Method D5240/ D5240M is now a stand-alone test and does not require the user to cross-reference Test Method C88 during testing. The Test Method C88 content was adapted for slab specimen testing and incorporated within the text of Test Method D5240/D5240M. (12) Rationalized SI and inch-pound units were added throughout the standard.

(13) The Calculation (Section 11) was updated to indicate that the percent loss is to be determined to the nearest 0.1 percent. (14) The Qualitative Examination (Section 12) was added to clarify the sequencing of, and to remove ambiguity from, the test.

(15) The Report: Test Data Sheet(s)/Form(s) (Section 13) was expanded to specify the manner in which the data is recorded and reported.

(16) Appendix X1 was added to provide the user with a worksheet for data recording. This worksheet is strictly an example that the user may vary to suit their particular requirements.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).