



# Standard Specification for Styrene Butadiene Styrene (SBS) Modified Bituminous Sheet Materials Using Polyester Reinforcements<sup>1</sup>

This standard is issued under the fixed designation D6164/D6164M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers prefabricated modified bituminous sheet materials reinforced with polyester fabric as the primary reinforcement, (see [Note 1](#)) with or without granules, which use styrene butadiene styrene (SBS) thermoplastic elastomer as the primary modifier and are intended for use in the fabrication of multiple ply roofing and waterproofing membranes.

NOTE 1—Many modified bituminous sheets are currently marketed with polyester mat reinforced with glass yarns to improve processing in the manufacture of the finished modified bitumen product and to reduce distortions that may be introduced during production. These glass yarns are typically a small percentage of the reinforcement and do not contribute to the physical properties of the finished product so much as to make these products be classified by Specification [D6162/D6162M](#).

1.2 This specification is intended as a material specification only. Issues regarding the suitability of the specific roof constructions or application techniques are beyond this scope.

1.3 The specified tests and property limits used to characterize the sheet materials are intended to establish minimum properties. In-place roof system design criteria, such as fire resistance, field strength, impact/puncture resistance, material compatibility, uplift resistance, and others, are factors beyond the scope of this material specification.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

[D1079 Terminology Relating to Roofing and Waterproofing](#)

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.04 on Felts, Fabrics and Bituminous Sheet Materials.

Current edition approved Nov. 1, 2016. Published November 2016. Originally approved in 1997. Last previous edition approved in 2011 as D6164/D6164M – 11. DOI: 10.1520/D6164\_D6164M-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

[D5147/D5147M Test Methods for Sampling and Testing Modified Bituminous Sheet Material](#)

[D6162/D6162M Specification for Styrene Butadiene Styrene \(SBS\) Modified Bituminous Sheet Materials Using a Combination of Polyester and Glass Fiber Reinforcements](#)

## 3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology [D1079](#).

## 4. Classification

4.1 Modified bituminous sheet materials reinforced with polyester fabric, Type I and Type II, are covered by this specification.

4.2 The following grades are used to describe the material surfacing:

4.2.1 Grade *G*—Granule Surfaced.

4.2.2 Grade *S*—Smooth Surfaced.

## 5. Material and Manufacture

5.1 In the process of manufacture, the reinforcement is saturated with asphalt or modified asphalt and is impregnated and coated on both sides with an SBS modified bituminous coating. The SBS modified bituminous coating shall be permitted to be compounded with a mineral stabilizer.

5.2 The Grade *G* sheet is surfaced on the weather side with mineral granules, except for any selvage. To prevent sticking in the roll, the reverse side and any selvage shall be permitted to be covered with a fine mineral surfacing or any other surfacing that will not interfere with adhesion or bonding of the lap during application.

5.3 Sheet material intended for application by heat welding (torching) shall meet the minimum bottom coating requirement found in [Table 1](#).

## 6. Physical Properties

6.1 The sheet shall conform to the minimum physical properties prescribed in [Table 2](#).

6.2 The finished product shall not crack nor be so sticky as to cause tearing or other material damage upon being unrolled at any product temperature between 4 and 60°C [40 and 140°F].

**TABLE 1 Dimensions and Masses of SBS Modified Bituminous Sheet Materials Using Polyester Reinforcements**

| Description   | Type I    | Type II   |
|---|-----------|-----------|
| Thickness, min, mm [mils],  |           |           |
| Grade S   | 2.2 [85]  | 2.9 [115] |
| Grade G   | 3.3 [130] | 3.3 [130] |
| Net mass/unit area, min, g/m <sup>2</sup> [lbs/100 ft <sup>2</sup> ]        |           |           |
| Grade S   | 2636 [54] | 3417 [70] |
| Grade G   | 3661 [75] | 4394 [90] |
| Bottom coating thickness, heat welding application products, min, mm [mils] |           |           |
| Grade S   | 1.0 [40]  | 1.0 [40]  |
| Grade G   | 1.0 [40]  | 1.0 [40]  |

**TABLE 2 Physical Properties of SBS Modified Bituminous Sheet Materials Using Polyester Reinforcements<sup>A</sup>**

| Property  | Type I<br>Grade: G and S | Type II<br>Grade: G and S |
|---|--------------------------|---------------------------|
| Peak load at $-18 \pm 2^\circ\text{C}$ [ $0 \pm 3.6^\circ\text{F}$ ], MD and XMD, before and after heat conditioning, min, kN/m [lb/in.]      | 12.3 [70]                | 17.5 [100]                |
| Elongation at $-18 \pm 2^\circ\text{C}$ [ $0 \pm 3.6^\circ\text{F}$ ], MD and XMD, at peak load, before and after heat conditioning, min, %   | 20                       | 20                        |
| Peak load at $23 \pm 2^\circ\text{C}$ [ $73.4 \pm 3.6^\circ\text{F}$ ], MD and XMD, before and after heat conditioning, min, kN/m [lb/in.]    | 8.8 [50]                 | 12.3 [70]                 |
| Elongation at $23 \pm 2^\circ\text{C}$ [ $73.4 \pm 3.6^\circ\text{F}$ ], MD and XMD, at peak load, before and after heat conditioning, min, % | 35                       | 50                        |
| Ultimate elongation $23 \pm 2^\circ\text{C}$ [ $73.4 \pm 3.6^\circ\text{F}$ ], MD and XMD, before and after heat conditioning, min, %         | 38                       | 60                        |
| Tear strength at $23 \pm 2^\circ\text{C}$ [ $73.4 \pm 3.6^\circ\text{F}$ ], min, N [lbf]  | 246 [55]                 | 311 [70]                  |
| Low temperature flexibility, before and after heat conditioning, max, $^\circ\text{C}$ [ $^\circ\text{F}$ ]                                   | $-18$ [0]                | $-18$ [0]                 |
| Dimensional stability, max, %   | 1                        | 1                         |
| Compound stability at $102^\circ\text{C}$ [ $215^\circ\text{F}$ ]   | no failures              | no failures               |
| Granule embedment, max, g, (Grade G only)   | 2                        | 2                         |

<sup>A</sup> The properties in this table are "as manufactured" unless otherwise noted.

## 7. Dimensions, Mass, and Permissible Variations

7.1 The finished product shall conform to the following dimensions and variations:

7.1.1 The width of the roll shall be as agreed between the purchaser and the seller and shall not vary more than 1 %.

7.1.2 The area of the roll shall be no less than as agreed between the purchaser and the seller.

7.1.3 The selvage width shall be within 6.4 mm [ $\frac{1}{4}$  in.] of the nominal selvage width and shall be not less than 76.2 mm [3 in.] in width without a laying line and 63.5 mm [2.5 in.] in width if the sheet has a laying line. If a laying line is provided, the line must not be less than 76.2 mm [3 in.] from the edge of the sheet.

7.2 The mass and thickness of the finished product shall be as prescribed in Table 1.

## 8. Workmanship, Finish, and Appearance

8.1 The finished product shall be coated completely in a continuous, unbroken film and shall be free of such defects as holes, tears, cracks, wrinkles, or permanent deformations, blisters, ragged or untrue edges, and areas of uncoated reinforcement.

8.2 The surface of the weather side shall be uniform in finish and texture.

8.3 For Grade G material, the mineral granules shall be distributed uniformly over the entire surface in an even layer excluding any selvage, shall be embedded firmly in the SBS modified bituminous coating, and the line of demarcation between the granule-surfaced portion of the weather side and any selvage shall be straight and parallel to the edges of the sheet.

8.4 When unrolled on a smooth plane, the sheet shall be straight and true so that the lap will mate with the adjacent sheet within the tolerance for the lap without wrinkles, buckles, or fishmouths.

## 9. Sampling and Test Methods

9.1 Sample the material and determine the properties described in this specification in accordance with Test Methods D5147/D5147M, unless otherwise indicated.

9.2 *Ultimate Elongation*—See Test Methods D5147/D5147M, Section 6.

## 10. Inspection

10.1 *Inspection*—Inspection shall be in accordance with the requirements of this specification.

10.2 *Inspection Alternatives*—Alternative inspection requirements shall be determined by and as agreed upon between the purchaser and supplier.

## 11. Rejection and Resubmittal

11.1 *Failure to Conform*—Failure to conform to any of the requirements as stated in this specification constitutes grounds for rejection.

11.2 *Rejection Redress*—The supplier shall have the right to inspect the rejected materials. The supplier and the purchaser shall agree to the quantity of rolls deemed unacceptable. The supplier shall then have the right to submit the same number of new rolls as replacement.

## 12. Packaging and Package Marking

12.1 The finished material shall be furnished as rolls. The rolls shall be wrapped securely to prevent shifting of material and to permit normal handling. If a roll contains a manufacturing splice, the splice shall be marked clearly; no roll shall contain more than one splice or two pieces.

12.2 Unless otherwise agreed upon by the supplier and purchaser, each product package shall be marked plainly with the supplier's name, the product name, "SBS" or similar



indication that the product is a SBS modified bitumen sheet material, the ASTM designation including type and grade, and the net coverage.

### 13. Keywords

13.1 modified bituminous sheet; polyester reinforcement; styrene butadiene styrene (SBS); thermoplastic elastomer

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*