



# Standard Specification for Atactic Polypropylene (APP) Modified Bituminous Sheet Materials Using a Combination of Polyester and Glass Fiber Reinforcements<sup>1</sup>

This standard is issued under the fixed designation D6223/D6223M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers prefabricated modified bituminous sheet materials reinforced with a combination of polyester fabric and glass fiber, with or without granules, that use atactic polypropylene (APP) as the primary modifier and are intended for use in the fabrication of multiple ply roofing and waterproofing membranes.

1.2 This specification is intended as a material specification only. Issues regarding the suitability of specific roof constructions or application techniques are beyond the scope of this specification.

1.3 The specified tests and property limits used to characterize the sheet materials covered by this specification are intended to establish minimum properties. In-place roof system design criteria such as fire resistance, field strength, impact/puncture resistance, material compatibility, uplift resistance, the need for field applied coatings, and others, are factors beyond the scope of this material specification.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.04 on Felts, Fabrics and Bituminous Sheet Materials.

Current edition approved Nov. 1, 2016. Published November 2016. Originally approved in 1998. Last previous edition approved in 2009 as D6223/D6223M – 02 (2009)<sup>ε</sup>. DOI: 10.1520/D6223\_D6223M-16.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

D1079 Terminology Relating to Roofing and Waterproofing  
D5147/D5147M Test Methods for Sampling and Testing  
Modified Bituminous Sheet Material  
D5636/D5636M Test Method for Low Temperature Unrolling  
of Felt or Sheet Roofing and Waterproofing Materials

## 3. Terminology

### 3.1 Definitions:

3.1.1 For definitions of terms used in this specification, refer to Terminology D1079.

## 4. Classification

4.1 Type I and II modified bituminous sheet materials reinforced with a combination of polyester fabric and glass fiber reinforcements, are covered by this specification (see Table 1).

4.2 The following grades are used to describe the material surfacing:

4.2.1 Grade G—Granule surfacing.

4.2.2 Grade S—Smooth surfacing.

## 5. Material and Manufacture

5.1 In the process of manufacture, the reinforcement is saturated with APP modified asphalt and is impregnated and coated on both sides with an APP modified bituminous coating. The APP modified bituminous coating shall be permitted to be compounded with a mineral stabilizer.

5.2 Grade G materials are surfaced on the weather side with mineral granules, except for any selvage. To prevent sticking in the roll, the reverse side and any selvage shall be permitted to be covered with a fine mineral surfacing or any other surfacing that will not interfere with adhesion or bonding of the lap during application.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Physical Properties of APP Modified Bituminous Sheet Materials Using a Combination of Polyester and Glass Fiber Reinforcements<sup>A</sup>**

Property	Type I	Type II
Peak load at 23 ± 2°C [73.4 ± 3.6°F] MD and XMD, before and after heat conditioning, min, kN/m [lbf/in.]	11.4 [65]	17.5 [100]
Elongation at 23 ± 2°C [73.4 ± 3.6°F] MD and XMD, before and after heat conditioning, at peak load, min, %	3	3
Peak load at -18 ± 2°C [0 ± 3.6°F] MD and XMD, min, kN/m [lbf/in.]	26.3 [150]	35 [200]
Elongation at -18 ± 2°C [0 ± 3.6°F] MD and XMD, at peak load, min, %	3	3
Tear Strength at 23 ± 2°C [73.4 ± 3.6°F], min, N [lbf]	533 [120]	800 [180]
Low temperature flexibility, before and after heat conditioning, max, °C [°F]	0 [32]	0 [32]
Dimensional stability, max, %	1	1
Compound stability, min, °C [°F]	110 [230]	110 [230]
Granule embedment, Grade G only, max, grams	2	2
Water absorption, max, %	3.2	3.2
Moisture content, max, %	1	1
Low temperature unrolling, max, °C [°F]	5 [41]	5 [41]

<sup>A</sup> The properties in this table are “as manufactured” unless otherwise noted.

5.3 To prevent sticking in the roll, any selvage will be surfaced with mineral or other surfacing material which will not interfere with adhesion or bonding during application.

## 6. Physical Properties

6.1 The sheet shall conform to the minimum physical properties prescribed in [Table 1](#).

6.2 The finished product shall not crack or be so sticky as to cause tearing or other material damage upon being unrolled at any product temperature between 4 and 60°C [40 and 140°F].

## 7. Dimensions, Mass, and Permissible Variations

7.1 The finished product shall conform to the following dimensions and variations:

7.1.1 The width of the roll shall be as agreed upon between the purchaser and the supplier and shall not vary more than 1 %.

7.1.2 The area of the roll shall be no less than as agreed upon between the purchaser and the supplier.

7.1.3 The selvage width shall be within 6 mm [ $\frac{1}{4}$  in.] of the nominal selvage width and shall be not less than 76 mm [3 in.] in width from the width edge of the sheet.

7.2 The mass and thickness of the finished product shall be as prescribed in [Table 2](#).

**TABLE 2 Dimensions and Mass of APP Modified Bituminous Sheet Materials Using a Combination of Polyester and Glass Fiber Reinforcements<sup>A</sup>**

Property	Type I	Type II
Thickness, min, mm [mils], Grade S	3.5 [140]	3.5 [140]
Grade G	4.0 [160]	4.0 [160]
Net mass per unit area, min., g/m <sup>2</sup> [lbs/100 ft <sup>2</sup> ] Grade S	3662 [75]	3662 [75]
Grade G	4394 [90]	4394 [90]
Bottom side coating thickness, min, mm [mils], Grade S	1 [40]	1 [40]
Grade G	1 [40]	1 [40]

<sup>A</sup> The properties in this table are “as manufactured” unless otherwise noted.

## 8. Workmanship, Finish, and Appearance

8.1 The finished product shall be completely coated in a continuous, unbroken film and shall be free of such defects as holes, tears, cracks, wrinkles or permanent deformations, blisters, ragged or untrue edges, and areas of uncoated reinforcement.

8.2 The surface of the weather side shall be uniform in finish and texture.

8.3 For Grade G products, mineral granules shall be uniformly distributed over the entire surface of the sheet in an even layer, excluding any selvage, and shall be firmly embedded in the APP modified bituminous coating. The line of demarcation between the granule surfaced portion of the weather side and any selvage shall be straight and parallel to the edges of the sheet.

8.4 When unrolled on a smooth plane, the sheet shall be straight and true so that the selvage will mate with an adjacent sheet, within the tolerance for the lap without wrinkles, buckles or fishmouths.

## 9. Sampling and Test Methods

9.1 Sample the material and determine the properties described in this specification in accordance with Test Methods [D5147/D5147M](#) unless otherwise indicated.

9.2 *Ultimate Elongation*—See Test Methods [D5147/D5147M](#), Section 6.

9.3 *High Temperature Stability*—Sample the material and determine the high temperature stability in accordance with Test Methods [D5147/D5147M](#), Section 15, and as described herein. Report the highest test temperature at which flowing, dripping, or drop formation does not occur. Materials may be tested in 5.5°C [10°F] increments.

9.4 *Low Temperature Unrolling*—Sample the material and determine the low temperature unrolling in accordance with Test Methods [D5636/D5636M](#), and as described herein. Report the lowest test temperature at which none of the specimens show cracking or surface rupture. The temperature, at or below which the product must pass is stated in [Table 1](#).



## 10. Inspection

10.1 *Inspection*—Inspection shall be in accordance with the requirements of this specification.

10.2 *Inspection Alternatives*—Alternative inspection requirements shall be determined by and as agreed upon between the purchaser and supplier.

## 11. Rejection and Resubmittal

11.1 *Failure to Conform*—Failure to conform to any of the requirements as stated in this specification constitutes grounds for rejection.

11.2 *Rejection Redress*—The supplier shall have the right to inspect the rejected materials. The supplier shall then have the right to submit the same number of new rolls as replacements.

## 12. Packaging and Package Marking

12.1 Unless otherwise agreed upon by the purchaser and supplier, each product package shall be plainly marked with the

supplier's name, the product brand, "APP" or similar indication that the product is an APP modified bitumen sheet material, the ASTM designation including type and grade, and the net coverage.

12.2 The rolls shall be securely wrapped or banded in a manner that completely encircles the roll and will prevent slipping or unrolling.

12.3 No roll shall contain more than two pieces, and no more than 3 % of the rolls in any lot shall contain two pieces. If a roll contains a manufacturing splice, the splice shall be clearly marked.

## 13. Keywords

13.1 atactic polypropylene (APP); glass fiber reinforcement; modified bituminous sheet; polyolefin film; polyester reinforcement

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*