



Designation: D6382/D6382M – 99 (Reapproved 2017)

Standard Practice for Dynamic Mechanical Analysis and Thermogravimetry of Roofing and Waterproofing Membrane Material¹

This standard is issued under the fixed designation D6382/D6382M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice covers test procedures and conditions that are applicable when Test Methods [D5023](#), [D5024](#), [D5026](#), [D5279](#), and [D5418](#) are used for conducting dynamic mechanical analysis of roofing and waterproofing membrane material in three-point bending, compression, tension, torsion, and dual cantilever modes, respectively. The specific method is selected by the analyst and depends on the membrane material and the operating principles of the individual instrument used for the analysis.

1.2 This practice covers test procedures and conditions that are applicable when Test Method [E1131](#) is used for conducting thermogravimetry of roofing and waterproofing membrane material.

1.3 Membrane materials include bituminous built-up roofing, polymer-modified bitumen sheets, vulcanized rubbers, non-vulcanized polymeric sheets, and thermoplastics. The membrane materials can be either nonreinforced or reinforced.

1.4 This practice is applicable to new membrane materials received from the supplier, those exposed artificially in the laboratory or outdoors on an exposure rack, and those sampled from field installations.

1.5 This practice contains notes which are explanatory and are not part of the mandatory requirements of this practice.

1.6 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appro-*

priate safety and health practices and determine the applicability of regulatory limitations prior to use.

1.8 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

2. Referenced Documents

2.1 *ASTM Standards:*²

[D1079](#) Terminology Relating to Roofing and Waterproofing
[D4092](#) Terminology for Plastics: Dynamic Mechanical Properties

[D5023](#) Test Method for Plastics: Dynamic Mechanical Properties: In Flexure (Three-Point Bending)

[D5024](#) Test Method for Plastics: Dynamic Mechanical Properties: In Compression

[D5026](#) Test Method for Plastics: Dynamic Mechanical Properties: In Tension

[D5279](#) Test Method for Plastics: Dynamic Mechanical Properties: In Torsion

[D5418](#) Test Method for Plastics: Dynamic Mechanical Properties: In Flexure (Dual Cantilever Beam)

[E473](#) Terminology Relating to Thermal Analysis and Rheology

[E1131](#) Test Method for Compositional Analysis by Thermogravimetry

[E1142](#) Terminology Relating to Thermophysical Properties

3. Terminology

3.1 *Definitions*—For definitions of terms used in this practice, refer to Terminologies [E473](#), [D1079](#), [D4092](#), and [E1142](#).

4. Summary of Practice

4.1 In conducting a dynamic mechanical analysis, the roofing or waterproofing membrane specimen is placed in a test

¹ This practice is under the jurisdiction of ASTM Committee [D08](#) on Roofing and Waterproofing and is the direct responsibility of Subcommittee [D08.20](#) on Roofing Membrane Systems.

Current edition approved May 1, 2017. Published May 2017. Originally approved in 1999. Last previous edition approved in 2011 as D6382/D6382M – 99 (2011) ^{ϵ 1}. DOI: 10.1520/D6382_D6382M-99R17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

chamber and subjected to a controlled, increasing temperature program. The temperature range can be from well-below (for example, -80°C) to somewhat (for example, 50°C) above room temperature. The glass transition temperature, storage modulus, loss modulus, and damping factor of the specimen are measured.

4.2 In conducting a thermogravimetry analysis, the roofing or waterproofing membrane specimen is placed in a test chamber and subjected to a controlled, increasing temperature program. The temperature range can be from about room temperature (for example, 20 to 40°C) to well-above room temperature (for example, 900°C), and the atmosphere of the chamber is controlled through the use of inert gas such as nitrogen or reactive gas such as air. The percent mass loss of the specimen is determined as a function of temperature.

5. Significance and Use

5.1 Dynamic mechanical analysis provides a measure of the rheological properties of roofing and waterproofing membrane materials.

5.2 Thermogravimetry is used to characterize the thermal stability of roofing and waterproofing membrane materials under the specific temperature program and gaseous atmosphere conditions selected for the analysis.

5.3 Both dynamic mechanical analysis and thermogravimetry are used to evaluate the effect of either laboratory-simulated or in-service exposure on roofing and waterproofing membrane materials.

5.4 Both dynamic mechanical analysis and thermogravimetry can be applied to asphalt shingles. However, their application to asphalt shingles is beyond the scope of this practice, which is limited to low-slope membrane materials at this time.

5.5 This practice can be useful in the development of performance criteria for roofing and waterproofing membrane materials.

DYNAMIC MECHANICAL ANALYSIS

6. Test Procedure

6.1 Select the specific test method (that is, Test Method **D5023**, **D5024**, **D5026**, **D5279**, or **D5418**) depending on the available instrument and specific type of roofing or waterproofing membrane material to be analyzed. If questions arise, consult the individual manufacturer's literature on instrument operation.

6.2 Prepare a specimen, appropriately sized for the specific instrument, cut in either the machine or cross machine direction of the membrane material.

6.3 Remove granules, if present on the surface of the membrane material, taking care to avoid damage to the specimen.

NOTE 1—Tweezers or a razor-edged laboratory knife have been found to be suitable for this purpose.

6.4 Remove dirt and bonding adhesive to the extent possible, if present on the surface of membrane materials sampled after outdoor exposure or from field installations (see

Note 2), taking care to avoid damage to the specimen. Use of solvents other than water is not permissible. If water is used, dry the sample overnight at $23 \pm 2^{\circ}\text{C}$ [$74 \pm 4^{\circ}\text{F}$] before analysis.

NOTE 2—In some cases where dirt or bonding adhesive is well adhered to the membrane material, it may not be possible to completely remove it. In such cases, the decision to conduct the analysis is left to the analyst. If the analysis is conducted, the presence of dirt or bonding adhesive on the specimen is included in the report.

7. Test Conditions

7.1 Conduct the dynamic mechanical analysis using the following conditions and parameters:

7.1.1 *Preconditioning*—Precondition the specimen in an oven for 1 h at $80 \pm 2^{\circ}\text{C}$ [$176 \pm 4^{\circ}\text{F}$] to provide a consistent thermal history prior to analysis. Then allow the preconditioned specimen to cool to $23 \pm 2^{\circ}\text{C}$ [$74 \pm 4^{\circ}\text{F}$] in a desiccator. Store the preconditioned specimen in the desiccator at $23 \pm 2^{\circ}\text{C}$ [$74 \pm 4^{\circ}\text{F}$] until conducting the analysis.

7.1.2 *Temperature Range*—The temperature range shall be -80 to 50°C [-112 to 122°F], with an allowed variation of $\pm 2^{\circ}\text{C}$ [$\pm 4^{\circ}\text{F}$].

7.1.3 *Low Temperature Stabilization*—The specimen shall remain at -80°C [-112°F] for 5 min before beginning an analysis.

7.1.4 *Heating Rate*—The heating rate shall be $2^{\circ}\text{C}/\text{min}$ [$4^{\circ}\text{F}/\text{min}$].

7.1.5 *Frequency*—The frequency shall be 1 Hz.

7.1.6 *Clamping Pressure*—The clamping pressure shall be in accordance with the equipment manufacturer's instructions.

8. Test Report

8.1 Report the generic type of membrane material, and indicate whether it was new, exposed artificially in the laboratory or outdoors on an exposure rack, or sampled from a field installation.

8.1.1 For membrane materials exposed in the laboratory, indicate the conditions and length of exposure.

8.1.2 For membrane materials exposed outdoors or sampled from field installations, indicate pertinent information including geographical location and exposure time or sample age.

8.2 Report whether dirt or bonding adhesive was removed from, or remained on, surfaces of membrane materials sampled after outdoor exposure or from field installations.

8.3 Report the test method used to conduct the dynamic mechanical analysis.

8.4 Report the information as required in the report section of the test method used.

THERMOGRAVIMETRY

9. Test Procedure

9.1 Conduct the thermogravimetry procedure in accordance with Test Method **E1131**.

9.2 Prepare a specimen having a mass within the range from 10 to 25 mg. The specimen shall be cut through the full thickness of the membrane material.

9.3 Remove granules, if present on the surface of the membrane material, taking care to avoid damage to the specimen (see **Note 1**).

9.4 Remove dirt and bonding adhesive to the extent possible, if present on the surface of membrane materials sampled after outdoor exposure or from field installations (see **Note 2**), taking care to avoid damage to the specimen. Use of solvents other than water is not permissible. If water is used, dry the sample overnight at $23 \pm 2^{\circ}\text{C}$ [$74 \pm 4^{\circ}\text{F}$] before analysis.

10. Test Conditions

10.1 Conduct the thermogravimetry analysis using the following conditions and parameters:

10.1.1 *Test Atmosphere*—The test atmosphere shall consist of an inert gas (for example, nitrogen or argon) for temperatures up to 600°C [1112°F], and air for temperatures beyond 600°C [1112°F].

10.1.2 *Temperature Range*—The minimum temperature shall be between 20 to 40°C [68 and 104°F], with an allowed variation of $\pm 2^{\circ}\text{C}$ [$\pm 4^{\circ}\text{F}$]. The maximum temperature shall be at least 900°C [1652°F].

10.1.3 *Heating Rate*—The heating rate shall be $20^{\circ}\text{C}/\text{min}$ [$36^{\circ}\text{F}/\text{min}$].

11. Test Report

11.1 Report the generic type of membrane material, and indicate whether it was new, exposed artificially in the laboratory or outdoors on an exposure rack, or sampled from a field installation.

11.1.1 For membrane materials exposed in the laboratory, indicate the conditions and length of exposure.

11.1.2 For membrane materials exposed outdoors or sampled from field installations, indicate pertinent information including geographical location and exposure time or sample age.

11.2 Report whether dirt or bonding adhesive was removed from, or remained on, surfaces of membrane materials sampled after outdoor exposure or from field installations.

11.3 In addition to the items specified in the Report Section of Test Method **E1131**, the report shall include the following information:

11.3.1 The percent mass lost on heating to 600°C [1112°F].

11.3.2 The percent mass lost on heating from 600°C [1112°F] to termination of the analysis.

11.3.3 The percent mass remaining as residue upon termination of the analysis.

12. Keywords

12.1 dynamic mechanical analysis; membrane materials; roofing; thermal analysis; thermogravimetry; waterproofing

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>