

Standard Practice for Sampling of Expanded Polystyrene Geofoam Specimens¹

This standard is issued under the fixed designation D7557/D7557M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

 ϵ^1 NOTE—Units information was editorially corrected in July 2013.

1. Scope

TERNATIONAL

1.1 This practice provides guidance on the location, frequency, and method of sampling representative specimens from large blocks of Expanded Polystyrene (EPS) Geofoam.

1.2 This practice is not intended to replace professional judgments nor should this guide be applied without consideration of a project's many unique aspects.

1.3 The word "standard" in the title of this guide means only that this guide has been approved through the ASTM International consensus process.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

D4439 Terminology for Geosynthetics

D6817 Specification for Rigid Cellular Polystyrene Geofoam

2.2 ISO Standard:³

ISO/IEC 17025:2005 General Requirements for the Competence of Testing and Calibration Laboratories

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, CP 56, CH-1211 Geneva 20, Switzerland, http://www.iso.org.

3. Terminology

3.1 *Definitions*—For definitions of general geosynthetic terms used in this standard refer to Terminology, D4439.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *Geofoam Lot*—a definite quantity of EPS Geofoam manufactured under conditions of production that are considered uniform.

4. Summary of Practice

4.1 EPS Geofoam is commonly used in geotechnical applications when an extremely lightweight material is required. This practice provides guidance for sampling EPS Geofoam specimens for ongoing quality control compliance to Specification D6817.

5. Significance and Use

5.1 This practice provides guidance on sampling of EPS geofoam in order to determine compliance to Specification D6817.

6. Procedure

6.1 Initial Sampling:

6.1.1 Select samples of the EPS Geofoam from a first production lot to ensure compliance with Specification D6817. Selection of samples shall be as agreed on between purchaser and supplier.

6.1.2 Initial sampling shall include sampling of three sets of specimens. The sets shall be selected from different regions of a single EPS Geofoam block. The regions shall include the corners of the EPS Geofoam block and the center of the EPS Geofoam block as shown in Fig. 1.

Note 1—Some EPS Geofoam suppliers may cut larger sized blocks into two or three smaller sized blocks. The smallest dimension of the block is the height.

6.1.3 A minimum of five specimens shall be cut from each of the three regions of the block. The specimens shall be distributed evenly through the height of the block. The specimens shall not be selected adjacent to the surface of the block.

6.1.4 The specimens shall be tested in accordance with Section 13.2 of Specification D6817.

¹ This practice is under the jurisdiction of ASTM Committee D35 on Geosynthetics and is the direct responsibility of Subcommittee D35.03 on Permeability and Filtration.

Current edition approved July 1, 2013. Published July 2013. Originally approved in 2009. Last previous edition approved in 2009 as D7557–09. DOI: 10.1520/D7557 _D7557M-09R13E01.

∰ D7557/D7557M – 09 (2013)^{ε1}



FIG. 1 EPS Geofoam Block Initial Sampling Locations

TABLE 1 EPS Geofoam Sampling Frequency

Initial Sampling	Ongoing Sample	
1 block from first lot	1 block per each 500 m ³ [650 yd ³] for first 2,000 m ³ [2600 yd ³]	1 block per each 2,000 m ³ [2600 yd ³] thereafter

6.1.5 Testing shall be conducted by a test laboratory in compliance with ISO/IEC 17025.

6.1.6 The average compressive resistance for the five specimens shall meet the requirements of Table 1 of Specification D6817 for the Type(s) tested. No individual sample result may be less than 90% of the minimum requirement.

6.2 Ongoing Sample:

6.2.1 Select samples of the EPS Geofoam from ongoing production lots at the frequency noted in Table 1 to ensure compliance with Specification D6817. Selection of samples shall be as agreed on between purchaser and supplier.

6.2.2 Ongoing sampling shall include sampling of one set of specimens. The set shall be selected from a random region of a single EPS Geofoam block.

6.2.3 A minimum of five specimens shall be cut from the random region of the block. The specimens shall be distributed evenly through the height of the block. The specimens shall not be selected adjacent to the surface of the block.

6.2.4 Sample testing shall be in accordance with 6.1.4 through 6.1.6.

7. Keywords

7.1 EPS; expanded polystyrenes; geofoams; geofoam lots; rigid cellular polystyrenes

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/