

INTERNATIONAL STANDARD

**Coaxial communication cables –
Part 1-308: Mechanical test methods – Test for tensile strength and elongation
for copper-clad metals**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2012 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

Useful links:

IEC publications search - www.iec.ch/searchpub

The advanced search enables you to find IEC publications by a variety of criteria (reference number, text, technical committee,...).

It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available on-line and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary (IEV) on-line.

Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.



IEC 61196-1-308

Edition 2.0 2012-10

INTERNATIONAL STANDARD

**Coaxial communication cables –
Part 1-308: Mechanical test methods – Test for tensile strength and elongation
for copper-clad metals**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

G

ICS 33.120.10

ISBN 978-2-83220-474-0

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references	5
3 Terms and definitions	5
4 Test for tensile strength and elongation at fracture for metals.....	6
4.1 Principle	6
4.2 Test equipment	6
4.3 Test specimen	6
4.4 Procedure	6
4.4.1 Determination of the original cross-sectional area (S_0)	6
4.4.2 Perform tensile and elongation test.....	6
4.5 Expression of results	7
4.6 Requirement.....	7

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COAXIAL COMMUNICATION CABLES –

**Part 1-308: Mechanical test methods –
Test for tensile strength and elongation
for copper-clad metals**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61196-1-308 has been prepared by subcommittee 46A: Coaxial cables, of IEC technical committee 46: Cables, wires, waveguides, R.F. connectors, R.F. and microwave passive components and accessories.

This second edition cancels and replaces the first edition published in 2005. It constitutes a technical revision. Changes from the previous edition of the document are the addition of test methods for annealed copper-clad conductors. This second edition makes a distinction between annealed and hard-drawn solid copper clad metals. Requirements are more precise than in the first edition.

The text of this standard is based on the following documents:

FDIS	Report on voting
46A/1041/FDIS	46A/1062/RVD

4 Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 61196 series, published under the general title *Coaxial communication cables*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

COAXIAL COMMUNICATION CABLES –

Part 1-308: Mechanical test methods – Test for tensile strength and elongation for copper-clad metals

1 Scope

This part of IEC 61196 applies to coaxial communication cables. It specifies test methods for tensile strength and percentage elongation at fracture for annealed and hard-drawn solid copper clad metals to be used as inner conductor for coaxial cables.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61196-1, *Coaxial communication cables – Part 1: Generic specification – General, definitions and requirements*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 61196-1, as well as the following, apply.

3.1 gauge length

L

length of the section of the test piece on which elongation is measured

3.1.1 original gauge length

L_0

gauge length before application of force

3.1.2 gauge length at fracture

L_t

gauge length at fracture of the test piece

3.2 tensile strength

R_m

stress corresponding to the maximum force (F_m)

3.3 maximum force

F_m

the greatest force which the test piece withstands during the test once the yield point has been passed

For materials without yield point, it is the maximum value during the test.

3.4

percentage elongation at fracture

A_t

total elongation (elastic elongation plus plastic elongation) of the gauge length at the moment of fracture expressed as a percentage of the original gauge length (L_o)

4 Test for tensile strength and elongation at fracture for metals

4.1 Principle

The test involves straining a test piece by tensile force, for the determination of the tensile strength and percentage elongation at the time of fracture.

The test is carried out at ambient temperature between 10 °C and 35 °C, unless otherwise specified.

4.2 Test equipment

The error of indication of the force-measuring system of the testing machine shall not be greater than 1 %.

An extensometer or other device suitable for measuring elongation over a gauge length of 250 mm shall be used. The equipment shall have a vernier resolution not worse than 0,25 mm.

4.3 Test specimen

The original gauge length (L_o) of test specimen should be 250 mm, and the total length of the test specimen should be about 300 mm.

The test specimen shall be straightened by hand or other applicable manners.

4.4 Procedure

4.4.1 Determination of the original cross-sectional area (S_o)

The original cross-sectional area (S_o) shall be determined to an accuracy of ± 1 %.

The original cross-sectional area shall be expressed as follows.

$$S_o = \frac{1}{4} \pi d^2$$

where

S_o is the original cross-sectional area, in mm²;

D is the arithmetic mean of diameter, in mm; it is calculated from the arithmetic mean of two 90° measurements carried out around the circumference of the conductor.

4.4.2 Perform tensile and elongation test

A test specimen shall be fitted in the jaws of the testing machine and loaded to 10 % of the minimum specified breaking load. An extensometer or other suitable device shall be attached to the test specimen to measure the extension over 250 mm.

The elongation shall be observed while applying a tensile load to the specimen and the maximum tensile force and elongation at which fracture occurs shall be recorded as the tensile force (F_m) and elongation (L_f) of the specimen.

For hard-drawn conductors, the rate of jaw travel shall not exceed 25 mm/min.

For annealed conductors, the rate of jaw travel shall not exceed 300 mm/min.

Tests in which a fracture occurs within 25 mm of the jaws or extensometer clamps shall be disregarded.

4.5 Expression of results

The tensile strength shall be expressed as follows.

$$R_m = F_m/S_0$$

where

R_m is the tensile strength, in N/mm²;

F_m is the stress corresponding to the maximum force, in N;

S_0 is the original cross-sectional area, in mm².

The percentage elongation at fracture shall be expressed as follows.

$$A_t = (L_t - L_0)/L_0 \times 100 \%$$

where

A_t is the percentage elongation at fracture;

L_t is the gauge length at fracture;

L_0 is the original gauge length.

4.6 Requirement

The tensile strength and elongation shall be as specified in the relevant cable specification.

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

3, rue de Varembé
PO Box 131
CH-1211 Geneva 20
Switzerland

Tel: + 41 22 919 02 11
Fax: + 41 22 919 03 00
info@iec.ch
www.iec.ch