TECHNICALIECSPECIFICATIONTS 61244-3

Second edition 2005-11

Long-term radiation ageing in polymers -

Part 3: Procedures for in-service monitoring of low-voltage cable materials



Reference number IEC/TS 61244-3:2005(E)

Publication numbering

As from 1 January 1997 all IEC publications are issued with a designation in the 60000 series. For example, IEC 34-1 is now referred to as IEC 60034-1.

Consolidated editions

The IEC is now publishing consolidated versions of its publications. For example, edition numbers 1.0, 1.1 and 1.2 refer, respectively, to the base publication, the base publication incorporating amendment 1 and the base publication incorporating amendments 1 and 2.

Further information on IEC publications

The technical content of IEC publications is kept under constant review by the IEC, thus ensuring that the content reflects current technology. Information relating to this publication, including its validity, is available in the IEC Catalogue of publications (see below) in addition to new editions, amendments and corrigenda. Information on the subjects under consideration and work in progress undertaken by the technical committee which has prepared this publication, as well as the list of publications issued, is also available from the following:

IEC Web Site (<u>www.iec.ch</u>)

Catalogue of IEC publications

The on-line catalogue on the IEC web site (<u>www.iec.ch/searchpub</u>) enables you to search by a variety of criteria including text searches, technical committees and date of publication. On-line information is also available on recently issued publications, withdrawn and replaced publications, as well as corrigenda.

• IEC Just Published

This summary of recently issued publications (<u>www.iec.ch/online_news/justpub</u>) is also available by email. Please contact the Customer Service Centre (see below) for further information.

• Customer Service Centre

If you have any questions regarding this publication or need further assistance, please contact the Customer Service Centre:

Email: <u>custserv@iec.ch</u> Tel: +41 22 919 02 11 Fax: +41 22 919 03 00

TECHNICALIECSPECIFICATIONTS 61244-3

Second edition 2005-11

Long-term radiation ageing in polymers –

Part 3: Procedures for in-service monitoring of low-voltage cable materials

© IEC 2005 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale International Electrotechnical Commission Международная Электротехническая Комиссия



For price, see current catalogue

U

CONTENTS

– 2 –

FO	REWORD	4	
INT	RODUCTION	6	
1	Scope	7	
2	Normative references	7	
3	Abbreviations	7	
4	Requirements of a monitoring technique	8	
5 Techniques available			
	5.1 General	8	
	5.2 Local tests without sampling	9	
~	5.3 Local tests with micro-sampling	.11	
6	Summary	.14	
Rih	liography	28	
010		.20	
- :	. Ochomotic diagram chewing the execution principles of the conic velocity		
met	ter [1]	. 16	
Fig	ure 2 – Sonic velocity test results [3]	. 17	
Fig first	ure 3 – Variation in IR absorbance with wavelength for PVC material and the use of t derivative to eliminate baseline shifts [1]	. 18	
Fig eloi	ure 4 – Correlation of first derivative of IR absorbance at 1 640 nm to 1 650 nm and ngation at break for thermal ageing of PVC at 110 °C [1]	.19	
Fig	ure 5 – Schematic diagram and photographs of prototype torque tester	. 20	
Fig the	ure 6 – Elongation at break versus torque value for flame-retardant PVC cables rmally aged at 158 °C [5]	.21	
Fig seq	ure 7 – Elongation at break versus torque value for PVC cables exposed to quential radiation ageing to 0,5 MGy and thermal ageing at 120 °C [5]	.21	
Fig 120	ure 8 – Elongation at break versus torque value for PVC cables thermally aged at) °C [5]	.22	
Fig the tem	ure 9 – Correlation of tensile elongation with modulus measurements made using modulus profiling apparatus for a CSPE jacket aged at the five indicated nperatures [6]	.22	
Fig the tem	ure 10 – Correlation of tensile elongation with modulus measurements made using modulus profiling apparatus for a CP jacket aged at the three indicated peratures (from Reference [8])	.23	
Fig the env	ure 11 – Correlation of tensile elongation with modulus measurements made using modulus profiling apparatus for a CSPE jacket aged at the four indicated combined vironments [9]	.23	
Fig for	ure 12 – Correlation of tensile elongation with NMR relaxation time measurements a CP jacket aged at the three indicated temperatures (from Reference [8])	.24	
Fig for	ure 13 – Correlation of tensile elongation with NMR relaxation time measurements a XLPO insulation aged at the two indicated temperatures [12]	.24	
Fig	ure 14 – Carbonyl absorbance as a function of the radiation dose for XLPE [15]	.25	

Figure 15 – Carbonyl absorbance as a function of thermal ageing for XLPE [14]	25
Figure 16 – Correlation of tensile elongation with solvent uptake factor for a CP jacket aged at the three indicated temperatures [8]	26
Figure 17 – Elongation results compared to uptake and gel results for XLPE insulation aged at 130 °C [18]	26
Figure 18 – Elongation results compared to uptake and gel results for an XLPO insulation aged at 125 °C [18]	27

Table 1 – Summary of currently available techniques for cable condition monitoring......15

INTERNATIONAL ELECTROTECHNICAL COMMISSION

LONG-TERM RADIATION AGEING IN POLYMERS -

Part 3: Procedures for in-service monitoring of low-voltage cable materials

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committee; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a technical specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC 61244-3, which is a technical specification, was prepared by subcommittee 15E: Methods of test, of IEC technical committee 15: Insulating materials, which has now been merged with IEC technical committee 98: Electrical insulation systems into IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems (provisional title).

This second edition cancels and replaces the first edition, published in 1998, and constitutes a technical revision. The main technical changes with regard to the previous edition are as follows:

- a) as there have been technical advances in established test methods and newer methods have become available, several additions have been made to the techniques available in Clause 5;
- b) some of the techniques listed in the previous edition were found to be either unsuitable for use as cable monitoring methods in plants, or less sensitive to radiation ageing than other methods; these techniques have now been removed;
- c) a list of abbreviations and their meanings has been added.

The text of this technical specification is based on the following documents:

Enquiry draft	Report on voting
15E/252/DTS	15E/258/RVC

Full information on the voting for the approval of this technical specification can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

IEC 61244 consists of the following parts, under the general title *Long-term radiation ageing in polymers*:

- Part 1 Techniques for monitoring diffusion-limited oxidation
- Part 2: Procedures for predicting ageing at low dose rates
- Part 3: Procedures for in-service monitoring of low-voltage cable materials

The committee has decided that the contents of this publication will remain unchanged until the maintenance result dateindicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- transformed into an International standard,
- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

INTRODUCTION

Polymers are widely used as electric insulating materials (e.g. in cables for control, instrumentation and power) in environments in which they are exposed to radiation. In such applications, these materials may well be required to survive the full working life of the plant, which may be more than 40 years, and possibly accident conditions up to and at the end of their working life. Although considerable data are available on the behaviour of polymeric insulating materials under irradiation, there is still some uncertainty on the effects of long-term, low-dose rate irradiation such as would be experienced by cables. There is, therefore, a requirement for techniques for monitoring the state of degradation of cable materials *in situ* throughout the lifetime of the plant. Suitable cable monitoring techniques would also be important to surveillance programmes in support of plant life extension and licence renewal. Although this technical specification is primarily aimed at cable condition monitoring in radiation environments, it can also be applied to other polymeric components. Many of the techniques are equally applicable to thermal-only ageing of polymeric components.

LONG-TERM RADIATION AGEING IN POLYMERS -

Part 3: Procedures for in-service monitoring of low-voltage cable materials

1 Scope

This part of IEC 61244, which is a technical specification, summarizes the main cable monitoring techniques which are currently being assessed worldwide. These techniques are primarily aimed at monitoring degradation of low-voltage cables. Most of the methods are at the development stage and require more in-plant evaluation before they could be recommended as standard techniques. The advantages and disadvantages of each method, and its current state of development, are outlined in the following clauses.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60544-5:2003, Electrical insulating materials – Determination of the effect of ionizing radiation – Part 5: Procedures for assessment of ageing in service

3 Abbreviations

Butyl rubber
Condition monitoring
Chlorosulphonated polyethylene
Chloroprene
Diffusion limited oxidation
Differential scanning calorimetry
Ethylene propylene rubber
Ethylene vinyl acetate
Infrared
Oxidation induction time
Oxidation induction temperature
Near infra-red reflectance
Nuclear magnetic resonance
Polyethylene
Polyvinyl chloride
Polyetheretherketone
Styrene butadiene rubber
Thermo-gravimetric analysis
Cross-linked polyethylene
Cross-linked polyolefin

4 Requirements of a monitoring technique

There is a range of requirements which the ideal cable monitoring technique would need to satisfy. In practice, no one technique can currently satisfy all of the requirements and a range of techniques is likely to be needed. In each case, baseline data (i.e. data on unaged material of the same formulation and manufacturer) are needed to make full use of the techniques.

- 8 -

The ideal monitoring technique would have the following attributes:

- non-intrusive, causing minimal cable disturbance;
- capable of use during normal operation;
- not require disconnection of equipment;
- related to an identifiable degradation criterion;
- applicable to a wide range of cable materials and configuration;
- applicable at accessible locations;
- capable of measuring degradation at hot-spots;
- reproducible and capable of compensating for environmental conditions (temperature, humidity);
- less expensive to implement than periodic cable replacement;
- readily available reference data.

5 Techniques available

5.1 General

There is a wide range of possible techniques which are being considered for cable monitoring. A few are already in use in-plant, whilst others are only at the laboratory evaluation stage. Those methods for which there is most experience have been published in IEC 60544-5. Such methods consist of:

- indenter;
- oxidation induction time and oxidation induction temperature;
- thermo-gravimetric analysis;
- density measurements;
- equipment deposit.

The monitoring methods which have been evaluated can be grouped together under generic types, as follows:

- a) Local tests without sampling
 - indenter;
 - sonic velocity;
 - near infrared reflectance;
 - torque testing;
- b) Local tests with micro-sampling
 - modulus profiling;
 - NMR relaxation;
 - infrared spectroscopy;
 - oxidation induction time (OIT) and temperature (OITP);

- thermogravimetric analysis (TGA);
- density measurements;
- gel fraction and solvent uptake.

Each of these types of test is described in more detail in the following subclauses.

5.2 Local tests without sampling

5.2.1 General

The term "local" refers to techniques which give information on the state of the cable at the measuring point only and are thus likely to miss localized degraded areas. These methods can only be applied in man-accessible areas and are generally limited to tests of the cable jacket material except at terminations where the insulation is exposed. Where the techniques have been cross-correlated with changes in elongation at break, which is a consistent indicator of degradation, these methods have a predictive capability. This type of test will provide immediate data in-plant on the state of the cable. Where the cable jacket is more likely to degrade than the insulation (which is often true), the methods provide early warning of cable failure. Local bend tests by manipulation of the cable by hand can give qualitative information when carried out by experienced personnel.

5.2.2 Indenter

The indenter is an instrument that determines a parameter related to the compressive modulus of a polymer. By driving an instrumented probe of known shape into the surface of the polymer, the load exerted is measured. Details of the method are given in IEC 60544-5.

5.2.3 Sonic velocity

This technique is under development and at present (2005), has only been tested on PVC based cables [1-3]¹. Sonic velocity testing is based on the fact that the velocity of sound in a solid medium is dependent on both the density and the elastic modulus and is given by:

$$C^2 = \frac{E}{\rho}$$

where

- C is the sonic velocity;
- *E* is the elastic modulus;
- ρ is the polymer density.

Since both modulus and density can change during ageing of cable materials, changes in sonic velocity would be expected to occur on ageing.

The tester uses piezoelectric transducers to transmit and receive a series of pulses as shown schematically in Figure 1. The signal transit times can be plotted as a function of transducer separation distance (up to a few centimetres) to obtain the slope which represents velocity. Sonic velocity measurements have been made at 20 kHz on a series of PVC jacketed cables and on strips of jacket material cut from the cables. Comparison between the data obtained on the test strips and the complete cables has shown that the technique is dependent on the cable geometry and adjacent shielding and insulation components. The magnitude of the sonic velocity at this frequency also varies considerably with different formulations of PVC, therefore baseline data would be required for each type of cable used in a plant if the technique was to be of practical use [1]. Other work, using 1MHz pulses [2][3], found the sonic velocity to be strongly dependent on the degradation of PVC jacket materials but independent of cable geometry and PVC formulation (Figure 2).

¹ Figures in square brackets refer to the bibliography.

Limitations

The sonic velocity tester measures properties of the cable jacket over a small volume between the transducer probes. The measurements obtained can be strongly dependent on the cable construction and the specific formulation of the jacket material. Therefore, extensive baseline data may be required. The technique is still under development and has so far only been tested on PVC jacketed cables. At present, a prototype portable tester has been developed but it has not been used for field use. Its high sensitivity to ageing degradation indicates that it may well be worth further development.

5.2.4 Near infrared reflectance

Changes in the infrared spectrum of polymers are known to occur with ageing, primarily in functional groups such as carbonyl (C=O), hydroxyl (O-H) and carboxyl (COOH). These functional groups are normally observed in the infrared spectrum in transmission, but for use in-plant a portable unit based on near-IR reflectance (NIR) using a fibre optic probe would be more suitable. NIR is also being used as a method for identifying cable materials and compounds [4].

NIR reflectance measurements have been carried out on PVC jacketed cables in the wavelength range 1 300 nm to 2 100 nm (7 692 cm⁻¹ to 4 762 cm⁻¹) [1] using a fibre optic probe pressed against the cable jacket. Baseline shifts arising from small changes in optical path length are often seen in the absorbance spectra. These small baseline shifts can be eliminated by using the first derivative of the absorbance spectra (Figure 3), since the first derivative is the slope of the absorbance spectrum at each wavelength. Various regions of the IR spectrum were found to correlate well with changes in the elongation at break of the PVC material tested; for example, changes in the spectrum at 1 640 nm to 1 650 nm (6 098 cm⁻¹ to 6 060 cm⁻¹) are shown in Figure 4 for thermal ageing of PVC. This technique using fibre optic probes for reflectance measurements is at an early stage of development.

Limitations

The NIR reflectance spectrum obtained is only from a thin surface layer of the cable material being tested. This surface may not be representative of the state of degradation of the bulk of the material. As in the other techniques in this category, data are limited to the immediate area of the probe. Care must also be taken in interpreting the data as some stabilizing additives in polymers have peaks in the same range of wavelengths. The technique is not sensitive to the cable geometry or construction but calibration curves would be required for each cable material. NIR is not applicable to carbon-filled materials.

5.2.5 Torque tester

The degradation of cable jacket materials can also be determined using a torque-strain response method [5]. A pair of chucks are used to grip the outside of the cable and a small angle torque, in the range 5° to 10°, is applied to one of the chucks at up to 2 Hz. A schematic diagram of the apparatus for such measurements is shown in Figure 5a; Figures 5b and 5c show prototype benchtop and portable versions of the torque tester. Preliminary data on the behaviour of PVC cables have been used to optimize the test conditions for the torque method.

The effect of torsion frequency on the torque values obtained is small in the frequency range 0 Hz to 2 Hz; for PVC the optimum frequency is 0,8 Hz. In both as-received and aged cables the torque values measured increase linearly with the applied torque angle up to 10°. At higher torque angles, components other than the jacket material will significantly contribute to the values obtained. For a non-destructive technique, a maximum torque angle of 10° is recommended. The effect of the length of cable between the chucks has also been investigated. At shorter cable lengths, the measured response will be strongly dependent on the insulation, conductors and any shielding components, whereas as the cable length increases, the sensitivity of the torque-strain response will decrease. The optimum cable length between chucks is 50 mm for PVC cables.

There is a strong correlation between the torque values measured using the prototype tester and elongation at break, both for thermally aged material and for cables subjected to sequential radiation and thermal chemical ageing (Figures 6 and 7). A linear relationship between elongation and torque is found over a wide range of elongation values. Deviations from this linear relationship are only observed when heterogeneous oxidation has occurred in the accelerated tests (Figure 8). The torsion test is a measure of the bulk properties of the jacket material whereas elongation at break is determined by crack initiation in the more highly oxidised surface layer in this material. In most cable applications in nuclear plants, homogeneous oxidation is likely to occur.

A portable version of the torque tester which could be clamped onto sections of cable in-plant has been developed (Figure 5c). This enables data to be taken non-destructively on accessible lengths of cable *in situ*.

Limitations

As in all local tests, measurements are limited to man-accessible areas. Since torque values will be significantly affected by differences in cable construction and geometry, baseline data for a wide range of cable types would be needed in practice. If there are environmental conditions in-plant which give rise to heterogeneous oxidation, the technique would tend to underestimate the degree of degradation of the jacket material. The technique is invasive as it requires significant manipulation of the cable, but is essentially non-destructive.

5.3 Local tests with micro-sampling

5.3.1 General

These methods are also limited to man-accessible areas and mainly provide information on the jacket materials. Insulation materials can only be accessed at terminations. Where the methods are cross-correlated with baseline data on changes in elongation at break they have a predictive capability. All of these techniques are laboratory based with a varying degree of complexity of equipment required.

Although some experience of use of these methods in-plant has been built up, there is considerable resistance from utilities in some countries over the application of sampling techniques. Each of these methods is briefly described in the following subclauses. For details of these methods, the cited references should be consulted.

5.3.2 Modulus profiling

Modulus profiling is a technique that has been developed over the past 15 years that allows quantitative mapping of inverse tensile compliance measurements (closely related to tensile modulus) to be made with a resolution of ~50 μ m [6][7]. The resolution implies that measurements can be made on small pieces of cable jacket or insulation material. The technique is based on extensive but relatively simple modifications of a commercial thermomechanical analyser. It involves sequential two-step loading of a stainless steel, paraboloidally-shaped tip into the polished cross-section of the sample of interest with quantitative monitoring of the indentation using a linearly variable differential transducer. The amount of indentation coupled with the probe geometry and the loading history leads to "modulus" values with typical scatter usually around ± 5 %.

Since the technique is sensitive to changes in modulus, it has been found to be applicable to the same types of materials as the indenter. Figures 9 and 10 show typical correlations found between tensile elongation results and modulus measurements from accelerated thermal ageing studies. Figure 9 gives the correlations found for five ageing temperatures for thin (0,4 mm thick) individual chlorosulphonated polyethylene (CSPE) jackets, whereas Figure 10 shows such correlations at three accelerated ageing temperatures for a chloroprene (CP) jacket. Figure 11 shows results for a CSPE jacket aged at the four different combined radiation plus temperature environments indicated on the figure. For all three examples it is clear that an excellent correlation exists that appears to be independent of the ageing condition.

This observation is extremely encouraging since this suggests that similar correlations might be expected under the lower temperatures and dose rates occurring in actual plant environments. In addition it is clear that 50 % absolute elongation (a "failure" criterion that is often used) is reached when the modulus value reaches ~25 MPa to 35 MPa. Similar results taken on one CP jacket and seven CSPE jackets aged in thermal-only and combined environments indicate that 50 % absolute elongation is typically reached when the modulus attains a value of around 35 MPa \pm 15 MPa [8][9].

Therefore a "universal" failure value of \sim 35 MPa for CP and CSPE jacket materials might be appropriate when monitoring modulus results, a tremendous potential advantage when monitoring materials that have not been or cannot be studied under accelerated ageing conditions.

Limitation

Sampling can only be made in man-accessible areas and is therefore limited mainly to the jacket materials or insulation materials at accessible conductor terminations. Considerable baseline data may be needed to find the correlation of the technique to elongation.

5.3.3 NMR relaxation

This method is based on increasing the sensitivity of nuclear magnetic resonance (NMR) relaxation measurements by swelling the sample in a suitable solvent [8][10-12]. Measurements are easily done on many commercial NMR machines, are extremely reproducible and typically require less than 15 min to 20 min for sample preparation, data accumulation and data analysis.

Screening studies of thermally aged materials indicate that the NMR approach is applicable to most important cable materials. This applicability includes XLPO insulations [12] that are generally difficult to evaluate with many available CM techniques, because their material properties are dominated by the presence of a high modulus crystalline phase. Since NMR relaxation times are sensitive to the crosslink density in the amorphous phase of a material, the confounding effects of the crystallites on mechanical properties are eliminated.

Figures 12 and 13 show the correlation of NMR results (proton spin-spin relaxation time T_2) with elongation results for a thermally aged CP jacket and a thermally aged XLPO insulation, respectively. Typically, 10 mg samples are utilized for the measurements. However, since results have been demonstrated on samples as small as 0,1 mg [11], the NMR approach can be considered as essentially non-destructive. In addition, the ability to monitor such small samples might prove useful for assaying the condition of samples that would otherwise be difficult to study such as composite thin insulations.

Limitations

Even though extremely small samples are needed for this technique, sampling can only be made in man-accessible areas and is therefore limited mainly to the jacket materials or insulation materials at accessible conductor terminations. Considerable baseline data are required on the specific polymers used in cables in order to determine how much the NMR relaxation time must change before concern over degradation exists.

5.3.4 Infrared spectroscopy (IR)

Changes in the infrared spectrum of polymers are known to occur with ageing, primarily in functional groups such as carbonyl (C=O), hydroxyl (O-H) and carboxyl (COOH). An alternative to reflectance measurements in-plant is to take samples from the cable material and measure the IR spectrum in the laboratory. Such samples would usually be in the form of scrapings or slivers of material cut from the surface, but sufficiently small to not affect the operation of the cable. Changes in the carbonyl peak at about 1 720 cm⁻¹ are most frequently used for monitoring changes in the state of degradation of the material [13-15].

Figure 14 shows the change in carbonyl absorbance for radiation aged XLPE and Figure 15 shows the change for thermal ageing of XLPE. This functional group is sensitive to the early stages of oxidative degradation but may not be sufficiently sensitive in the later stages when mechanical properties are significantly degraded.

Limitations

IR spectra taken from samples are limited to the surface layers of the cable jacket unless exposed insulation is accessible. The depth of material sampled is greater than for the inplant IR reflectance measurements, but may still not be representative of the bulk material. The technique is limited to those parts of the cables that are man-accessible for sampling and is not very sensitive to the later stages of degradation. The technique is not suitable for carbon-filled polymers.

5.3.5 Oxidation induction time (OIT) and temperature (OITP)

Oxidation induction tests utilize micro-samples of material which can be taken from the component (e.g. cable jacket material) without affecting functionality. These tests utilize thermal analysis using commercial differential scanning calorimetry (DSC) equipment to determine either an oxidation induction time at constant temperature, or an oxidation induction temperature (OITP) at a constant temperature ramp rate. The two methods are complementary, in that OITP is often useful where OIT is difficult to determine. The OIT decreases with increasing degradation of the material. Details of the method are given in IEC 60544-5.

5.3.6 Thermogravimetric analysis (TGA)

Like oxidation induction tests, thermogravimetric analysis utilizes micro-samples of material which can be taken from the component without affecting functionality. These tests use commercial standard laboratory thermal analysis equipment to monitor the mass loss in the sample as the sample temperature is ramped up at a constant rate. The absolute values obtained in the TGA tests are dependent on the oxygen content in the sample chamber, with higher onset values being observed with lower oxygen content. The TGA temperature tends to decrease with increasing radiation degradation. Details of the method are given in IEC 60544-5.

5.3.7 Density

When polymeric materials age in air, oxidation normally dominates the degradation. The oxidation involves a mixture of scission and crosslinking processes, leading to the generation of oxidation products along the polymer chain and the generation of gaseous degradation products. Easily measurable density increases result from these chemical changes. Details of the method are given in IEC 60544-5.

5.3.8 Gel fraction and solvent uptake measurements

These relatively simple measurements [8][16-18] require small samples of material to be removed from cables. The sample is initially weighed then boiled in a good solvent after which it is weighed when swollen by the solvent. The sample is then dried in a vacuum oven to drive off the solvent and finally weighed when dry. The solvent uptake is defined as the swollen weight over the final dried weight and the gel fraction is given by the final weight divided by the initial weight. The gel fraction goes up when crosslinking processes dominate scission and down when the opposite occurs. Higher crosslinking leads to less swelling, whereas swelling goes up when scission dominates crosslinking. Since changes in modulus and hardness have similar sensitivities to the mix between crosslinking and scission, swelling and gel measurements are found to be good condition monitoring techniques for materials and environments similar to those found appropriate to the indenter and modulus profiling. The measurements have been found to be useful for PVC and many rubbers including butyl, CP, and CSPE [8][18]. Figure 16 for example shows solvent uptake ratio versus elongation results

for a CP jacket at three different ageing temperatures [8]. These techniques also show promise for XLPO materials as seen for an XLPE material [18] aged at 130 °C (Figure 17) and an XLPO material aged at 125 °C (Figure 18). When solvent uptake shows sensitivity to ageing, the difficulties associated with weighing swollen samples accurately leads to a sample size requirement of ~50 mg [8]. On the other hand, when gel is an appropriate technique, the ease of obtaining very accurate values for the initial and final dry weights means that samples weighing 1 mg or less can be used.

Limitations

Sampling can only be made in man-accessible areas and is therefore limited mainly to the jacket materials or insulation materials at accessible conductor terminations. Considerable baseline data are required on the specific polymers used in cables in order to determine how much the gel and solvent uptake must change before concern over degradation exists.

6 Summary

There is a wide range of techniques in use or being developed for condition monitoring in cables. These methods are summarized in Table 1, with an indication of their main limitations, current status and relative equipment cost. The most advanced techniques are published in IEC 60544-5.

No one technique is likely to be suitable for all types of cable materials or cable configurations, but sufficient techniques are available, or are being developed, to cover most of the requirements for condition monitoring in the near future.

Technique	Parameter measured	Materials tested	Limitations *	Current status (as per 2005	Relative instrumentation cost	References
Local tests – without sampling *						
– Indenter	Modulus of elasticity	Elastomers, CSPE, thermally aged PVC, polyolefins		а	Moderate	IEC 60544-5
- Sonic velocity Velocity of sound		Thermally aged PVC	Can be dependent on cable construction and formulation	С	Moderate	[1-3]
 Near infrared reflectance 	IR reflectance	Thermally aged PVC	Surface contamination; not applicable to carbon- filled polymers	С	High	[4]
- Torque tester Torque		PVC	Dependent on cable construction	С	Moderate	[5]
Local tests – with sampling *						
- Modulus profiling	Modulus of elasticity	Elastomers, CP, CSPE, EPR, silicone		а	Moderate	[6], [7]
- NMR relaxation	NMR relaxation time	Elastomers, CP, CSPE, EPR, XLPO		b	Moderate	[8],[10-12]
- IR spectroscopy	IR absorbance	XLPE, PE, SBR, EPR	Less sensitive to late stages of degradation; not applicable to carbon-filled polymers	b	High	[13-15]
 Oxidation induction time/temperature 	Onset of oxidation	XLPE, EPR, PEEK, EVA	Surface contamination; not recommended for PVC	а	Moderate	IEC 60544-5
- Thermogravimetric analysis	Mass loss	Radiation aged PVC	Not applicable to thermally aged PVC	а	Moderate	IEC 60544-5
– Density	Density	XLPE, PE, EPR, CSPE, PVC		а	low	IEC 60544-5
 Gel fraction and solvent uptake 	Final dry weight/initial weight	Elastomers, CP, CSPE, XLPO, PVC, BR		а	Low (but labour intensive)	[8],[16-18]
	Weight swollen/final dry weight					

Table 1 – Summary of currently available techniques for cable condition monitoring

* All local tests limited to man-access areas, and limited to jacket materials except at terminations. For local tests with sampling, all techniques limited to surface properties.

^a Technique currently in use, considerable experience and data.

^b Technique at laboratory stage, still under development.

^c Technique investigated, not under active development. or in active use

LICENSED TO MECON Limited. - RANCHI/BANGALORE FOR INTERNAL USE AT THIS LOCATION ONLY, SUPPLIED BY BOOK SUPPLY BUREAU.

TS 61244-3 © IEC:2005(E)

-15 -



– 16 –

Figure 1 – Schematic diagram showing the operating principles of the sonic velocity meter [1]



- 17 -

Figure 2a – Example of the relation between the propagation time of ultrasonic waves and elongation at break for a PVC sheath material



Figure 2b – Comparison between the master curve and various cables from different manufacturers Figure 2 – Sonic velocity test results [3]



– 18 –

Figure 3 – Variation in IR absorbance with wavelength for PVC material and the use of first derivative to eliminate baseline shifts [1]



- 19 -

Figure 4 – Correlation of first derivative of IR absorbance at 1 640 nm to 1 650 nm and elongation at break for thermal ageing of PVC at 110 °C [1]



Figure 5a – Schematic diagram of prototype device for torque measurement of cables [5]



- 20 -

Figure 5b – Prototype bench top torque tester

IEC 2351/05



Figure 5c – Prototype portable version of the torque tester

Figure 5 – Schematic diagram and photographs of prototype torque tester



Figure 6 – Elongation at break versus torque value for flame-retardant PVC cables thermally aged at 158 °C [5]



Figure 7 – Elongation at break versus torque value for PVC cables exposed to sequential radiation ageing to 0,5 MGy and thermal ageing at 120 °C [5]



- 22 -

Figure 8 – Elongation at break versus torque value for PVC cables thermally aged at 120 °C [5]



Figure 9 – Correlation of tensile elongation with modulus measurements made using the modulus profiling apparatus for a CSPE jacket aged at the five indicated temperatures [6]



Figure 10 – Correlation of tensile elongation with modulus measurements made using the modulus profiling apparatus for a CP jacket aged at the three indicated temperatures (from Reference [8])



Figure 11 – Correlation of tensile elongation with modulus measurements made using the modulus profiling apparatus for a CSPE jacket aged at the four indicated combined environments [9]



- 24 -

Figure 12 – Correlation of tensile elongation with NMR relaxation time measurements for a CP jacket aged at the three indicated temperatures (from Reference [8])



Figure 13 – Correlation of tensile elongation with NMR relaxation time measurements for a XLPO insulation aged at the two indicated temperatures [12]



- 25 -

Figure 14 – Carbonyl absorbance as a function of the radiation dose for XLPE [15]



Figure 15 – Carbonyl absorbance as a function of thermal ageing for XLPE [14]



- 26 -

Figure 16 – Correlation of tensile elongation with solvent uptake factor for a CP jacket aged at the three indicated temperatures [8]



Figure 17 – Elongation results compared to uptake and gel results for XLPE insulation aged at 130 °C [18]



- 27 -

Figure 18 – Elongation results compared to uptake and gel results for an XLPO insulation aged at 125 °C [18]

Bibliography

- 28 -

IEC 60505:2004, Evaluation and qualification of electrical insulation systems

IEC 60544-1:1994, Electrical insulating materials – Determination of the effects of ionizing radiation – Part 1: Radiation interaction and dosimetry

IEC 60544-2:1991, Guide for determining the effects of ionization radiation on insulating materials – Part 2: Procedures for irradiation and test

IEC 60544-4:2003, *Electrical insulating materials* – *Determination of the effect of ionizing radiation* – *Part 4: Classification system for service in radiation environments*

IEC 61244-1:1993, Determination of long-term radiation ageing in polymers – Part 1: Techniques for monitoring diffusion-limited oxidation

IEC 61244-2:1996, Determination of long-term radiation ageing in polymers – Part 2: Procedures for predicting ageing at low dose rates

- [1] STONKUS, D.J., LEHOCKEY, E.M., AZIZIAN, H. and ANANDAKUMARAN, K. *In situ diagnostic monitoring of power plant cables*, Proceedings EPRI workshop on *Power plant cable condition monitoring*, San Francisco, Feb. 1993
- [2] IKEDA, T., IKEHARA, J., ASHIDA, T. and FUJII, M. The degradation diagnosis of polymeric materials by ultrasonic waves – Part 1: Degrading mechanisms of polymeric materials and the degradation diagnosis of low voltage cables by the ultrasonic method, Mitsubishi Cable Industries Review, Mitsubishi Cable Industries Ltd, No. 94, 43-47 (Nov 1998) (in Japanese, with English summary and figure captions)
- [3] IKEDA, T., IKEHARA, J., ASHIDA, T., FUJII, M. and KAWASAKI, K. The degradation diagnosis of polymeric materials by ultrasonic waves – Part 2: Development of the ultrasonic degradation tester 'U-203', Mitsubishi Cable Industries Review, Mitsubishi Cable Industries Ltd, No. 95, 27-32 (Jun 1999) (in Japanese, with English summary and figure captions)
- [4] AZIZIAN, H., Cable Material Identification and Cable Ageing Monitoring using Non-Destructive, Non-Invasive Near Infrared Spectroscopy, EPRI Cable Condition Monitoring WG Meeting, July21-23, 1998, Albuquerque, New Mexico, USA.
- [5] KUSAMA, Y., YAGI, T., MORITA, Y, KAMIMURA, S. and YAGYU, H. New method for detecting degradation in installed cables in nuclear power plants, NUREG/CP- 0119 (1991) Vol. 1 p. 261, Proc. 19th Water Reactor Safety Information meeting, USNRC
- [6] GILLEN, K.T., CLOUGH, R. L. and QUINTANA, C.A. *Modulus Profiling of Polymers*, Polym. Degrad. Stabil., 17, 31 (1987).
- [7] GILLEN, K. T., TERRILL, E. R. and WINTER, R.W. *Modulus Mapping of Rubbers Using Micro- and Nano-Indentation Techniques*, Rubber Chemistry and Technology- Rubber Reviews. Invited Review, 74, 428 (2001).
- [8] GILLEN, K.T., ASSINK, R.A. and BERNSTEIN, R. Condition Monitoring Approaches Applied to a Polychloroprene Cable Jacketing Material, Polym. Degrad. Stabil., 84, 419 (2004).

TS 61244-3 © IEC:2005(E)

- [9] GILLEN, K.T. and BERNSTEIN, R. Condition Monitoring Approaches Applied to a CSPE Cable Jacketing Material, in preparation.
- [10] ASSINK, R.A., CELINA, M. and MINIER, L.M. Condition Monitoring of a Thermally Aged Elastomer by 1H NMR T2 Relaxation Measurements of Solvent Swelled Samples, J. Appl. Polym. Sci., 86, 3636 (2002).
- [11] ASSINK, R.A. CELINA, M. and GILLEN,K.T. *Monitoring the Condition of Thermally Aged Polymers by NMR Relaxation Measurements,* Polymer News, 28, 102 (2003).
- [12] HARRIS, D.J., ASSINK, R.A. and GILLEN, K.T. 1H T2 NMR Monitoring of Crosslinked Polyolefin Ageing, J. Appl. Poly. Sci., 90, 2578 (2003).
- [13] ANANDAKUMARAN, K., BRAUN, J.M., MORRA, R. and STONKUS, D.J. Characterisation of aged station cable insulations – comparison of electrical and physical tests, Proceedings EPRI workshop on Power plant cable condition monitoring, San Francisco, Feb. 1993
- [14] ANANDAKUMARAN, K. and STONKUS, D.J. Assessment of oxidative thermal degradation of crosslinked PE and EPR cable insulation, Polymer Eng. Sci. <u>32</u>, p. 1386-1393 (1992)
- [15] ANANDAKUMARAN, K. and STONKUS, D.J. Accessing radiation induced degradation at low and high dose rates, IAEA Advisory Group Meeting on Stabilisation of polymers and organic materials in radiation field, College Park, Maryland, 1991
- [16] CELINA, M., GILLEN, K.T., WISE, J. and CLOUGH, R.L. Anomalous Ageing Phenomena in a Crosslinked Polyolefin Cable Insulation, Radiat. Phys. Chem., <u>48</u>, 613 (1996).
- [17] CELINA, M., GILLEN, K.T. and CLOUGH, R.L. Inverse Temperature and Annealing Phenomena During Degradation of Crosslinked Polyolefins, Polym. Degrad. Stabil., <u>61</u>, 231 (1998).
- [18] ANANDAKUMARAN, K. et al., Improved Conventional Testing of Power Plant Cables, EPRI TR-105581, September, 1995.

LICENSED TO MECON Limited. - RANCHI/BANGALORE FOR INTERNAL USE AT THIS LOCATION ONLY, SUPPLIED BY BOOK SUPPLY BUREAU.



The IEC would like to offer you the best quality standards possible. To make sure that we continue to meet your needs, your feedback is essential. Would you please take a minute to answer the questions overleaf and fax them to us at +41 22 919 03 00 or mail them to the address below. Thank you!

Customer Service Centre (CSC)

International Electrotechnical Commission 3, rue de Varembé 1211 Genève 20 Switzerland

or

Fax to: IEC/CSC at +41 22 919 03 00

Thank you for your contribution to the standards-making process.







Non affrancare No stamp required

RÉPONSE PAYÉE SUISSE

Customer Service Centre (CSC) International Electrotechnical Commission 3, rue de Varembé 1211 GENEVA 20 Switzerland

Q1	Please report on ONE STANDARD and ONE STANDARD ONLY . Enter the exact number of the standard: (e.g. 60601-1-1)			If you ticked NOT AT ALL in Question 5 the reason is: <i>(tick all that apply)</i>		
		,		standard is out of date		
				standard is incomplete		
				standard is too academic		
Q2	Please tell us in what capacity(ies) yo	u		standard is too superficial		
	bought the standard (<i>tick all that apply</i>).			title is misleading		
				I made the wrong choice		
	purchasing agent			other		
	librarian					
	researcher					
	design engineer		07	Please assess the standard in the		
	safety engineer		u ,	following categories, using		
	testing engineer			the numbers:		
	marketing specialist			(1) unacceptable,		
	other			(2) below average, (3) average		
				(4) above average.		
03	Lwork for/in/ac a:			(5) exceptional,		
Q.)	(tick all that apply)			(6) not applicable		
				timolinoco		
	manufacturing			quality of writing		
	consultant			technical contents		
	government			logic of arrangement of contents		
	test/certification facility			tables, charts, graphs, figures		
	public utility			other		
	education					
	military					
	other		Q8	I read/use the: (tick one)		
04	This standard will be used for:			French text only		
44	(tick all that apply)			English text only		
				both English and French texts		
	general reference				_	
	product research					
	product design/development					
	specifications		Q9	Please share any comment on any		
	tenders			aspect of the IEC that you would like		
	quality assessment			us to know.		
	certification					
	technical documentation					
	thesis					
	manufacturing					
	other					
Q5	This standard meets my needs:				•••••	
	(tick one)					
	not at all					
	fairly well					
	exactly					

LICENSED TO MECON Limited. - RANCHI/BANGALORE FOR INTERNAL USE AT THIS LOCATION ONLY, SUPPLIED BY BOOK SUPPLY BUREAU.



ICS 17.240; 29.035.01