

INTERNATIONAL STANDARD

**Materials for printed boards and other interconnecting structures –
Part 4-1: Sectional specification set for prepreg materials, unclad (for the
manufacture of multilayer boards) – Epoxide woven E-glass prepreg of defined
flammability**



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2008 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch
Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00



IEC 61249-4-1

Edition 1.0 2008-01

INTERNATIONAL STANDARD

**Materials for printed boards and other interconnecting structures –
Part 4-1: Sectional specification set for prepreg materials, unclad (for the
manufacture of multilayer boards) – Epoxide woven E-glass prepreg of defined
flammability**

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

PRICE CODE

M

ICS 31.180

ISBN 2-8318-9585-5

LICENSED TO MECON Limited, - RANCHI/BANGALORE.
FOR INTERNAL USE AT THIS LOCATION ONLY, SUPPLIED BY BOOK SUPPLY BUREAU.

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references	5
3 Materials and construction.....	5
3.1 Reinforcement.....	6
3.2 Epoxide resin	6
4 Properties.....	6
4.1 Properties related to the appearance of the prepreg	6
4.1.1 Dewetted areas (fish eyes).....	6
4.1.2 Broken filaments.....	6
4.1.3 Distortion.....	6
4.1.4 Creases.....	6
4.1.5 Edge conditions.....	6
4.2 Properties related to B stage prepreg	7
4.2.1 Resin content	7
4.2.2 Treated weight.....	7
4.2.3 Resin flow	7
4.2.4 Scaled flow thickness	7
4.2.5 Melting viscosity	8
4.2.6 Gel time.....	8
4.2.7 Volatile content.....	8
4.3 Properties of prepregs after curing to C stage	8
4.3.1 Electric strength	8
4.3.2 Flammability.....	8
4.3.3 Relative permittivity and dissipation factor	9
4.3.4 Cured thickness.....	9
5 Delivery form.....	9
5.1 Rolls.....	9
5.2 Sheets.....	9
5.3 Cut panels.....	9
6 Quality assurance.....	10
6.1 Quality system.....	10
6.2 Responsibility for inspection	10
6.3 Qualification inspection	10
6.4 Quality conformance inspection.....	10
6.5 Certificate of conformance.....	10
6.6 Safety data sheet	10
7 Packaging and marking	10
8 Shelf life	11
9 Ordering information.....	11
Bibliography.....	12
Table 1 – Flammability.....	9

INTERNATIONAL ELECTROTECHNICAL COMMISSION

MATERIALS FOR PRINTED BOARDS AND OTHER INTERCONNECTING STRUCTURES –

Part 4-1: Sectional specification set for prepreg materials, unclad (for the manufacture of multilayer boards) – Epoxide woven E-glass prepreg of defined flammability

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61249-4-1 has been prepared by IEC technical committee 91: Electronics assembly technology.

The text of this standard is based on the following documents:

FDIS	Report on voting
91/739/FDIS	91/747/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts belonging to the IEC 61249 series, under the general title *Materials for printed boards and other interconnecting structures*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed;
- withdrawn;
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

MATERIALS FOR PRINTED BOARDS AND OTHER INTERCONNECTING STRUCTURES –

Part 4-1: Sectional specification set for prepreg materials, unclad (for the manufacture of multilayer boards) – Epoxide woven E-glass prepreg of defined flammability

1 Scope

This part of IEC 61249 gives requirements for properties of prepreg that is mainly intended to be used as bonding sheets in connection with laminates according to IEC 61249-2-7 when manufacturing multilayer boards in line with IEC 62326-4. This material may be also used to bond other types of laminates.

Prepreg according to this standard is of defined flammability (vertical burning test). The flammability rating on fully cured prepreg is achieved through the use of brominated fire retardants contained as an integral part of the polymeric structure. After lamination according to the supplier's instructions, the glass transition temperature is defined as being 120 °C minimum.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61189-2:2006, *Test methods for electrical materials, printed boards and other interconnection structures and assemblies – Part 2: Test methods for materials for interconnection structures*

IEC 61189-3:1997, *Test methods for electrical materials, printed boards and other interconnection structures and assemblies – Part 3: Test methods for interconnection structures (printed boards)*

IEC 61249-2-7:2002, *Materials for printed boards and other interconnecting structures – Part 2-7: Reinforced base materials clad and unclad – Epoxide woven E-glass laminated sheet of defined flammability (vertical burning test), copper-clad*

IEC 62326-4, *Printed boards – Part 4: Rigid multilayer printed boards with interlayer connections – Sectional specification*

ISO 9000:2005, *Quality management systems – Fundamentals and vocabulary*

ISO 11014-1:1994, *Safety data sheet for chemical products – Part 1: Content and order of sections*

ISO 14001:2004, *Environmental management systems – Requirements with guidance for use*

3 Materials and construction

The prepreg consists of a reinforcing E-glass fabric which is impregnated with epoxide resin and partially cured to the B stage.

3.1 Reinforcement

NOTE Woven E-glass is intended to be specified in the future IEC 61249-6-3.

3.2 Epoxide resin

Majority di-functional epoxide resin with a glass transition temperature of ≥ 120 °C when cured according to the manufacturer's recommendation.

Contrast agents may be added to enhance processing such as optical inspection. Its flame resistance is defined in terms of the flammability requirements of 4.3.2.

4 Properties

4.1 Properties related to the appearance of the prepreg

The prepreg shall be substantially free from defects that may have an impact on the material's fitness for use for the intended purpose.

For the following specific defects, the requirements given shall apply when inspection is made in accordance with IEC 61189-3, method 3V01: Visual examination 3× magnification.

4.1.1 Dewetted areas (fish eyes)

Dewetted areas with a diameter > 5 mm are not permissible.

Dewetted areas with a diameter ≤ 5 mm are permitted to an extent of a maximum 10 fish eyes in any 300 mm × 300 mm area of the prepreg.

4.1.2 Broken filaments

When judging the presence of broken filaments their sizes and frequency of occurrence are important for assessing acceptability but also the flow characteristic of the prepreg must be taken into consideration. The acceptance conditions for broken filaments shall be as agreed upon between the user and supplier.

4.1.3 Distortion

When the prepreg is tested in accordance with test method 2M29 the distortion of the fill yarns in the glass fabric shall not exceed 10 % measured over any 300 mm test distance.

NOTE 2M29 is intended to be specified in a future edition of IEC 61189-2.

4.1.4 Creases

Creases caused by handling of the prepreg where only a negligible loss of resin has occurred are permitted.

Creases where the glass yarns are exposed due to loss of resin are not permitted.

4.1.5 Edge conditions

Cut-to-size panels shall have even edges and shall not show loss of resin at the edge due to the cutting process more than 2 mm. Excessive occurrence of resin dust released during the cutting shall be removed before packaging for shipment.

4.2 Properties related to B stage prepreg

A number of characteristics can describe thickness, reactivity and rheology of B stage prepreg. The choice of characteristics to be used as qualification and quality conformance testing as well as the nominal performance levels are as agreed upon between the user and supplier.

Several of the characteristics shown below are interrelated and should not be specified individually. Ordering requirements should preferably be restricted to the glass style, one characteristics marked (a) in combination with one characteristic marked (b). A maximum of one optional characteristic (c) of B stage prepreg may be included.

Glass style

Thickness parameter

- Resin content (a)
- Treated weight (a)

Reactivity/rheology parameter

- Resin flow (b)
- Scaled flow thickness (b)
- Melt viscosity (b)
- Cured thickness (b)

Optional parameter

- Volatile content (c)
- Gel time (c)

4.2.1 Resin content

When tested in accordance with test method 2C03 or 2C10 of IEC 61189-2, the nominal resin content shall be as agreed upon between the user and supplier.

The tolerance around the ordered nominal value shall be ± 3 %, e.g. (45 ± 3) %.

4.2.2 Treated weight

When tested in accordance with test method 2C03 of IEC 61189-2, the nominal treated weight shall be as agreed upon between the user and supplier.

The tolerance around the ordered nominal value shall be ± 3 %, e.g. $(16,8 \pm 0,5)$ g.

4.2.3 Resin flow

When tested in accordance with test method 2M09 of IEC 61189-2, the nominal resin flow shall be as agreed upon between the user and supplier.

The tolerance around the ordered nominal value shall be ± 5 %, e.g. (25 ± 5) %.

4.2.4 Scaled flow thickness

When tested in accordance with test method 2M26 of IEC 61189-2, the nominal scaled flow and the tolerance shall be as agreed upon between the user and supplier.

4.2.5 Melting viscosity

When tested in accordance with test method 2C09 of IEC 61189-2, the nominal melt viscosity shall be as agreed upon between the user and supplier.

The tolerance around the ordered nominal value shall be ± 20 mPa s, e.g. (240 ± 20) mPa s.

4.2.6 Gel time

When tested in accordance with test method 2C02 of IEC 61189-2, the nominal gel time shall be as agreed upon between the user and supplier.

The tolerance around the ordered nominal value shall be ± 20 s, e.g. (160 ± 20) s.

4.2.7 Volatile content

When tested in accordance with test method 2C04 of IEC 61189-2, the volatile content shall be 0,5 % maximum.

4.3 Properties of prepregs after curing to C stage

4.3.1 Electric strength

A total of 2 plies of prepreg of minimum size 300 mm \times 300 mm shall be bonded together and cured in accordance with the manufacturer's recommendations whereupon the thickness shall be determined using a micrometer.

When tested in accordance with test method 2E11 of IEC 61189-2, the minimum electric strength shall be 25 V/ μ m.

4.3.2 Flammability

A number of plies of minimum size 300 mm \times 300 mm of the prepreg under test shall be bonded together and cured in accordance with the manufacturers' recommendations. The number of plies shall be chosen so that a specimen thickness of 0,4 mm – 0,5 mm is obtained as measured with a micrometer.

When tested in accordance with test method 2C06 of IEC 61189-2, the flammability shall meet the requirements as shown in Table 1.

Table 1 – Flammability

Property	Test method IEC 61189-2	Requirement	
		Designation	
		FV0	FV1
Flammability (vertical burning test): nominal material thickness $\geq 0,4$ mm	2C06		
1. Flaming combustion time after each application of the flame for each test specimen		≤ 10 s	≤ 30 s
2. Total flaming combustion time for the 10 flame applications for each set of five specimens		≤ 50 s	≤ 250 s
3. Glowing combustion time after the second removal of the flame		≤ 30 s	≤ 60 s
4. Flaming or glowing combustion up to the holding clamp		None	None
5. Dripping flaming particles that ignite the tissue paper		None	None

4.3.3 Relative permittivity and dissipation factor

A total of 2 plies of prepreg of minimum size 300 mm × 300 mm shall be bonded together and cured in accordance with the manufacturer's recommendations whereupon the thickness shall be determined using a micrometer.

When tested in accordance with test method 2E10 of IEC 61189-2, the relative permittivity and dissipation factor shall be 5,4 and 0,035 minimum, respectively.

4.3.4 Cured thickness

The nominal thickness and the tolerance of the cured prepreg using the user's lamination cycle shall be as agreed upon between the user and supplier.

5 Delivery form

Prepreg may be ordered and delivered as rolls, sheets or cut panels.

5.1 Rolls

Roll sizes shall be as agreed upon between the user and supplier. For rolls ≥ 50 m in length, cut-outs from quality conformance inspection are allowed. The size of the roll delivered by the supplier shall not deviate more than $^{+20}_0$ mm in the width and ± 5 m in the length from the ordered size.

5.2 Sheets

Sheet sizes shall be as agreed upon between the user and supplier. The size of the sheet delivered shall not deviate more than $^{+20}_0$ mm from the ordered size.

5.3 Cut panels

Cut panel sizes shall be as agreed upon between the user and supplier. The size of the cut panels delivered shall not deviate more than ± 3 mm from the ordered size.

6 Quality assurance

6.1 Quality system

The supplier shall operate a quality system, ISO 9000 or similar, to support quality conformance inspection. The supplier shall maintain a Management System for Environmental Control in compliance with ISO14001 or similar, to support environmental considerations.

6.2 Responsibility for inspection

The supplier is responsible for all inspection of the manufactured material. Inspection is auditable by the purchaser or an appointed third party.

6.3 Qualification inspection

Prepregs furnished under this specification shall be qualified. Qualification testing shall be performed to demonstrate the manufacturer's ability to meet the requirements of this standard. Qualification testing shall be conducted at a laboratory compliant with IEC laboratory requirements. The manufacturer shall retain on file the data which supports that the materials meet this specification and shall be readily available for review upon request.

6.4 Quality conformance inspection

The supplier shall operate a quality plan to assure product conformance to this standard. Such a quality plan, when appropriate, should utilize statistical methods rather than lot-by-lot inspection. It is the responsibility of the supplier based on the quality plan to determine the frequency of test to assure conforming products.

A combination of the following techniques may be used to show compliance with the requirements which can be used to reduce the frequency of testing. The data supporting the reduction of testing frequency shall be available for review upon request:

- in process parameter control;
- in process inspection;
- periodic final inspection;
- final lot inspection .

6.5 Certificate of conformance

The supplier shall on request from the purchaser issue a certificate of conformance to this standard in electronic or paper format.

6.6 Safety data sheet

A safety data sheet in accordance with ISO 11014-1 shall be available for products manufactured and delivered against this standard.

7 Packaging and marking

Prepreg in rolls, sheets and cut panels shall be packaged in a manner, which will provide adequate protection against deterioration and physical damage during shipment and storage.

If not otherwise specified in the purchase order, prepreg shall be marked on the smallest package with the manufacturer's designation, lot number and date of manufacture.

The shipping container shall have a label that shall remain securely affixed and legible during normal handling. Location of the label and the type of marking shall be as specified in the

drawing or ordering data, or if not specified, shall be the supplier's standard labelling and marking. The following information shall be included:

- a) type of material
- b) manufacturer's designation
- c) lot number
- d) quantity
- e) dimensions
- f) gross weight
- g) date of manufacture
- h) manufacturer's name and address
- i) date packed

8 Shelf life

Prepreg shall be capable of being stored at either of the beneath conditions for the specified time and still be fit for its intended use.

Condition 1: Temperature ≤ 10 °C, relative humidity not specified, minimum 6 months after shipping to the customer.

Condition 2: Temperature ≤ 20 °C, relative humidity ≤ 50 %, minimum 3 months after shipment to the customer.

Prepreg should not be stored in a catalytic environment such as UV light or excessive radiation. Material that has been stored at lower temperature should be allowed to equilibrate to ambient temperature before the packing is opened to avoid condensation of moisture on the prepreg itself.

9 Ordering information

The purchase order shall include the following information:

- a) a reference to this specification;
- b) type of material;
- c) size;
- d) glass style;
- e) the selected thickness parameter and nominal value;
- f) the selected reactivity/rheology parameter and nominal value;
- g) the selected optional parameter and nominal value (if any);
- h) request for certificate of conformance if applicable.

Bibliography

IEC 60194:2006, *Printed board design, manufacture and assembly – Terms and definitions*

IEC 61249-6-3: –, *Materials for printed boards and other interconnecting structures – Part 6-3: Reinforcements – Woven fibreglass fabrics*¹

¹ Under consideration.

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

3, rue de Varembé
P.O. Box 131
CH-1211 Geneva 20
Switzerland

Tel: + 41 22 919 02 11
Fax: + 41 22 919 03 00
info@iec.ch
www.iec.ch