TECHNICAL REPORT

IEC TR 62392

First edition 2006-11

Suitability of typical electrical insulating material (EIM) for polymer recycling



Reference number IEC/TR 62392:2006(E)

Publication numbering

As from 1 January 1997 all IEC publications are issued with a designation in the 60000 series. For example, IEC 34-1 is now referred to as IEC 60034-1.

Consolidated editions

The IEC is now publishing consolidated versions of its publications. For example, edition numbers 1.0, 1.1 and 1.2 refer, respectively, to the base publication, the base publication incorporating amendment 1 and the base publication incorporating amendments 1 and 2.

Further information on IEC publications

The technical content of IEC publications is kept under constant review by the IEC, thus ensuring that the content reflects current technology. Information relating to this publication, including its validity, is available in the IEC Catalogue of publications (see below) in addition to new editions, amendments and corrigenda. Information on the subjects under consideration and work in progress undertaken by the technical committee which has prepared this publication, as well as the list of publications issued, is also available from the following:

IEC Web Site (<u>www.iec.ch</u>)

• Catalogue of IEC publications

The on-line catalogue on the IEC web site (<u>www.iec.ch/searchpub</u>) enables you to search by a variety of criteria including text searches, technical committees and date of publication. On-line information is also available on recently issued publications, withdrawn and replaced publications, as well as corrigenda.

IEC Just Published

This summary of recently issued publications (<u>www.iec.ch/online_news/justpub</u>) is also available by email. Please contact the Customer Service Centre (see below) for further information.

Customer Service Centre

If you have any questions regarding this publication or need further assistance, please contact the Customer Service Centre:

Email: <u>custserv@iec.ch</u> Tel: +41 22 919 02 11 Fax: +41 22 919 03 00

TECHNICAL REPORT

IEC TR 62392

First edition 2006-11

Suitability of typical electrical insulating material (EIM) for polymer recycling

© IEC 2006 — Copyright - all rights reserved

No part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Electrotechnical Commission, 3, rue de Varembé, PO Box 131, CH-1211 Geneva 20, Switzerland Telephone: +41 22 919 02 11 Telefax: +41 22 919 03 00 E-mail: inmail@iec.ch Web: www.iec.ch



Commission Electrotechnique Internationale International Electrotechnical Commission Международная Электротехническая Комиссия



For price, see current catalogue

R

CONTENTS

FO	REW	DRD	3			
1	Scop	ре	5			
2	Normative references					
3	Terms and definitions					
4	Envi	ronmental aspects of polymeric materials at the End Of Life (EOL) stage	8			
5	Processing and separation of recycled materials					
	5.1	General	10			
	5.2	Separation methods	10			
	5.3	Recycling of the polymeric materials in WEEE	11			
6	Mate	rial factors	12			
	6.1	General	12			
	6.2	Mechanical properties – Tensile strength and toughness	12			
	6.3	Thermal endurance	13			
	6.4	Flammability/ignitability	14			
	6.5	Arc resistance	14			
	6.6	Comparative Tracking Index	14			
	6.7	Insulating performance (volume resistivity, dielectric strength)	14			
	6.8	Weatherability – UV-resistance	15			
7	Design factors					
	7.1	Ease of dismantlement	15			
	7.2	Part labelling	16			
	7.3	Paints/finishes	16			
~	<i>1</i> .4	Metallized parts "	16			
8	Agei – Ge	ng evaluation/life estimation of recycled electrical insulating materials (EIMS) neral remarks	17			
Bib	lioora	nhy	18			
DID	nogra	p.,,				
Fig	ure 1	 Overview of possible ways to recover polymers 	8			
Fig	Figure 2 – Energy consumption and recycled fraction					
Fig	Figure 3 – Tensile strength of reprocessed material					
Fig	Figure 4 – Izod impact strength of reprocessed material					
Tab	ole 1 -	- WEEE typical composition	11			

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUITABILITY OF TYPICAL ELECTRICAL INSULATING MATERIAL (EIM) FOR POLYMER RECYCLING

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. However, a technical committee may propose the publication of a technical report when it has collected data of a different kind from that which is normally published as an International Standard, for example "state of the art".

IEC 62392, which is a technical report, has been prepared by IEC technical committee 112: Evaluation and qualification of electrical insulating materials and systems.¹

The text of this technical report is based on the following documents:

Enquiry draft	Report on voting
15/235/DTR	15/263/RVC

¹ Technical committee 112 was created by combining the activities of sub-committee 15E and technical committee 98. This project was initially developed in technical committee 15 and then transferred to technical committee 112.

Full information on the voting for the approval of this technical report can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

SUITABILITY OF TYPICAL ELECTRICAL INSULATING MATERIAL (EIM) FOR POLYMER RECYCLING

1 Scope

This Technical Report gives information for the assessment of factors associated with the polymer recycling and/or reuse of typical insulating materials in electrotechnical equipment. It gives information and assistance to developers and design engineers for assessment in selecting polymers and polymer combinations, and is a contribution to the preservation of resources and the minimization of disposal costs at the end of a product life. The environmental compatibility of polymers must be assessed in the light of the function of the materials in the product and the total service life. An important aspect is the recovery of the material at the end of the product life. The value level of material recycling as recovery option can be improved by incorporation of suitability for dismantling into the design of the article and the choice of insulating materials which are generally used. This document will cover material recycling only as part of recovery.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60093, Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials

IEC 60112, Method for the determination of the proof and the comparative tracking indices of solid insulating materials

IEC 60216-1, Electrical insulating materials – Properties of thermal endurance – Part 1: Ageing procedures and evaluation of test results

IEC 60216-2, Electrical insulating materials – Thermal endurance properties – Part 2: Determination of thermal endurance properties of electrical insulating materials – Choice of test criteria

IEC 60216-3, *Electrical insulating materials* – *Thermal endurance properties* – *Part* 3: *Instructions for calculating thermal endurance characteristics*

IEC 60216-4-1, *Electrical insulating materials* – *Thermal endurance properties* – *Part 4-1: Ageing ovens* – *Single-chamber ovens*

IEC 60216-4-2, Electrical insulating materials – Thermal endurance properties – Part 4-2: Ageing ovens – Precision ovens for use up to 300 °C

IEC 60216-4-3, *Electrical insulating materials* – *Thermal endurance properties* – *Part 4-3: Ageing ovens* – *Multi-chamber ovens*

IEC 60216-5, Electrical insulating materials – Thermal endurance properties – Part 5: Determination of relative thermal endurance index (RTE) of an insulating material

IEC 60216-6, Electrical insulating materials – Thermal endurance properties – Part 6: Determination of thermal endurance indices (TI and RTE) of an insulating material using the fixed time frame method

- 6 -

IEC 60505, Evaluation and qualification of electrical insulation systems

IEC 61244-3, Long-term radiation ageing in polymers – Part 3: Procedures for in-service monitoring of low-voltage cable materials

ISO 179 (all parts), Plastics – Determination of Charpy impact properties

ISO 527 (all parts), Plastics – Determination of tensile properties

ISO 11469, Plastics – Generic identification and marking of plastics products

ISO 1043-1, *Plastics – Symbols and abbreviated terms – Part 1: Basic polymers and their special characteristics*

ISO 1043-2, Plastics – Symbols and abbreviated terms – Part 2: Fillers and reinforcing materials

ISO 1043-3, Plastics – Symbols and abbreviated terms – Part 3: Plasticizers

ISO 1043-4, Plastics – Symbols and abbreviated terms – Part 4: Flame retardants

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

electrical insulating material

EIM

material with negligibly low electric conductivity, used to separate conducting parts at different electrical potentials

[IEV 212-01-01:1990, MOD]

3.2

composite

1) solid product consisting of two or more distinct phases, including a binding material (matrix) and a particulate or fibrous material

NOTE Example: Moulding material containing reinforcing fibres, particulate fillers or hollow spheres.

 solid product consisting of two or more layers (often in a symmetrical assembly) of plastic film or sheet, normal or syntactic cellular plastic, metal, wood, composite according to definition 1), etc. with or without adhesive interlayers

NOTE Examples: Film composites for packaging, sandwich cellular composite for structural applications, laminates made with paper, fabric, etc.

[ISO 472: 1999]

3.3

(mechanical) recycling

reprocessing in a production process of the waste materials for the original purpose or for other purposes but excluding energy recovery

[IEC Guide 109:2003]

NOTE This definition excludes the chemical recycling during which the molecular structure is broken down to produce monomers.

3.4

feedstock recycling

processing of plastic waste material, with significant change to the chemical structure of the material including cracking, gasification and de-polymerisation but excluding energy recovery or incineration

3.5

recyclability

property of a substance or a material and parts/products made thereof that makes it possible for them to be recycled

NOTE Recyclability of a product is not only determined by the recyclability of the materials it contains. Product structure and logistics are also very important factors.

[IEC Guide 109, 2003]

3.6

recycled polymer

materials resulting from recycling

3.7

commingled

A mixture of materials or products consisting of different types of plastics

3.8

contamination

unwanted substance in polymeric materials according to the intended use

3.9

halogen containing

material containing the elements F, CI or Br either in the polymer (as in PVC, PTFE, ...) or in the fire-retardant additive package

3.10

thermoplastic

plastic capable of being repeatedly softened by heating and hardened by cooling through a temperature range characteristic of the plastic and, in the softened state, capable of being repeatedly shaped by flow into articles by moulding, extrusion or forming

NOTE 1 Thermoplastics can be reprocessed and recycled by remelting.

NOTE 2 Examples are given below as abbreviations after ISO 1043-1: PE, PVC, PS, PC, PP, PA, POM, SAN, ABS, PBT, PET, PMMA, ASA, TPU, LCP, PEEK, PPS, PBT + PC, PC + ABS, PC + PBT, PPE, PPE + PS.

3.11 thermoplastic elastomer

TPE

general term for specific elastomers like thermoplastic polyurethane (TPU)

NOTE For further abbreviations see ISO 18064:2003.

3.12

elastomer and other crosslinked polymer

macromolecular material which returns rapidly to approximately its initial dimensions and shape after substantial deformation by a week stress and release of the stress

NOTE 1 The definition applies to room temperature test conditions.

NOTE 2 Examples are EPR, nitril rubber, cross-linked PE according to ISO 1629 and ISO 1382 and cross-linked PE (PE-X according to ISO 1043-1).

3.13

thermoset

plastic which, when cured by heat or other means, changes into a substantially infusible and insoluble product

NOTE 1 Thermosets are often called thermosetting before curing and thermosets after cure. Their polymeric structure is cross-linked by curing.

NOTE 2 Examples are EP, SI, UP, MF, PF, UF, MP, PUR (thermoset polyurethane, PIR (polyisocyanurate).

NOTE 3 For a more complete list of vocabulary see ISO 472.

4 Environmental aspects of polymeric materials at the End Of Life (EOL) stage

The choice of the polymeric material for electrical applications should be done incorporating environmental considerations from a life cycle perspective. Handling of polymer waste is an important issue in the life cycle of polymers. Polymer waste can be recycled, incinerated or landfilled. Landfill deposition should be avoided, as it implies no recovery of materials or energy and may cause uncontrolled release of harmful additives or degradation products. Thus, the options that should be considered are mechanical recycling, feedstock recycling which may be the choice in case the material is commingled, and incineration with energy recovery. Overview of possible ways to recover polymers is shown in Figure 1.





Mechanical recycling may be the choice if the waste material comply with the requirements of the recycling process intended to be used, and well-defined and there is an efficient infrastructure for collection, dismantling, and re-processing into new products.

However, if recycling conditions are not fulfilled, incineration with energy recovery is probably the most suitable treatment. Using polymer waste as fuel for power/heat generation is advantageous when the polymers have a high energy content. It is important, however, that incineration is carried out under controlled conditions in plants with efficient air pollution control. Polymers may for instance contain nitrogen, chlorine, fluorine, bromine and sulphur in their structure or in additives and combustion of such compounds may give rise to harmful substances. The preferred and most appropriate treatment of polymer waste containing undesired organic additives is incineration, enabling the destruction and removal of harmful compounds.

Whether or not a product or product part should be reused, recycled or incinerated is a complex issue which has to be considered from case to case.

Recycling of thermoplastic-based products is increasing. The recycling environmental benefits depend on the efficiency of the collecting mechanisms because the impacts arising from the collection could eliminate the environmental credits due to the recycled material availability. Energy consumption and recycled fraction are shown in Figure 2.

-9-



Environmental efficiency of a recovery program

optimum A = maximum energy recovery optimum B = maximum material recovery in respect of energy balance

Figure 2 – Energy consumption and recycled fraction

If thermoplastics are incinerated under unregulated conditions with no air pollution control, harmful combustion products may be emitted into the air. This is particularly true if the polymer has other atoms than carbon, hydrogen and oxygen present in its structure (or in additives). Incineration of nitrogen-containing polymers induces the formation of cyanides/ cyanates and NO_x, whereas hazardous halogenated organic compounds (dioxins, furans, etc.) may be formed under inappropriate incineration of halogen-containing polymers. If the latter polymers are incinerated in a plant with tuned combustion conditions, the halogens will come out as acids (HCI, HF) in the combustion gases. These acids can be neutralised with common air pollution control equipment.

If thermoplastics are deposited at a landfill site, the complete degradation of the material may take more than a century, and during this time span harmful additives (e.g. lead-based stabilisers) may be leached from the landfill site. It is generally accepted that land filling is not preferred. Incineration should be done under state of the art conditions.

Thermosets are currently not recycled to a great extent. Recycling is restricted to milling and use of the resultant powder as a filler. Methods for chemical recycling of thermosets, i.e. controlled degradation and recovery of components, have been developed but are presently not used on a large scale. If a thermoset resin contains substances which are classified as environmentally hazardous, then the waste may also be environmentally hazardous depending on applicable legislation.

Recycling of rubber materials has so far been limited to grinding and use of the milled rubber as a filler in other materials such as asphalt and athletic field materials. Rubbers may contain metal compounds (additives) which are classified as environmentally hazardous, which means that the waste is classified as environmentally hazardous. Thermoplastic elastomers can be recycled as the thermoplastics.

At the same time that plastic parts have been substituted for metals in many applications, plastic recycling has become more difficult. Special plastic composites, such as those with glass additives, require special separation. The introduction of more powerful electronic products, more sensitive to electronic noise, has led to the use of plastic resins containing

conductive stainless steel fibers, further complicating separation for recycling. Embedded metal fasteners in moulded plastics have long created recycling problems.

5 Processing and separation of recycled materials

5.1 General

Excluding land filling, there are three main options for the recovery of the polymeric electricalinsulating materials:

- material recycling;
- recovery of raw materials;
- energy recovery.

Thermosets, chemically crosslinked thermosets, elastomers – crosslinked PE and some not crosslinked but unmeltable polymers like PTFE – cannot be reprocessed as recovered materials. They can be grinded to powder or granules and incorporated as a filler or – alternatively – decomposed thermically, chemically or by irradiation.

The material recycling requires a level of separation to obtain the recyclate quality compatible with the intended recycling process. Alternatively, other options can perform better especially for complex mixed material fractions

5.2 Separation methods

The basic separation processes are as follows:

a) Separation based on polymer density

The separation in water of the materials below and above a relative density of 1,00 is the easiest to perform.

A heavy-media flotation where fine solids such as brine are added into water to increase its relative density is also possible.

By having several density baths in the processing line, several density cuts could be established, sorting out polymers and other materials by density.

b) Separation based on polymers surface properties

Froth flotation uses additives in water, such as pine oil, to modify the polymers surface properties. Gas bubbles that are injected in the flotation bath bottom attach to certain hydrophobic polymer(s). The gas bubble lifts the polymer grain up to the bath surface where it can be recovered.

- c) Separation based on polymers softening temperatures (i.e. thermo-adhesion). By heating polymers, certain achieve their softening temperature at lower temperatures. A mechanical device, such as a roll, can be used to pick out softened material.
- d) Sorting of plastics with spectroscopic devices. Identifying and separating plastic granules in an automatic recycling line.

The spectroscopic method typically requires a very low quantity of contaminants, such as some percent.

e) Separation based on selective dissolution in a solvent, e.g. impurities from PVC.

A filtration in the solvent phase allows to eliminate the impurities (rubber, glass, metals, fibers, labels, other polymers...).

An effective separation will be achieved in some cases especially if the waste consists only of two materials significantly differing from each other in some property.

The separation of a conglomerate of materials is much more difficult and cost-intensive and this will be mostly the case for the end of life polymeric electrical insulating materials.

The presence of metal and other conducting contamination (e.g. carbon) will pose a specific problem with regard to the reuse of the recyclate material as an electrical insulation material.

5.3 Recycling of the polymeric materials in WEEE

Most of the end of life polymeric electro-insulation materials will be included in the WEEE (Waste Electrical and Electronic Equipment).

The collection, processing and recycling steps of the WEEE could be as follows:

- a) Collecting Electric and Electronic (E&E) equipment via permanent drop-off locations, waste collection networks etc.;
- b) Evaluating E&E equipment re-use potential. They can be refurbished or donated if possible;
- c) Disassembly of hazardous components such as batteries. Some valuable parts or components might also be recovered;
- d) Metals recovery and recycling;
- e) Other materials including the polymeric electro-insulation materials.

Typical compositions of some types of WEEE are shown in Table 1.

	Brown goods	Data processing & office equipment	White goods	Printed circuit boards
	%	%	%	%
Polymers	26	13	7	30
Ferrous	35	40	44	
Non-ferrous	26	30	32	30
Glass	4	5	4,5	30
Wood	1	1	1	
Other	8	11	11,5	10
Total	100	100	100	100

Table 1 – WEEE typical composition ^{[13], [14]}

It shows a very high mass proportion of metals – that are rather easily recovered and recycled after simple mechanical separation processes.

After metals have been sorted out, the plastics will be in the form of granules and might remain mixed with glass, wood, metal contaminations and other remaining materials.

The estimation of the plastics fraction in the WEEE was 17,7% for a total of 4 395 000 tons in Western Europe in 2000.

There are technical constraints involved in determining the most appropriate polymers recycling chain. For any recycling process, the feed materials need to be de-dusted and hazardous materials need to be removed.

A presorting of the WEEE can sometimes be of interest to simplify the separation operations and to recover high quality recycled polymers with a lowest global cost.

Besides mechanical recycling there are methods of chemical or feedstock recycling residues that are more complex waste than WEEE. Such methods could be more expensive than mechanical recycling routes for certain sufficiently pure polymer wastes.

However, they offer a solution for the most complex mixed plastics waste treatment.

In the future, it might be advantageous to combine several treatment methods to recover several metals and polymers gathering the most economical and environmental value from the WEEE waste streams.

Detailed and in-depth research and development work has already been carried out and will clearly continue in the future in order to increase the performances of the different recycling methods.

6 Material factors

6.1 General

Product committees should not compromise on safety requirements. When considering that the products are allowed to contain recycled plastics, recycled materials and end-products will have to comply with the requirements as specified in the relevant end-product standards.

6.2 Mechanical properties – Tensile strength and toughness

Strength is a mechanical property. It is outlined in ISO 527 and ISO 179.

In general, recycled polymers have inferior mechanical properties than the same polymers in virgin form. Examples are shown in Figures 3 and 4.

Therefore, recycled polymers are usually used in mixtures of recyclate and virgin polymers. In this case, the ratio of recyclate-to-virgin components is a major parameter to manage, in order to achieve specified level of performance ^[1]. Co-injection (sandwich) moulding and coextrusion employing virgin polymer for the outside and recycled polymer as the core material of a core-skin structure is also used.

The impact of recycling on the mechanical properties of polymers may be seen especially from the tensile strength and the toughness characteristics.

Tensile strength ^[2] is the ability of a material to withstand tensile loads without rupture when the material is in tension.

Toughness is the ability of a material to withstand crack propagation. A material in which the cracks easily propagate when mechanically stressed is brittle. Toughness indicates the ability of a material to absorb energy without rupture.

Toughness is an important material property ^[3]. Different types of toughness measurements may give different or even contradictory test results. It is recommended that the toughness properties should be evaluated by two or more complementary methods. The J-integral method and the common Charpy impact test or Izod impact strength method constitute such a pair.



- 13 -

Figure 3 – Tensile strength of reprocessed material



Figure 4 – Izod impact strength of reprocessed material

Figures 3 and 4 show the mechanical degradation as a result of reprocessing ^[4].

When considering the effects of polymer recycling it should be emphasised that for some materials the mechanical properties such as impact strength and resilience are most likely to be compromised. Non-impact mechanical strength on the other hand may well be enhanced.

6.3 Thermal endurance

Thermal endurance is assessed by several test methods including the IEC 60216 series. Service degradation over the long life of products is simulated via moderately elevated test temperatures to produce a manifestation of thermal degradation in a reasonable though protracted test time.

The relative thermal endurance index (RTE) as defined in IEC 60216-5 is the numerical value of the temperature in degrees Celsius at which the estimated time to endpoint of a candidate

material is the same as the estimated time to endpoint of the control material at a temperature equal to its assessed thermal endurance (ATE) which is the numerical value of the temperature in degrees Celsius, up to which the control material possesses known, satisfactory service performance in the specified application.

It can be expected that at this temperature a class of critical material properties is acceptably stable over the full service life of equipment. As a measure of thermal stability, thermal degradation may well be enhanced by moderate additional heat histories; i.e. as a measure of sensitivity to relative property changes, thermal degradation will naturally be decreased if material property is stabilized to lower performance levels by the additional heat histories of material recycling.

Thermal analysis, especially differential scanning calorimetry (DSC), to measure the remaining thermal stabilization of a material after ageing, allows evaluating the so-called Oxygen Induction Time or Temperature OIT/OITP, according to IEC 61244-3.

6.4 Flammability/ignitability

All thermoplastics, flame retardant and non flame retardant, can be recycled. Recycled materials may have different fire behaviour compared to the virgin materials they are derived from.

6.5 Arc resistance

This method is intended to differentiate, in a preliminary fashion, among similar materials with respect to their resistance to the action of a high-voltage, low-current arc close to the surface of insulation, in tending to form a conducting path therein or in causing the material to become conducting due to the localized thermal and chemical decomposition and erosion. A test gives a relative measure of the tendency of an insulator to become surface tracking due to repeated low current arc contacts under high voltage.

6.6 Comparative Tracking Index

IEC 60112 is the preferred method and uses a "contaminating" solution dropped between energized electrodes at the specimen surface, intended to accelerate the development of a self-propagating and self-enhancing tracking.

Ultimately, while either in service or while testing, tracking will develop with a sufficient quantity of partially conducting contaminant, from either or both degraded material (e.g. material burned or degraded from exposure to arcing, etc.) or externally deposited material (e.g. dirt, dust, salt, moisture, etc.).

In service tracking failure is a likely source of ignition and fire since the partially conducting track has a resistance high enough to prevent activation of circuit protective devices, yet low enough to produce considerable electrical heating.

Subtle changes in the surface material are known to have profound effects on tracking resistance. A recycle process will expose the bulk of material to additional thermal cycles, and may influence material degradation leading to the formation of a track.

6.7 Insulating performance (volume resistivity, dielectric strength)

The insulating resistance of solid electrical insulating materials is commonly measured using test methods outlined in IEC 60093. In many end product applications the insulating resistance of the polymeric material is significantly higher than the minimum necessary for the safe operation of the device. Recycled polymeric materials would be expected to exhibit insulating resistance similar to the virgin material. Some degradation is possible depending on the impurities in a particular recycle stream; however, conductive impurities are to be

TR 62392 © IEC:2006(E)

avoided. Some polymeric materials, designed specifically for applications requiring higher conductivity, are of a particular concern regarding insulating resistance after recycling.

6.8 Weatherability – UV-resistance

The performance of all polymers is affected by UV radiation. UV radiation acts upon the molecular structure of the polymers with the result of changes in optical and mechanical behaviour or properties. Long-term exposure to the weather can be specially harmful to many materials. With respect to most plastics, ultraviolet (UV) light from the sun is the major culprit. Other environmental factors, such as moisture and extreme temperatures, simply make the problem worse. Long-term, continuous outdoor exposure of most unstabilized thermoplastics normally results in changes in colour and other physical properties. These changes can usually be measured quantitatively as indicators of a material's long-term weathering stability:

- colour and haze clear materials may develop a yellow cast and a white surface film;
- impact strength tough resilient materials may become brittle.

Long-term impact strength may be critical, considering factors such as wind load and low temperatures.

NOTE The performance of most thermoplastic materials depends largely on their molecular structure. A tough, material will generally exhibit a structure in which the molecules are arranged in long, chain-like configurations. UV light causes the molecular chains to break up into shorter chains. This process, known as photo degradation, results in molecular structure more typical of brittle materials.

Product Committees should make sure that the degradation by UV radiation of the recycled material does not exceed their requirements.

7 Design factors

7.1 Ease of dismantlement

Optimum recycling of thermoplastic polymers is normally only possible if they belong to the same polymer type. To guarantee this without expensive dismantling and sorting, only a single type of polymer should be used in one product where possible. Recyclable waste and components should if possible be sorted according to moulding compounds and colours. In most cases, this will not be completely possible. If two incompatible polymers are mixed together, a process called phase separation occurs. Distinct regions of each polymer will be visible under a microscope or the naked eye; no chemical bond exists between these materials. To be able then to recycle the mixtures of polymer which arise whilst at the same time ensuring that completely worthless elements are not obtained, the selected combinations of polymers must to some extent be miscible with each other [12].

In order to reprocess materials and retain good properties for a new product, well sorted materials are needed rather than a blend of a number of immiscible plastics. Before moving on the process of sorting one should visualize the most important points^[5]:

- processing causes degradation of the material as a result of heat and shear;
- mechanical actions such as grinding also exert shearing stresses and even chemical modification;
- plastics have different melting points, different softening temperatures and different temperatures for the onset of thermal degradation;
- immiscibility of plastics with each other, leads to deterioration in mechanical performance;
- good dispersion and homogeneity are required.

Partially compatible polymers can be homogenized by so called compatibilizing agents or polymers. Most often the balance of material properties, part design, production process, product performance, dismantlement/recycling processes, and finally product and life cycle costs, is a compromise where any change influences all the other aspects.

NOTE In recycling of cable materials the purpose is to recover the conductor metal (copper), not the polymer material. The remaining polymer waste is then often contaminated with copper; this heavy metal contamination in turn may result in a classification of the polymer waste as a special waste (same problem as stated for thermosets and elastomers (see 6.7).

- 16 -

7.2 Part labelling

Products that have been fabricated from plastics materials should be marked in accordance with the system specified in ISO 11469. The generic identification uses the symbols and abbreviated terms found in ISO 1043-1 to 1043-4.

NOTE The minimum size of the article to be marked and the size of the lettering are not specified in ISO 11469.

7.3 Paints/finishes

The paint film in almost all paints/finishes is cross-linked and not recyclable. The paint film may produce harmful emissions in case of reprocessing the coated polymer.

Specific paints may degrade during reprocessing of the plastic and give rise to toxic emissions. Painted thermoplastic parts can be recovered by first granulating the parts, melting the granulated pieces in an extruder and filtering the melt. Depending on the effectiveness of this filtration step, the cleaned granulate can be used for simple industrial products or for items with better appearance and performance qualities.

Painted products manufactured from filled or reinforced thermoplastics can be granulated and then melt processed without filtration. This process increases the filler type and level in the thermoplastic material and, thus, produces a new product formulation. The new product formulation may be suitable for use in a number of applications but the new formulation must be evaluated in each application.

7.4 Metallized parts ^[4]

Conductive coatings on plastic. Conductive spray paint offers shielding but the critical orientation of the metal particles is unpredictable and coating uniformity on internal features can often be a problem. No coating alternative is compatible with current product recyclability objectives.

Metal foil & moulded metallized liners. Metal foil has been widely used for lower-cost shielding inside a plastic housing with relatively simple shapes, but foil slippage out of position must be guarded against, particularly in field maintenance. Moulded or formed metallized fabric liners can usually be removed for product recycling.

Metallized plastic resins. Metallic fillers in plastic have been the subject of resin experimentation for many years. Such resins theoretically offer inherent conductivity, but the essential orientation and contact between the internal particles are an unknown with every part moulded. Likewise, such unpredictability makes continuity across a seam a difficult problem. If sufficient conductive filler is added to guarantee internal shielding, the strength of the material can be compromised. Higher costs and faster tooling wear can be expected, and post-consumer recyclability of the housing will be a concern.

Plastic housing with metal subchassis. Incorporating a complete metal enclosure inside their resin housing is a superior solution from the shielding perspective, although it comes at increased cost and, in the case of small portable and hand-held products with tightly packed interiors, often at a sacrifice to innovative exterior housing design. Post-consumer recyclability is practical with such designs.

8 Ageing evaluation/life estimation of recycled electrical insulating materials (EIMs) – General remarks

With the assumption that the recycled material shall be used as an electrical insulation material again, ageing evaluation and life estimation of that electrical insulation material (EIM) should be evaluated by the same evaluations criteria that applies to virgin insulation material. This evaluation procedure has to follow the guidelines given in IEC 60505.

Bibliography

- [1] DeRosa, R., manuscript submitted to Revista do Plástico Reforçado, Recycling Glass-Reinforced Thermoset Polymer Composite Materials
- [2] Odian, George: Priciples of polymerisation, 3rd Ed., J.Wiley, New York, 1991, p. 34
- [3] Xiaodong Liu Mechanical Recycling of Engineering Thermoplastics using Alloying Techniques, Chalmers dissertations, 2001– Chalmers University, School of Mechanical and Vehicular Engineering, Department of Polymeric Materials, Postgraduate Programme in Polymeric Material
- [4] Goodship, Vanessa: Introduction to plastic recycling, Rapra Techn. LTD. Shawbury, 2001.
- [5] Die Cast Solutions Archives: Bulletin No. 34: "CWM Specifications for Miniature Die Cast Zn & ZA-8 Parts, Past Product Tech Notes: http://www.cwmdiecast.com/solution/solution.htm
- [6] IEC 60721, Classification of environmental conditions
- [7] UL standard 746 B: Polymeric Materials Long Term Property Evaluations
- [8] UL standard 746 A: Polymeric Materials Short Term Property Evaluations
- [9] ASTM D 257: Standard Test Methods for DC Resistance or Conductance of Insulating Materials
- [10] ASTM D 495: Standard Test Method for High-Voltage, Low-Current, Dry Arc Resistance of Solid Electrical Insulation
- [11] Directive 2002/96/EC of the European Parliament and of the Council of 27 January 2003 on waste electrical and electronic equipment (WEEE)
- [12] BAYER AG, Application Technology Information ATI 0305: Recycling and Design
- [13] European Brominated Flame retardants Industry Panel Recovery of bromine & antimony from waste electrical & electronic equipment containing bromine in the European Union, PB Kennedy & Donkin Limited report, BECCH074.1071, May 1999.
- [14] APME EEE consumption and WEEE in Western Europe Evolution 1980/2000/ Forecast 2005, Taylor Nelson Sofres S.A. report, December 2000
- [15] IEC 60068, Environmental testing Part 1: General and guidance; Part 2: Tests; Part 3: Supporting documentation and guidance
- [16] IEC 60212, Standard conditions for use prior to and during the testing of solid electrical insulating materials
- [17] IEC 60727-1, Evaluation of electrical endurance of electrical insulation systems. Part 1: General considerations and evaluation procedures based on normal distributions
- [18] ISO 472:1999, Plastics Vocabulary
- [19] IEC 60544-1, *Electrical insulating materials Determination of the effects of ionizing radiation Part 1: Radiation interaction and dosimetry*
- [20] IEC/TS 61244-1, Determination of long-term radiation ageing in polymers Part 1: techniques for monitoring diffusion-limited oxidation
- [21] ISO 1382, Rubber Vocabulary
- [22] IEC 60050-212:1990, International Electrotechnical Vocabulary Chapter 212: Insulating solids, liquids and gases

- [23] IEC Guide 109:2003, Environmental Aspects Inclusion in electrotechnical product standards
- [24] ISO 18064:2003, Thermoplastic elastomers Nomenclature and abbreviated terms
- [25] ISO 1629: Rubber and latices Nomenclature

LICENSED TO MECON Limited. - RANCHI/BANGALORE FOR INTERNAL USE AT THIS LOCATION ONLY, SUPPLIED BY BOOK SUPPLY BUREAU.



The IEC would like to offer you the best quality standards possible. To make sure that we continue to meet your needs, your feedback is essential. Would you please take a minute to answer the questions overleaf and fax them to us at +41 22 919 03 00 or mail them to the address below. Thank you!

Customer Service Centre (CSC)

International Electrotechnical Commission 3, rue de Varembé 1211 Genève 20 Switzerland

or

Fax to: IEC/CSC at +41 22 919 03 00

Thank you for your contribution to the standards-making process.







Non affrancare No stamp required

RÉPONSE PAYÉE SUISSE

Customer Service Centre (CSC) International Electrotechnical Commission 3, rue de Varembé 1211 GENEVA 20 Switzerland

Q1	Please report on ONE STANDARD and ONE STANDARD ONLY . Enter the exact number of the standard: $(e, q, 60601-1-1)$			If you ticked NOT AT ALL in Question 5 the reason is: (tick all that apply)	
		,		standard is out of date	
				standard is incomplete	
				standard is too academic	
Q2	Please tell us in what capacity(ies) you			standard is too superficial	
	bought the standard (tick all that apply).			title is misleading	
				I made the wrong choice	
	purchasing agent			other	
	librarian				
	researcher				
	design engineer		07	Please assess the standard in the	
	safety engineer		u ,	following categories, using	
	testing engineer			the numbers:	
	marketing specialist			(1) unacceptable,	
	other			(2) below average, (3) average	
				(4) above average.	
03	Lwork for/in/ac a:			(5) exceptional,	
Q.)	(tick all that apply)			(6) not applicable	
				timolinoco	
	manufacturing			quality of writing	
	consultant			technical contents	
	government			logic of arrangement of contents	
	test/certification facility			tables, charts, graphs, figures	
	public utility			other	
	education				
	military				
	other		Q8	I read/use the: (tick one)	
04	This standard will be used for:			French text only	
44	(tick all that apply)			English text only	
				both English and French texts	
	general reference				
	product research				
	product design/development				
	specifications		Q9	Please share any comment on any	
	tenders			aspect of the IEC that you would like	
	quality assessment			us to know.	
	certification				
	technical documentation				
	thesis				
	manufacturing				
	other				
Q5	This standard meets my needs:				•••••
	(tick one)				
	not at all				
	fairly well				
	exactly				
		-			

LICENSED TO MECON Limited. - RANCHI/BANGALORE FOR INTERNAL USE AT THIS LOCATION ONLY, SUPPLIED BY BOOK SUPPLY BUREAU.



ICS 13.030.50; 29.035.01