

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Temperature – Electromotive force (EMF) tables for pure-element thermocouple combinations

Tableaux température – Force électromotrice (F.É.M.) pour les combinaisons de couples thermoélectriques à éléments purs



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2008 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester.

If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

Droits de reproduction réservés. Sauf indication contraire, aucune partie de cette publication ne peut être reproduite ni utilisée sous quelque forme que ce soit et par aucun procédé, électronique ou mécanique, y compris la photocopie et les microfilms, sans l'accord écrit de la CEI ou du Comité national de la CEI du pays du demandeur.

Si vous avez des questions sur le copyright de la CEI ou si vous désirez obtenir des droits supplémentaires sur cette publication, utilisez les coordonnées ci-après ou contactez le Comité national de la CEI de votre pays de résidence.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland
Email: inmail@iec.ch
Web: www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

- Catalogue of IEC publications: www.iec.ch/searchpub

The IEC on-line Catalogue enables you to search by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, withdrawn and replaced publications.

- IEC Just Published: www.iec.ch/online_news/justpub

Stay up to date on all new IEC publications. Just Published details twice a month all new publications released. Available on-line and also by email.

- Electropedia: www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 20 000 terms and definitions in English and French, with equivalent terms in additional languages. Also known as the International Electrotechnical Vocabulary online.

- Customer Service Centre: www.iec.ch/webstore/custserv

If you wish to give us your feedback on this publication or need further assistance, please visit the Customer Service Centre FAQ or contact us:

Email: csc@iec.ch

Tel.: +41 22 919 02 11

Fax: +41 22 919 03 00

A propos de la CEI

La Commission Electrotechnique Internationale (CEI) est la première organisation mondiale qui élabore et publie des normes internationales pour tout ce qui a trait à l'électricité, à l'électronique et aux technologies apparentées.

A propos des publications CEI

Le contenu technique des publications de la CEI est constamment revu. Veuillez vous assurer que vous possédez l'édition la plus récente, un corrigendum ou amendement peut avoir été publié.

- Catalogue des publications de la CEI: www.iec.ch/searchpub/cur_fut-f.htm

Le Catalogue en-ligne de la CEI vous permet d'effectuer des recherches en utilisant différents critères (numéro de référence, texte, comité d'études,...). Il donne aussi des informations sur les projets et les publications retirées ou remplacées.

- Just Published CEI: www.iec.ch/online_news/justpub

Restez informé sur les nouvelles publications de la CEI. Just Published détaille deux fois par mois les nouvelles publications parues. Disponible en-ligne et aussi par email.

- Electropedia: www.electropedia.org

Le premier dictionnaire en ligne au monde de termes électroniques et électriques. Il contient plus de 20 000 termes et définitions en anglais et en français, ainsi que les termes équivalents dans les langues additionnelles. Egalement appelé Vocabulaire Electrotechnique International en ligne.

- Service Clients: www.iec.ch/webstore/custserv/custserv_entry-f.htm

Si vous désirez nous donner des commentaires sur cette publication ou si vous avez des questions, visitez le FAQ du Service clients ou contactez-nous:

Email: csc@iec.ch

Tél.: +41 22 919 02 11

Fax: +41 22 919 03 00



IEC 62460

Edition 1.0 2008-07

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Temperature – Electromotive force (EMF) tables for pure-element thermocouple combinations

Tableaux température – Force électromotrice (F.É.M.) pour les combinaisons de couples thermoélectriques à éléments purs

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

U

ICS 17.200.20; 25.040.40

ISBN 2-8318-9852-8

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references	5
3 Terms and definitions	5
4 Information on tables and equations	6
5 Tables for Gold versus Platinum thermocouples	7
5.1 Gold versus Platinum: EMF at intervals of 1 °C	7
5.2 Gold versus Platinum: Temperature at intervals of 10 µV	10
5.3 Thermoelectric values at the defining fixed points of the ITS-90 for Au/Pt thermocouples (informative)	14
6 Tables for Platinum versus Palladium thermocouples	15
6.1 Platinum versus Palladium: EMF at intervals of 1 °C	15
6.2 Platinum versus Palladium: Temperature at intervals of 10 µV	19
6.3 Thermoelectric values at the defining fixed points of the ITS-90 for Pt/Pd thermocouples (informative)	25
Annex A Gold versus Platinum coefficients	26
Annex B Platinum versus Palladium Coefficients	28

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**TEMPERATURE – ELECTROMOTIVE FORCE (EMF) TABLES FOR
PURE-ELEMENT THERMOCOUPLE COMBINATIONS**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62460 has been prepared by subcommittee 65B: Devices and process analysis, of IEC technical committee 65: Industrial-process measurement, control and automation.

The text of this standard is based on the following documents:

FDIS	Report on voting
65B/665/FDIS	65B/684/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

TEMPERATURE – ELECTROMOTIVE FORCE (EMF) TABLES FOR PURE-ELEMENT THERMOCOUPLE COMBINATIONS

1 Scope

This International Standard specifies the equations and reference tables relating temperature to EMF (electro-motive force) for Gold versus Platinum and Platinum versus Palladium thermocouples. For information and convenience of use it also provides the approximate equations for temperature as functions of EMF.

The tables and equations in this standard are intended for use with thermocouples made from elements of purity not less than 99.999 % for Platinum and Gold and of 99.99 % for Palladium, by weight.

Tolerances on initial values of EMF versus temperature have not been established for the thermocouples in this standard. Where required, these tolerances should be agreed between the wire manufacturer and the user.

Temperatures in this standard are based on the International Temperature Scale of 1990 (ITS-90). They are expressed in degrees Celsius, symbol t_{90} . Values of EMF, symbol $E/\mu V$, are given in microvolts.

This standard does not cover extension or compensating wires for use with the pure-element thermocouples. The questions of their use shall be agreed between the manufacturer and the user.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60584-1, *Thermocouples – Reference tables*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60584-1 apply, as well as the following.

3.1

thermocouple types

the following thermocouple wire types are covered by this standard:

- Gold versus Platinum (Au/Pt or Gold/Platinum)
- Platinum versus Palladium (Pt/Pd or Platinum/Palladium)

Following international convention, as in IEC 60584-1, when identifying thermocouples the positive element/wire is given first.

3.2 thermoelectric values at the ITS-90 fixed points

values are given for the defining triple points (TP), melting points (MP) and freezing points (FP) in the temperature range of the corresponding tables. The Seebeck coefficient S is the first derivative of the EMF with respect to temperature.

4 Information on tables and equations

The following tables are included in this standard:

- Gold versus Platinum: EMF at intervals of 1 °C
- Gold versus Platinum: temperatures at intervals of 10 μV
- Gold versus Platinum: thermoelectric values at the fixed points of the ITS-90
- Platinum versus Palladium: EMF at intervals of 1 °C
- Platinum versus Palladium: temperatures at intervals of 10 μV
- Platinum versus Palladium: thermoelectric values at the fixed points of the ITS-90

For the tables in this document, the reference temperature is 0 °C.

The definitive equations of EMF, $E/\mu\text{V}$, as functions of temperature, $t_{90}/^{\circ}\text{C}$, which are used to generate the tables, are given in Annex A for Gold/Platinum thermocouples and Annex B for Platinum/Palladium thermocouples.

For information and convenience in use, approximate equations are also given, expressing $t_{90}/^{\circ}\text{C}$ as functions of $E/\mu\text{V}$ for the respective thermocouples within the stated error limits.

5 Tables for Gold versus Platinum thermocouples

5.1 Gold versus Platinum: EMF at intervals of 1 °C

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
0	0.0	6.1	12.1	18.3	24.5	30.7	36.9	43.2	49.5	55.9	0
10	62.3	68.7	75.2	81.7	88.2	94.8	101.4	108.1	114.8	121.5	10
20	128.3	135.1	141.9	148.8	155.7	162.7	169.7	176.7	183.7	190.8	20
30	197.9	205.1	212.3	219.5	226.8	234.1	241.4	248.8	256.2	263.6	30
40	271.1	278.6	286.1	293.7	301.3	308.9	316.6	324.3	332.1	339.8	40
50	347.6	355.5	363.3	371.2	379.2	387.1	395.1	403.2	411.2	419.3	50
60	427.5	435.6	443.8	452.1	460.3	468.6	476.9	485.3	493.6	502.1	60
70	510.5	519.0	527.5	536.0	544.6	553.2	561.8	570.5	579.2	587.9	70
80	596.6	605.4	614.2	623.1	632.0	640.9	649.8	658.7	667.7	676.8	80
90	685.8	694.9	704.0	713.1	722.3	731.5	740.7	750.0	759.2	768.6	90
100	777.9	787.3	796.7	806.1	815.5	825.0	834.5	844.1	853.6	863.2	100
110	872.8	882.5	892.2	901.9	911.6	921.4	931.2	941.0	950.8	960.7	110
120	970.6	980.5	990.5	1000.4	1010.4	1020.5	1030.5	1040.6	1050.7	1060.9	120
130	1071.0	1081.2	1091.4	1101.7	1112.0	1122.3	1132.6	1142.9	1153.3	1163.7	130
140	1174.1	1184.6	1195.1	1205.6	1216.1	1226.7	1237.2	1247.8	1258.5	1269.1	140
150	1279.8	1290.5	1301.3	1312.0	1322.8	1333.6	1344.4	1355.3	1366.2	1377.1	150
160	1388.0	1399.0	1410.0	1421.0	1432.0	1443.1	1454.1	1465.3	1476.4	1487.5	160
170	1498.7	1509.9	1521.1	1532.4	1543.7	1555.0	1566.3	1577.6	1589.0	1600.4	170
180	1611.8	1623.3	1634.7	1646.2	1657.7	1669.3	1680.8	1692.4	1704.0	1715.6	180
190	1727.3	1739.0	1750.7	1762.4	1774.1	1785.9	1797.7	1809.5	1821.3	1833.2	190
200	1845.1	1857.0	1868.9	1880.9	1892.8	1904.8	1916.8	1928.9	1941.0	1953.0	200
210	1965.1	1977.3	1989.4	2001.6	2013.8	2026.0	2038.3	2050.5	2062.8	2075.1	210
220	2087.4	2099.8	2112.2	2124.6	2137.0	2149.4	2161.9	2174.4	2186.9	2199.4	220
230	2211.9	2224.5	2237.1	2249.7	2262.3	2275.0	2287.7	2300.4	2313.1	2325.8	230
240	2338.6	2351.4	2364.2	2377.0	2389.8	2402.7	2415.6	2428.5	2441.4	2454.4	240
250	2467.3	2480.3	2493.3	2506.4	2519.4	2532.5	2545.6	2558.7	2571.9	2585.0	250
260	2598.2	2611.4	2624.6	2637.8	2651.1	2664.4	2677.7	2691.0	2704.3	2717.7	260
270	2731.1	2744.5	2757.9	2771.3	2784.8	2798.3	2811.8	2825.3	2838.9	2852.4	270
280	2866.0	2879.6	2893.2	2906.9	2920.5	2934.2	2947.9	2961.6	2975.4	2989.1	280
290	3002.9	3016.7	3030.5	3044.4	3058.2	3072.1	3086.0	3099.9	3113.8	3127.8	290
300	3141.8	3155.8	3169.8	3183.8	3197.9	3211.9	3226.0	3240.1	3254.3	3268.4	300
310	3282.6	3296.8	3311.0	3325.2	3339.4	3353.7	3368.0	3382.3	3396.6	3410.9	310
320	3425.3	3439.7	3454.1	3468.5	3482.9	3497.4	3511.8	3526.3	3540.8	3555.4	320
330	3569.9	3584.5	3599.1	3613.7	3628.3	3642.9	3657.6	3672.2	3686.9	3701.7	330
340	3716.4	3731.1	3745.9	3760.7	3775.5	3790.3	3805.2	3820.0	3834.9	3849.8	340
350	3864.7	3879.6	3894.6	3909.6	3924.6	3939.6	3954.6	3969.6	3984.7	3999.8	350
360	4014.9	4030.0	4045.1	4060.3	4075.4	4090.6	4105.8	4121.0	4136.3	4151.5	360
370	4166.8	4182.1	4197.4	4212.8	4228.1	4243.5	4258.9	4274.3	4289.7	4305.1	370
380	4320.6	4336.1	4351.6	4367.1	4382.6	4398.1	4413.7	4429.3	4444.9	4460.5	380
390	4476.1	4491.8	4507.4	4523.1	4538.8	4554.6	4570.3	4586.1	4601.8	4617.6	390

Gold versus Platinum
EMF at intervals of 1 °C (*continued*)

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
400	4633.4	4649.3	4665.1	4681.0	4696.8	4712.7	4728.6	4744.6	4760.5	4776.5	400
410	4792.5	4808.5	4824.5	4840.5	4856.6	4872.7	4888.7	4904.9	4921.0	4937.1	410
420	4953.3	4969.4	4985.6	5001.8	5018.1	5034.3	5050.6	5066.9	5083.1	5099.5	420
430	5115.8	5132.1	5148.5	5164.9	5181.3	5197.7	5214.1	5230.6	5247.0	5263.5	430
440	5280.0	5296.5	5313.1	5329.6	5346.2	5362.8	5379.4	5396.0	5412.6	5429.3	440
450	5446.0	5462.6	5479.4	5496.1	5512.8	5529.6	5546.3	5563.1	5579.9	5596.8	450
460	5613.6	5630.5	5647.3	5664.2	5681.1	5698.0	5715.0	5731.9	5748.9	5765.9	460
470	5782.9	5799.9	5817.0	5834.0	5851.1	5868.2	5885.3	5902.4	5919.6	5936.8	470
480	5953.9	5971.1	5988.3	6005.6	6022.8	6040.1	6057.3	6074.6	6091.9	6109.3	480
490	6126.6	6144.0	6161.3	6178.7	6196.1	6213.6	6231.0	6248.5	6265.9	6283.4	490
500	6301.0	6318.5	6336.0	6353.6	6371.2	6388.7	6406.4	6424.0	6441.6	6459.3	500
510	6477.0	6494.7	6512.4	6530.1	6547.8	6565.6	6583.4	6601.1	6619.0	6636.8	510
520	6654.6	6672.5	6690.4	6708.2	6726.2	6744.1	6762.0	6780.0	6797.9	6815.9	520
530	6833.9	6852.0	6870.0	6888.1	6906.1	6924.2	6942.3	6960.4	6978.6	6996.7	530
540	7014.9	7033.1	7051.3	7069.5	7087.7	7106.0	7124.3	7142.6	7160.9	7179.2	540
550	7197.5	7215.9	7234.2	7252.6	7271.0	7289.4	7307.9	7326.3	7344.8	7363.3	550
560	7381.8	7400.3	7418.8	7437.4	7455.9	7474.5	7493.1	7511.7	7530.3	7549.0	560
570	7567.6	7586.3	7605.0	7623.7	7642.5	7661.2	7680.0	7698.7	7717.5	7736.3	570
580	7755.2	7774.0	7792.9	7811.7	7830.6	7849.5	7868.5	7887.4	7906.4	7925.3	580
590	7944.3	7963.3	7982.3	8001.4	8020.4	8039.5	8058.6	8077.7	8096.8	8115.9	590
600	8135.1	8154.3	8173.4	8192.6	8211.9	8231.1	8250.3	8269.6	8288.9	8308.2	600
610	8327.5	8346.8	8366.2	8385.5	8404.9	8424.3	8443.7	8463.2	8482.6	8502.1	610
620	8521.5	8541.0	8560.5	8580.1	8599.6	8619.2	8638.7	8658.3	8677.9	8697.6	620
630	8717.2	8736.9	8756.5	8776.2	8795.9	8815.6	8835.4	8855.1	8874.9	8894.7	630
640	8914.5	8934.3	8954.1	8974.0	8993.9	9013.7	9033.6	9053.6	9073.5	9093.4	640
650	9113.4	9133.4	9153.4	9173.4	9193.4	9213.5	9233.5	9253.6	9273.7	9293.8	650
660	9313.9	9334.1	9354.2	9374.4	9394.6	9414.8	9435.0	9455.3	9475.5	9495.8	660
670	9516.1	9536.4	9556.7	9577.0	9597.4	9617.8	9638.2	9658.6	9679.0	9699.4	670
680	9719.9	9740.3	9760.8	9781.3	9801.8	9822.3	9842.9	9863.5	9884.0	9904.6	680
690	9925.2	9945.9	9966.5	9987.2	10007.9	10028.5	10049.3	10070.0	10090.7	10111.5	690
700	10132.2	10153.0	10173.8	10194.7	10215.5	10236.4	10257.2	10278.1	10299.0	10319.9	700
710	10340.9	10361.8	10382.8	10403.8	10424.8	10445.8	10466.8	10487.9	10508.9	10530.0	710
720	10551.1	10572.2	10593.3	10614.5	10635.6	10656.8	10678.0	10699.2	10720.4	10741.7	720
730	10762.9	10784.2	10805.5	10826.8	10848.1	10869.5	10890.8	10912.2	10933.6	10955.0	730
740	10976.4	10997.8	11019.3	11040.8	11062.2	11083.7	11105.3	11126.8	11148.3	11169.9	740
750	11191.5	11213.1	11234.7	11256.3	11277.9	11299.6	11321.3	11343.0	11364.7	11386.4	750
760	11408.1	11429.9	11451.7	11473.5	11495.3	11517.1	11538.9	11560.8	11582.6	11604.5	760
770	11626.4	11648.3	11670.3	11692.2	11714.2	11736.2	11758.2	11780.2	11802.2	11824.3	770
780	11846.3	11868.4	11890.5	11912.6	11934.7	11956.9	11979.0	12001.2	12023.4	12045.6	780
790	12067.8	12090.0	12112.3	12134.6	12156.8	12179.1	12201.5	12223.8	12246.1	12268.5	790

Gold versus Platinum
EMF at intervals of 1 °C (*continued*)

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
800	12290.9	12313.3	12335.7	12358.1	12380.6	12403.0	12425.5	12448.0	12470.5	12493.0	800
810	12515.6	12538.1	12560.7	12583.3	12605.9	12628.5	12651.2	12673.8	12696.5	12719.2	810
820	12741.9	12764.6	12787.3	12810.1	12832.8	12855.6	12878.4	12901.2	12924.0	12946.9	820
830	12969.7	12992.6	13015.5	13038.4	13061.3	13084.3	13107.2	13130.2	13153.2	13176.2	830
840	13199.2	13222.2	13245.3	13268.4	13291.4	13314.5	13337.7	13360.8	13383.9	13407.1	840
850	13430.3	13453.5	13476.7	13499.9	13523.1	13546.4	13569.7	13593.0	13616.3	13639.6	850
860	13662.9	13686.3	13709.6	13733.0	13756.4	13779.8	13803.3	13826.7	13850.2	13873.6	860
870	13897.1	13920.7	13944.2	13967.7	13991.3	14014.9	14038.4	14062.0	14085.7	14109.3	870
880	14133.0	14156.6	14180.3	14204.0	14227.7	14251.5	14275.2	14299.0	14322.7	14346.5	880
890	14370.3	14394.2	14418.0	14441.9	14465.7	14489.6	14513.5	14537.5	14561.4	14585.3	890
900	14609.3	14633.3	14657.3	14681.3	14705.3	14729.4	14753.4	14777.5	14801.6	14825.7	900
910	14849.9	14874.0	14898.2	14922.3	14946.5	14970.7	14994.9	15019.2	15043.4	15067.7	910
920	15092.0	15116.3	15140.6	15164.9	15189.3	15213.6	15238.0	15262.4	15286.8	15311.2	920
930	15335.7	15360.1	15384.6	15409.1	15433.6	15458.1	15482.6	15507.2	15531.7	15556.3	930
940	15580.9	15605.5	15630.1	15654.8	15679.4	15704.1	15728.8	15753.5	15778.2	15803.0	940
950	15827.7	15852.5	15877.3	15902.1	15926.9	15951.7	15976.6	16001.4	16026.3	16051.2	950
960	16076.1	16101.0	16126.0	16150.9	16175.9	16200.9	16225.9	16250.9	16276.0	16301.0	960
970	16326.1	16351.2	16376.2	16401.4	16426.5	16451.6	16476.8	16502.0	16527.2	16552.4	970
980	16577.6	16602.8	16628.1	16653.3	16678.6	16703.9	16729.2	16754.6	16779.9	16805.3	980
990	16830.7	16856.1	16881.5	16906.9	16932.3	16957.8	16983.3	17008.8	17034.3	17059.8	990
1000	17085.3										1000

5.2 Gold versus Platinum: Temperature at intervals of 10 μV

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
0	0.00	1.65	3.28	4.89	6.49	8.07	9.64	11.20	12.74	14.27	0
100	15.78	17.28	18.77	20.25	21.72	23.17	24.62	26.05	27.47	28.89	100
200	30.29	31.68	33.07	34.44	35.81	37.17	38.52	39.86	41.19	42.51	200
300	43.83	45.14	46.44	47.74	49.02	50.30	51.58	52.84	54.10	55.36	300
400	56.60	57.84	59.08	60.31	61.53	62.75	63.96	65.17	66.37	67.56	400
500	68.75	69.94	71.12	72.29	73.46	74.63	75.79	76.94	78.09	79.24	500
600	80.38	81.52	82.65	83.78	84.90	86.02	87.14	88.25	89.36	90.46	600
700	91.56	92.66	93.75	94.84	95.92	97.01	98.08	99.16	100.23	101.29	700
800	102.36	103.42	104.47	105.53	106.58	107.62	108.67	109.71	110.74	111.78	800
900	112.81	113.84	114.86	115.88	116.90	117.92	118.93	119.94	120.95	121.95	900
1000	122.96	123.96	124.95	125.95	126.94	127.93	128.91	129.90	130.88	131.86	1000
1100	132.83	133.81	134.78	135.75	136.72	137.68	138.64	139.60	140.56	141.52	1100
1200	142.47	143.42	144.37	145.31	146.26	147.20	148.14	149.08	150.02	150.95	1200
1300	151.88	152.81	153.74	154.67	155.59	156.51	157.43	158.35	159.27	160.18	1300
1400	161.09	162.00	162.91	163.82	164.72	165.63	166.53	167.43	168.33	169.22	1400
1500	170.12	171.01	171.90	172.79	173.68	174.56	175.45	176.33	177.21	178.09	1500
1600	178.97	179.84	180.72	181.59	182.46	183.33	184.20	185.06	185.93	186.79	1600
1700	187.65	188.52	189.37	190.23	191.09	191.94	192.80	193.65	194.50	195.35	1700
1800	196.19	197.04	197.89	198.73	199.57	200.41	201.25	202.09	202.93	203.76	1800
1900	204.60	205.43	206.26	207.09	207.92	208.75	209.58	210.40	211.22	212.05	1900
2000	212.87	213.69	214.51	215.32	216.14	216.96	217.77	218.58	219.40	220.21	2000
2100	221.02	221.82	222.63	223.44	224.24	225.05	225.85	226.65	227.45	228.25	2100
2200	229.05	229.84	230.64	231.44	232.23	233.02	233.81	234.61	235.39	236.18	2200
2300	236.97	237.76	238.54	239.33	240.11	240.89	241.67	242.46	243.23	244.01	2300
2400	244.79	245.57	246.34	247.12	247.89	248.66	249.43	250.20	250.97	251.74	2400
2500	252.51	253.28	254.04	254.81	255.57	256.34	257.10	257.86	258.62	259.38	2500
2600	260.14	260.90	261.65	262.41	263.16	263.92	264.67	265.42	266.18	266.93	2600
2700	267.68	268.42	269.17	269.92	270.67	271.41	272.16	272.90	273.64	274.39	2700
2800	275.13	275.87	276.61	277.35	278.09	278.82	279.56	280.30	281.03	281.76	2800
2900	282.50	283.23	283.96	284.69	285.42	286.15	286.88	287.61	288.34	289.06	2900
3000	289.79	290.52	291.24	291.96	292.69	293.41	294.13	294.85	295.57	296.29	3000
3100	297.01	297.73	298.44	299.16	299.87	300.59	301.30	302.02	302.73	303.44	3100
3200	304.15	304.86	305.57	306.28	306.99	307.70	308.41	309.11	309.82	310.52	3200
3300	311.23	311.93	312.64	313.34	314.04	314.74	315.44	316.14	316.84	317.54	3300
3400	318.24	318.93	319.63	320.33	321.02	321.72	322.41	323.11	323.80	324.49	3400
3500	325.18	325.87	326.56	327.25	327.94	328.63	329.32	330.01	330.69	331.38	3500
3600	332.06	332.75	333.43	334.12	334.80	335.48	336.17	336.85	337.53	338.21	3600
3700	338.89	339.57	340.24	340.92	341.60	342.28	342.95	343.63	344.30	344.98	3700
3800	345.65	346.33	347.00	347.67	348.34	349.01	349.68	350.35	351.02	351.69	3800
3900	352.36	353.03	353.70	354.36	355.03	355.69	356.36	357.02	357.69	358.35	3900

Gold versus Platinum
Temperature at intervals of 10 μV (*continued*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
4000	359.01	359.68	360.34	361.00	361.66	362.32	362.98	363.64	364.30	364.96	4000
4100	365.62	366.27	366.93	367.59	368.24	368.90	369.55	370.21	370.86	371.51	4100
4200	372.17	372.82	373.47	374.12	374.77	375.42	376.07	376.72	377.37	378.02	4200
4300	378.67	379.31	379.96	380.61	381.25	381.90	382.54	383.19	383.83	384.48	4300
4400	385.12	385.76	386.40	387.05	387.69	388.33	388.97	389.61	390.25	390.89	4400
4500	391.52	392.16	392.80	393.44	394.07	394.71	395.35	395.98	396.62	397.25	4500
4600	397.88	398.52	399.15	399.78	400.42	401.05	401.68	402.31	402.94	403.57	4600
4700	404.20	404.83	405.46	406.08	406.71	407.34	407.97	408.59	409.22	409.85	4700
4800	410.47	411.10	411.72	412.34	412.97	413.59	414.21	414.83	415.46	416.08	4800
4900	416.70	417.32	417.94	418.56	419.18	419.80	420.42	421.03	421.65	422.27	4900
5000	422.89	423.50	424.12	424.73	425.35	425.97	426.58	427.19	427.81	428.42	5000
5100	429.03	429.65	430.26	430.87	431.48	432.09	432.70	433.31	433.92	434.53	5100
5200	435.14	435.75	436.36	436.97	437.57	438.18	438.79	439.39	440.00	440.60	5200
5300	441.21	441.81	442.42	443.02	443.63	444.23	444.83	445.44	446.04	446.64	5300
5400	447.24	447.84	448.44	449.04	449.64	450.24	450.84	451.44	452.04	452.64	5400
5500	453.24	453.83	454.43	455.03	455.62	456.22	456.81	457.41	458.00	458.60	5500
5600	459.19	459.79	460.38	460.97	461.57	462.16	462.75	463.34	463.93	464.53	5600
5700	465.12	465.71	466.30	466.89	467.48	468.06	468.65	469.24	469.83	470.42	5700
5800	471.00	471.59	472.18	472.76	473.35	473.93	474.52	475.10	475.69	476.27	5800
5900	476.86	477.44	478.02	478.61	479.19	479.77	480.35	480.94	481.52	482.10	5900
6000	482.68	483.26	483.84	484.42	485.00	485.58	486.15	486.73	487.31	487.89	6000
6100	488.47	489.04	489.62	490.20	490.77	491.35	491.92	492.50	493.07	493.65	6100
6200	494.22	494.80	495.37	495.94	496.51	497.09	497.66	498.23	498.80	499.37	6200
6300	499.95	500.52	501.09	501.66	502.23	502.80	503.37	503.93	504.50	505.07	6300
6400	505.64	506.21	506.77	507.34	507.91	508.47	509.04	509.61	510.17	510.74	6400
6500	511.30	511.87	512.43	513.00	513.56	514.12	514.69	515.25	515.81	516.37	6500
6600	516.94	517.50	518.06	518.62	519.18	519.74	520.30	520.86	521.42	521.98	6600
6700	522.54	523.10	523.66	524.21	524.77	525.33	525.89	526.44	527.00	527.56	6700
6800	528.11	528.67	529.23	529.78	530.34	530.89	531.45	532.00	532.55	533.11	6800
6900	533.66	534.21	534.77	535.32	535.87	536.42	536.98	537.53	538.08	538.63	6900
7000	539.18	539.73	540.28	540.83	541.38	541.93	542.48	543.03	543.57	544.12	7000
7100	544.67	545.22	545.77	546.31	546.86	547.41	547.95	548.50	549.04	549.59	7100
7200	550.14	550.68	551.22	551.77	552.31	552.86	553.40	553.94	554.49	555.03	7200
7300	555.57	556.12	556.66	557.20	557.74	558.28	558.82	559.36	559.90	560.44	7300
7400	560.98	561.52	562.06	562.60	563.14	563.68	564.22	564.76	565.30	565.83	7400
7500	566.37	566.91	567.44	567.98	568.52	569.05	569.59	570.13	570.66	571.20	7500
7600	571.73	572.27	572.80	573.33	573.87	574.40	574.94	575.47	576.00	576.53	7600
7700	577.07	577.60	578.13	578.66	579.19	579.73	580.26	580.79	581.32	581.85	7700
7800	582.38	582.91	583.44	583.97	584.50	585.02	585.55	586.08	586.61	587.14	7800
7900	587.66	588.19	588.72	589.25	589.77	590.30	590.83	591.35	591.88	592.40	7900

Gold versus Platinum
Temperature at intervals of 10 μV (*continued*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
8000	592.93	593.45	593.98	594.50	595.03	595.55	596.07	596.60	597.12	597.64	8000
8100	598.17	598.69	599.21	599.73	600.26	600.78	601.30	601.82	602.34	602.86	8100
8200	603.38	603.90	604.42	604.94	605.46	605.98	606.50	607.02	607.54	608.06	8200
8300	608.58	609.09	609.61	610.13	610.65	611.16	611.68	612.20	612.71	613.23	8300
8400	613.75	614.26	614.78	615.29	615.81	616.32	616.84	617.35	617.87	618.38	8400
8500	618.89	619.41	619.92	620.43	620.95	621.46	621.97	622.48	623.00	623.51	8500
8600	624.02	624.53	625.04	625.55	626.06	626.57	627.09	627.60	628.11	628.61	8600
8700	629.12	629.63	630.14	630.65	631.16	631.67	632.18	632.68	633.19	633.70	8700
8800	634.21	634.71	635.22	635.73	636.23	636.74	637.25	637.75	638.26	638.76	8800
8900	639.27	639.77	640.28	640.78	641.29	641.79	642.30	642.80	643.30	643.81	8900
9000	644.31	644.81	645.31	645.82	646.32	646.82	647.32	647.83	648.33	648.83	9000
9100	649.33	649.83	650.33	650.83	651.33	651.83	652.33	652.83	653.33	653.83	9100
9200	654.33	654.83	655.33	655.82	656.32	656.82	657.32	657.82	658.31	658.81	9200
9300	659.31	659.81	660.30	660.80	661.29	661.79	662.29	662.78	663.28	663.77	9300
9400	664.27	664.76	665.26	665.75	666.25	666.74	667.23	667.73	668.22	668.71	9400
9500	669.21	669.70	670.19	670.69	671.18	671.67	672.16	672.65	673.15	673.64	9500
9600	674.13	674.62	675.11	675.60	676.09	676.58	677.07	677.56	678.05	678.54	9600
9700	679.03	679.52	680.01	680.50	680.98	681.47	681.96	682.45	682.94	683.42	9700
9800	683.91	684.40	684.89	685.37	685.86	686.35	686.83	687.32	687.80	688.29	9800
9900	688.78	689.26	689.75	690.23	690.72	691.20	691.68	692.17	692.65	693.14	9900
10000	693.62	694.10	694.59	695.07	695.55	696.04	696.52	697.00	697.48	697.97	10000
10100	698.45	698.93	699.41	699.89	700.37	700.85	701.33	701.82	702.30	702.78	10100
10200	703.26	703.74	704.22	704.70	705.17	705.65	706.13	706.61	707.09	707.57	10200
10300	708.05	708.53	709.00	709.48	709.96	710.44	710.91	711.39	711.87	712.34	10300
10400	712.82	713.30	713.77	714.25	714.72	715.20	715.68	716.15	716.63	717.10	10400
10500	717.58	718.05	718.53	719.00	719.47	719.95	720.42	720.89	721.37	721.84	10500
10600	722.31	722.79	723.26	723.73	724.21	724.68	725.15	725.62	726.09	726.56	10600
10700	727.04	727.51	727.98	728.45	728.92	729.39	729.86	730.33	730.80	731.27	10700
10800	731.74	732.21	732.68	733.15	733.62	734.09	734.56	735.02	735.49	735.96	10800
10900	736.43	736.90	737.36	737.83	738.30	738.77	739.23	739.70	740.17	740.63	10900
11000	741.10	741.57	742.03	742.50	742.96	743.43	743.90	744.36	744.83	745.29	11000
11100	745.76	746.22	746.68	747.15	747.61	748.08	748.54	749.00	749.47	749.93	11100
11200	750.39	750.86	751.32	751.78	752.25	752.71	753.17	753.63	754.09	754.56	11200
11300	755.02	755.48	755.94	756.40	756.86	757.32	757.78	758.24	758.70	759.16	11300
11400	759.62	760.08	760.54	761.00	761.46	761.92	762.38	762.84	763.30	763.76	11400
11500	764.22	764.67	765.13	765.59	766.05	766.51	766.96	767.42	767.88	768.34	11500
11600	768.79	769.25	769.71	770.16	770.62	771.08	771.53	771.99	772.44	772.90	11600
11700	773.35	773.81	774.26	774.72	775.17	775.63	776.08	776.54	776.99	777.45	11700
11800	777.90	778.35	778.81	779.26	779.71	780.17	780.62	781.07	781.53	781.98	11800
11900	782.43	782.88	783.33	783.79	784.24	784.69	785.14	785.59	786.04	786.50	11900

Gold versus Platinum
Temperature at intervals of 10 μV (*continued*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90}/^{\circ}\text{C}$											
12000	786.95	787.40	787.85	788.30	788.75	789.20	789.65	790.10	790.55	791.00	12000
12100	791.45	791.90	792.35	792.80	793.24	793.69	794.14	794.59	795.04	795.49	12100
12200	795.93	796.38	796.83	797.28	797.73	798.17	798.62	799.07	799.51	799.96	12200
12300	800.41	800.85	801.30	801.75	802.19	802.64	803.08	803.53	803.97	804.42	12300
12400	804.87	805.31	805.76	806.20	806.64	807.09	807.53	807.98	808.42	808.87	12400
12500	809.31	809.75	810.20	810.64	811.08	811.53	811.97	812.41	812.85	813.30	12500
12600	813.74	814.18	814.62	815.07	815.51	815.95	816.39	816.83	817.27	817.71	12600
12700	818.16	818.60	819.04	819.48	819.92	820.36	820.80	821.24	821.68	822.12	12700
12800	822.56	823.00	823.44	823.88	824.32	824.75	825.19	825.63	826.07	826.51	12800
12900	826.95	827.39	827.82	828.26	828.70	829.14	829.57	830.01	830.45	830.89	12900
13000	831.32	831.76	832.20	832.63	833.07	833.51	833.94	834.38	834.81	835.25	13000
13100	835.69	836.12	836.56	836.99	837.43	837.86	838.30	838.73	839.17	839.60	13100
13200	840.03	840.47	840.90	841.34	841.77	842.20	842.64	843.07	843.50	843.94	13200
13300	844.37	844.80	845.24	845.67	846.10	846.53	846.97	847.40	847.83	848.26	13300
13400	848.69	849.13	849.56	849.99	850.42	850.85	851.28	851.71	852.14	852.57	13400
13500	853.00	853.44	853.87	854.30	854.73	855.16	855.58	856.01	856.44	856.87	13500
13600	857.30	857.73	858.16	858.59	859.02	859.45	859.88	860.30	860.73	861.16	13600
13700	861.59	862.02	862.44	862.87	863.30	863.73	864.15	864.58	865.01	865.43	13700
13800	865.86	866.29	866.71	867.14	867.57	867.99	868.42	868.84	869.27	869.70	13800
13900	870.12	870.55	870.97	871.40	871.82	872.25	872.67	873.10	873.52	873.95	13900
14000	874.37	874.79	875.22	875.64	876.07	876.49	876.91	877.34	877.76	878.18	14000
14100	878.61	879.03	879.45	879.87	880.30	880.72	881.14	881.56	881.99	882.41	14100
14200	882.83	883.25	883.67	884.10	884.52	884.94	885.36	885.78	886.20	886.62	14200
14300	887.04	887.46	887.88	888.30	888.72	889.15	889.57	889.99	890.40	890.82	14300
14400	891.24	891.66	892.08	892.50	892.92	893.34	893.76	894.18	894.60	895.01	14400
14500	895.43	895.85	896.27	896.69	897.11	897.52	897.94	898.36	898.78	899.19	14500
14600	899.61	900.03	900.45	900.86	901.28	901.70	902.11	902.53	902.94	903.36	14600
14700	903.78	904.19	904.61	905.03	905.44	905.86	906.27	906.69	907.10	907.52	14700
14800	907.93	908.35	908.76	909.18	909.59	910.01	910.42	910.83	911.25	911.66	14800
14900	912.08	912.49	912.90	913.32	913.73	914.14	914.56	914.97	915.38	915.80	14900
15000	916.21	916.62	917.03	917.45	917.86	918.27	918.68	919.10	919.51	919.92	15000
15100	920.33	920.74	921.15	921.56	921.98	922.39	922.80	923.21	923.62	924.03	15100
15200	924.44	924.85	925.26	925.67	926.08	926.49	926.90	927.31	927.72	928.13	15200
15300	928.54	928.95	929.36	929.77	930.18	930.59	931.00	931.40	931.81	932.22	15300
15400	932.63	933.04	933.45	933.85	934.26	934.67	935.08	935.49	935.89	936.30	15400
15500	936.71	937.12	937.52	937.93	938.34	938.74	939.15	939.56	939.96	940.37	15500
15600	940.78	941.18	941.59	941.99	942.40	942.81	943.21	943.62	944.02	944.43	15600
15700	944.83	945.24	945.64	946.05	946.45	946.86	947.26	947.67	948.07	948.48	15700
15800	948.88	949.28	949.69	950.09	950.50	950.90	951.30	951.71	952.11	952.51	15800
15900	952.92	953.32	953.72	954.13	954.53	954.93	955.33	955.74	956.14	956.54	15900

Gold versus Platinum
Temperature at intervals of 10 μV (*continued*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$T_{90}/^{\circ}\text{C}$											
16000	956.94	957.34	957.75	958.15	958.55	958.95	959.35	959.75	960.16	960.56	16000
16100	960.96	961.36	961.76	962.16	962.56	962.96	963.36	963.76	964.16	964.56	16100
16200	964.96	965.36	965.76	966.16	966.56	966.96	967.36	967.76	968.16	968.56	16200
16300	968.96	969.36	969.76	970.16	970.56	970.95	971.35	971.75	972.15	972.55	16300
16400	972.95	973.34	973.74	974.14	974.54	974.93	975.33	975.73	976.13	976.52	16400
16500	976.92	977.32	977.72	978.11	978.51	978.91	979.30	979.70	980.10	980.49	16500
16600	980.89	981.28	981.68	982.08	982.47	982.87	983.26	983.66	984.05	984.45	16600
16700	984.84	985.24	985.63	986.03	986.42	986.82	987.21	987.61	988.00	988.40	16700
16800	988.79	989.19	989.58	989.97	990.37	990.76	991.15	991.55	991.94	992.34	16800
16900	992.73	993.12	993.51	993.91	994.30	994.69	995.09	995.48	995.87	996.26	16900
17000	996.66	997.05	997.44	997.83	998.23	998.62	999.01	999.40	999.79	1000.19	17000

5.3 Thermoelectric values at the defining fixed points of the ITS-90 for Au/Pt thermocouples (informative)

Fixed point	$t_{90}/^{\circ}\text{C}$	$E/\mu\text{V}$	$S/(\mu\text{V}/^{\circ}\text{C})$
Water TP	0.01	0.06	6.037
Gallium MP	29.7646	196.25	7.133
Indium FP	156.5985	1350.94	10.861
Tin FP	231.928	2236.18	12.599
Zinc FP	419.527	4945.63	16.157
Aluminum FP	660.323	9320.44	20.139
Silver FP	961.78	16120.49	24.945

6 Tables for Platinum versus Palladium thermocouples

6.1 Platinum versus Palladium: EMF at intervals of 1 °C

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
	$E/\mu\text{V}$										
0	0.0	5.3	10.6	15.9	21.3	26.6	31.9	37.3	42.7	48.0	0
10	53.4	58.8	64.2	69.6	75.0	80.5	85.9	91.3	96.8	102.2	10
20	107.7	113.2	118.7	124.2	129.7	135.2	140.7	146.2	151.7	157.3	20
30	162.8	168.4	173.9	179.5	185.1	190.7	196.3	201.9	207.5	213.1	30
40	218.7	224.3	230.0	235.6	241.3	246.9	252.6	258.3	264.0	269.7	40
50	275.4	281.1	286.8	292.5	298.2	303.9	309.7	315.4	321.2	326.9	50
60	332.7	338.5	344.3	350.1	355.9	361.7	367.5	373.3	379.1	384.9	60
70	390.8	396.6	402.5	408.3	414.2	420.1	425.9	431.8	437.7	443.6	70
80	449.5	455.4	461.3	467.3	473.2	479.1	485.1	491.0	497.0	502.9	80
90	508.9	514.9	520.9	526.9	532.9	538.9	544.9	550.9	556.9	562.9	90
100	569.0	575.0	581.1	587.1	593.2	599.3	605.3	611.4	617.5	623.6	100
110	629.7	635.8	641.9	648.1	654.2	660.3	666.5	672.6	678.8	684.9	110
120	691.1	697.3	703.5	709.7	715.9	722.1	728.3	734.5	740.7	746.9	120
130	753.2	759.4	765.7	771.9	778.2	784.5	790.7	797.0	803.3	809.6	130
140	815.9	822.2	828.6	834.9	841.2	847.6	853.9	860.3	866.6	873.0	140
150	879.4	885.8	892.2	898.6	905.0	911.4	917.8	924.2	930.7	937.1	150
160	943.6	950.0	956.5	962.9	969.4	975.9	982.4	988.9	995.4	1001.9	160
170	1008.5	1015.0	1021.5	1028.1	1034.6	1041.2	1047.8	1054.4	1060.9	1067.5	170
180	1074.1	1080.7	1087.4	1094.0	1100.6	1107.3	1113.9	1120.6	1127.2	1133.9	180
190	1140.6	1147.3	1154.0	1160.7	1167.4	1174.1	1180.9	1187.6	1194.4	1201.1	190
200	1207.9	1214.7	1221.4	1228.2	1235.0	1241.8	1248.7	1255.5	1262.3	1269.2	200
210	1276.0	1282.9	1289.7	1296.6	1303.5	1310.4	1317.3	1324.2	1331.2	1338.1	210
220	1345.0	1352.0	1358.9	1365.9	1372.9	1379.9	1386.9	1393.9	1400.9	1407.9	220
230	1415.0	1422.0	1429.1	1436.1	1443.2	1450.3	1457.4	1464.5	1471.6	1478.7	230
240	1485.9	1493.0	1500.2	1507.3	1514.5	1521.7	1528.9	1536.1	1543.3	1550.5	240
250	1557.7	1565.0	1572.2	1579.5	1586.8	1594.1	1601.4	1608.7	1616.0	1623.3	250
260	1630.7	1638.0	1645.4	1652.7	1660.1	1667.5	1674.9	1682.3	1689.7	1697.2	260
270	1704.6	1712.1	1719.6	1727.0	1734.5	1742.0	1749.5	1757.1	1764.6	1772.2	270
280	1779.7	1787.3	1794.9	1802.5	1810.1	1817.7	1825.3	1833.0	1840.6	1848.3	280
290	1856.0	1863.6	1871.3	1879.1	1886.8	1894.5	1902.3	1910.0	1917.8	1925.6	290
300	1933.4	1941.2	1949.0	1956.8	1964.7	1972.5	1980.4	1988.3	1996.2	2004.1	300
310	2012.0	2019.9	2027.9	2035.9	2043.8	2051.8	2059.8	2067.8	2075.8	2083.9	310
320	2091.9	2100.0	2108.1	2116.2	2124.3	2132.4	2140.5	2148.6	2156.8	2165.0	320
330	2173.1	2181.3	2189.5	2197.8	2206.0	2214.2	2222.5	2230.8	2239.1	2247.4	330
340	2255.7	2264.0	2272.4	2280.7	2289.1	2297.5	2305.9	2314.3	2322.7	2331.2	340
350	2339.6	2348.1	2356.6	2365.1	2373.6	2382.1	2390.7	2399.2	2407.8	2416.4	350
360	2425.0	2433.6	2442.2	2450.9	2459.5	2468.2	2476.9	2485.6	2494.3	2503.1	360
370	2511.8	2520.6	2529.3	2538.1	2546.9	2555.8	2564.6	2573.5	2582.3	2591.2	370
380	2600.1	2609.0	2617.9	2626.9	2635.8	2644.8	2653.8	2662.8	2671.8	2680.9	380
390	2689.9	2699.0	2708.1	2717.2	2726.3	2735.4	2744.6	2753.7	2762.9	2772.1	390

Platinum versus Palladium
EMF at intervals of 1 °C (*continued*)

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
400	2781.3	2790.5	2799.8	2809.0	2818.3	2827.6	2836.9	2846.2	2855.6	2864.9	400
410	2874.3	2883.7	2893.1	2902.5	2911.9	2921.4	2930.8	2940.3	2949.8	2959.3	410
420	2968.9	2978.4	2988.0	2997.6	3007.2	3016.8	3026.4	3036.0	3045.7	3055.4	420
430	3065.1	3074.8	3084.5	3094.3	3104.1	3113.8	3123.6	3133.5	3143.3	3153.1	430
440	3163.0	3172.9	3182.8	3192.7	3202.6	3212.6	3222.6	3232.5	3242.6	3252.6	440
450	3262.6	3272.7	3282.7	3292.8	3302.9	3313.1	3323.2	3333.4	3343.5	3353.7	450
460	3363.9	3374.2	3384.4	3394.7	3405.0	3415.3	3425.6	3435.9	3446.3	3456.6	460
470	3467.0	3477.4	3487.9	3498.3	3508.8	3519.2	3529.7	3540.2	3550.8	3561.3	470
480	3571.9	3582.5	3593.1	3603.7	3614.3	3625.0	3635.7	3646.4	3657.1	3667.8	480
490	3678.5	3689.3	3700.1	3710.9	3721.7	3732.5	3743.4	3754.3	3765.2	3776.1	490
500	3787.0	3797.9	3808.9	3819.9	3830.9	3841.9	3853.0	3864.0	3875.1	3886.2	500
510	3897.3	3908.4	3919.6	3930.7	3941.9	3953.1	3964.3	3975.6	3986.8	3998.1	510
520	4009.4	4020.7	4032.1	4043.4	4054.8	4066.2	4077.6	4089.0	4100.5	4111.9	520
530	4123.4	4134.9	4146.4	4158.0	4169.5	4181.1	4192.7	4204.3	4215.9	4227.6	530
540	4239.3	4250.9	4262.7	4274.4	4286.1	4297.9	4309.7	4321.5	4333.3	4345.1	540
550	4357.0	4368.9	4380.8	4392.7	4404.6	4416.6	4428.5	4440.5	4452.5	4464.6	550
560	4476.6	4488.7	4500.8	4512.9	4525.0	4537.1	4549.3	4561.5	4573.7	4585.9	560
570	4598.1	4610.4	4622.7	4635.0	4647.3	4659.6	4672.0	4684.3	4696.7	4709.1	570
580	4721.6	4734.0	4746.5	4759.0	4771.5	4784.0	4796.5	4809.1	4821.7	4834.3	580
590	4846.9	4859.5	4872.2	4884.9	4897.6	4910.3	4923.0	4935.8	4948.5	4961.3	590
600	4974.1	4987.0	4999.8	5012.7	5025.6	5038.5	5051.4	5064.4	5077.3	5090.3	600
610	5103.3	5116.3	5129.4	5142.4	5155.5	5168.6	5181.7	5194.9	5208.0	5221.2	610
620	5234.4	5247.6	5260.8	5274.1	5287.4	5300.6	5314.0	5327.3	5340.6	5354.0	620
630	5367.4	5380.8	5394.2	5407.7	5421.1	5434.6	5448.1	5461.6	5475.2	5488.7	630
640	5502.3	5515.9	5529.5	5543.1	5556.8	5570.5	5584.2	5597.9	5611.6	5625.4	640
650	5639.1	5652.9	5666.7	5680.6	5694.4	5708.3	5722.1	5736.0	5750.0	5763.9	650
660	5777.9	5791.8	5805.8	5819.9	5833.9	5848.0	5862.0	5876.1	5890.2	5904.4	660
670	5918.5	5932.7	5946.9	5961.1	5975.3	5989.5	6003.8	6018.1	6032.4	6046.7	670
680	6061.1	6075.4	6089.8	6104.2	6118.6	6133.0	6147.5	6162.0	6176.4	6191.0	680
690	6205.5	6220.0	6234.6	6249.2	6263.8	6278.4	6293.1	6307.7	6322.4	6337.1	690
700	6351.8	6366.5	6381.3	6396.1	6410.9	6425.7	6440.5	6455.3	6470.2	6485.1	700
710	6500.0	6514.9	6529.9	6544.8	6559.8	6574.8	6589.8	6604.9	6619.9	6635.0	710
720	6650.1	6665.2	6680.3	6695.5	6710.6	6725.8	6741.0	6756.2	6771.5	6786.7	720
730	6802.0	6817.3	6832.6	6847.9	6863.3	6878.7	6894.0	6909.4	6924.9	6940.3	730
740	6955.8	6971.2	6986.7	7002.3	7017.8	7033.3	7048.9	7064.5	7080.1	7095.7	740
750	7111.4	7127.0	7142.7	7158.4	7174.1	7189.9	7205.6	7221.4	7237.2	7253.0	750
760	7268.8	7284.7	7300.5	7316.4	7332.3	7348.2	7364.2	7380.1	7396.1	7412.1	760
770	7428.1	7444.1	7460.1	7476.2	7492.3	7508.4	7524.5	7540.6	7556.8	7572.9	770
780	7589.1	7605.3	7621.5	7637.8	7654.0	7670.3	7686.6	7702.9	7719.3	7735.6	780
790	7752.0	7768.3	7784.7	7801.2	7817.6	7834.0	7850.5	7867.0	7883.5	7900.0	790

Platinum versus Palladium
EMF at intervals of 1 °C (*continued*)

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
800	7916.6	7933.1	7949.7	7966.3	7982.9	7999.5	8016.2	8032.9	8049.5	8066.2	800
810	8082.9	8099.7	8116.4	8133.2	8150.0	8166.8	8183.6	8200.4	8217.3	8234.2	810
820	8251.1	8268.0	8284.9	8301.8	8318.8	8335.8	8352.8	8369.8	8386.8	8403.8	820
830	8420.9	8438.0	8455.1	8472.2	8489.3	8506.5	8523.6	8540.8	8558.0	8575.2	830
840	8592.5	8609.7	8627.0	8644.3	8661.6	8678.9	8696.2	8713.6	8730.9	8748.3	840
850	8765.7	8783.1	8800.6	8818.0	8835.5	8853.0	8870.5	8888.0	8905.5	8923.1	850
860	8940.7	8958.3	8975.9	8993.5	9011.1	9028.8	9046.4	9064.1	9081.8	9099.5	860
870	9117.3	9135.0	9152.8	9170.6	9188.4	9206.2	9224.0	9241.9	9259.7	9277.6	870
880	9295.5	9313.4	9331.4	9349.3	9367.3	9385.3	9403.3	9421.3	9439.3	9457.4	880
890	9475.4	9493.5	9511.6	9529.7	9547.8	9566.0	9584.1	9602.3	9620.5	9638.7	890
900	9656.9	9675.2	9693.4	9711.7	9730.0	9748.3	9766.6	9784.9	9803.3	9821.6	900
910	9840.0	9858.4	9876.8	9895.3	9913.7	9932.2	9950.7	9969.1	9987.7	10006.2	910
920	10024.7	10043.3	10061.8	10080.4	10099.0	10117.7	10136.3	10154.9	10173.6	10192.3	920
930	10211.0	10229.7	10248.4	10267.2	10285.9	10304.7	10323.5	10342.3	10361.1	10379.9	930
940	10398.8	10417.6	10436.5	10455.4	10474.3	10493.3	10512.2	10531.2	10550.1	10569.1	940
950	10588.1	10607.1	10626.2	10645.2	10664.3	10683.3	10702.4	10721.5	10740.7	10759.8	950
960	10779.0	10798.1	10817.3	10836.5	10855.7	10874.9	10894.2	10913.4	10932.7	10952.0	960
970	10971.3	10990.6	11010.0	11029.3	11048.7	11068.0	11087.4	11106.8	11126.3	11145.7	970
980	11165.1	11184.6	11204.1	11223.6	11243.1	11262.6	11282.1	11301.7	11321.3	11340.8	980
990	11360.4	11380.0	11399.7	11419.3	11439.0	11458.6	11478.3	11498.0	11517.7	11537.4	990
1000	11557.2	11576.9	11596.7	11616.5	11636.3	11656.1	11675.9	11695.7	11715.6	11735.5	1000
1010	11755.3	11775.2	11795.1	11815.1	11835.0	11855.0	11874.9	11894.9	11914.9	11934.9	1010
1020	11954.9	11975.0	11995.0	12015.1	12035.2	12055.2	12075.3	12095.5	12115.6	12135.7	1020
1030	12155.9	12176.1	12196.3	12216.5	12236.7	12256.9	12277.2	12297.4	12317.7	12338.0	1030
1040	12358.3	12378.6	12398.9	12419.3	12439.6	12460.0	12480.3	12500.7	12521.2	12541.6	1040
1050	12562.0	12582.5	12602.9	12623.4	12643.9	12664.4	12684.9	12705.4	12726.0	12746.5	1050
1060	12767.1	12787.7	12808.3	12828.9	12849.5	12870.1	12890.8	12911.4	12932.1	12952.8	1060
1070	12973.5	12994.2	13014.9	13035.7	13056.4	13077.2	13098.0	13118.8	13139.6	13160.4	1070
1080	13181.2	13202.1	13222.9	13243.8	13264.7	13285.6	13306.5	13327.4	13348.4	13369.3	1080
1090	13390.3	13411.2	13432.2	13453.2	13474.2	13495.3	13516.3	13537.4	13558.4	13579.5	1090
1100	13600.6	13621.7	13642.8	13663.9	13685.1	13706.2	13727.4	13748.6	13769.8	13791.0	1100
1110	13812.2	13833.4	13854.7	13875.9	13897.2	13918.5	13939.8	13961.1	13982.4	14003.7	1110
1120	14025.1	14046.4	14067.8	14089.2	14110.6	14132.0	14153.4	14174.8	14196.3	14217.7	1120
1130	14239.2	14260.6	14282.1	14303.6	14325.2	14346.7	14368.2	14389.8	14411.3	14432.9	1130
1140	14454.5	14476.1	14497.7	14519.3	14541.0	14562.6	14584.3	14606.0	14627.7	14649.4	1140
1150	14671.1	14692.8	14714.5	14736.3	14758.0	14779.8	14801.6	14823.4	14845.2	14867.0	1150
1160	14888.8	14910.7	14932.5	14954.4	14976.3	14998.2	15020.1	15042.0	15063.9	15085.8	1160
1170	15107.8	15129.7	15151.7	15173.7	15195.7	15217.7	15239.7	15261.8	15283.8	15305.9	1170
1180	15327.9	15350.0	15372.1	15394.2	15416.3	15438.4	15460.6	15482.7	15504.9	15527.0	1180
1190	15549.2	15571.4	15593.6	15615.8	15638.1	15660.3	15682.6	15704.8	15727.1	15749.4	1190

Platinum versus Palladium
EMF at intervals of 1 °C (*continued*)

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
<i>E</i> /μV											
1200	15771.7	15794.0	15816.3	15838.6	15861.0	15883.3	15905.7	15928.1	15950.5	15972.9	1200
1210	15995.3	16017.7	16040.1	16062.6	16085.0	16107.5	16130.0	16152.5	16175.0	16197.5	1210
1220	16220.0	16242.5	16265.1	16287.6	16310.2	16332.8	16355.4	16378.0	16400.6	16423.2	1220
1230	16445.9	16468.5	16491.2	16513.8	16536.5	16559.2	16581.9	16604.6	16627.3	16650.1	1230
1240	16672.8	16695.6	16718.3	16741.1	16763.9	16786.7	16809.5	16832.3	16855.2	16878.0	1240
1250	16900.9	16923.7	16946.6	16969.5	16992.4	17015.3	17038.2	17061.2	17084.1	17107.0	1250
1260	17130.0	17153.0	17176.0	17199.0	17222.0	17245.0	17268.0	17291.0	17314.1	17337.2	1260
1270	17360.2	17383.3	17406.4	17429.5	17452.6	17475.7	17498.9	17522.0	17545.2	17568.3	1270
1280	17591.5	17614.7	17637.9	17661.1	17684.3	17707.6	17730.8	17754.0	17777.3	17800.6	1280
1290	17823.9	17847.1	17870.4	17893.8	17917.1	17940.4	17963.8	17987.1	18010.5	18033.9	1290
1300	18057.2	18080.6	18104.0	18127.5	18150.9	18174.3	18197.8	18221.2	18244.7	18268.2	1300
1310	18291.7	18315.2	18338.7	18362.2	18385.7	18409.3	18432.8	18456.4	18480.0	18503.5	1310
1320	18527.1	18550.7	18574.3	18598.0	18621.6	18645.2	18668.9	18692.6	18716.2	18739.9	1320
1330	18763.6	18787.3	18811.0	18834.7	18858.5	18882.2	18906.0	18929.7	18953.5	18977.3	1330
1340	19001.1	19024.9	19048.7	19072.5	19096.4	19120.2	19144.1	19167.9	19191.8	19215.7	1340
1350	19239.6	19263.5	19287.4	19311.3	19335.3	19359.2	19383.2	19407.1	19431.1	19455.1	1350
1360	19479.1	19503.1	19527.1	19551.1	19575.1	19599.2	19623.2	19647.3	19671.4	19695.5	1360
1370	19719.5	19743.6	19767.8	19791.9	19816.0	19840.1	19864.3	19888.5	19912.6	19936.8	1370
1380	19961.0	19985.2	20009.4	20033.6	20057.8	20082.1	20106.3	20130.6	20154.8	20179.1	1380
1390	20203.4	20227.7	20252.0	20276.3	20300.6	20325.0	20349.3	20373.7	20398.0	20422.4	1390
1400	20446.8	20471.2	20495.6	20520.0	20544.4	20568.8	20593.3	20617.7	20642.2	20666.6	1400
1410	20691.1	20715.6	20740.1	20764.6	20789.1	20813.6	20838.2	20862.7	20887.3	20911.8	1410
1420	20936.4	20961.0	20985.6	21010.2	21034.8	21059.4	21084.0	21108.6	21133.3	21157.9	1420
1430	21182.6	21207.3	21232.0	21256.7	21281.4	21306.1	21330.8	21355.5	21380.2	21405.0	1430
1440	21429.7	21454.5	21479.3	21504.1	21528.9	21553.7	21578.5	21603.3	21628.1	21653.0	1440
1450	21677.8	21702.7	21727.5	21752.4	21777.3	21802.2	21827.1	21852.0	21876.9	21901.8	1450
1460	21926.8	21951.7	21976.7	22001.7	22026.6	22051.6	22076.6	22101.6	22126.6	22151.6	1460
1470	22176.7	22201.7	22226.8	22251.8	22276.9	22301.9	22327.0	22352.1	22377.2	22402.3	1470
1480	22427.4	22452.6	22477.7	22502.9	22528.0	22553.2	22578.3	22603.5	22628.7	22653.9	1480
1490	22679.1	22704.3	22729.6	22754.8	22780.0	22805.3	22830.5	22855.8	22881.1	22906.4	1490
1500	22931.7										1500

6.2 Platinum versus Palladium: Temperature at intervals of 10 μ V

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
						$t_{90}/^{\circ}\text{C}$					
0	0.00	1.88	3.76	5.63	7.50	9.36	11.22	13.07	14.91	16.75	0
100	18.59	20.42	22.24	24.06	25.87	27.68	29.49	31.29	33.09	34.88	100
200	36.67	38.45	40.23	42.00	43.77	45.54	47.30	49.06	50.82	52.57	200
300	54.31	56.06	57.80	59.53	61.26	62.99	64.72	66.44	68.16	69.87	300
400	71.58	73.29	74.99	76.69	78.39	80.09	81.78	83.46	85.15	86.83	400
500	88.51	90.18	91.86	93.52	95.19	96.85	98.51	100.17	101.82	103.47	500
600	105.12	106.77	108.41	110.05	111.68	113.32	114.95	116.57	118.20	119.82	600
700	121.44	123.06	124.67	126.28	127.89	129.49	131.09	132.69	134.29	135.88	700
800	137.47	139.06	140.64	142.23	143.81	145.38	146.96	148.53	150.10	151.66	800
900	153.22	154.78	156.34	157.90	159.45	161.00	162.54	164.09	165.63	167.17	900
1000	168.70	170.23	171.76	173.29	174.82	176.34	177.86	179.37	180.89	182.40	1000
1100	183.91	185.41	186.91	188.41	189.91	191.40	192.90	194.38	195.87	197.35	1100
1200	198.83	200.31	201.79	203.26	204.73	206.20	207.66	209.12	210.58	212.04	1200
1300	213.49	214.94	216.39	217.83	219.28	220.71	222.15	223.59	225.02	226.45	1300
1400	227.87	229.29	230.71	232.13	233.55	234.96	236.37	237.77	239.18	240.58	1400
1500	241.98	243.37	244.77	246.16	247.55	248.93	250.31	251.69	253.07	254.44	1500
1600	255.81	257.18	258.55	259.91	261.27	262.63	263.99	265.34	266.69	268.03	1600
1700	269.38	270.72	272.06	273.40	274.73	276.06	277.39	278.71	280.04	281.36	1700
1800	282.68	283.99	285.30	286.61	287.92	289.23	290.53	291.83	293.12	294.42	1800
1900	295.71	297.00	298.28	299.57	300.85	302.13	303.40	304.68	305.95	307.22	1900
2000	308.48	309.75	311.01	312.26	313.52	314.77	316.02	317.27	318.52	319.76	2000
2100	321.00	322.24	323.48	324.71	325.94	327.17	328.39	329.62	330.84	332.06	2100
2200	333.27	334.48	335.70	336.90	338.11	339.31	340.52	341.72	342.91	344.11	2200
2300	345.30	346.49	347.68	348.86	350.04	351.22	352.40	353.58	354.75	355.92	2300
2400	357.09	358.26	359.42	360.58	361.74	362.90	364.05	365.21	366.36	367.50	2400
2500	368.65	369.79	370.93	372.07	373.21	374.35	375.48	376.61	377.74	378.86	2500
2600	379.99	381.11	382.23	383.35	384.46	385.58	386.69	387.80	388.90	390.01	2600
2700	391.11	392.21	393.31	394.41	395.50	396.59	397.68	398.77	399.86	400.94	2700
2800	402.02	403.10	404.18	405.26	406.33	407.41	408.48	409.54	410.61	411.67	2800
2900	412.74	413.80	414.86	415.91	416.97	418.02	419.07	420.12	421.17	422.21	2900
3000	423.25	424.30	425.34	426.37	427.41	428.44	429.48	430.51	431.53	432.56	3000
3100	433.59	434.61	435.63	436.65	437.67	438.68	439.70	440.71	441.72	442.73	3100
3200	443.73	444.74	445.74	446.75	447.75	448.74	449.74	450.74	451.73	452.72	3200
3300	453.71	454.70	455.68	456.67	457.65	458.63	459.61	460.59	461.57	462.54	3300
3400	463.52	464.49	465.46	466.43	467.39	468.36	469.32	470.29	471.25	472.21	3400
3500	473.16	474.12	475.07	476.03	476.98	477.93	478.87	479.82	480.77	481.71	3500
3600	482.65	483.59	484.53	485.47	486.41	487.34	488.27	489.21	490.14	491.06	3600
3700	491.99	492.92	493.84	494.77	495.69	496.61	497.53	498.44	499.36	500.27	3700
3800	501.19	502.10	503.01	503.92	504.83	505.73	506.64	507.54	508.44	509.34	3800
3900	510.24	511.14	512.04	512.93	513.83	514.72	515.61	516.50	517.39	518.28	3900

Platinum versus Palladium
Temperature at intervals of 10 μ V (*continued*)

E/μ V	0	10	20	30	40	50	60	70	80	90	E/μ V
$t_{90} / ^\circ\text{C}$											
4000	519.17	520.05	520.93	521.82	522.70	523.58	524.46	525.33	526.21	527.09	4000
4100	527.96	528.83	529.70	530.57	531.44	532.31	533.18	534.04	534.90	535.77	4100
4200	536.63	537.49	538.35	539.21	540.06	540.92	541.77	542.63	543.48	544.33	4200
4300	545.18	546.03	546.87	547.72	548.57	549.41	550.25	551.09	551.93	552.77	4300
4400	553.61	554.45	555.29	556.12	556.95	557.79	558.62	559.45	560.28	561.11	4400
4500	561.94	562.76	563.59	564.41	565.23	566.06	566.88	567.70	568.52	569.33	4500
4600	570.15	570.97	571.78	572.60	573.41	574.22	575.03	575.84	576.65	577.46	4600
4700	578.26	579.07	579.87	580.68	581.48	582.28	583.08	583.88	584.68	585.48	4700
4800	586.28	587.07	587.87	588.66	589.45	590.25	591.04	591.83	592.62	593.41	4800
4900	594.19	594.98	595.76	596.55	597.33	598.12	598.90	599.68	600.46	601.24	4900
5000	602.01	602.79	603.57	604.34	605.12	605.89	606.66	607.44	608.21	608.98	5000
5100	609.75	610.52	611.28	612.05	612.82	613.58	614.34	615.11	615.87	616.63	5100
5200	617.39	618.15	618.91	619.67	620.43	621.18	621.94	622.69	623.45	624.20	5200
5300	624.95	625.70	626.45	627.20	627.95	628.70	629.45	630.20	630.94	631.69	5300
5400	632.43	633.17	633.92	634.66	635.40	636.14	636.88	637.62	638.36	639.09	5400
5500	639.83	640.57	641.30	642.03	642.77	643.50	644.23	644.96	645.69	646.42	5500
5600	647.15	647.88	648.61	649.34	650.06	650.79	651.51	652.24	652.96	653.68	5600
5700	654.40	655.12	655.84	656.56	657.28	658.00	658.72	659.43	660.15	660.87	5700
5800	661.58	662.30	663.01	663.72	664.43	665.15	665.86	666.57	667.27	667.98	5800
5900	668.69	669.40	670.10	670.81	671.51	672.22	672.92	673.63	674.33	675.03	5900
6000	675.73	676.43	677.13	677.83	678.53	679.23	679.92	680.62	681.32	682.01	6000
6100	682.71	683.40	684.09	684.79	685.48	686.17	686.86	687.55	688.24	688.93	6100
6200	689.62	690.31	690.99	691.68	692.37	693.05	693.74	694.42	695.11	695.79	6200
6300	696.47	697.15	697.83	698.52	699.20	699.87	700.55	701.23	701.91	702.59	6300
6400	703.26	703.94	704.61	705.29	705.96	706.64	707.31	707.98	708.66	709.33	6400
6500	710.00	710.67	711.34	712.01	712.68	713.34	714.01	714.68	715.34	716.01	6500
6600	716.68	717.34	718.00	718.67	719.33	719.99	720.66	721.32	721.98	722.64	6600
6700	723.30	723.96	724.62	725.28	725.93	726.59	727.25	727.90	728.56	729.21	6700
6800	729.87	730.52	731.18	731.83	732.48	733.13	733.79	734.44	735.09	735.74	6800
6900	736.39	737.04	737.68	738.33	738.98	739.63	740.27	740.92	741.57	742.21	6900
7000	742.85	743.50	744.14	744.79	745.43	746.07	746.71	747.35	747.99	748.63	7000
7100	749.27	749.91	750.55	751.19	751.83	752.46	753.10	753.74	754.37	755.01	7100
7200	755.64	756.28	756.91	757.55	758.18	758.81	759.44	760.08	760.71	761.34	7200
7300	761.97	762.60	763.23	763.86	764.49	765.11	765.74	766.37	767.00	767.62	7300
7400	768.25	768.87	769.50	770.12	770.75	771.37	771.99	772.62	773.24	773.86	7400
7500	774.48	775.10	775.72	776.34	776.96	777.58	778.20	778.82	779.44	780.06	7500
7600	780.67	781.29	781.91	782.52	783.14	783.75	784.37	784.98	785.60	786.21	7600
7700	786.82	787.44	788.05	788.66	789.27	789.88	790.49	791.10	791.71	792.32	7700
7800	792.93	793.54	794.15	794.76	795.36	795.97	796.58	797.18	797.79	798.39	7800
7900	799.00	799.60	800.21	800.81	801.42	802.02	802.62	803.22	803.83	804.43	7900

Platinum versus Palladium
Temperature at intervals of 10 μV (*continued*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90}/^{\circ}\text{C}$											
8000	805.03	805.63	806.23	806.83	807.43	808.03	808.63	809.23	809.83	810.42	8000
8100	811.02	811.62	812.21	812.81	813.41	814.00	814.60	815.19	815.79	816.38	8100
8200	816.98	817.57	818.16	818.75	819.35	819.94	820.53	821.12	821.71	822.30	8200
8300	822.89	823.48	824.07	824.66	825.25	825.84	826.43	827.01	827.60	828.19	8300
8400	828.78	829.36	829.95	830.53	831.12	831.70	832.29	832.87	833.46	834.04	8400
8500	834.62	835.21	835.79	836.37	836.95	837.53	838.12	838.70	839.28	839.86	8500
8600	840.44	841.02	841.60	842.17	842.75	843.33	843.91	844.49	845.06	845.64	8600
8700	846.22	846.79	847.37	847.95	848.52	849.10	849.67	850.25	850.82	851.39	8700
8800	851.97	852.54	853.11	853.68	854.26	854.83	855.40	855.97	856.54	857.11	8800
8900	857.68	858.25	858.82	859.39	859.96	860.53	861.10	861.67	862.23	862.80	8900
9000	863.37	863.94	864.50	865.07	865.64	866.20	866.77	867.33	867.90	868.46	9000
9100	869.03	869.59	870.15	870.72	871.28	871.84	872.40	872.97	873.53	874.09	9100
9200	874.65	875.21	875.77	876.33	876.89	877.45	878.01	878.57	879.13	879.69	9200
9300	880.25	880.81	881.36	881.92	882.48	883.04	883.59	884.15	884.71	885.26	9300
9400	885.82	886.37	886.93	887.48	888.04	888.59	889.14	889.70	890.25	890.81	9400
9500	891.36	891.91	892.46	893.01	893.57	894.12	894.67	895.22	895.77	896.32	9500
9600	896.87	897.42	897.97	898.52	899.07	899.62	900.17	900.72	901.26	901.81	9600
9700	902.36	902.91	903.45	904.00	904.55	905.09	905.64	906.18	906.73	907.27	9700
9800	907.82	908.36	908.91	909.45	910.00	910.54	911.08	911.63	912.17	912.71	9800
9900	913.25	913.80	914.34	914.88	915.42	915.96	916.50	917.04	917.58	918.12	9900
10000	918.66	919.20	919.74	920.28	920.82	921.36	921.90	922.44	922.98	923.51	10000
10100	924.05	924.59	925.12	925.66	926.20	926.73	927.27	927.81	928.34	928.88	10100
10200	929.41	929.95	930.48	931.02	931.55	932.08	932.62	933.15	933.68	934.22	10200
10300	934.75	935.28	935.81	936.35	936.88	937.41	937.94	938.47	939.00	939.53	10300
10400	940.06	940.59	941.12	941.65	942.18	942.71	943.24	943.77	944.30	944.83	10400
10500	945.35	945.88	946.41	946.94	947.47	947.99	948.52	949.05	949.57	950.10	10500
10600	950.62	951.15	951.68	952.20	952.73	953.25	953.77	954.30	954.82	955.35	10600
10700	955.87	956.39	956.92	957.44	957.96	958.49	959.01	959.53	960.05	960.58	10700
10800	961.10	961.62	962.14	962.66	963.18	963.70	964.22	964.74	965.26	965.78	10800
10900	966.30	966.82	967.34	967.86	968.38	968.90	969.41	969.93	970.45	970.97	10900
11000	971.48	972.00	972.52	973.04	973.55	974.07	974.58	975.10	975.62	976.13	11000
11100	976.65	977.16	977.68	978.19	978.71	979.22	979.74	980.25	980.76	981.28	11100
11200	981.79	982.30	982.82	983.33	983.84	984.35	984.87	985.38	985.89	986.40	11200
11300	986.91	987.43	987.94	988.45	988.96	989.47	989.98	990.49	991.00	991.51	11300
11400	992.02	992.53	993.04	993.54	994.05	994.56	995.07	995.58	996.09	996.59	11400
11500	997.10	997.61	998.12	998.62	999.13	999.64	1000.14	1000.65	1001.16	1001.66	11500
11600	1002.17	1002.67	1003.18	1003.68	1004.19	1004.69	1005.20	1005.70	1006.21	1006.71	11600
11700	1007.22	1007.72	1008.22	1008.73	1009.23	1009.73	1010.24	1010.74	1011.24	1011.74	11700
11800	1012.24	1012.75	1013.25	1013.75	1014.25	1014.75	1015.25	1015.75	1016.26	1016.76	11800
11900	1017.26	1017.76	1018.26	1018.76	1019.26	1019.76	1020.25	1020.75	1021.25	1021.75	11900

Platinum versus Palladium
Temperature at intervals of 10 μ V (*continued*)

E/μ V	0	10	20	30	40	50	60	70	80	90	E/μ V
$t_{90} / ^\circ\text{C}$											
12000	1022.25	1022.75	1023.25	1023.74	1024.24	1024.74	1025.24	1025.74	1026.23	1026.73	12000
12100	1027.23	1027.72	1028.22	1028.72	1029.21	1029.71	1030.20	1030.70	1031.20	1031.69	12100
12200	1032.19	1032.68	1033.18	1033.67	1034.17	1034.66	1035.15	1035.65	1036.14	1036.64	12200
12300	1037.13	1037.62	1038.12	1038.61	1039.10	1039.59	1040.09	1040.58	1041.07	1041.56	12300
12400	1042.06	1042.55	1043.04	1043.53	1044.02	1044.51	1045.00	1045.49	1045.98	1046.47	12400
12500	1046.97	1047.46	1047.95	1048.44	1048.92	1049.41	1049.90	1050.39	1050.88	1051.37	12500
12600	1051.86	1052.35	1052.84	1053.32	1053.81	1054.30	1054.79	1055.28	1055.76	1056.25	12600
12700	1056.74	1057.22	1057.71	1058.20	1058.68	1059.17	1059.66	1060.14	1060.63	1061.11	12700
12800	1061.60	1062.09	1062.57	1063.06	1063.54	1064.03	1064.51	1065.00	1065.48	1065.96	12800
12900	1066.45	1066.93	1067.42	1067.90	1068.38	1068.87	1069.35	1069.83	1070.32	1070.80	12900
13000	1071.28	1071.76	1072.25	1072.73	1073.21	1073.69	1074.17	1074.65	1075.14	1075.62	13000
13100	1076.10	1076.58	1077.06	1077.54	1078.02	1078.50	1078.98	1079.46	1079.94	1080.42	13100
13200	1080.90	1081.38	1081.86	1082.34	1082.82	1083.30	1083.78	1084.26	1084.73	1085.21	13200
13300	1085.69	1086.17	1086.65	1087.12	1087.60	1088.08	1088.56	1089.03	1089.51	1089.99	13300
13400	1090.46	1090.94	1091.42	1091.89	1092.37	1092.85	1093.32	1093.80	1094.27	1094.75	13400
13500	1095.23	1095.70	1096.18	1096.65	1097.13	1097.60	1098.08	1098.55	1099.02	1099.50	13500
13600	1099.97	1100.45	1100.92	1101.39	1101.87	1102.34	1102.81	1103.29	1103.76	1104.23	13600
13700	1104.71	1105.18	1105.65	1106.12	1106.60	1107.07	1107.54	1108.01	1108.48	1108.95	13700
13800	1109.43	1109.90	1110.37	1110.84	1111.31	1111.78	1112.25	1112.72	1113.19	1113.66	13800
13900	1114.13	1114.60	1115.07	1115.54	1116.01	1116.48	1116.95	1117.42	1117.89	1118.36	13900
14000	1118.83	1119.29	1119.76	1120.23	1120.70	1121.17	1121.64	1122.10	1122.57	1123.04	14000
14100	1123.51	1123.97	1124.44	1124.91	1125.38	1125.84	1126.31	1126.78	1127.24	1127.71	14100
14200	1128.17	1128.64	1129.11	1129.57	1130.04	1130.50	1130.97	1131.43	1131.90	1132.37	14200
14300	1132.83	1133.30	1133.76	1134.22	1134.69	1135.15	1135.62	1136.08	1136.55	1137.01	14300
14400	1137.47	1137.94	1138.40	1138.86	1139.33	1139.79	1140.25	1140.72	1141.18	1141.64	14400
14500	1142.10	1142.57	1143.03	1143.49	1143.95	1144.42	1144.88	1145.34	1145.80	1146.26	14500
14600	1146.72	1147.18	1147.65	1148.11	1148.57	1149.03	1149.49	1149.95	1150.41	1150.87	14600
14700	1151.33	1151.79	1152.25	1152.71	1153.17	1153.63	1154.09	1154.55	1155.01	1155.47	14700
14800	1155.93	1156.39	1156.84	1157.30	1157.76	1158.22	1158.68	1159.14	1159.59	1160.05	14800
14900	1160.51	1160.97	1161.43	1161.88	1162.34	1162.80	1163.26	1163.71	1164.17	1164.63	14900
15000	1165.08	1165.54	1166.00	1166.45	1166.91	1167.36	1167.82	1168.28	1168.73	1169.19	15000
15100	1169.64	1170.10	1170.55	1171.01	1171.47	1171.92	1172.38	1172.83	1173.28	1173.74	15100
15200	1174.19	1174.65	1175.10	1175.56	1176.01	1176.46	1176.92	1177.37	1177.83	1178.28	15200
15300	1178.73	1179.19	1179.64	1180.09	1180.55	1181.00	1181.45	1181.90	1182.36	1182.81	15300
15400	1183.26	1183.71	1184.17	1184.62	1185.07	1185.52	1185.97	1186.42	1186.88	1187.33	15400
15500	1187.78	1188.23	1188.68	1189.13	1189.58	1190.03	1190.48	1190.93	1191.39	1191.84	15500
15600	1192.29	1192.74	1193.19	1193.64	1194.09	1194.54	1194.98	1195.43	1195.88	1196.33	15600
15700	1196.78	1197.23	1197.68	1198.13	1198.58	1199.03	1199.47	1199.92	1200.37	1200.82	15700
15800	1201.27	1201.72	1202.16	1202.61	1203.06	1203.51	1203.95	1204.40	1204.85	1205.30	15800
15900	1205.74	1206.19	1206.64	1207.08	1207.53	1207.98	1208.42	1208.87	1209.32	1209.76	15900

Platinum versus Palladium
Temperature at intervals of 10 μ V (*continued*)

E/μ V	0	10	20	30	40	50	60	70	80	90	E/μ V
$t_{90} / ^\circ\text{C}$											
16000	1210.21	1210.66	1211.10	1211.55	1211.99	1212.44	1212.88	1213.33	1213.77	1214.22	16000
16100	1214.67	1215.11	1215.56	1216.00	1216.44	1216.89	1217.33	1217.78	1218.22	1218.67	16100
16200	1219.11	1219.55	1220.00	1220.44	1220.89	1221.33	1221.77	1222.22	1222.66	1223.10	16200
16300	1223.55	1223.99	1224.43	1224.88	1225.32	1225.76	1226.20	1226.65	1227.09	1227.53	16300
16400	1227.97	1228.41	1228.86	1229.30	1229.74	1230.18	1230.62	1231.07	1231.51	1231.95	16400
16500	1232.39	1232.83	1233.27	1233.71	1234.15	1234.59	1235.03	1235.48	1235.92	1236.36	16500
16600	1236.80	1237.24	1237.68	1238.12	1238.56	1239.00	1239.44	1239.88	1240.32	1240.75	16600
16700	1241.19	1241.63	1242.07	1242.51	1242.95	1243.39	1243.83	1244.27	1244.71	1245.14	16700
16800	1245.58	1246.02	1246.46	1246.90	1247.34	1247.77	1248.21	1248.65	1249.09	1249.52	16800
16900	1249.96	1250.40	1250.84	1251.27	1251.71	1252.15	1252.59	1253.02	1253.46	1253.90	16900
17000	1254.33	1254.77	1255.21	1255.64	1256.08	1256.51	1256.95	1257.39	1257.82	1258.26	17000
17100	1258.69	1259.13	1259.56	1260.00	1260.44	1260.87	1261.31	1261.74	1262.18	1262.61	17100
17200	1263.05	1263.48	1263.91	1264.35	1264.78	1265.22	1265.65	1266.09	1266.52	1266.96	17200
17300	1267.39	1267.82	1268.26	1268.69	1269.12	1269.56	1269.99	1270.42	1270.86	1271.29	17300
17400	1271.72	1272.16	1272.59	1273.02	1273.46	1273.89	1274.32	1274.75	1275.19	1275.62	17400
17500	1276.05	1276.48	1276.91	1277.35	1277.78	1278.21	1278.64	1279.07	1279.50	1279.94	17500
17600	1280.37	1280.80	1281.23	1281.66	1282.09	1282.52	1282.95	1283.38	1283.81	1284.25	17600
17700	1284.68	1285.11	1285.54	1285.97	1286.40	1286.83	1287.26	1287.69	1288.12	1288.55	17700
17800	1288.98	1289.41	1289.84	1290.27	1290.69	1291.12	1291.55	1291.98	1292.41	1292.84	17800
17900	1293.27	1293.70	1294.13	1294.55	1294.98	1295.41	1295.84	1296.27	1296.70	1297.12	17900
18000	1297.55	1297.98	1298.41	1298.84	1299.26	1299.69	1300.12	1300.55	1300.97	1301.40	18000
18100	1301.83	1302.26	1302.68	1303.11	1303.54	1303.96	1304.39	1304.82	1305.24	1305.67	18100
18200	1306.10	1306.52	1306.95	1307.37	1307.80	1308.23	1308.65	1309.08	1309.50	1309.93	18200
18300	1310.36	1310.78	1311.21	1311.63	1312.06	1312.48	1312.91	1313.33	1313.76	1314.18	18300
18400	1314.61	1315.03	1315.46	1315.88	1316.31	1316.73	1317.15	1317.58	1318.00	1318.43	18400
18500	1318.85	1319.28	1319.70	1320.12	1320.55	1320.97	1321.39	1321.82	1322.24	1322.66	18500
18600	1323.09	1323.51	1323.93	1324.36	1324.78	1325.20	1325.63	1326.05	1326.47	1326.89	18600
18700	1327.32	1327.74	1328.16	1328.58	1329.00	1329.43	1329.85	1330.27	1330.69	1331.11	18700
18800	1331.54	1331.96	1332.38	1332.80	1333.22	1333.64	1334.07	1334.49	1334.91	1335.33	18800
18900	1335.75	1336.17	1336.59	1337.01	1337.43	1337.85	1338.27	1338.69	1339.11	1339.53	18900
19000	1339.96	1340.38	1340.80	1341.22	1341.64	1342.05	1342.47	1342.89	1343.31	1343.73	19000
19100	1344.15	1344.57	1344.99	1345.41	1345.83	1346.25	1346.67	1347.09	1347.51	1347.93	19100
19200	1348.34	1348.76	1349.18	1349.60	1350.02	1350.44	1350.85	1351.27	1351.69	1352.11	19200
19300	1352.53	1352.95	1353.36	1353.78	1354.20	1354.62	1355.03	1355.45	1355.87	1356.29	19300
19400	1356.70	1357.12	1357.54	1357.95	1358.37	1358.79	1359.21	1359.62	1360.04	1360.46	19400
19500	1360.87	1361.29	1361.71	1362.12	1362.54	1362.95	1363.37	1363.79	1364.20	1364.62	19500
19600	1365.03	1365.45	1365.87	1366.28	1366.70	1367.11	1367.53	1367.94	1368.36	1368.77	19600
19700	1369.19	1369.60	1370.02	1370.43	1370.85	1371.26	1371.68	1372.09	1372.51	1372.92	19700
19800	1373.34	1373.75	1374.17	1374.58	1374.99	1375.41	1375.82	1376.24	1376.65	1377.06	19800
19900	1377.48	1377.89	1378.30	1378.72	1379.13	1379.55	1379.96	1380.37	1380.78	1381.20	19900

Platinum versus Palladium
Temperature at intervals of 10 μ V (*continued*)

E/μ V	0	10	20	30	40	50	60	70	80	90	E/μ V
$t_{90} / ^\circ\text{C}$											
20000	1381.61	1382.02	1382.44	1382.85	1383.26	1383.68	1384.09	1384.50	1384.91	1385.33	20000
20100	1385.74	1386.15	1386.56	1386.98	1387.39	1387.80	1388.21	1388.62	1389.04	1389.45	20100
20200	1389.86	1390.27	1390.68	1391.09	1391.50	1391.92	1392.33	1392.74	1393.15	1393.56	20200
20300	1393.97	1394.38	1394.79	1395.21	1395.62	1396.03	1396.44	1396.85	1397.26	1397.67	20300
20400	1398.08	1398.49	1398.90	1399.31	1399.72	1400.13	1400.54	1400.95	1401.36	1401.77	20400
20500	1402.18	1402.59	1403.00	1403.41	1403.82	1404.23	1404.64	1405.05	1405.46	1405.86	20500
20600	1406.27	1406.68	1407.09	1407.50	1407.91	1408.32	1408.73	1409.14	1409.54	1409.95	20600
20700	1410.36	1410.77	1411.18	1411.59	1411.99	1412.40	1412.81	1413.22	1413.63	1414.03	20700
20800	1414.44	1414.85	1415.26	1415.67	1416.07	1416.48	1416.89	1417.30	1417.70	1418.11	20800
20900	1418.52	1418.92	1419.33	1419.74	1420.15	1420.55	1420.96	1421.37	1421.77	1422.18	20900
21000	1422.59	1422.99	1423.40	1423.80	1424.21	1424.62	1425.02	1425.43	1425.84	1426.24	21000
21100	1426.65	1427.05	1427.46	1427.87	1428.27	1428.68	1429.08	1429.49	1429.89	1430.30	21100
21200	1430.70	1431.11	1431.51	1431.92	1432.32	1432.73	1433.13	1433.54	1433.94	1434.35	21200
21300	1434.75	1435.16	1435.56	1435.97	1436.37	1436.78	1437.18	1437.58	1437.99	1438.39	21300
21400	1438.80	1439.20	1439.61	1440.01	1440.41	1440.82	1441.22	1441.62	1442.03	1442.43	21400
21500	1442.84	1443.24	1443.64	1444.05	1444.45	1444.85	1445.25	1445.66	1446.06	1446.46	21500
21600	1446.87	1447.27	1447.67	1448.08	1448.48	1448.88	1449.28	1449.69	1450.09	1450.49	21600
21700	1450.89	1451.29	1451.70	1452.10	1452.50	1452.90	1453.31	1453.71	1454.11	1454.51	21700
21800	1454.91	1455.31	1455.72	1456.12	1456.52	1456.92	1457.32	1457.72	1458.12	1458.53	21800
21900	1458.93	1459.33	1459.73	1460.13	1460.53	1460.93	1461.33	1461.73	1462.13	1462.53	21900
22000	1462.93	1463.34	1463.74	1464.14	1464.54	1464.94	1465.34	1465.74	1466.14	1466.54	22000
22100	1466.94	1467.34	1467.74	1468.14	1468.54	1468.94	1469.34	1469.74	1470.13	1470.53	22100
22200	1470.93	1471.33	1471.73	1472.13	1472.53	1472.93	1473.33	1473.73	1474.13	1474.53	22200
22300	1474.92	1475.32	1475.72	1476.12	1476.52	1476.92	1477.32	1477.71	1478.11	1478.51	22300
22400	1478.91	1479.31	1479.71	1480.10	1480.50	1480.90	1481.30	1481.70	1482.09	1482.49	22400
22500	1482.89	1483.29	1483.68	1484.08	1484.48	1484.88	1485.27	1485.67	1486.07	1486.47	22500
22600	1486.86	1487.26	1487.66	1488.05	1488.45	1488.85	1489.24	1489.64	1490.04	1490.43	22600
22700	1490.83	1491.23	1491.62	1492.02	1492.42	1492.81	1493.21	1493.60	1494.00	1494.40	22700
22800	1494.79	1495.19	1495.58	1495.98	1496.38	1496.77	1497.17	1497.56	1497.96	1498.35	22800
22900	1498.75	1499.14	1499.54	1499.93	1500.33						22900

6.3 Thermoelectric values at the defining fixed points of the ITS-90 for Pt/Pd thermocouples (informative)

Fixed point	$t_{90} / ^\circ\text{C}$	$E/\mu\text{V}$	$S/(\mu\text{V}/^\circ\text{C})$
Water TP	0.01	0.05	5.297
Gallium MP	29.7646	161.52	5.549
Indium FP	156.5985	921.65	6.429
Tin FP	231.928	1428.56	7.059
Zinc FP	419.527	2964.35	9.533
Aluminum FP	660.323	5782.38	13.975
Silver FP	961.78	10813.09	19.187
Gold FP	1064.18	12853.21	20.631
Copper FP	1084.62	13277.65	20.899

Annex A

Gold versus Platinum coefficients

A.1 (normative) Coefficients of the reference function for Au/Pt thermocouples

The form of the function for the temperature range 0 °C to 1 000 °C is:

$$E / \mu\text{V} = \sum_{i=0}^9 a_i (t_{90} / ^\circ\text{C})^i$$

The function gives EMF, $E/\mu\text{V}$, in microvolts as a function of temperature, t_{90} , in the stated range.

Temperature range	0 °C to 1 000 °C
EMF range	0 μV to 17085.3 μV
$a_0 =$	0.000 000 00
$a_1 =$	6.036 198 61
$a_2 =$	1.936 729 74E–02
$a_3 =$	–2.229 986 14E–05
$a_4 =$	3.287 118 59E–08
$a_5 =$	–4.242 061 93E–11
$a_6 =$	4.569 270 38E–14
$a_7 =$	–3.394 302 59E–17
$a_8 =$	1.429 815 90E–20
$a_9 =$	–2.516 727 87E–24

A.2 (informative) Coefficients of an approximate inverse function for Au/Pt thermocouples

The form of the inverse function for the temperature range 0 °C to 209 °C is:

$$t_{90} / ^\circ\text{C} = \sum_{i=0}^8 b_i (E / \mu\text{V})^i$$

The form of the inverse function for the temperature range 209 °C to 1 000 °C is:

$$t_{90} / ^\circ\text{C} = \sum_{i=0}^{11} b_i ((E / \mu\text{V} - 9645) / 7620)^i$$

The function is used to calculate approximate values of temperature, t_{90} , in degrees Celsius as a function of the EMF, $E/\mu\text{V}$, in microvolts in the stated ranges.

Temperature range	0 °C to 209 °C	209 °C to 1 000 °C
EMF range	0 μV to 1953 μV	1953 μV to 17085 μV
$b_0 =$	0.000 000	6.763 360E+02
$b_1 =$	1.654 390 3E–01	3.735 504E+02
$b_2 =$	–8.409 883 5E–05	–5.537 363E+01
$b_3 =$	8.416 613 2E–08	1.701 900E+01
$b_4 =$	–7.517 469 1E–11	–6.098 761E+00
$b_5 =$	4.849 553 6E–14	2.457 162E+00
$b_6 =$	–2.013 876 0E–17	–3.385 575E+00
$b_7 =$	4.747 562 6E–21	3.853 735E+00
$b_8 =$	–4.797 308 2E–25	1.178 891E+00
$b_9 =$		–2.702 558E+00
$b_{10} =$		–1.686 158E+00
$b_{11} =$		1.876 968E+00
Error range	–5 mK to 3 mK	–2 mK to 2 mK

Annex B

Platinum versus Palladium Coefficients

B.1 (normative) Coefficients of the reference function for Pt/Pd thermocouples

The form of the function for both temperature ranges is:

$$E / \mu\text{V} = \sum_{i=0}^n a_i (t_{90} / ^\circ\text{C})^i$$

The function gives the EMF, $E / \mu\text{V}$, in microvolts as a function of the temperature, t_{90} , in degrees Celsius in the stated ranges.

Temperature range	0 °C to 660.323 °C	660.323 °C to 1 500 °C
EMF range	0 μV to 5782.4 μV	5782.4 μV to 22 932 μV
$a_0 =$	0.000 000	−4.977 137 0E+02
$a_1 =$	5.296 958	1.018 254 5E+01
$a_2 =$	4.610 494E−03	−1.579 351 5E−02
$a_3 =$	−9.602 271E−06	3.636 170 0E−05
$a_4 =$	2.992 243E−08	−2.690 150 9E−08
$a_5 =$	−2.012 523E−11	9.562 736 6E−12
$a_6 =$	−1.268 514E−14	−1.357 073 7E−15
$a_7 =$	2.257 823E−17	
$a_8 =$	−8.510 068E−21	

B.2 (informative) Coefficients of an approximate inverse function for Pt/Pd thermocouples

The form of the inverse function for the temperature ranges 0 °C to 660.323 °C and 660.323 °C to 1 500 °C is:

$$t_{90} / ^\circ\text{C} = \sum_{i=0}^n b_i (E / \mu\text{V})^i$$

The function gives temperature, t_{90} , in degrees Celsius as a function of the EMF, $E/\mu\text{V}$, in microvolts in the stated ranges.

Temperature range	0 °C to 660.323 °C	660.323 °C to 1 500 °C
EMF range	0 μV to 5782.4 μV	5782.4 μV to 22 932 μV
$b_0 =$	1.128 648 1E–03	1.681 398 72E+01
$b_1 =$	1.886 785 0E–01	1.831 741 63E–01
$b_2 =$	–3.001 252 1E–05	–2.091 790 74E–05
$b_3 =$	1.846 873 7E–08	2.142 812 41E–09
$b_4 =$	–1.249 860 8E–11	–1.518 770 21E–13
$b_5 =$	5.241 650 9E–15	7.212 177 60E–18
$b_6 =$	–1.391 528 6E–18	–2.185 981 64E–22
$b_7 =$	2.387 290 8E–22	3.815 100 60E–27
$b_8 =$	–2.580 243 6E–26	–2.912 944 07E–32
$b_9 =$	1.601 881 9E–30	
$b_{10} =$	–4.360 816 6E–35	
Error range	–3 mK to 2 mK	–2.7 mK to 2.0 mK

SOMMAIRE

AVANT-PROPOS	31
1 Domaine d'application	33
2 Références normatives	33
3 Termes et définitions	33
4 Informations relatives aux tableaux et aux équations	34
5 Tableaux pour les couples thermoélectriques Or/Platine	35
5.1 Or/Platine: f.é.m. à intervalles de 1 °C	35
5.2 Or/Platine: Température à intervalles de 10 µV	38
5.3 Valeurs thermoélectriques aux points fixes de l'EIT-90 pour les couples thermoélectriques Au/Pt (informative)	42
6 Tableaux pour les couples thermoélectriques Platine/Palladium	43
6.1 Platine/Palladium: f.é.m. à intervalles de 1 °C	43
6.2 Platine/Palladium: Température à intervalles de 10 µV	47
6.3 Valeurs thermoélectriques aux points fixes de l'EIT-90 pour les couples thermoélectriques Pt/Pd (informative)	53
Annexe A Coefficients Or / Platine	54
Annexe B Coefficients Platine/Palladium	56

COMMISSION ÉLECTROTECHNIQUE INTERNATIONALE

TABLEAUX TEMPÉRATURE – FORCE ÉLECTROMOTRICE (F.É.M.) POUR LES COMBINAISONS DE COUPLES THERMOÉLECTRIQUES À ÉLÉMENTS PURS

AVANT-PROPOS

- 1) La Commission Electrotechnique Internationale (CEI) est une organisation mondiale de normalisation composée de l'ensemble des comités électrotechniques nationaux (Comités nationaux de la CEI). La CEI a pour objet de favoriser la coopération internationale pour toutes les questions de normalisation dans les domaines de l'électricité et de l'électronique. A cet effet, la CEI – entre autres activités – publie des Normes internationales, des Spécifications techniques, des Rapports techniques, des Spécifications accessibles au public (PAS) et des Guides (ci-après dénommés "Publication(s) de la CEI"). Leur élaboration est confiée à des comités d'études, aux travaux desquels tout Comité national intéressé par le sujet traité peut participer. Des organisations internationales, gouvernementales et non gouvernementales peuvent également participer à ces travaux en liaison avec la CEI. La CEI collabore étroitement avec l'Organisation Internationale de Normalisation (ISO), selon des conditions fixées par accord entre les deux organisations.
- 2) Les décisions ou accords officiels de la CEI concernant les questions techniques représentent, dans la mesure du possible, un accord international sur les sujets étudiés, étant donné que les Comités nationaux intéressés sont représentés dans chaque comité d'études.
- 3) Les Publications de la CEI se présentent sous la forme de recommandations internationales et sont agréées comme telles par les Comités nationaux de la CEI. Tous les efforts raisonnables sont entrepris afin que la CEI s'assure de l'exactitude du contenu technique de ses publications; la CEI ne peut pas être tenue responsable de l'éventuelle mauvaise utilisation ou interprétation qui en est faite par un quelconque utilisateur final.
- 4) Dans le but d'encourager l'uniformité internationale, les Comités nationaux de la CEI s'engagent, dans toute la mesure possible, à appliquer de façon transparente les Publications de la CEI dans leurs publications nationales et régionales. Toutes divergences entre toutes Publications de la CEI et toutes publications nationales ou régionales correspondantes doivent être indiquées en termes clairs dans ces dernières.
- 5) La CEI n'a prévu aucune procédure de marquage valant indication d'approbation et n'engage pas sa responsabilité pour les équipements déclarés conformes à une de ses Publications.
- 6) Tous les utilisateurs doivent s'assurer qu'ils sont en possession de la dernière édition de cette publication.
- 7) Aucune responsabilité ne doit être imputée à la CEI, à ses administrateurs, employés, auxiliaires ou mandataires, y compris ses experts particuliers et les membres de ses comités d'études et des Comités nationaux de la CEI, pour tout préjudice causé en cas de dommages corporels et matériels, ou de tout autre dommage de quelque nature que ce soit, directe ou indirecte, ou pour supporter les coûts (y compris les frais de justice) et les dépenses découlant de la publication ou de l'utilisation de cette Publication de la CEI ou de toute autre Publication de la CEI, ou au crédit qui lui est accordé.
- 8) L'attention est attirée sur les références normatives citées dans cette publication. L'utilisation de publications référencées est obligatoire pour une application correcte de la présente publication.
- 9) L'attention est attirée sur le fait que certains des éléments de la présente Publication de la CEI peuvent faire l'objet de droits de propriété intellectuelle ou de droits analogues. La CEI ne saurait être tenue pour responsable de ne pas avoir identifié de tels droits de propriété et de ne pas avoir signalé leur existence.

La Norme internationale CEI 62460 a été établie par le sous-comité 65B: Dispositifs, du comité d'étude 65: Mesure, commande et automation dans les processus industriels.

Le texte de cette norme est issu des documents suivants:

FDIS	Rapport de vote
65B/665/FDIS	65B/684/RVD

Le rapport de vote indiqué dans le tableau ci-dessus donne toute information sur le vote ayant abouti à l'approbation de cette norme.

Cette publication a été rédigée selon les Directives ISO/CEI, Partie 2.

Le comité a décidé que le contenu de cette publication ne sera pas modifié avant la date de maintenance indiquée sur le site web de la CEI sous "<http://webstore.iec.ch>" dans les données relatives à la publication recherchée. A cette date, la publication sera

- reconduite,
- supprimée,
- remplacée par une édition révisée, ou
- amendée.

TABLEAUX TEMPÉRATURE – FORCE ÉLECTROMOTRICE (F.É.M.) POUR LES COMBINAISONS DE COUPLES THERMOÉLECTRIQUES À ÉLÉMENTS PURS

1 Domaine d'application

La présente Norme internationale spécifie les équations et les tableaux de référence donnant la relation entre la température et la f.é.m. (force électromotrice) pour les couples thermoélectriques Or/Platine et Platine/Palladium. Pour information et facilité d'usage, les équations approchées donnant la température en fonction de la f.é.m. sont aussi données.

Les tableaux et équations de la présente norme sont à utiliser avec des couples thermoélectriques constitués d'éléments de pureté 99,999 % ou plus pour le platine et l'or et 99,99 % ou plus pour le palladium (pureté pondérale).

Les tolérances sur les valeurs initiales de la f.é.m. en fonction de la température n'ont pas été établies pour les couples thermoélectriques, dans la présente norme. Si nécessaire, il convient que ces tolérances fassent l'objet d'un accord entre le fabricant de fils et l'utilisateur.

Dans la présente norme, les températures sont basées sur l'Echelle Internationale de Température de 1990 (EIT-90). Elles sont exprimées en degrés Celsius, symbole t_{90} et les valeurs de f.é.m. E/ μ V sont données en microvolts.

La présente norme ne couvre pas les fils de compensation ou d'extension utilisables avec les couples thermoélectriques à éléments purs couverts par la norme. Leur utilisation doit faire l'objet d'un accord entre le fabricant et l'utilisateur.

2 Références normatives

Les documents de référence suivants sont indispensables pour l'application du présent document. Pour les références datées, seule l'édition citée s'applique. Pour les références non datées, la dernière édition du document de référence s'applique (y compris les éventuels amendements).

CEI 60584-1, *Couples thermoélectriques – Partie 1: Tables de référence*

3 Termes et définitions

Pour les besoins du présent document, les termes et définitions donnés dans la CEI 60584-1 sont applicables, ainsi que les suivants.

3.1

types de couples thermoélectriques

les types de fils pour couples thermoélectriques suivants sont couverts par la présente norme:

- Or/Platine (Au/Pt ou Or/Platine)
- Platine/Palladium (Pt/Pd ou Platine/Palladium)

Par convention internationale, comme dans la CEI 60584-1, dans l'identification des couples thermoélectriques, l'élément/fil positif est cité en premier.

3.2 valeurs thermoélectriques aux points fixes de l'EIT-90

les valeurs sont données pour les points triples (PT), les points de fusion (PF) et les points de congélation (PC) dans le domaine de températures des tableaux correspondants. Le coefficient de Seebeck S est la dérivée première de la f.é.m. par rapport à la température.

4 Informations relatives aux tableaux et aux équations

Les tableaux suivants sont inclus dans la présente norme:

- Or/Platine f.é.m. par pas de 1 °C
- Or/Platine: températures à intervalles de 10μV
- Or/Platine: valeurs thermoélectriques aux points fixes de l'EIT-90
- Platine/Palladium f.é.m. par pas de 1 °C
- Platine/Palladium: températures à intervalles de 10μV
- Platine/Palladium: valeurs thermoélectriques aux points fixes de l'EIT-90

Pour les tableaux de la présente norme, la température de référence est 0 °C.

Les équations définitives de la f.é.m., de $E/\mu V$, en fonction de la température $t_{90}/^{\circ}C$, qui ont été utilisées pour obtenir ces tableaux sont données en Annexe A pour les couples thermoélectriques Or/Platine et dans l'Annexe B pour les couples thermoélectriques Platine/Palladium.

Pour information et facilité d'utilisation, les équations approchées exprimant $t_{90}/^{\circ}C$ en fonction de $E/\mu V$ pour chaque thermocouple dans ses limites établies sont aussi données.

NOTE Pour des raisons d'ordre pratique, les tableaux suivants sont ceux de la version anglaise. Dans ces tableaux, le signe décimal est un point.

5 Tableaux pour les couples thermoélectriques Or/Platine

5.1 Or/Platine: f.é.m. à intervalles de 1 °C

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
0	0.0	6.1	12.1	18.3	24.5	30.7	36.9	43.2	49.5	55.9	0
10	62.3	68.7	75.2	81.7	88.2	94.8	101.4	108.1	114.8	121.5	10
20	128.3	135.1	141.9	148.8	155.7	162.7	169.7	176.7	183.7	190.8	20
30	197.9	205.1	212.3	219.5	226.8	234.1	241.4	248.8	256.2	263.6	30
40	271.1	278.6	286.1	293.7	301.3	308.9	316.6	324.3	332.1	339.8	40
50	347.6	355.5	363.3	371.2	379.2	387.1	395.1	403.2	411.2	419.3	50
60	427.5	435.6	443.8	452.1	460.3	468.6	476.9	485.3	493.6	502.1	60
70	510.5	519.0	527.5	536.0	544.6	553.2	561.8	570.5	579.2	587.9	70
80	596.6	605.4	614.2	623.1	632.0	640.9	649.8	658.7	667.7	676.8	80
90	685.8	694.9	704.0	713.1	722.3	731.5	740.7	750.0	759.2	768.6	90
100	777.9	787.3	796.7	806.1	815.5	825.0	834.5	844.1	853.6	863.2	100
110	872.8	882.5	892.2	901.9	911.6	921.4	931.2	941.0	950.8	960.7	110
120	970.6	980.5	990.5	1000.4	1010.4	1020.5	1030.5	1040.6	1050.7	1060.9	120
130	1071.0	1081.2	1091.4	1101.7	1112.0	1122.3	1132.6	1142.9	1153.3	1163.7	130
140	1174.1	1184.6	1195.1	1205.6	1216.1	1226.7	1237.2	1247.8	1258.5	1269.1	140
150	1279.8	1290.5	1301.3	1312.0	1322.8	1333.6	1344.4	1355.3	1366.2	1377.1	150
160	1388.0	1399.0	1410.0	1421.0	1432.0	1443.1	1454.1	1465.3	1476.4	1487.5	160
170	1498.7	1509.9	1521.1	1532.4	1543.7	1555.0	1566.3	1577.6	1589.0	1600.4	170
180	1611.8	1623.3	1634.7	1646.2	1657.7	1669.3	1680.8	1692.4	1704.0	1715.6	180
190	1727.3	1739.0	1750.7	1762.4	1774.1	1785.9	1797.7	1809.5	1821.3	1833.2	190
200	1845.1	1857.0	1868.9	1880.9	1892.8	1904.8	1916.8	1928.9	1941.0	1953.0	200
210	1965.1	1977.3	1989.4	2001.6	2013.8	2026.0	2038.3	2050.5	2062.8	2075.1	210
220	2087.4	2099.8	2112.2	2124.6	2137.0	2149.4	2161.9	2174.4	2186.9	2199.4	220
230	2211.9	2224.5	2237.1	2249.7	2262.3	2275.0	2287.7	2300.4	2313.1	2325.8	230
240	2338.6	2351.4	2364.2	2377.0	2389.8	2402.7	2415.6	2428.5	2441.4	2454.4	240
250	2467.3	2480.3	2493.3	2506.4	2519.4	2532.5	2545.6	2558.7	2571.9	2585.0	250
260	2598.2	2611.4	2624.6	2637.8	2651.1	2664.4	2677.7	2691.0	2704.3	2717.7	260
270	2731.1	2744.5	2757.9	2771.3	2784.8	2798.3	2811.8	2825.3	2838.9	2852.4	270
280	2866.0	2879.6	2893.2	2906.9	2920.5	2934.2	2947.9	2961.6	2975.4	2989.1	280
290	3002.9	3016.7	3030.5	3044.4	3058.2	3072.1	3086.0	3099.9	3113.8	3127.8	290
300	3141.8	3155.8	3169.8	3183.8	3197.9	3211.9	3226.0	3240.1	3254.3	3268.4	300
310	3282.6	3296.8	3311.0	3325.2	3339.4	3353.7	3368.0	3382.3	3396.6	3410.9	310
320	3425.3	3439.7	3454.1	3468.5	3482.9	3497.4	3511.8	3526.3	3540.8	3555.4	320
330	3569.9	3584.5	3599.1	3613.7	3628.3	3642.9	3657.6	3672.2	3686.9	3701.7	330
340	3716.4	3731.1	3745.9	3760.7	3775.5	3790.3	3805.2	3820.0	3834.9	3849.8	340
350	3864.7	3879.6	3894.6	3909.6	3924.6	3939.6	3954.6	3969.6	3984.7	3999.8	350
360	4014.9	4030.0	4045.1	4060.3	4075.4	4090.6	4105.8	4121.0	4136.3	4151.5	360
370	4166.8	4182.1	4197.4	4212.8	4228.1	4243.5	4258.9	4274.3	4289.7	4305.1	370
380	4320.6	4336.1	4351.6	4367.1	4382.6	4398.1	4413.7	4429.3	4444.9	4460.5	380

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
390	4476.1	4491.8	4507.4	4523.1	4538.8	4554.6	4570.3	4586.1	4601.8	4617.6	390
400	4633.4	4649.3	4665.1	4681.0	4696.8	4712.7	4728.6	4744.6	4760.5	4776.5	400
410	4792.5	4808.5	4824.5	4840.5	4856.6	4872.7	4888.7	4904.9	4921.0	4937.1	410
420	4953.3	4969.4	4985.6	5001.8	5018.1	5034.3	5050.6	5066.9	5083.1	5099.5	420
430	5115.8	5132.1	5148.5	5164.9	5181.3	5197.7	5214.1	5230.6	5247.0	5263.5	430
440	5280.0	5296.5	5313.1	5329.6	5346.2	5362.8	5379.4	5396.0	5412.6	5429.3	440
450	5446.0	5462.6	5479.4	5496.1	5512.8	5529.6	5546.3	5563.1	5579.9	5596.8	450
460	5613.6	5630.5	5647.3	5664.2	5681.1	5698.0	5715.0	5731.9	5748.9	5765.9	460
470	5782.9	5799.9	5817.0	5834.0	5851.1	5868.2	5885.3	5902.4	5919.6	5936.8	470
480	5953.9	5971.1	5988.3	6005.6	6022.8	6040.1	6057.3	6074.6	6091.9	6109.3	480
490	6126.6	6144.0	6161.3	6178.7	6196.1	6213.6	6231.0	6248.5	6265.9	6283.4	490
500	6301.0	6318.5	6336.0	6353.6	6371.2	6388.7	6406.4	6424.0	6441.6	6459.3	500
510	6477.0	6494.7	6512.4	6530.1	6547.8	6565.6	6583.4	6601.1	6619.0	6636.8	510
520	6654.6	6672.5	6690.4	6708.2	6726.2	6744.1	6762.0	6780.0	6797.9	6815.9	520
530	6833.9	6852.0	6870.0	6888.1	6906.1	6924.2	6942.3	6960.4	6978.6	6996.7	530
540	7014.9	7033.1	7051.3	7069.5	7087.7	7106.0	7124.3	7142.6	7160.9	7179.2	540
550	7197.5	7215.9	7234.2	7252.6	7271.0	7289.4	7307.9	7326.3	7344.8	7363.3	550
560	7381.8	7400.3	7418.8	7437.4	7455.9	7474.5	7493.1	7511.7	7530.3	7549.0	560
570	7567.6	7586.3	7605.0	7623.7	7642.5	7661.2	7680.0	7698.7	7717.5	7736.3	570
580	7755.2	7774.0	7792.9	7811.7	7830.6	7849.5	7868.5	7887.4	7906.4	7925.3	580
590	7944.3	7963.3	7982.3	8001.4	8020.4	8039.5	8058.6	8077.7	8096.8	8115.9	590
600	8135.1	8154.3	8173.4	8192.6	8211.9	8231.1	8250.3	8269.6	8288.9	8308.2	600
610	8327.5	8346.8	8366.2	8385.5	8404.9	8424.3	8443.7	8463.2	8482.6	8502.1	610
620	8521.5	8541.0	8560.5	8580.1	8599.6	8619.2	8638.7	8658.3	8677.9	8697.6	620
630	8717.2	8736.9	8756.5	8776.2	8795.9	8815.6	8835.4	8855.1	8874.9	8894.7	630
640	8914.5	8934.3	8954.1	8974.0	8993.9	9013.7	9033.6	9053.6	9073.5	9093.4	640
650	9113.4	9133.4	9153.4	9173.4	9193.4	9213.5	9233.5	9253.6	9273.7	9293.8	650
660	9313.9	9334.1	9354.2	9374.4	9394.6	9414.8	9435.0	9455.3	9475.5	9495.8	660
670	9516.1	9536.4	9556.7	9577.0	9597.4	9617.8	9638.2	9658.6	9679.0	9699.4	670
680	9719.9	9740.3	9760.8	9781.3	9801.8	9822.3	9842.9	9863.5	9884.0	9904.6	680
690	9925.2	9945.9	9966.5	9987.2	10007.9	10028.5	10049.3	10070.0	10090.7	10111.5	690
700	10132.2	10153.0	10173.8	10194.7	10215.5	10236.4	10257.2	10278.1	10299.0	10319.9	700
710	10340.9	10361.8	10382.8	10403.8	10424.8	10445.8	10466.8	10487.9	10508.9	10530.0	710
720	10551.1	10572.2	10593.3	10614.5	10635.6	10656.8	10678.0	10699.2	10720.4	10741.7	720
730	10762.9	10784.2	10805.5	10826.8	10848.1	10869.5	10890.8	10912.2	10933.6	10955.0	730
740	10976.4	10997.8	11019.3	11040.8	11062.2	11083.7	11105.3	11126.8	11148.3	11169.9	740
750	11191.5	11213.1	11234.7	11256.3	11277.9	11299.6	11321.3	11343.0	11364.7	11386.4	750
760	11408.1	11429.9	11451.7	11473.5	11495.3	11517.1	11538.9	11560.8	11582.6	11604.5	760
770	11626.4	11648.3	11670.3	11692.2	11714.2	11736.2	11758.2	11780.2	11802.2	11824.3	770
780	11846.3	11868.4	11890.5	11912.6	11934.7	11956.9	11979.0	12001.2	12023.4	12045.6	780
790	12067.8	12090.0	12112.3	12134.6	12156.8	12179.1	12201.5	12223.8	12246.1	12268.5	790
800	12290.9	12313.3	12335.7	12358.1	12380.6	12403.0	12425.5	12448.0	12470.5	12493.0	800
810	12515.6	12538.1	12560.7	12583.3	12605.9	12628.5	12651.2	12673.8	12696.5	12719.2	810
820	12741.9	12764.6	12787.3	12810.1	12832.8	12855.6	12878.4	12901.2	12924.0	12946.9	820
830	12969.7	12992.6	13015.5	13038.4	13061.3	13084.3	13107.2	13130.2	13153.2	13176.2	830

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
840	13199.2	13222.2	13245.3	13268.4	13291.4	13314.5	13337.7	13360.8	13383.9	13407.1	840
850	13430.3	13453.5	13476.7	13499.9	13523.1	13546.4	13569.7	13593.0	13616.3	13639.6	850
860	13662.9	13686.3	13709.6	13733.0	13756.4	13779.8	13803.3	13826.7	13850.2	13873.6	860
870	13897.1	13920.7	13944.2	13967.7	13991.3	14014.9	14038.4	14062.0	14085.7	14109.3	870
880	14133.0	14156.6	14180.3	14204.0	14227.7	14251.5	14275.2	14299.0	14322.7	14346.5	880
890	14370.3	14394.2	14418.0	14441.9	14465.7	14489.6	14513.5	14537.5	14561.4	14585.3	890
900	14609.3	14633.3	14657.3	14681.3	14705.3	14729.4	14753.4	14777.5	14801.6	14825.7	900
910	14849.9	14874.0	14898.2	14922.3	14946.5	14970.7	14994.9	15019.2	15043.4	15067.7	910
920	15092.0	15116.3	15140.6	15164.9	15189.3	15213.6	15238.0	15262.4	15286.8	15311.2	920
930	15335.7	15360.1	15384.6	15409.1	15433.6	15458.1	15482.6	15507.2	15531.7	15556.3	930
940	15580.9	15605.5	15630.1	15654.8	15679.4	15704.1	15728.8	15753.5	15778.2	15803.0	940
950	15827.7	15852.5	15877.3	15902.1	15926.9	15951.7	15976.6	16001.4	16026.3	16051.2	950
960	16076.1	16101.0	16126.0	16150.9	16175.9	16200.9	16225.9	16250.9	16276.0	16301.0	960
970	16326.1	16351.2	16376.2	16401.4	16426.5	16451.6	16476.8	16502.0	16527.2	16552.4	970
980	16577.6	16602.8	16628.1	16653.3	16678.6	16703.9	16729.2	16754.6	16779.9	16805.3	980
990	16830.7	16856.1	16881.5	16906.9	16932.3	16957.8	16983.3	17008.8	17034.3	17059.8	990
1000	17085.3										1000

5.2 Or/Platine: Température à intervalles de 10 μV

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
0	0.00	1.65	3.28	4.89	6.49	8.07	9.64	11.20	12.74	14.27	0
100	15.78	17.28	18.77	20.25	21.72	23.17	24.62	26.05	27.47	28.89	100
200	30.29	31.68	33.07	34.44	35.81	37.17	38.52	39.86	41.19	42.51	200
300	43.83	45.14	46.44	47.74	49.02	50.30	51.58	52.84	54.10	55.36	300
400	56.60	57.84	59.08	60.31	61.53	62.75	63.96	65.17	66.37	67.56	400
500	68.75	69.94	71.12	72.29	73.46	74.63	75.79	76.94	78.09	79.24	500
600	80.38	81.52	82.65	83.78	84.90	86.02	87.14	88.25	89.36	90.46	600
700	91.56	92.66	93.75	94.84	95.92	97.01	98.08	99.16	100.23	101.29	700
800	102.36	103.42	104.47	105.53	106.58	107.62	108.67	109.71	110.74	111.78	800
900	112.81	113.84	114.86	115.88	116.90	117.92	118.93	119.94	120.95	121.95	900
1000	122.96	123.96	124.95	125.95	126.94	127.93	128.91	129.90	130.88	131.86	1000
1100	132.83	133.81	134.78	135.75	136.72	137.68	138.64	139.60	140.56	141.52	1100
1200	142.47	143.42	144.37	145.31	146.26	147.20	148.14	149.08	150.02	150.95	1200
1300	151.88	152.81	153.74	154.67	155.59	156.51	157.43	158.35	159.27	160.18	1300
1400	161.09	162.00	162.91	163.82	164.72	165.63	166.53	167.43	168.33	169.22	1400
1500	170.12	171.01	171.90	172.79	173.68	174.56	175.45	176.33	177.21	178.09	1500
1600	178.97	179.84	180.72	181.59	182.46	183.33	184.20	185.06	185.93	186.79	1600
1700	187.65	188.52	189.37	190.23	191.09	191.94	192.80	193.65	194.50	195.35	1700
1800	196.19	197.04	197.89	198.73	199.57	200.41	201.25	202.09	202.93	203.76	1800
1900	204.60	205.43	206.26	207.09	207.92	208.75	209.58	210.40	211.22	212.05	1900
2000	212.87	213.69	214.51	215.32	216.14	216.96	217.77	218.58	219.40	220.21	2000
2100	221.02	221.82	222.63	223.44	224.24	225.05	225.85	226.65	227.45	228.25	2100
2200	229.05	229.84	230.64	231.44	232.23	233.02	233.81	234.61	235.39	236.18	2200
2300	236.97	237.76	238.54	239.33	240.11	240.89	241.67	242.46	243.23	244.01	2300
2400	244.79	245.57	246.34	247.12	247.89	248.66	249.43	250.20	250.97	251.74	2400
2500	252.51	253.28	254.04	254.81	255.57	256.34	257.10	257.86	258.62	259.38	2500
2600	260.14	260.90	261.65	262.41	263.16	263.92	264.67	265.42	266.18	266.93	2600
2700	267.68	268.42	269.17	269.92	270.67	271.41	272.16	272.90	273.64	274.39	2700
2800	275.13	275.87	276.61	277.35	278.09	278.82	279.56	280.30	281.03	281.76	2800
2900	282.50	283.23	283.96	284.69	285.42	286.15	286.88	287.61	288.34	289.06	2900
3000	289.79	290.52	291.24	291.96	292.69	293.41	294.13	294.85	295.57	296.29	3000
3100	297.01	297.73	298.44	299.16	299.87	300.59	301.30	302.02	302.73	303.44	3100
3200	304.15	304.86	305.57	306.28	306.99	307.70	308.41	309.11	309.82	310.52	3200
3300	311.23	311.93	312.64	313.34	314.04	314.74	315.44	316.14	316.84	317.54	3300
3400	318.24	318.93	319.63	320.33	321.02	321.72	322.41	323.11	323.80	324.49	3400
3500	325.18	325.87	326.56	327.25	327.94	328.63	329.32	330.01	330.69	331.38	3500
3600	332.06	332.75	333.43	334.12	334.80	335.48	336.17	336.85	337.53	338.21	3600
3700	338.89	339.57	340.24	340.92	341.60	342.28	342.95	343.63	344.30	344.98	3700
3800	345.65	346.33	347.00	347.67	348.34	349.01	349.68	350.35	351.02	351.69	3800
3900	352.36	353.03	353.70	354.36	355.03	355.69	356.36	357.02	357.69	358.35	3900

Or/Platine:
Température à intervalles de 10 μV (*suite*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
4000	359.01	359.68	360.34	361.00	361.66	362.32	362.98	363.64	364.30	364.96	4000
4100	365.62	366.27	366.93	367.59	368.24	368.90	369.55	370.21	370.86	371.51	4100
4200	372.17	372.82	373.47	374.12	374.77	375.42	376.07	376.72	377.37	378.02	4200
4300	378.67	379.31	379.96	380.61	381.25	381.90	382.54	383.19	383.83	384.48	4300
4400	385.12	385.76	386.40	387.05	387.69	388.33	388.97	389.61	390.25	390.89	4400
4500	391.52	392.16	392.80	393.44	394.07	394.71	395.35	395.98	396.62	397.25	4500
4600	397.88	398.52	399.15	399.78	400.42	401.05	401.68	402.31	402.94	403.57	4600
4700	404.20	404.83	405.46	406.08	406.71	407.34	407.97	408.59	409.22	409.85	4700
4800	410.47	411.10	411.72	412.34	412.97	413.59	414.21	414.83	415.46	416.08	4800
4900	416.70	417.32	417.94	418.56	419.18	419.80	420.42	421.03	421.65	422.27	4900
5000	422.89	423.50	424.12	424.73	425.35	425.97	426.58	427.19	427.81	428.42	5000
5100	429.03	429.65	430.26	430.87	431.48	432.09	432.70	433.31	433.92	434.53	5100
5200	435.14	435.75	436.36	436.97	437.57	438.18	438.79	439.39	440.00	440.60	5200
5300	441.21	441.81	442.42	443.02	443.63	444.23	444.83	445.44	446.04	446.64	5300
5400	447.24	447.84	448.44	449.04	449.64	450.24	450.84	451.44	452.04	452.64	5400
5500	453.24	453.83	454.43	455.03	455.62	456.22	456.81	457.41	458.00	458.60	5500
5600	459.19	459.79	460.38	460.97	461.57	462.16	462.75	463.34	463.93	464.53	5600
5700	465.12	465.71	466.30	466.89	467.48	468.06	468.65	469.24	469.83	470.42	5700
5800	471.00	471.59	472.18	472.76	473.35	473.93	474.52	475.10	475.69	476.27	5800
5900	476.86	477.44	478.02	478.61	479.19	479.77	480.35	480.94	481.52	482.10	5900
6000	482.68	483.26	483.84	484.42	485.00	485.58	486.15	486.73	487.31	487.89	6000
6100	488.47	489.04	489.62	490.20	490.77	491.35	491.92	492.50	493.07	493.65	6100
6200	494.22	494.80	495.37	495.94	496.51	497.09	497.66	498.23	498.80	499.37	6200
6300	499.95	500.52	501.09	501.66	502.23	502.80	503.37	503.93	504.50	505.07	6300
6400	505.64	506.21	506.77	507.34	507.91	508.47	509.04	509.61	510.17	510.74	6400
6500	511.30	511.87	512.43	513.00	513.56	514.12	514.69	515.25	515.81	516.37	6500
6600	516.94	517.50	518.06	518.62	519.18	519.74	520.30	520.86	521.42	521.98	6600
6700	522.54	523.10	523.66	524.21	524.77	525.33	525.89	526.44	527.00	527.56	6700
6800	528.11	528.67	529.23	529.78	530.34	530.89	531.45	532.00	532.55	533.11	6800
6900	533.66	534.21	534.77	535.32	535.87	536.42	536.98	537.53	538.08	538.63	6900
7000	539.18	539.73	540.28	540.83	541.38	541.93	542.48	543.03	543.57	544.12	7000
7100	544.67	545.22	545.77	546.31	546.86	547.41	547.95	548.50	549.04	549.59	7100
7200	550.14	550.68	551.22	551.77	552.31	552.86	553.40	553.94	554.49	555.03	7200
7300	555.57	556.12	556.66	557.20	557.74	558.28	558.82	559.36	559.90	560.44	7300
7400	560.98	561.52	562.06	562.60	563.14	563.68	564.22	564.76	565.30	565.83	7400
7500	566.37	566.91	567.44	567.98	568.52	569.05	569.59	570.13	570.66	571.20	7500
7600	571.73	572.27	572.80	573.33	573.87	574.40	574.94	575.47	576.00	576.53	7600
7700	577.07	577.60	578.13	578.66	579.19	579.73	580.26	580.79	581.32	581.85	7700
7800	582.38	582.91	583.44	583.97	584.50	585.02	585.55	586.08	586.61	587.14	7800
7900	587.66	588.19	588.72	589.25	589.77	590.30	590.83	591.35	591.88	592.40	7900

Or/Platine:
Température à intervalles de 10 μV (*suite*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
8000	592.93	593.45	593.98	594.50	595.03	595.55	596.07	596.60	597.12	597.64	8000
8100	598.17	598.69	599.21	599.73	600.26	600.78	601.30	601.82	602.34	602.86	8100
8200	603.38	603.90	604.42	604.94	605.46	605.98	606.50	607.02	607.54	608.06	8200
8300	608.58	609.09	609.61	610.13	610.65	611.16	611.68	612.20	612.71	613.23	8300
8400	613.75	614.26	614.78	615.29	615.81	616.32	616.84	617.35	617.87	618.38	8400
8500	618.89	619.41	619.92	620.43	620.95	621.46	621.97	622.48	623.00	623.51	8500
8600	624.02	624.53	625.04	625.55	626.06	626.57	627.09	627.60	628.11	628.61	8600
8700	629.12	629.63	630.14	630.65	631.16	631.67	632.18	632.68	633.19	633.70	8700
8800	634.21	634.71	635.22	635.73	636.23	636.74	637.25	637.75	638.26	638.76	8800
8900	639.27	639.77	640.28	640.78	641.29	641.79	642.30	642.80	643.30	643.81	8900
9000	644.31	644.81	645.31	645.82	646.32	646.82	647.32	647.83	648.33	648.83	9000
9100	649.33	649.83	650.33	650.83	651.33	651.83	652.33	652.83	653.33	653.83	9100
9200	654.33	654.83	655.33	655.82	656.32	656.82	657.32	657.82	658.31	658.81	9200
9300	659.31	659.81	660.30	660.80	661.29	661.79	662.29	662.78	663.28	663.77	9300
9400	664.27	664.76	665.26	665.75	666.25	666.74	667.23	667.73	668.22	668.71	9400
9500	669.21	669.70	670.19	670.69	671.18	671.67	672.16	672.65	673.15	673.64	9500
9600	674.13	674.62	675.11	675.60	676.09	676.58	677.07	677.56	678.05	678.54	9600
9700	679.03	679.52	680.01	680.50	680.98	681.47	681.96	682.45	682.94	683.42	9700
9800	683.91	684.40	684.89	685.37	685.86	686.35	686.83	687.32	687.80	688.29	9800
9900	688.78	689.26	689.75	690.23	690.72	691.20	691.68	692.17	692.65	693.14	9900
10000	693.62	694.10	694.59	695.07	695.55	696.04	696.52	697.00	697.48	697.97	10000
10100	698.45	698.93	699.41	699.89	700.37	700.85	701.33	701.82	702.30	702.78	10100
10200	703.26	703.74	704.22	704.70	705.17	705.65	706.13	706.61	707.09	707.57	10200
10300	708.05	708.53	709.00	709.48	709.96	710.44	710.91	711.39	711.87	712.34	10300
10400	712.82	713.30	713.77	714.25	714.72	715.20	715.68	716.15	716.63	717.10	10400
10500	717.58	718.05	718.53	719.00	719.47	719.95	720.42	720.89	721.37	721.84	10500
10600	722.31	722.79	723.26	723.73	724.21	724.68	725.15	725.62	726.09	726.56	10600
10700	727.04	727.51	727.98	728.45	728.92	729.39	729.86	730.33	730.80	731.27	10700
10800	731.74	732.21	732.68	733.15	733.62	734.09	734.56	735.02	735.49	735.96	10800
10900	736.43	736.90	737.36	737.83	738.30	738.77	739.23	739.70	740.17	740.63	10900
11000	741.10	741.57	742.03	742.50	742.96	743.43	743.90	744.36	744.83	745.29	11000
11100	745.76	746.22	746.68	747.15	747.61	748.08	748.54	749.00	749.47	749.93	11100
11200	750.39	750.86	751.32	751.78	752.25	752.71	753.17	753.63	754.09	754.56	11200
11300	755.02	755.48	755.94	756.40	756.86	757.32	757.78	758.24	758.70	759.16	11300
11400	759.62	760.08	760.54	761.00	761.46	761.92	762.38	762.84	763.30	763.76	11400
11500	764.22	764.67	765.13	765.59	766.05	766.51	766.96	767.42	767.88	768.34	11500
11600	768.79	769.25	769.71	770.16	770.62	771.08	771.53	771.99	772.44	772.90	11600
11700	773.35	773.81	774.26	774.72	775.17	775.63	776.08	776.54	776.99	777.45	11700
11800	777.90	778.35	778.81	779.26	779.71	780.17	780.62	781.07	781.53	781.98	11800
11900	782.43	782.88	783.33	783.79	784.24	784.69	785.14	785.59	786.04	786.50	11900

Or/Platine:
Température à intervalles de 10 μV (*suite*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
12000	786.95	787.40	787.85	788.30	788.75	789.20	789.65	790.10	790.55	791.00	12000
12100	791.45	791.90	792.35	792.80	793.24	793.69	794.14	794.59	795.04	795.49	12100
12200	795.93	796.38	796.83	797.28	797.73	798.17	798.62	799.07	799.51	799.96	12200
12300	800.41	800.85	801.30	801.75	802.19	802.64	803.08	803.53	803.97	804.42	12300
12400	804.87	805.31	805.76	806.20	806.64	807.09	807.53	807.98	808.42	808.87	12400
12500	809.31	809.75	810.20	810.64	811.08	811.53	811.97	812.41	812.85	813.30	12500
12600	813.74	814.18	814.62	815.07	815.51	815.95	816.39	816.83	817.27	817.71	12600
12700	818.16	818.60	819.04	819.48	819.92	820.36	820.80	821.24	821.68	822.12	12700
12800	822.56	823.00	823.44	823.88	824.32	824.75	825.19	825.63	826.07	826.51	12800
12900	826.95	827.39	827.82	828.26	828.70	829.14	829.57	830.01	830.45	830.89	12900
13000	831.32	831.76	832.20	832.63	833.07	833.51	833.94	834.38	834.81	835.25	13000
13100	835.69	836.12	836.56	836.99	837.43	837.86	838.30	838.73	839.17	839.60	13100
13200	840.03	840.47	840.90	841.34	841.77	842.20	842.64	843.07	843.50	843.94	13200
13300	844.37	844.80	845.24	845.67	846.10	846.53	846.97	847.40	847.83	848.26	13300
13400	848.69	849.13	849.56	849.99	850.42	850.85	851.28	851.71	852.14	852.57	13400
13500	853.00	853.44	853.87	854.30	854.73	855.16	855.58	856.01	856.44	856.87	13500
13600	857.30	857.73	858.16	858.59	859.02	859.45	859.88	860.30	860.73	861.16	13600
13700	861.59	862.02	862.44	862.87	863.30	863.73	864.15	864.58	865.01	865.43	13700
13800	865.86	866.29	866.71	867.14	867.57	867.99	868.42	868.84	869.27	869.70	13800
13900	870.12	870.55	870.97	871.40	871.82	872.25	872.67	873.10	873.52	873.95	13900
14000	874.37	874.79	875.22	875.64	876.07	876.49	876.91	877.34	877.76	878.18	14000
14100	878.61	879.03	879.45	879.87	880.30	880.72	881.14	881.56	881.99	882.41	14100
14200	882.83	883.25	883.67	884.10	884.52	884.94	885.36	885.78	886.20	886.62	14200
14300	887.04	887.46	887.88	888.30	888.72	889.15	889.57	889.99	890.40	890.82	14300
14400	891.24	891.66	892.08	892.50	892.92	893.34	893.76	894.18	894.60	895.01	14400
14500	895.43	895.85	896.27	896.69	897.11	897.52	897.94	898.36	898.78	899.19	14500
14600	899.61	900.03	900.45	900.86	901.28	901.70	902.11	902.53	902.94	903.36	14600
14700	903.78	904.19	904.61	905.03	905.44	905.86	906.27	906.69	907.10	907.52	14700
14800	907.93	908.35	908.76	909.18	909.59	910.01	910.42	910.83	911.25	911.66	14800
14900	912.08	912.49	912.90	913.32	913.73	914.14	914.56	914.97	915.38	915.80	14900
15000	916.21	916.62	917.03	917.45	917.86	918.27	918.68	919.10	919.51	919.92	15000
15100	920.33	920.74	921.15	921.56	921.98	922.39	922.80	923.21	923.62	924.03	15100
15200	924.44	924.85	925.26	925.67	926.08	926.49	926.90	927.31	927.72	928.13	15200
15300	928.54	928.95	929.36	929.77	930.18	930.59	931.00	931.40	931.81	932.22	15300
15400	932.63	933.04	933.45	933.85	934.26	934.67	935.08	935.49	935.89	936.30	15400
15500	936.71	937.12	937.52	937.93	938.34	938.74	939.15	939.56	939.96	940.37	15500
15600	940.78	941.18	941.59	941.99	942.40	942.81	943.21	943.62	944.02	944.43	15600
15700	944.83	945.24	945.64	946.05	946.45	946.86	947.26	947.67	948.07	948.48	15700
15800	948.88	949.28	949.69	950.09	950.50	950.90	951.30	951.71	952.11	952.51	15800
15900	952.92	953.32	953.72	954.13	954.53	954.93	955.33	955.74	956.14	956.54	15900

Or/Platine:
Température à intervalles de 10 μV (suite)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$T_{90}/^{\circ}\text{C}$											
16000	956.94	957.34	957.75	958.15	958.55	958.95	959.35	959.75	960.16	960.56	16000
16100	960.96	961.36	961.76	962.16	962.56	962.96	963.36	963.76	964.16	964.56	16100
16200	964.96	965.36	965.76	966.16	966.56	966.96	967.36	967.76	968.16	968.56	16200
16300	968.96	969.36	969.76	970.16	970.56	970.95	971.35	971.75	972.15	972.55	16300
16400	972.95	973.34	973.74	974.14	974.54	974.93	975.33	975.73	976.13	976.52	16400
16500	976.92	977.32	977.72	978.11	978.51	978.91	979.30	979.70	980.10	980.49	16500
16600	980.89	981.28	981.68	982.08	982.47	982.87	983.26	983.66	984.05	984.45	16600
16700	984.84	985.24	985.63	986.03	986.42	986.82	987.21	987.61	988.00	988.40	16700
16800	988.79	989.19	989.58	989.97	990.37	990.76	991.15	991.55	991.94	992.34	16800
16900	992.73	993.12	993.51	993.91	994.30	994.69	995.09	995.48	995.87	996.26	16900
17000	996.66	997.05	997.44	997.83	998.23	998.62	999.01	999.40	999.79	1000.19	17000

5.3 Valeurs thermoélectriques aux points fixes de l'EIT-90 pour les couples thermoélectriques Au/Pt (informatives)

Point fixé	$t_{90}/^{\circ}\text{C}$	$E/\mu\text{V}$	$S/(\mu\text{V}/^{\circ}\text{C})$
PT Eau	0.01	0.06	6.037
PF Gallium	29.7646	196.25	7.133
PC Indium	156.5985	1350.94	10.861
PC Etain	231.928	2236.18	12.599
PC Zinc	419.527	4945.63	16.157
PC Aluminium	660.323	9320.44	20.139
PC Argent	961.78	16120.49	24.945

6 Tableaux pour les couples thermoélectriques Platine/Palladium

6.1 Platine/Palladium: f.é.m. à intervalles de 1 °C

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
	$E/\mu\text{V}$										
0	0.0	5.3	10.6	15.9	21.3	26.6	31.9	37.3	42.7	48.0	0
10	53.4	58.8	64.2	69.6	75.0	80.5	85.9	91.3	96.8	102.2	10
20	107.7	113.2	118.7	124.2	129.7	135.2	140.7	146.2	151.7	157.3	20
30	162.8	168.4	173.9	179.5	185.1	190.7	196.3	201.9	207.5	213.1	30
40	218.7	224.3	230.0	235.6	241.3	246.9	252.6	258.3	264.0	269.7	40
50	275.4	281.1	286.8	292.5	298.2	303.9	309.7	315.4	321.2	326.9	50
60	332.7	338.5	344.3	350.1	355.9	361.7	367.5	373.3	379.1	384.9	60
70	390.8	396.6	402.5	408.3	414.2	420.1	425.9	431.8	437.7	443.6	70
80	449.5	455.4	461.3	467.3	473.2	479.1	485.1	491.0	497.0	502.9	80
90	508.9	514.9	520.9	526.9	532.9	538.9	544.9	550.9	556.9	562.9	90
100	569.0	575.0	581.1	587.1	593.2	599.3	605.3	611.4	617.5	623.6	100
110	629.7	635.8	641.9	648.1	654.2	660.3	666.5	672.6	678.8	684.9	110
120	691.1	697.3	703.5	709.7	715.9	722.1	728.3	734.5	740.7	746.9	120
130	753.2	759.4	765.7	771.9	778.2	784.5	790.7	797.0	803.3	809.6	130
140	815.9	822.2	828.6	834.9	841.2	847.6	853.9	860.3	866.6	873.0	140
150	879.4	885.8	892.2	898.6	905.0	911.4	917.8	924.2	930.7	937.1	150
160	943.6	950.0	956.5	962.9	969.4	975.9	982.4	988.9	995.4	1001.9	160
170	1008.5	1015.0	1021.5	1028.1	1034.6	1041.2	1047.8	1054.4	1060.9	1067.5	170
180	1074.1	1080.7	1087.4	1094.0	1100.6	1107.3	1113.9	1120.6	1127.2	1133.9	180
190	1140.6	1147.3	1154.0	1160.7	1167.4	1174.1	1180.9	1187.6	1194.4	1201.1	190
200	1207.9	1214.7	1221.4	1228.2	1235.0	1241.8	1248.7	1255.5	1262.3	1269.2	200
210	1276.0	1282.9	1289.7	1296.6	1303.5	1310.4	1317.3	1324.2	1331.2	1338.1	210
220	1345.0	1352.0	1358.9	1365.9	1372.9	1379.9	1386.9	1393.9	1400.9	1407.9	220
230	1415.0	1422.0	1429.1	1436.1	1443.2	1450.3	1457.4	1464.5	1471.6	1478.7	230
240	1485.9	1493.0	1500.2	1507.3	1514.5	1521.7	1528.9	1536.1	1543.3	1550.5	240
250	1557.7	1565.0	1572.2	1579.5	1586.8	1594.1	1601.4	1608.7	1616.0	1623.3	250
260	1630.7	1638.0	1645.4	1652.7	1660.1	1667.5	1674.9	1682.3	1689.7	1697.2	260
270	1704.6	1712.1	1719.6	1727.0	1734.5	1742.0	1749.5	1757.1	1764.6	1772.2	270
280	1779.7	1787.3	1794.9	1802.5	1810.1	1817.7	1825.3	1833.0	1840.6	1848.3	280
290	1856.0	1863.6	1871.3	1879.1	1886.8	1894.5	1902.3	1910.0	1917.8	1925.6	290
300	1933.4	1941.2	1949.0	1956.8	1964.7	1972.5	1980.4	1988.3	1996.2	2004.1	300
310	2012.0	2019.9	2027.9	2035.9	2043.8	2051.8	2059.8	2067.8	2075.8	2083.9	310
320	2091.9	2100.0	2108.1	2116.2	2124.3	2132.4	2140.5	2148.6	2156.8	2165.0	320
330	2173.1	2181.3	2189.5	2197.8	2206.0	2214.2	2222.5	2230.8	2239.1	2247.4	330
340	2255.7	2264.0	2272.4	2280.7	2289.1	2297.5	2305.9	2314.3	2322.7	2331.2	340
350	2339.6	2348.1	2356.6	2365.1	2373.6	2382.1	2390.7	2399.2	2407.8	2416.4	350
360	2425.0	2433.6	2442.2	2450.9	2459.5	2468.2	2476.9	2485.6	2494.3	2503.1	360
370	2511.8	2520.6	2529.3	2538.1	2546.9	2555.8	2564.6	2573.5	2582.3	2591.2	370
380	2600.1	2609.0	2617.9	2626.9	2635.8	2644.8	2653.8	2662.8	2671.8	2680.9	380
390	2689.9	2699.0	2708.1	2717.2	2726.3	2735.4	2744.6	2753.7	2762.9	2772.1	390

Platine/Palladium:
f.é.m. à intervalles de 1 °C (*suite*)

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
400	2781.3	2790.5	2799.8	2809.0	2818.3	2827.6	2836.9	2846.2	2855.6	2864.9	400
410	2874.3	2883.7	2893.1	2902.5	2911.9	2921.4	2930.8	2940.3	2949.8	2959.3	410
420	2968.9	2978.4	2988.0	2997.6	3007.2	3016.8	3026.4	3036.0	3045.7	3055.4	420
430	3065.1	3074.8	3084.5	3094.3	3104.1	3113.8	3123.6	3133.5	3143.3	3153.1	430
440	3163.0	3172.9	3182.8	3192.7	3202.6	3212.6	3222.6	3232.5	3242.6	3252.6	440
450	3262.6	3272.7	3282.7	3292.8	3302.9	3313.1	3323.2	3333.4	3343.5	3353.7	450
460	3363.9	3374.2	3384.4	3394.7	3405.0	3415.3	3425.6	3435.9	3446.3	3456.6	460
470	3467.0	3477.4	3487.9	3498.3	3508.8	3519.2	3529.7	3540.2	3550.8	3561.3	470
480	3571.9	3582.5	3593.1	3603.7	3614.3	3625.0	3635.7	3646.4	3657.1	3667.8	480
490	3678.5	3689.3	3700.1	3710.9	3721.7	3732.5	3743.4	3754.3	3765.2	3776.1	490
500	3787.0	3797.9	3808.9	3819.9	3830.9	3841.9	3853.0	3864.0	3875.1	3886.2	500
510	3897.3	3908.4	3919.6	3930.7	3941.9	3953.1	3964.3	3975.6	3986.8	3998.1	510
520	4009.4	4020.7	4032.1	4043.4	4054.8	4066.2	4077.6	4089.0	4100.5	4111.9	520
530	4123.4	4134.9	4146.4	4158.0	4169.5	4181.1	4192.7	4204.3	4215.9	4227.6	530
540	4239.3	4250.9	4262.7	4274.4	4286.1	4297.9	4309.7	4321.5	4333.3	4345.1	540
550	4357.0	4368.9	4380.8	4392.7	4404.6	4416.6	4428.5	4440.5	4452.5	4464.6	550
560	4476.6	4488.7	4500.8	4512.9	4525.0	4537.1	4549.3	4561.5	4573.7	4585.9	560
570	4598.1	4610.4	4622.7	4635.0	4647.3	4659.6	4672.0	4684.3	4696.7	4709.1	570
580	4721.6	4734.0	4746.5	4759.0	4771.5	4784.0	4796.5	4809.1	4821.7	4834.3	580
590	4846.9	4859.5	4872.2	4884.9	4897.6	4910.3	4923.0	4935.8	4948.5	4961.3	590
600	4974.1	4987.0	4999.8	5012.7	5025.6	5038.5	5051.4	5064.4	5077.3	5090.3	600
610	5103.3	5116.3	5129.4	5142.4	5155.5	5168.6	5181.7	5194.9	5208.0	5221.2	610
620	5234.4	5247.6	5260.8	5274.1	5287.4	5300.6	5314.0	5327.3	5340.6	5354.0	620
630	5367.4	5380.8	5394.2	5407.7	5421.1	5434.6	5448.1	5461.6	5475.2	5488.7	630
640	5502.3	5515.9	5529.5	5543.1	5556.8	5570.5	5584.2	5597.9	5611.6	5625.4	640
650	5639.1	5652.9	5666.7	5680.6	5694.4	5708.3	5722.1	5736.0	5750.0	5763.9	650
660	5777.9	5791.8	5805.8	5819.9	5833.9	5848.0	5862.0	5876.1	5890.2	5904.4	660
670	5918.5	5932.7	5946.9	5961.1	5975.3	5989.5	6003.8	6018.1	6032.4	6046.7	670
680	6061.1	6075.4	6089.8	6104.2	6118.6	6133.0	6147.5	6162.0	6176.4	6191.0	680
690	6205.5	6220.0	6234.6	6249.2	6263.8	6278.4	6293.1	6307.7	6322.4	6337.1	690
700	6351.8	6366.5	6381.3	6396.1	6410.9	6425.7	6440.5	6455.3	6470.2	6485.1	700
710	6500.0	6514.9	6529.9	6544.8	6559.8	6574.8	6589.8	6604.9	6619.9	6635.0	710
720	6650.1	6665.2	6680.3	6695.5	6710.6	6725.8	6741.0	6756.2	6771.5	6786.7	720
730	6802.0	6817.3	6832.6	6847.9	6863.3	6878.7	6894.0	6909.4	6924.9	6940.3	730
740	6955.8	6971.2	6986.7	7002.3	7017.8	7033.3	7048.9	7064.5	7080.1	7095.7	740
750	7111.4	7127.0	7142.7	7158.4	7174.1	7189.9	7205.6	7221.4	7237.2	7253.0	750
760	7268.8	7284.7	7300.5	7316.4	7332.3	7348.2	7364.2	7380.1	7396.1	7412.1	760
770	7428.1	7444.1	7460.1	7476.2	7492.3	7508.4	7524.5	7540.6	7556.8	7572.9	770
780	7589.1	7605.3	7621.5	7637.8	7654.0	7670.3	7686.6	7702.9	7719.3	7735.6	780
790	7752.0	7768.3	7784.7	7801.2	7817.6	7834.0	7850.5	7867.0	7883.5	7900.0	790

Platine/Palladium:
f.é.m. à intervalles de 1 °C (*suite*)

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
<i>E</i> / μV											
800	7916.6	7933.1	7949.7	7966.3	7982.9	7999.5	8016.2	8032.9	8049.5	8066.2	800
810	8082.9	8099.7	8116.4	8133.2	8150.0	8166.8	8183.6	8200.4	8217.3	8234.2	810
820	8251.1	8268.0	8284.9	8301.8	8318.8	8335.8	8352.8	8369.8	8386.8	8403.8	820
830	8420.9	8438.0	8455.1	8472.2	8489.3	8506.5	8523.6	8540.8	8558.0	8575.2	830
840	8592.5	8609.7	8627.0	8644.3	8661.6	8678.9	8696.2	8713.6	8730.9	8748.3	840
850	8765.7	8783.1	8800.6	8818.0	8835.5	8853.0	8870.5	8888.0	8905.5	8923.1	850
860	8940.7	8958.3	8975.9	8993.5	9011.1	9028.8	9046.4	9064.1	9081.8	9099.5	860
870	9117.3	9135.0	9152.8	9170.6	9188.4	9206.2	9224.0	9241.9	9259.7	9277.6	870
880	9295.5	9313.4	9331.4	9349.3	9367.3	9385.3	9403.3	9421.3	9439.3	9457.4	880
890	9475.4	9493.5	9511.6	9529.7	9547.8	9566.0	9584.1	9602.3	9620.5	9638.7	890
900	9656.9	9675.2	9693.4	9711.7	9730.0	9748.3	9766.6	9784.9	9803.3	9821.6	900
910	9840.0	9858.4	9876.8	9895.3	9913.7	9932.2	9950.7	9969.1	9987.7	10006.2	910
920	10024.7	10043.3	10061.8	10080.4	10099.0	10117.7	10136.3	10154.9	10173.6	10192.3	920
930	10211.0	10229.7	10248.4	10267.2	10285.9	10304.7	10323.5	10342.3	10361.1	10379.9	930
940	10398.8	10417.6	10436.5	10455.4	10474.3	10493.3	10512.2	10531.2	10550.1	10569.1	940
950	10588.1	10607.1	10626.2	10645.2	10664.3	10683.3	10702.4	10721.5	10740.7	10759.8	950
960	10779.0	10798.1	10817.3	10836.5	10855.7	10874.9	10894.2	10913.4	10932.7	10952.0	960
970	10971.3	10990.6	11010.0	11029.3	11048.7	11068.0	11087.4	11106.8	11126.3	11145.7	970
980	11165.1	11184.6	11204.1	11223.6	11243.1	11262.6	11282.1	11301.7	11321.3	11340.8	980
990	11360.4	11380.0	11399.7	11419.3	11439.0	11458.6	11478.3	11498.0	11517.7	11537.4	990
1000	11557.2	11576.9	11596.7	11616.5	11636.3	11656.1	11675.9	11695.7	11715.6	11735.5	1000
1010	11755.3	11775.2	11795.1	11815.1	11835.0	11855.0	11874.9	11894.9	11914.9	11934.9	1010
1020	11954.9	11975.0	11995.0	12015.1	12035.2	12055.2	12075.3	12095.5	12115.6	12135.7	1020
1030	12155.9	12176.1	12196.3	12216.5	12236.7	12256.9	12277.2	12297.4	12317.7	12338.0	1030
1040	12358.3	12378.6	12398.9	12419.3	12439.6	12460.0	12480.3	12500.7	12521.2	12541.6	1040
1050	12562.0	12582.5	12602.9	12623.4	12643.9	12664.4	12684.9	12705.4	12726.0	12746.5	1050
1060	12767.1	12787.7	12808.3	12828.9	12849.5	12870.1	12890.8	12911.4	12932.1	12952.8	1060
1070	12973.5	12994.2	13014.9	13035.7	13056.4	13077.2	13098.0	13118.8	13139.6	13160.4	1070
1080	13181.2	13202.1	13222.9	13243.8	13264.7	13285.6	13306.5	13327.4	13348.4	13369.3	1080
1090	13390.3	13411.2	13432.2	13453.2	13474.2	13495.3	13516.3	13537.4	13558.4	13579.5	1090
1100	13600.6	13621.7	13642.8	13663.9	13685.1	13706.2	13727.4	13748.6	13769.8	13791.0	1100
1110	13812.2	13833.4	13854.7	13875.9	13897.2	13918.5	13939.8	13961.1	13982.4	14003.7	1110
1120	14025.1	14046.4	14067.8	14089.2	14110.6	14132.0	14153.4	14174.8	14196.3	14217.7	1120
1130	14239.2	14260.6	14282.1	14303.6	14325.2	14346.7	14368.2	14389.8	14411.3	14432.9	1130
1140	14454.5	14476.1	14497.7	14519.3	14541.0	14562.6	14584.3	14606.0	14627.7	14649.4	1140
1150	14671.1	14692.8	14714.5	14736.3	14758.0	14779.8	14801.6	14823.4	14845.2	14867.0	1150
1160	14888.8	14910.7	14932.5	14954.4	14976.3	14998.2	15020.1	15042.0	15063.9	15085.8	1160
1170	15107.8	15129.7	15151.7	15173.7	15195.7	15217.7	15239.7	15261.8	15283.8	15305.9	1170
1180	15327.9	15350.0	15372.1	15394.2	15416.3	15438.4	15460.6	15482.7	15504.9	15527.0	1180
1190	15549.2	15571.4	15593.6	15615.8	15638.1	15660.3	15682.6	15704.8	15727.1	15749.4	1190

Platine/Palladium:
f.é.m. à intervalles de 1 °C (*suite*)

$t_{90} / ^\circ\text{C}$	0	1	2	3	4	5	6	7	8	9	$t_{90} / ^\circ\text{C}$
$E/\mu\text{V}$											
1200	15771.7	15794.0	15816.3	15838.6	15861.0	15883.3	15905.7	15928.1	15950.5	15972.9	1200
1210	15995.3	16017.7	16040.1	16062.6	16085.0	16107.5	16130.0	16152.5	16175.0	16197.5	1210
1220	16220.0	16242.5	16265.1	16287.6	16310.2	16332.8	16355.4	16378.0	16400.6	16423.2	1220
1230	16445.9	16468.5	16491.2	16513.8	16536.5	16559.2	16581.9	16604.6	16627.3	16650.1	1230
1240	16672.8	16695.6	16718.3	16741.1	16763.9	16786.7	16809.5	16832.3	16855.2	16878.0	1240
1250	16900.9	16923.7	16946.6	16969.5	16992.4	17015.3	17038.2	17061.2	17084.1	17107.0	1250
1260	17130.0	17153.0	17176.0	17199.0	17222.0	17245.0	17268.0	17291.0	17314.1	17337.2	1260
1270	17360.2	17383.3	17406.4	17429.5	17452.6	17475.7	17498.9	17522.0	17545.2	17568.3	1270
1280	17591.5	17614.7	17637.9	17661.1	17684.3	17707.6	17730.8	17754.0	17777.3	17800.6	1280
1290	17823.9	17847.1	17870.4	17893.8	17917.1	17940.4	17963.8	17987.1	18010.5	18033.9	1290
1300	18057.2	18080.6	18104.0	18127.5	18150.9	18174.3	18197.8	18221.2	18244.7	18268.2	1300
1310	18291.7	18315.2	18338.7	18362.2	18385.7	18409.3	18432.8	18456.4	18480.0	18503.5	1310
1320	18527.1	18550.7	18574.3	18598.0	18621.6	18645.2	18668.9	18692.6	18716.2	18739.9	1320
1330	18763.6	18787.3	18811.0	18834.7	18858.5	18882.2	18906.0	18929.7	18953.5	18977.3	1330
1340	19001.1	19024.9	19048.7	19072.5	19096.4	19120.2	19144.1	19167.9	19191.8	19215.7	1340
1350	19239.6	19263.5	19287.4	19311.3	19335.3	19359.2	19383.2	19407.1	19431.1	19455.1	1350
1360	19479.1	19503.1	19527.1	19551.1	19575.1	19599.2	19623.2	19647.3	19671.4	19695.5	1360
1370	19719.5	19743.6	19767.8	19791.9	19816.0	19840.1	19864.3	19888.5	19912.6	19936.8	1370
1380	19961.0	19985.2	20009.4	20033.6	20057.8	20082.1	20106.3	20130.6	20154.8	20179.1	1380
1390	20203.4	20227.7	20252.0	20276.3	20300.6	20325.0	20349.3	20373.7	20398.0	20422.4	1390
1400	20446.8	20471.2	20495.6	20520.0	20544.4	20568.8	20593.3	20617.7	20642.2	20666.6	1400
1410	20691.1	20715.6	20740.1	20764.6	20789.1	20813.6	20838.2	20862.7	20887.3	20911.8	1410
1420	20936.4	20961.0	20985.6	21010.2	21034.8	21059.4	21084.0	21108.6	21133.3	21157.9	1420
1430	21182.6	21207.3	21232.0	21256.7	21281.4	21306.1	21330.8	21355.5	21380.2	21405.0	1430
1440	21429.7	21454.5	21479.3	21504.1	21528.9	21553.7	21578.5	21603.3	21628.1	21653.0	1440
1450	21677.8	21702.7	21727.5	21752.4	21777.3	21802.2	21827.1	21852.0	21876.9	21901.8	1450
1460	21926.8	21951.7	21976.7	22001.7	22026.6	22051.6	22076.6	22101.6	22126.6	22151.6	1460
1470	22176.7	22201.7	22226.8	22251.8	22276.9	22301.9	22327.0	22352.1	22377.2	22402.3	1470
1480	22427.4	22452.6	22477.7	22502.9	22528.0	22553.2	22578.3	22603.5	22628.7	22653.9	1480
1490	22679.1	22704.3	22729.6	22754.8	22780.0	22805.3	22830.5	22855.8	22881.1	22906.4	1490
1500	22931.7										1500

6.2 Platine/Palladium: Température à intervalles de 10 μV

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
						$t_{90}/^{\circ}\text{C}$					
0	0.00	1.88	3.76	5.63	7.50	9.36	11.22	13.07	14.91	16.75	0
100	18.59	20.42	22.24	24.06	25.87	27.68	29.49	31.29	33.09	34.88	100
200	36.67	38.45	40.23	42.00	43.77	45.54	47.30	49.06	50.82	52.57	200
300	54.31	56.06	57.80	59.53	61.26	62.99	64.72	66.44	68.16	69.87	300
400	71.58	73.29	74.99	76.69	78.39	80.09	81.78	83.46	85.15	86.83	400
500	88.51	90.18	91.86	93.52	95.19	96.85	98.51	100.17	101.82	103.47	500
600	105.12	106.77	108.41	110.05	111.68	113.32	114.95	116.57	118.20	119.82	600
700	121.44	123.06	124.67	126.28	127.89	129.49	131.09	132.69	134.29	135.88	700
800	137.47	139.06	140.64	142.23	143.81	145.38	146.96	148.53	150.10	151.66	800
900	153.22	154.78	156.34	157.90	159.45	161.00	162.54	164.09	165.63	167.17	900
1000	168.70	170.23	171.76	173.29	174.82	176.34	177.86	179.37	180.89	182.40	1000
1100	183.91	185.41	186.91	188.41	189.91	191.40	192.90	194.38	195.87	197.35	1100
1200	198.83	200.31	201.79	203.26	204.73	206.20	207.66	209.12	210.58	212.04	1200
1300	213.49	214.94	216.39	217.83	219.28	220.71	222.15	223.59	225.02	226.45	1300
1400	227.87	229.29	230.71	232.13	233.55	234.96	236.37	237.77	239.18	240.58	1400
1500	241.98	243.37	244.77	246.16	247.55	248.93	250.31	251.69	253.07	254.44	1500
1600	255.81	257.18	258.55	259.91	261.27	262.63	263.99	265.34	266.69	268.03	1600
1700	269.38	270.72	272.06	273.40	274.73	276.06	277.39	278.71	280.04	281.36	1700
1800	282.68	283.99	285.30	286.61	287.92	289.23	290.53	291.83	293.12	294.42	1800
1900	295.71	297.00	298.28	299.57	300.85	302.13	303.40	304.68	305.95	307.22	1900
2000	308.48	309.75	311.01	312.26	313.52	314.77	316.02	317.27	318.52	319.76	2000
2100	321.00	322.24	323.48	324.71	325.94	327.17	328.39	329.62	330.84	332.06	2100
2200	333.27	334.48	335.70	336.90	338.11	339.31	340.52	341.72	342.91	344.11	2200
2300	345.30	346.49	347.68	348.86	350.04	351.22	352.40	353.58	354.75	355.92	2300
2400	357.09	358.26	359.42	360.58	361.74	362.90	364.05	365.21	366.36	367.50	2400
2500	368.65	369.79	370.93	372.07	373.21	374.35	375.48	376.61	377.74	378.86	2500
2600	379.99	381.11	382.23	383.35	384.46	385.58	386.69	387.80	388.90	390.01	2600
2700	391.11	392.21	393.31	394.41	395.50	396.59	397.68	398.77	399.86	400.94	2700
2800	402.02	403.10	404.18	405.26	406.33	407.41	408.48	409.54	410.61	411.67	2800
2900	412.74	413.80	414.86	415.91	416.97	418.02	419.07	420.12	421.17	422.21	2900
3000	423.25	424.30	425.34	426.37	427.41	428.44	429.48	430.51	431.53	432.56	3000
3100	433.59	434.61	435.63	436.65	437.67	438.68	439.70	440.71	441.72	442.73	3100
3200	443.73	444.74	445.74	446.75	447.75	448.74	449.74	450.74	451.73	452.72	3200
3300	453.71	454.70	455.68	456.67	457.65	458.63	459.61	460.59	461.57	462.54	3300
3400	463.52	464.49	465.46	466.43	467.39	468.36	469.32	470.29	471.25	472.21	3400
3500	473.16	474.12	475.07	476.03	476.98	477.93	478.87	479.82	480.77	481.71	3500
3600	482.65	483.59	484.53	485.47	486.41	487.34	488.27	489.21	490.14	491.06	3600
3700	491.99	492.92	493.84	494.77	495.69	496.61	497.53	498.44	499.36	500.27	3700
3800	501.19	502.10	503.01	503.92	504.83	505.73	506.64	507.54	508.44	509.34	3800
3900	510.24	511.14	512.04	512.93	513.83	514.72	515.61	516.50	517.39	518.28	3900

Platine/Palladium:
Température à intervalles de 10 μV (*suite*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
4000	519.17	520.05	520.93	521.82	522.70	523.58	524.46	525.33	526.21	527.09	4000
4100	527.96	528.83	529.70	530.57	531.44	532.31	533.18	534.04	534.90	535.77	4100
4200	536.63	537.49	538.35	539.21	540.06	540.92	541.77	542.63	543.48	544.33	4200
4300	545.18	546.03	546.87	547.72	548.57	549.41	550.25	551.09	551.93	552.77	4300
4400	553.61	554.45	555.29	556.12	556.95	557.79	558.62	559.45	560.28	561.11	4400
4500	561.94	562.76	563.59	564.41	565.23	566.06	566.88	567.70	568.52	569.33	4500
4600	570.15	570.97	571.78	572.60	573.41	574.22	575.03	575.84	576.65	577.46	4600
4700	578.26	579.07	579.87	580.68	581.48	582.28	583.08	583.88	584.68	585.48	4700
4800	586.28	587.07	587.87	588.66	589.45	590.25	591.04	591.83	592.62	593.41	4800
4900	594.19	594.98	595.76	596.55	597.33	598.12	598.90	599.68	600.46	601.24	4900
5000	602.01	602.79	603.57	604.34	605.12	605.89	606.66	607.44	608.21	608.98	5000
5100	609.75	610.52	611.28	612.05	612.82	613.58	614.34	615.11	615.87	616.63	5100
5200	617.39	618.15	618.91	619.67	620.43	621.18	621.94	622.69	623.45	624.20	5200
5300	624.95	625.70	626.45	627.20	627.95	628.70	629.45	630.20	630.94	631.69	5300
5400	632.43	633.17	633.92	634.66	635.40	636.14	636.88	637.62	638.36	639.09	5400
5500	639.83	640.57	641.30	642.03	642.77	643.50	644.23	644.96	645.69	646.42	5500
5600	647.15	647.88	648.61	649.34	650.06	650.79	651.51	652.24	652.96	653.68	5600
5700	654.40	655.12	655.84	656.56	657.28	658.00	658.72	659.43	660.15	660.87	5700
5800	661.58	662.30	663.01	663.72	664.43	665.15	665.86	666.57	667.27	667.98	5800
5900	668.69	669.40	670.10	670.81	671.51	672.22	672.92	673.63	674.33	675.03	5900
6000	675.73	676.43	677.13	677.83	678.53	679.23	679.92	680.62	681.32	682.01	6000
6100	682.71	683.40	684.09	684.79	685.48	686.17	686.86	687.55	688.24	688.93	6100
6200	689.62	690.31	690.99	691.68	692.37	693.05	693.74	694.42	695.11	695.79	6200
6300	696.47	697.15	697.83	698.52	699.20	699.87	700.55	701.23	701.91	702.59	6300
6400	703.26	703.94	704.61	705.29	705.96	706.64	707.31	707.98	708.66	709.33	6400
6500	710.00	710.67	711.34	712.01	712.68	713.34	714.01	714.68	715.34	716.01	6500
6600	716.68	717.34	718.00	718.67	719.33	719.99	720.66	721.32	721.98	722.64	6600
6700	723.30	723.96	724.62	725.28	725.93	726.59	727.25	727.90	728.56	729.21	6700
6800	729.87	730.52	731.18	731.83	732.48	733.13	733.79	734.44	735.09	735.74	6800
6900	736.39	737.04	737.68	738.33	738.98	739.63	740.27	740.92	741.57	742.21	6900
7000	742.85	743.50	744.14	744.79	745.43	746.07	746.71	747.35	747.99	748.63	7000
7100	749.27	749.91	750.55	751.19	751.83	752.46	753.10	753.74	754.37	755.01	7100
7200	755.64	756.28	756.91	757.55	758.18	758.81	759.44	760.08	760.71	761.34	7200
7300	761.97	762.60	763.23	763.86	764.49	765.11	765.74	766.37	767.00	767.62	7300
7400	768.25	768.87	769.50	770.12	770.75	771.37	771.99	772.62	773.24	773.86	7400
7500	774.48	775.10	775.72	776.34	776.96	777.58	778.20	778.82	779.44	780.06	7500
7600	780.67	781.29	781.91	782.52	783.14	783.75	784.37	784.98	785.60	786.21	7600
7700	786.82	787.44	788.05	788.66	789.27	789.88	790.49	791.10	791.71	792.32	7700
7800	792.93	793.54	794.15	794.76	795.36	795.97	796.58	797.18	797.79	798.39	7800
7900	799.00	799.60	800.21	800.81	801.42	802.02	802.62	803.22	803.83	804.43	7900

Platine/Palladium:
Température à intervalles de 10 μV (*suite*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
8000	805.03	805.63	806.23	806.83	807.43	808.03	808.63	809.23	809.83	810.42	8000
8100	811.02	811.62	812.21	812.81	813.41	814.00	814.60	815.19	815.79	816.38	8100
8200	816.98	817.57	818.16	818.75	819.35	819.94	820.53	821.12	821.71	822.30	8200
8300	822.89	823.48	824.07	824.66	825.25	825.84	826.43	827.01	827.60	828.19	8300
8400	828.78	829.36	829.95	830.53	831.12	831.70	832.29	832.87	833.46	834.04	8400
8500	834.62	835.21	835.79	836.37	836.95	837.53	838.12	838.70	839.28	839.86	8500
8600	840.44	841.02	841.60	842.17	842.75	843.33	843.91	844.49	845.06	845.64	8600
8700	846.22	846.79	847.37	847.95	848.52	849.10	849.67	850.25	850.82	851.39	8700
8800	851.97	852.54	853.11	853.68	854.26	854.83	855.40	855.97	856.54	857.11	8800
8900	857.68	858.25	858.82	859.39	859.96	860.53	861.10	861.67	862.23	862.80	8900
9000	863.37	863.94	864.50	865.07	865.64	866.20	866.77	867.33	867.90	868.46	9000
9100	869.03	869.59	870.15	870.72	871.28	871.84	872.40	872.97	873.53	874.09	9100
9200	874.65	875.21	875.77	876.33	876.89	877.45	878.01	878.57	879.13	879.69	9200
9300	880.25	880.81	881.36	881.92	882.48	883.04	883.59	884.15	884.71	885.26	9300
9400	885.82	886.37	886.93	887.48	888.04	888.59	889.14	889.70	890.25	890.81	9400
9500	891.36	891.91	892.46	893.01	893.57	894.12	894.67	895.22	895.77	896.32	9500
9600	896.87	897.42	897.97	898.52	899.07	899.62	900.17	900.72	901.26	901.81	9600
9700	902.36	902.91	903.45	904.00	904.55	905.09	905.64	906.18	906.73	907.27	9700
9800	907.82	908.36	908.91	909.45	910.00	910.54	911.08	911.63	912.17	912.71	9800
9900	913.25	913.80	914.34	914.88	915.42	915.96	916.50	917.04	917.58	918.12	9900
10000	918.66	919.20	919.74	920.28	920.82	921.36	921.90	922.44	922.98	923.51	10000
10100	924.05	924.59	925.12	925.66	926.20	926.73	927.27	927.81	928.34	928.88	10100
10200	929.41	929.95	930.48	931.02	931.55	932.08	932.62	933.15	933.68	934.22	10200
10300	934.75	935.28	935.81	936.35	936.88	937.41	937.94	938.47	939.00	939.53	10300
10400	940.06	940.59	941.12	941.65	942.18	942.71	943.24	943.77	944.30	944.83	10400
10500	945.35	945.88	946.41	946.94	947.47	947.99	948.52	949.05	949.57	950.10	10500
10600	950.62	951.15	951.68	952.20	952.73	953.25	953.77	954.30	954.82	955.35	10600
10700	955.87	956.39	956.92	957.44	957.96	958.49	959.01	959.53	960.05	960.58	10700
10800	961.10	961.62	962.14	962.66	963.18	963.70	964.22	964.74	965.26	965.78	10800
10900	966.30	966.82	967.34	967.86	968.38	968.90	969.41	969.93	970.45	970.97	10900
11000	971.48	972.00	972.52	973.04	973.55	974.07	974.58	975.10	975.62	976.13	11000
11100	976.65	977.16	977.68	978.19	978.71	979.22	979.74	980.25	980.76	981.28	11100
11200	981.79	982.30	982.82	983.33	983.84	984.35	984.87	985.38	985.89	986.40	11200
11300	986.91	987.43	987.94	988.45	988.96	989.47	989.98	990.49	991.00	991.51	11300
11400	992.02	992.53	993.04	993.54	994.05	994.56	995.07	995.58	996.09	996.59	11400
11500	997.10	997.61	998.12	998.62	999.13	999.64	1000.14	1000.65	1001.16	1001.66	11500
11600	1002.17	1002.67	1003.18	1003.68	1004.19	1004.69	1005.20	1005.70	1006.21	1006.71	11600
11700	1007.22	1007.72	1008.22	1008.73	1009.23	1009.73	1010.24	1010.74	1011.24	1011.74	11700
11800	1012.24	1012.75	1013.25	1013.75	1014.25	1014.75	1015.25	1015.75	1016.26	1016.76	11800
11900	1017.26	1017.76	1018.26	1018.76	1019.26	1019.76	1020.25	1020.75	1021.25	1021.75	11900

Platine/Palladium:
Température à intervalles de 10 μV (*suite*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
12000	1022.25	1022.75	1023.25	1023.74	1024.24	1024.74	1025.24	1025.74	1026.23	1026.73	12000
12100	1027.23	1027.72	1028.22	1028.72	1029.21	1029.71	1030.20	1030.70	1031.20	1031.69	12100
12200	1032.19	1032.68	1033.18	1033.67	1034.17	1034.66	1035.15	1035.65	1036.14	1036.64	12200
12300	1037.13	1037.62	1038.12	1038.61	1039.10	1039.59	1040.09	1040.58	1041.07	1041.56	12300
12400	1042.06	1042.55	1043.04	1043.53	1044.02	1044.51	1045.00	1045.49	1045.98	1046.47	12400
12500	1046.97	1047.46	1047.95	1048.44	1048.92	1049.41	1049.90	1050.39	1050.88	1051.37	12500
12600	1051.86	1052.35	1052.84	1053.32	1053.81	1054.30	1054.79	1055.28	1055.76	1056.25	12600
12700	1056.74	1057.22	1057.71	1058.20	1058.68	1059.17	1059.66	1060.14	1060.63	1061.11	12700
12800	1061.60	1062.09	1062.57	1063.06	1063.54	1064.03	1064.51	1065.00	1065.48	1065.96	12800
12900	1066.45	1066.93	1067.42	1067.90	1068.38	1068.87	1069.35	1069.83	1070.32	1070.80	12900
13000	1071.28	1071.76	1072.25	1072.73	1073.21	1073.69	1074.17	1074.65	1075.14	1075.62	13000
13100	1076.10	1076.58	1077.06	1077.54	1078.02	1078.50	1078.98	1079.46	1079.94	1080.42	13100
13200	1080.90	1081.38	1081.86	1082.34	1082.82	1083.30	1083.78	1084.26	1084.73	1085.21	13200
13300	1085.69	1086.17	1086.65	1087.12	1087.60	1088.08	1088.56	1089.03	1089.51	1089.99	13300
13400	1090.46	1090.94	1091.42	1091.89	1092.37	1092.85	1093.32	1093.80	1094.27	1094.75	13400
13500	1095.23	1095.70	1096.18	1096.65	1097.13	1097.60	1098.08	1098.55	1099.02	1099.50	13500
13600	1099.97	1100.45	1100.92	1101.39	1101.87	1102.34	1102.81	1103.29	1103.76	1104.23	13600
13700	1104.71	1105.18	1105.65	1106.12	1106.60	1107.07	1107.54	1108.01	1108.48	1108.95	13700
13800	1109.43	1109.90	1110.37	1110.84	1111.31	1111.78	1112.25	1112.72	1113.19	1113.66	13800
13900	1114.13	1114.60	1115.07	1115.54	1116.01	1116.48	1116.95	1117.42	1117.89	1118.36	13900
14000	1118.83	1119.29	1119.76	1120.23	1120.70	1121.17	1121.64	1122.10	1122.57	1123.04	14000
14100	1123.51	1123.97	1124.44	1124.91	1125.38	1125.84	1126.31	1126.78	1127.24	1127.71	14100
14200	1128.17	1128.64	1129.11	1129.57	1130.04	1130.50	1130.97	1131.43	1131.90	1132.37	14200
14300	1132.83	1133.30	1133.76	1134.22	1134.69	1135.15	1135.62	1136.08	1136.55	1137.01	14300
14400	1137.47	1137.94	1138.40	1138.86	1139.33	1139.79	1140.25	1140.72	1141.18	1141.64	14400
14500	1142.10	1142.57	1143.03	1143.49	1143.95	1144.42	1144.88	1145.34	1145.80	1146.26	14500
14600	1146.72	1147.18	1147.65	1148.11	1148.57	1149.03	1149.49	1149.95	1150.41	1150.87	14600
14700	1151.33	1151.79	1152.25	1152.71	1153.17	1153.63	1154.09	1154.55	1155.01	1155.47	14700
14800	1155.93	1156.39	1156.84	1157.30	1157.76	1158.22	1158.68	1159.14	1159.59	1160.05	14800
14900	1160.51	1160.97	1161.43	1161.88	1162.34	1162.80	1163.26	1163.71	1164.17	1164.63	14900
15000	1165.08	1165.54	1166.00	1166.45	1166.91	1167.36	1167.82	1168.28	1168.73	1169.19	15000
15100	1169.64	1170.10	1170.55	1171.01	1171.47	1171.92	1172.38	1172.83	1173.28	1173.74	15100
15200	1174.19	1174.65	1175.10	1175.56	1176.01	1176.46	1176.92	1177.37	1177.83	1178.28	15200
15300	1178.73	1179.19	1179.64	1180.09	1180.55	1181.00	1181.45	1181.90	1182.36	1182.81	15300
15400	1183.26	1183.71	1184.17	1184.62	1185.07	1185.52	1185.97	1186.42	1186.88	1187.33	15400
15500	1187.78	1188.23	1188.68	1189.13	1189.58	1190.03	1190.48	1190.93	1191.39	1191.84	15500
15600	1192.29	1192.74	1193.19	1193.64	1194.09	1194.54	1194.98	1195.43	1195.88	1196.33	15600
15700	1196.78	1197.23	1197.68	1198.13	1198.58	1199.03	1199.47	1199.92	1200.37	1200.82	15700
15800	1201.27	1201.72	1202.16	1202.61	1203.06	1203.51	1203.95	1204.40	1204.85	1205.30	15800
15900	1205.74	1206.19	1206.64	1207.08	1207.53	1207.98	1208.42	1208.87	1209.32	1209.76	15900

Platine/Palladium:
Température à intervalles de 10 μ V (*suite*)

E/μ V	0	10	20	30	40	50	60	70	80	90	E/μ V
$t_{90} / ^\circ\text{C}$											
16000	1210.21	1210.66	1211.10	1211.55	1211.99	1212.44	1212.88	1213.33	1213.77	1214.22	16000
16100	1214.67	1215.11	1215.56	1216.00	1216.44	1216.89	1217.33	1217.78	1218.22	1218.67	16100
16200	1219.11	1219.55	1220.00	1220.44	1220.89	1221.33	1221.77	1222.22	1222.66	1223.10	16200
16300	1223.55	1223.99	1224.43	1224.88	1225.32	1225.76	1226.20	1226.65	1227.09	1227.53	16300
16400	1227.97	1228.41	1228.86	1229.30	1229.74	1230.18	1230.62	1231.07	1231.51	1231.95	16400
16500	1232.39	1232.83	1233.27	1233.71	1234.15	1234.59	1235.03	1235.48	1235.92	1236.36	16500
16600	1236.80	1237.24	1237.68	1238.12	1238.56	1239.00	1239.44	1239.88	1240.32	1240.75	16600
16700	1241.19	1241.63	1242.07	1242.51	1242.95	1243.39	1243.83	1244.27	1244.71	1245.14	16700
16800	1245.58	1246.02	1246.46	1246.90	1247.34	1247.77	1248.21	1248.65	1249.09	1249.52	16800
16900	1249.96	1250.40	1250.84	1251.27	1251.71	1252.15	1252.59	1253.02	1253.46	1253.90	16900
17000	1254.33	1254.77	1255.21	1255.64	1256.08	1256.51	1256.95	1257.39	1257.82	1258.26	17000
17100	1258.69	1259.13	1259.56	1260.00	1260.44	1260.87	1261.31	1261.74	1262.18	1262.61	17100
17200	1263.05	1263.48	1263.91	1264.35	1264.78	1265.22	1265.65	1266.09	1266.52	1266.96	17200
17300	1267.39	1267.82	1268.26	1268.69	1269.12	1269.56	1269.99	1270.42	1270.86	1271.29	17300
17400	1271.72	1272.16	1272.59	1273.02	1273.46	1273.89	1274.32	1274.75	1275.19	1275.62	17400
17500	1276.05	1276.48	1276.91	1277.35	1277.78	1278.21	1278.64	1279.07	1279.50	1279.94	17500
17600	1280.37	1280.80	1281.23	1281.66	1282.09	1282.52	1282.95	1283.38	1283.81	1284.25	17600
17700	1284.68	1285.11	1285.54	1285.97	1286.40	1286.83	1287.26	1287.69	1288.12	1288.55	17700
17800	1288.98	1289.41	1289.84	1290.27	1290.69	1291.12	1291.55	1291.98	1292.41	1292.84	17800
17900	1293.27	1293.70	1294.13	1294.55	1294.98	1295.41	1295.84	1296.27	1296.70	1297.12	17900
18000	1297.55	1297.98	1298.41	1298.84	1299.26	1299.69	1300.12	1300.55	1300.97	1301.40	18000
18100	1301.83	1302.26	1302.68	1303.11	1303.54	1303.96	1304.39	1304.82	1305.24	1305.67	18100
18200	1306.10	1306.52	1306.95	1307.37	1307.80	1308.23	1308.65	1309.08	1309.50	1309.93	18200
18300	1310.36	1310.78	1311.21	1311.63	1312.06	1312.48	1312.91	1313.33	1313.76	1314.18	18300
18400	1314.61	1315.03	1315.46	1315.88	1316.31	1316.73	1317.15	1317.58	1318.00	1318.43	18400
18500	1318.85	1319.28	1319.70	1320.12	1320.55	1320.97	1321.39	1321.82	1322.24	1322.66	18500
18600	1323.09	1323.51	1323.93	1324.36	1324.78	1325.20	1325.63	1326.05	1326.47	1326.89	18600
18700	1327.32	1327.74	1328.16	1328.58	1329.00	1329.43	1329.85	1330.27	1330.69	1331.11	18700
18800	1331.54	1331.96	1332.38	1332.80	1333.22	1333.64	1334.07	1334.49	1334.91	1335.33	18800
18900	1335.75	1336.17	1336.59	1337.01	1337.43	1337.85	1338.27	1338.69	1339.11	1339.53	18900
19000	1339.96	1340.38	1340.80	1341.22	1341.64	1342.05	1342.47	1342.89	1343.31	1343.73	19000
19100	1344.15	1344.57	1344.99	1345.41	1345.83	1346.25	1346.67	1347.09	1347.51	1347.93	19100
19200	1348.34	1348.76	1349.18	1349.60	1350.02	1350.44	1350.85	1351.27	1351.69	1352.11	19200
19300	1352.53	1352.95	1353.36	1353.78	1354.20	1354.62	1355.03	1355.45	1355.87	1356.29	19300
19400	1356.70	1357.12	1357.54	1357.95	1358.37	1358.79	1359.21	1359.62	1360.04	1360.46	19400
19500	1360.87	1361.29	1361.71	1362.12	1362.54	1362.95	1363.37	1363.79	1364.20	1364.62	19500
19600	1365.03	1365.45	1365.87	1366.28	1366.70	1367.11	1367.53	1367.94	1368.36	1368.77	19600
19700	1369.19	1369.60	1370.02	1370.43	1370.85	1371.26	1371.68	1372.09	1372.51	1372.92	19700
19800	1373.34	1373.75	1374.17	1374.58	1374.99	1375.41	1375.82	1376.24	1376.65	1377.06	19800
19900	1377.48	1377.89	1378.30	1378.72	1379.13	1379.55	1379.96	1380.37	1380.78	1381.20	19900

Platine/Palladium:
Température à intervalles de 10 μV (*suite*)

$E/\mu\text{V}$	0	10	20	30	40	50	60	70	80	90	$E/\mu\text{V}$
$t_{90} / ^\circ\text{C}$											
20000	1381.61	1382.02	1382.44	1382.85	1383.26	1383.68	1384.09	1384.50	1384.91	1385.33	20000
20100	1385.74	1386.15	1386.56	1386.98	1387.39	1387.80	1388.21	1388.62	1389.04	1389.45	20100
20200	1389.86	1390.27	1390.68	1391.09	1391.50	1391.92	1392.33	1392.74	1393.15	1393.56	20200
20300	1393.97	1394.38	1394.79	1395.21	1395.62	1396.03	1396.44	1396.85	1397.26	1397.67	20300
20400	1398.08	1398.49	1398.90	1399.31	1399.72	1400.13	1400.54	1400.95	1401.36	1401.77	20400
20500	1402.18	1402.59	1403.00	1403.41	1403.82	1404.23	1404.64	1405.05	1405.46	1405.86	20500
20600	1406.27	1406.68	1407.09	1407.50	1407.91	1408.32	1408.73	1409.14	1409.54	1409.95	20600
20700	1410.36	1410.77	1411.18	1411.59	1411.99	1412.40	1412.81	1413.22	1413.63	1414.03	20700
20800	1414.44	1414.85	1415.26	1415.67	1416.07	1416.48	1416.89	1417.30	1417.70	1418.11	20800
20900	1418.52	1418.92	1419.33	1419.74	1420.15	1420.55	1420.96	1421.37	1421.77	1422.18	20900
21000	1422.59	1422.99	1423.40	1423.80	1424.21	1424.62	1425.02	1425.43	1425.84	1426.24	21000
21100	1426.65	1427.05	1427.46	1427.87	1428.27	1428.68	1429.08	1429.49	1429.89	1430.30	21100
21200	1430.70	1431.11	1431.51	1431.92	1432.32	1432.73	1433.13	1433.54	1433.94	1434.35	21200
21300	1434.75	1435.16	1435.56	1435.97	1436.37	1436.78	1437.18	1437.58	1437.99	1438.39	21300
21400	1438.80	1439.20	1439.61	1440.01	1440.41	1440.82	1441.22	1441.62	1442.03	1442.43	21400
21500	1442.84	1443.24	1443.64	1444.05	1444.45	1444.85	1445.25	1445.66	1446.06	1446.46	21500
21600	1446.87	1447.27	1447.67	1448.08	1448.48	1448.88	1449.28	1449.69	1450.09	1450.49	21600
21700	1450.89	1451.29	1451.70	1452.10	1452.50	1452.90	1453.31	1453.71	1454.11	1454.51	21700
21800	1454.91	1455.31	1455.72	1456.12	1456.52	1456.92	1457.32	1457.72	1458.12	1458.53	21800
21900	1458.93	1459.33	1459.73	1460.13	1460.53	1460.93	1461.33	1461.73	1462.13	1462.53	21900
22000	1462.93	1463.34	1463.74	1464.14	1464.54	1464.94	1465.34	1465.74	1466.14	1466.54	22000
22100	1466.94	1467.34	1467.74	1468.14	1468.54	1468.94	1469.34	1469.74	1470.13	1470.53	22100
22200	1470.93	1471.33	1471.73	1472.13	1472.53	1472.93	1473.33	1473.73	1474.13	1474.53	22200
22300	1474.92	1475.32	1475.72	1476.12	1476.52	1476.92	1477.32	1477.71	1478.11	1478.51	22300
22400	1478.91	1479.31	1479.71	1480.10	1480.50	1480.90	1481.30	1481.70	1482.09	1482.49	22400
22500	1482.89	1483.29	1483.68	1484.08	1484.48	1484.88	1485.27	1485.67	1486.07	1486.47	22500
22600	1486.86	1487.26	1487.66	1488.05	1488.45	1488.85	1489.24	1489.64	1490.04	1490.43	22600
22700	1490.83	1491.23	1491.62	1492.02	1492.42	1492.81	1493.21	1493.60	1494.00	1494.40	22700
22800	1494.79	1495.19	1495.58	1495.98	1496.38	1496.77	1497.17	1497.56	1497.96	1498.35	22800
22900	1498.75	1499.14	1499.54	1499.93	1500.33						22900

6.3 Valeurs thermoélectriques aux points fixes de l'EIT-90 pour les couples thermoélectriques Pt/Pd (informatives)

Point fixé	$t_{90} / ^\circ\text{C}$	$E/\mu\text{V}$	$S/(\mu\text{V}/^\circ\text{C})$
PT Eau	0.01	0.05	5.297
PF Gallium	29.7646	161.52	5.549
PC Indium	156.5985	921.65	6.429
PC Etain	231.928	1428.56	7.059
PC Zinc	419.527	2964.35	9.533
PC Aluminium	660.323	5782.38	13.975
PC Argent	961.78	10813.09	19.187
PC Or	1064.18	12853.21	20.631
PC Cuivre	1084.62	13277.65	20.899

Annexe A

Coefficients Or / Platine

A.1 (Article normatif) Coefficients pour la fonction de référence pour les couples thermoélectriques Au/Pt

La forme de la fonction pour le domaine de températures 0 °C à 1 000 °C est:

$$E / \mu V = \sum_{i=0}^9 a_i (t_{90} / ^\circ C)^i$$

La fonction donne la f.é.m., $E/\mu V$, en microvolts comme fonction de la température, t_{90} , dans le domaine de températures établi.

Domaine de température	0 °C à 1 000 °C
Domaine de f.é.m.	0 μV à 17085.3 μV
$a_0 =$	0.000 000 00
$a_1 =$	6.036 198 61
$a_2 =$	1.936 729 74E-02
$a_3 =$	-2.229 986 14E-05
$a_4 =$	3.287 118 59E-08
$a_5 =$	-4.242 061 93E-11
$a_6 =$	4.569 270 38E-14
$a_7 =$	-3.394 302 59E-17
$a_8 =$	1.429 815 90E-20
$a_9 =$	-2.516 727 87E-24

A.2 (Article informatif) Coefficients pour la fonction inverse approchée pour les couples thermoélectriques Au/Pt

La forme de la fonction inverse pour le domaine de températures 0 °C à 209 °C est:

$$t_{90} / ^\circ\text{C} = \sum_{i=0}^8 b_i (E / \mu\text{V})^i$$

La forme de la fonction inverse pour le domaine de températures 209 °C à 1 000 °C est:

$$t_{90} / ^\circ\text{C} = \sum_{i=0}^{11} b_i ((E / \mu\text{V} - 9645) / 7620)^i$$

La fonction est utilisée pour calculer les valeurs approchées de la température t_{90} , en degrés Celsius comme fonction de la f.é.m., $E/\mu\text{V}$, en microvolts dans les domaines de températures définis.

Domaine de température	0 °C à 209 °C	209 °C à 1 000 °C
Domaine de f.é.m.	0 μV à 1953 μV	1953 μV à 17085 μV
$b_0 =$	0.000 000	6.763 360E+02
$b_1 =$	1.654 390 3E–01	3.735 504E+02
$b_2 =$	–8.409 883 5E–05	–5.537 363E+01
$b_3 =$	8.416 613 2E–08	1.701 900E+01
$b_4 =$	–7.517 469 1E–11	–6.098 761E+00
$b_5 =$	4.849 553 6E–14	2.457 162E+00
$b_6 =$	–2.013 876 0E–17	–3.385 575E+00
$b_7 =$	4.747 562 6E–21	3.853 735E+00
$b_8 =$	–4.797 308 2E–25	1.178 891E+00
$b_9 =$		–2.702 558E+00
$b_{10} =$		–1.686 158E+00
$b_{11} =$		1.876 968E+00
Etendue de l'erreur	–5 mK à 3 mK	–2 mK à 2 mK

Annexe B

Coefficients Platine/Palladium

B.1 (Article normatif) Coefficients pour la fonction de référence des couples thermoélectriques Pt/Pd

Pour les deux domaines de températures, la forme de la fonction est:

$$E / \mu\text{V} = \sum_{i=0}^n a_i (t_{90} / ^\circ\text{C})^i$$

La tension donne la f.é.m., $E / \mu\text{V}$, en microvolts en fonction de la température, t_{90} , en degrés Celsius pour les domaines de températures établis.

Domaine de température	0 °C à 660.323 °C	660.323 °C à 1 500 °C
Domaine de f.é.m.	0 μV à 5782.4 μV	5782.4 μV à 22 932 μV
$a_0 =$	0.000 000	−4.977 137 0E+02
$a_1 =$	5.296 958	1.018 254 5E+01
$a_2 =$	4.610 494E−03	−1.579 351 5E−02
$a_3 =$	−9.602 271E−06	3.636 170 0E−05
$a_4 =$	2.992 243E−08	−2.690 150 9E−08
$a_5 =$	−2.012 523E−11	9.562 736 6E−12
$a_6 =$	−1.268 514E−14	−1.357 073 7E−15
$a_7 =$	2.257 823E−17	
$a_8 =$	−8.510 068E−21	

B.2 (Article informatif) Coefficients d'une fonction inverse approchée pour les couples thermoélectriques Pt/Pd

La forme de la fonction inverse pour les domaines de températures 0 °C à 660,323 °C et 660,323 °C à 1 500 °C est:

$$t_{90} / ^\circ\text{C} = \sum_{i=0}^n b_i (E / \mu\text{V})^i$$

La fonction donne la température t_{90} , en degrés Celsius en fonction de la f.é.m., $E/\mu\text{V}$, en microvolts dans les domaines établis.

Domaine de température	0 °C à 660.323 °C	660.323 °C à 1 500 °C
Domaine de f.é.m.	0 μV à 5782.4 μV	5782.4 μV à 22 932 μV
$b_0 =$	1.128 648 1E-03	1.681 398 72E+01
$b_1 =$	1.886 785 0E-01	1.831 741 63E-01
$b_2 =$	-3.001 252 1E-05	-2.091 790 74E-05
$b_3 =$	1.846 873 7E-08	2.142 812 41E-09
$b_4 =$	-1.249 860 8E-11	-1.518 770 21E-13
$b_5 =$	5.241 650 9E-15	7.212 177 60E-18
$b_6 =$	-1.391 528 6E-18	-2.185 981 64E-22
$b_7 =$	2.387 290 8E-22	3.815 100 60E-27
$b_8 =$	-2.580 243 6E-26	-2.912 944 07E-32
$b_9 =$	1.601 881 9E-30	
$b_{10} =$	-4.360 816 6E-35	
Etendue de l'erreur	-3 mK à 2 mK	-2.7 mK à 2.0 mK

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

3, rue de Varembé
PO Box 131
CH-1211 Geneva 20
Switzerland

Tel: + 41 22 919 02 11
Fax: + 41 22 919 03 00
info@iec.ch
www.iec.ch