



## Textiles — Tests for colour fastness —

### Part G02:

### Colour fastness to burnt-gas fumes

#### TECHNICAL CORRIGENDUM 1

*Textiles — Essais de solidité des teintures —*

*Partie G02: Solidité des teintures aux fumées de gaz brûlés*

*RECTIFICATIF TECHNIQUE 1*

Technical corrigendum 1 to International Standard ISO 105-G02:1993 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

---

Page 2

#### Subclause 4.6

Replace the existing text with the following:

**4.6 Urea**, solution containing, per litre, 10 g of urea ( $\text{NH}_2\text{CONH}_2$ ), buffered to pH 7 by the addition of 0,4 g of sodium dihydrogen orthophosphate dihydrate ( $\text{NaH}_2\text{PO}_4 \cdot 2\text{H}_2\text{O}$ ) and 2,5 g of disodium hydrogen orthophosphate dodecahydrate ( $\text{Na}_2\text{HPO}_4 \cdot 12\text{H}_2\text{O}$ ), and containing 0,1 g or less of a rapid-wetting surface-active agent, for example sodium dioctyl sulfosuccinate.

This page intentionally left blank