

INTERNATIONAL  
STANDARD

ISO  
16419

First edition  
2013-01-15

---

---

## Cork — Visual anomalies of cork stoppers for still wines

*Liège — Anomalies visuelles des bouchons de liège pour vins tranquilles*



Reference number  
ISO 16419:2013(E)

© ISO 2013



**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2013

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16419 was prepared by Technical Committee ISO/TC 87, *Cork*.



# Cork — Visual anomalies of cork stoppers for still wines

## 1 Scope

This International Standard applies to both

- semi-elaborated natural cork stoppers and colmated natural cork stoppers at the definitive dimensions stage, and
- finished natural cork stoppers and colmated natural cork stoppers ready to use.

It describes the anomalies of cork stoppers that can be detected by visual examination of the manufacturer or the end-user.

These anomalies, according to their size, can have functional or not functional consequences being able to alter, more or less, the cork stoppers' sealing capacity.

On the basis of a common sampling example, this International Standard proposes for all these anomalies some specifications for stoppers.

## 2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 633, *Cork — Vocabulary*

## 3 Designation for the different requirement levels

For natural cork stoppers for still wines, the following notion of range with three decreasing levels of requirement is introduced:

- superior range;
- standard range;
- entry of range.

Besides the commercial reference of the lot of cork stoppers, it belongs

- to the end-user to clarify what are his/her needs in relation to these three specifications (or range) levels, and
- to the manufacturer to define to which range the lot of cork stoppers belongs.

The definite ranges do not necessarily include the total amount of usable cork stoppers for sealing; there can also be other unanimous transactions that are out of the scope of this International Standard.

## 4 List of anomalies taken into account

Only the following will be considered cork stoppers' anomalies:

- longitudinal crack;
- transversal crack;

- parasite gallery;
- green corkwood stain;
- folded corkwood;
- dry vein;
- bevel and/or bevelled cork stopper;
- back;
- colmation excess;
- machining defects (asymmetries, tool bumps, gutters);
- belly.

Other aspect irregularities are not considered as anomalies since they only affect the cork stoppers' presentation and will be taken into account in the cork stoppers' visual classification.

In the case of having more than one anomaly with functional consequence in the same cork stopper, only the most important will be considered (penalized).

## 5 Anomalies of natural corkwood stoppers and colmated natural cork stoppers for still wines

Both [Table 1](#) and [Table 2](#) present the anomalies in relation to the raw material and to the fabrication process respectively, being:

- **columns 1 and 2** – The name and definition of the anomaly in accordance with ISO 633 (Vocabulary).
- **columns 3 and 4** – The threshold relates to the size and/or the position of the anomaly to be considered in order to assess whether it is likely to have a functional or not functional consequence (if the threshold is not reached, the observed visual irregularity does not count as an anomaly).
- **columns 5, 6, and 7** – The acceptance quality limit (AQL) specifications according to the cork stoppers' range.

These tables are considered for a working sample of 80 selected cork stoppers, which are considered a representative sample of a lot.

This value, which is given as an example, corresponds to day-to-day practices in the enterprises.

**Table 1 — Anomalies of raw material**

Name of the anomaly	Anomaly definition (given in ISO 633)	Potential functional consequence threshold taken into account	Not functional consequence threshold taken into account	Specifications for superior cork stoppers' range	Specifications for standard cork stoppers' range	Specifications for entry cork stoppers' range
Longitudinal crack	<b>Crack</b> (6.6.3): cork stopper presenting a (or several) hole of variable shape, lengthwise, or crosswise, which can occur on the back side of the reproduction cork.  A crack is called <b>longitudinal</b> whenever it touches or its projection meets the cork's end. In the remaining cases, it is called <b>transversal</b> .	A width $\geq 1,5$ mm and/or with a level difference between the two parts $\geq 1,5$ mm and $> 50\%$ length from (and touching) one of the ends.		(AQL=1,0) A2/R3	(AQL=1,5) A3/R4	(AQL=4,0) A7/R8
Transversal crack		A width higher than 1,5 mm and/or with a level difference between the two parts higher than 1,5 mm and $> 50\%$ of the circumference.		(AQL=1,0) A2/R3	(AQL=1,5) A3/R4	(AQL=6,5) A10/R11

**Table 1** (continued)

	<b>Worm hole</b> (6.6.6): cork stopper showing an (or several) obturated gallery caused by the larvae of <i>Coroebus undatus</i> Fabr., usually following an annual layer and affecting the whole or part of the stopper diameter or length and that may extend up to one or both stopper ends. Two orifices are visible on the cork stopper's surface.	An orifice situated on one end and > 50 % of the length between the two orifices.	(AQL=1,0) A2/R3	(AQL=1,0) A3/R4	(AQL=2,5) A5/R6
Parasite gallery		Two orifices situated at less than 10 mm from the ends and not from (not touching) any of the ends.	(AQL=1,5) A3/R4	(AQL=4,0) A7/R8	(AQL=6,5) A10/R11
	<b>Anthole</b> (6.6.7): cork stopper showing a (or several) clear and clean gallery caused by ants <i>Crematogaster scutellaris</i> Oliv., affecting the stopper diameter or roule and that may extend up to one or both stopper ends. Two orifices are visible on the cork stopper's surface.	An orifice situated on one end and > 50 % of the length between the two orifices.	(AQL=1,0) A2/R3	(AQL=1,0) A3/R4	(AQL=2,5) A5/R6
		Two orifices situated at less than 10 mm from the ends and not from (not touching) any of the ends.	(AQL=1,5) A3/R4	(AQL=4,0) A7/R8	(AQL=6,5) A10/R11
	<b>Green corkwood stain</b> (6.6.4): cork stopper showing a (or several) deformed dried green corkwood stain which may affect the whole or part of the stopper roule on the belly side and/or	Surface depression higher than 1 cm <sup>2</sup> .	(AQL=1,0) A2/R3	(AQL=1,5) A3/R4	(AQL=4,0) A7/R8
	Green corkwood	cork stopper showing a (or several) green corkwood stain {corkwood with a belly side showing a translucent appearance as the cells are still filled up with sap [Green corkwood (2.3.15)]} which may affect the whole or part of the stopper roule on the belly side.	Surface depression between 0,5 cm <sup>2</sup> and 1 cm <sup>2</sup> .	(AQL=1,5) A3/R4	(AQL=2,5) A5/R6
					(AQL=4,0) A7/R8

**Table 1** (*continued*)

Folded corkwood	<b>Folded corkwood</b> (2.3.6): cork stopper showing a (or several) veins with two autumn layers touching each other, which can (or might) lead to a local separation of layers in the suberous tissue.	Disjoining of the cork stopper in two parts under manual action.	(AQL=1,0) A2/R3	(AQL=1,5) A3/R4	(AQL=4,0) A7/R8
Dry vein	<b>Dry vein</b> (6.6.8): cork stopper which shows a lignified autumn layer with an abnormal over-thickness.	Disjoining of the cork stopper in two parts under manual action.	(AQL=1,0) A2/R3	(AQL=1,5) A3/R4	(AQL=4,0) A7/R8

.....,.....,.....,.....,.....,.....

**Table 2 — Anomalies of fabrication process**

Name of the anomaly	Anomaly definition (see ISO 633)	Potential functional consequence threshold taken into account	Not functional consequence threshold taken into account	Specifications for superior cork stoppers' range	Specifications for standard cork stoppers' range	Specifications for entry cork stoppers' range
Bevel and/or bevelled cork stopper	<b>Bevelled cork stopper</b> (6.6.10): cork stopper showing obliquity at one or both ends due to an imperfect hollow-punching or edge trimming.	Missing part $\geq 1/3$ of the circumference of one end with a depth $\geq 3$ mm.		(AQL=1,0) A2/R3	(AQL=2,5) A5/R6	(AQL=6,5) A10/R11
Back	<b>Back</b> (2.1.5): outer side of the suberous tissue, in relation to the tree.	Continuous lignified part resulting from an intubation too close to the outer face of the plank and visible on more than 20 % of the cork stopper's length.		(AQL=1,0) A2/R3	(AQL=1,5) A3/R4	(AQL=4,0) A7/R8
Colmation excess	<b>Colmation excess:</b> cork agglomeration of powder and glue localized on the ends and on the stopper rule.	Dome mass form with a surface higher than 3 mm <sup>2</sup> .		Not concerned	(AQL=1,5) A3/R4	(AQL=2,5) A5/R6



---

---

---

**ICS 55.100, 79.100**

Price based on 5 pages